CHEMIKALIENLISTE MACH I

WICHTIGER HINWEIS

Die Tabelle „Chemische Beständigkeit von Kunststoffen“ wurde aufgrund von Angaben verschiedener Rohstoffhersteller aufgelistet. Die Werte beziehen sich ausschließlich auf Labortests mit Rohstoffen. Daraus gefertigte Kunststoffteile unterliegen oftmals Einflüssen, die in Labortests nicht erkannt werden können (Temperatur, Druck, Materialspannungen, Einwirkung chemischer Substanzen, Konstruktionsmerkmale etc.). Die angegebenen Werte können aus diesen Gründen nur als Richtlinie dienen. In Zweifelsfällen empfehlen wir unbedingt einen Test durchzuführen. Ein Rechtsanspruch kann aus diesen Angaben nicht abgeleitet werden, wir schließen jegliche Gewähr und Haftung aus. Allein die chemische und mechanische Beständigkeit reicht für die Beurteilung der Gebrauchsfähigkeit eines Produktes nicht aus. Insbesondere sind z.B. die Vorschriften bei brennbaren Flüssigkeiten (Ex-Schutz) zu berücksichtigen.

COPYRIGHT

Wir bedanken uns bei der Bürkle GmbH, diese Tabelle verwenden zu dürfen.
Diese Tabelle wird von der Bürkle GmbH, D-79415 Bad Bellingen als Nachschlagewerk herausgegeben und gepflegt. Dieser Copyright-Vermerk darf nicht entfernt werden. Die Tabelle darf frei weitergegeben und kopiert werden, sofern der Hinweis auf den Urheber erhalten bleibt.

MATERIALLISTE MACH I

Tank:	PP	Saugschlauch:	PP, EVA
Schmutzwasserpumpe :	PP + GF20	Ablaufschlauch:	PP, EVA
Rückschlagventil:	PP	Bodendüse:	PP
Verschraubungen:	PP	Saugrohr:	PP
C-Kupplungen:	PA6 + GF30	Saugkopf:	ABS

							Thermoplaste												Fluor-Kunststoffe				Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZENTRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMERKUNG
Abgase, alkalisch	—	—		?		1/1	0/0	(2)	0/0	0/0	0/0	(1)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/4	1/0	1/0	1/0	0/0	(2)	(1)	(1)		
Abgase, fluorwasserstoffhaltig	—	—	gering	?		1/1	0/0	(3)	(3)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	(2)	(2)	1/1	
Abgase, kohlendioxidhaltig	—	—	gering	?		1/1	0/0	(1)	(1)	(1)	(1)	(1)	1/1	(1)	(1)	1/1	(1)	(1)	1/1	1/1	1/1	1/1	1/0	1/0	(1)	(1)	(1)	(1)	(1)	0/0	
Abgase, nitrosehaltig	—	—	gering	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	(3)	0/0	(2)	(1)	(1)		
Abgase, salzsäurehaltig	—	—	jede	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	2/2L	2/2L	3/3	
Abgase, schwefeldioxidhaltig	—	—	gering	?		1/1	0/0	(2)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	1/1	1/1	0/0	
Abgase, schwefelsäurehaltig	—	—	jede	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0	
Abgase, schwefeltrioxidhaltig	—	—	gering	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	4/4	0/0	0/0	1/1	0/0	0/0	(2)	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0	
Acetaldehyd	C_2H_4O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	3/4	
Acetaldehyd	C_2H_4O	000075-07-0	techn. rein	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Acetamid	C_2H_5NO	000060-35-5	gesättigt	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)	1/1	
Acetamino-4-ethoxybenzol, 1-	-> siehe: Phenacetin																														
Acetanhydrid	-> siehe: Essigsäureanhydrid																														
Aceton	C_3H_6O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	1/1	
Acetonitril	C_2H_3N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Acetophenon	C_8H_8O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Acetoxybenzoesäure, 2-	-> siehe: Acetylsalicylsäure																														
Acetyl-5-methyl-2,3-dihydropyran-2,4-dion, 2	-> siehe: Dehydracetsäure																														
Acetylchlorid	C_2H_3ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	0/0	
Acetylen	C_2H_2	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	1/1	0/0	1/0	1/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	
Acetylentetrabromid	-> siehe: Tetrabromethan, 1,1,2,2-																														
Acetylentetrachlorid	-> siehe: Tetrachlorethan-1,1,2,2																														
Acetylsalicylsäure	$C_9H_8O_4$	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	1/0	
Acrylnitril	C_3H_3N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	1/1	
Acrylsäurebutylester	-> siehe: Butylacrylat																														
Acrylsäureethylester	-> siehe: Ethylacrylat																														
Acrylsäuremethylester	-> siehe: Methylacrylat																														
Acrylsäurenitril	-> siehe: Acrylnitril																														
Adipinsäure	$C_6H_{10}O_4$	000124-04-9	gesättigt	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	1/0	(2)	(2)	1/1	
Adipinsäuredioctylester	-> siehe: Dioctyladipat																														
Akkusäure	H_2SO_4	007664-93-9	38 %	C		1/1	1/1	4/4	1/1	(4)	1/1	4/4	1/1	1/1	1/1	1/3	3/4	0/0	(1)	1/1	1/1	1/1	1/0	1/1	4/4	0/0	3/4	2/3	2/3	1/1	"Batteriesäure"
Alanin	$C_3H_7NO_2$	000056-41-7		—		1/1	1/1	1/1	4/4	(2)	1/1	(1)	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(2)	(2)	(2)		
Alaune	-> siehe: Kaliumaluminiumsulfat																														
Alkohol	-> siehe: Ethanol																														
Allylacetat	$C_5H_8O_2$	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		
Allylalkohol	C_3H_6O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	1/1	(2)	1/0	4/4	3/0	0/0	1/1	1/1	1/1	1/1	
Allylchlorid	C_3H_5Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)	0/0	
Allylisothiocyanat	-> siehe: Allylsenföl																														
Allylsenföl	C_4H_5NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		Oleum Sinapis
Aluminium(hydroxid)acetat	$C_4H_7AlO_5$	000139-12-8	wässrig	Xn		1/1	1/1	1/1	(1)	1/0	1/1	1/0	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	(1)	1/0	(3)	3/0	0/0	1/1	1/1	1/1	0/0	"Essigsaure Tonerde"
Aluminiumammoniumsulfat	$(NH_4)Al(SO_4)_2$	007784-26-1	gesättigt	Xi		1/1	1/1	3/4	(2)	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3	0/0	
Aluminiumchlorid	$AlCl_3$	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	1/1	0/0	1/1	0/0	1/1	2/2	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	4/4	3/4	1/1	
Aluminiumchlorid	$AlCl_3$	007784-13-6	fest	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	(3)	0/0	4/4	4/4	3/4	1/1	Salzsäure-Aluminiumsalz, wasserfrei
Aluminiumchlorid	$AlCl_3$	007784-13-6	gesättigt	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	(1)	1/1	(2)	1/0	1/1	0/0	4/4	4/4	3/4	1/1	Salzsäure-Aluminiumsalz, wasserfrei
Aluminiumfluorid	AlF_3	007789-18-1	wässrig	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	0/0	
Aluminiumhydroxid	$Al(HO)_3$	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1/1	1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	wegen geringer Löslichkeit keine chemische Einwirkung zu erwarten
Aluminiumhydroxiddiacetat	-> siehe: Essigsaure Tonerde																														
Aluminiumnitrat	$Al(NO_3)_3$	013473-90-0	wässrig	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Aluminiumoxid	Al_2O_3	001344-28-1	fest	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	wegen geringer Löslichkeit keine chemische Einwirkung zu erwarten
Aluminiumsulfat	$Al_2(SO_4)_3$	010043-01-3	10 %	?		1/1	1/1	1/0	1/0	(2)	1/1	3/4	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/2	1/1	1/1	
Aluminiumsulfat	$Al_2(SO_4)_3$	010043-01-3	gesättigt	Xn		1/1	1/1	3/4	1/0	0/0	1/1	3/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	2/2	1/2	1/1	
Aluminiumtrifluorid	-> siehe: Aluminiumfluorid																														
Ameisensäure	CH_2O_2	000064-18-6	50 %	C, F	X	1/1	1/2	4/4	3/3	0/0	1/2	4/4	1/2	3/3	2/2	2/3	0/0	1/3	1/1	1/1	1/1	1/1	3/4	4/4	4/4	0/0	(3)	1/3	1/2	1/1	
Ameisensäure	CH_2O_2	000064-18-6	98-100 %	C, F+, T	X	1/1	1/2	4/4	3/4	0/0	1/3	4/4	1/3	3/4	3/3	3/4	1/3	3/4	1/1	(1)	1/1	1/1	3/4	4/4	4/4	0/0	1/0	1/3	1/2	1/0	

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

							---------- Thermoplaste ----------		Fluor-Kunststoffe		--- Elastomere ---		------- Metalle -------		
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZÜNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Ameisensäure	CH_2O_2	000064-18-6	3 %	Xi		1/1	1/2	3/4	1/2	1/0	1/2	2/4	1/2	1/2	2/2	2/3	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(3)	4/4	0/0	(3)	1/2	1/1	1/1	
Ameisensäureamid	-> siehe: Formamid																														
Ameisensäureethylester	-> siehe: Ethylformiat																														
Ameisensäuremethylester	-> siehe: Methylformiat																														
Aminobenzol	-> siehe: Anilin																														
Aminobutan	-> siehe: Butylamin																														
Aminoessigsäure	$C_2H_5NO_2$	000056-40-6	10 %	—		1/1	1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	(2)	(2)	(2)	0/0	
Aminoethanol, 2-	-> siehe: Ethanolamin																														
Aminoethansäure	-> siehe: Aminoessigsäure																														
Aminomethan	-> siehe: Methylamin, (Mono-)																														
Aminopropan	-> siehe: Propylamin, n-																														
Aminopropionsäure, L-2-	-> siehe: Alanin, (L-)																														
Ammoniak	-> siehe: Ammoniumhydroxid																														
Ammoniak, schwefelsaures	-> siehe: Ammoniumsulfat																														
Ammoniakwasser	-> siehe: Ammoniumhydroxid																														
Ammonium-2-hydroxyacetat	-> siehe: Ammoniumglycolat																														
Ammoniumacetat	$C_2H_7NO_2$	000631-61-8	gesättigt	Xi		1/1	1/1	1/0	1/1	(2)	1/1	(1)	1/1	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(3)	2/2	0/0	1/1	(2)	(2)	1/1	
Ammoniumalaun	-> siehe: Aluminiumammoniumsulfat																														
Ammoniumaluminiumsulfat	-> siehe: Aluminiumammoniumsulfat																														
Ammoniumbicarbonat	-> siehe: Ammoniumhydrogencarbonat																														
Ammoniumbifluorid	-> siehe: Ammoniumhydrogendifluorid																														
Ammoniumcarbonat	$(NH_4)_2CO_3$	010361-29-2	50 %	Xn		1/1	1/1	1/0	3/0	0/0	1/0	(2)	1/1	1/1	1/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Hirschhornsalz
Ammoniumcarbonat	$(NH_4)_2CO_3$	010361-29-2	wässrig	Xn		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Hirschhornsalz
Ammoniumchlorid	$(NH_4)Cl$	012125-02-9	fest	Xn		1/1	1/1	1/0	1/0	(2)	0/0	2/3	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	3/4	1/3L	1/2L	1/1	Salmiak
Ammoniumchlorid	$(NH_4)Cl$	012125-02-9	wässrig	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	Salmiak
Ammoniumdihydrogenphosphat	$(NH_4)H_2PO_4$	007722-76-1	jede	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	3/0	1/1	0/0	4/4	(1)	(1)	1/1	
Ammoniumeisen-(II)-sulfat	$(NH_4)_2Fe(SO_4)_2$	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	(1)	(1)		
Ammoniumeisen-(III)-sulfat	$(NH_4)Fe(SO_4)_2$	007783-83-7	gesättigt	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0		
Ammoniumfluorid	$(NH_4)F$	012125-01-8	gesättigt	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)	?	
Ammoniumfluorid	$(NH_4)F$	012125-01-8	wässrig	T. C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3	1/1	
Ammoniumglycolat	$C_2H_7NO_3$	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)		
Ammoniumheptamolybdat	$(NH_4)_6Mo_7O_{24}$	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/0	(3)	(1)	0/0		(1)	(1)	0/0	
Ammoniumhydrogencarbonat	CH_5NO_3	001066-33-7	gesättigt	Xi		1/1	1/1	1/0	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	(3)	0/0	1/1	1/1	1/1	1/1	
Ammoniumhydrogendifluorid	F_2H_5N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0		
Ammoniumhydrogensulfid	-> siehe: Ammoniumhydrosulfid																														
Ammoniumhydrosulfid	$(NH_4)HS$	012124-99-1	jede	T, C		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	(2)	0/0	(2)	(1)	(1)	1/1	
Ammoniumhydroxid	$NH_3 + H_2O$	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	1/2	2/3	2/3	1/2	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1	1/1	
Ammoniumhydroxid	$NH_3 + H_2O$	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1	1/1	
Ammoniumhydroxid	$NH_3 + H_2O$	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1	1/1	
Ammoniummetaphosphat	$(NH_4PO_3)_n$	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)		
Ammoniummolybdat	-> siehe: Ammoniumheptamolybdat																														
Ammoniummonophosphat, monobasisch	-> siehe: Ammoniumdihydrogenphosphat																														
Ammoniumnitrat	$(NH_4)NO_3$	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	1/1	
Ammoniumnitrat	$(NH_4)NO_3$	006484-52-2	gesättigt	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1	1/1	
Ammoniumnitrit	$(NH_4)NO_2$	013446-48-5	wässrig	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/0	0/0	(2)	(1)	(1)		
Ammoniumoxalat	$C_2H_8N_2O_4$	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1	0/0	
Ammoniumperoxodisulfat	$(NH_4)_2S_2O_8$	007727-54-0	gesättigt	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0	
Ammoniumperoxodisulfat	$(NH_4)_2S_2O_8$	007727-54-0	wässrig	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0	
Ammoniumpersulfat	-> siehe: Ammoniumperoxodisulfat																														
Ammoniumphosphat, prim.	-> siehe: Ammoniumdihydrogenphosphat																														
Ammoniumpolyphosphat	-> siehe: Ammoniummetaphosphat																														
Ammoniumrhodanid	-> siehe: Ammoniumthiocyanat																														
Ammoniumsulfat	$(NH_4)_2SO_4$	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	1/1	schwefelsaures Ammoniak
Ammoniumsulfat	$(NH_4)_2SO_4$	007783-20-2	gesättigt	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2	1/1	schwefelsaures Ammoniak
Ammoniumsulfid	$(NH_4)_2S$	012135-76-1	jede	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	?	
Ammoniumsulfid	$(NH_4)_2S$	012135-76-1	wässrig	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)	1/1	

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste													Fluor-Kunststoffe				Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Ammoniumsulfocyanid	-> siehe: Ammoniumthiocyanat																													
Ammoniumthiocyanat	CH_4N_2S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)		
Ammonsalpeter	-> siehe: Ammoniumnitrat																													
Amylacetat, n-	$C_7H_{11}O_2$	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Amylalkohol, n-	$C_5H_{12}O$	000071-41-0		Xn	X	1/1	1/2	1/0	1/0	1/0	2/3	1/0	1/1	1/3	3/0	2/3	3/0	0/4	1/1	1/1	1/1	1/1	3/0	2/4	3/0	0/0	1/2	1/1	1/1	0/0	
Amylchlorid	$C_5H_{11}Cl$	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L	0/0	
Amylhydrosulfid	-> siehe: Pentanthiol, 1-																													
Amylmercaptan	-> siehe: Pentanthiol, 1-																													
Amylzimtaldehyd	$C_{14}H_{18}O$	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)	(1)		Riechstoff
Ananassaft	—	—		—		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	(1)	(1)		
Anilin	C_6H_7N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0	1/1	
Anilinchlorhydrat	$C_6H_3ClN_6$	000142-04-1	gesättigt	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4		
Anilinhydrochlorid	-> siehe: Anilinchlorhydrat																													
Aniliniumchlorid	-> siehe: Anilinchlorhydrat																													
Anis	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Anisol	C_7H_8O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Anisöl	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Anon	-> siehe: Cyclohexanon																													
Antimon-(III)-chlorid	-> siehe: Antimontrichlorid																													
Antimon-(V)-chlorid	-> siehe: Antimonpentachlorid																													
Antimonpentachlorid	$SbCl_5$	007647-18-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	(4)	0/0	
Antimontrichlorid	$SbCl_3$	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4	0/0	
Antimontrichlorid	$SbCl_3$	010025-91-9	wasserfrei	C		0/0	0/0	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	1/0	1/0	1/0	0/0	1/1	4/4	4/4		
Antimontrichlorid	$SbCl_3$	010025-91-9	wässrig	C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4		
Apfelsaft	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	(2)	(1)	(1)		
Apfelsinensaft	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(2)	1/1	1/1		
Apfelsinenschalenöl	—	008028-48-6		Xn		(3)	(3)	1/0	(3)	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	4/4	(2)	(3)	0/0	(1)	(1)	(1)		hauptsächlich +-Limonen
Arcton 12	-> siehe: Dichlordifluormethan																													
Arcton 21	-> siehe: Dichlorfluormethan																													
Arcton 22	-> siehe: Chlordifluormethan																													
Arsenanhydrid	-> siehe: Arsenpentoxid																													
Arsenpentoxid	As_2O_5	001303-28-2		T, N		1/1	1/1	(3)	(2)	0/0	0/0	(4)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	(2)	(3)	(3)	0/0	(3)	(1)	(1)		
Arsensäure	H_3AsO_4	022538-92-7	wässrig	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	1/1	
Arsensäure	H_3AsO_4	022538-92-7	80 %	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	0/0	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	1/1	
Arsensäureanhydrid	-> siehe: Arsenpentoxid																													
Ascorbinsäure	$C_6H_8O_6$	000050-81-7	wässrig	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	1/1	(1)	(1)	0/0	
Äther	-> siehe: Ethylether																													
Atropinsulfat	$C_{34}H_{48}N_2SO_{10}\cdot H_2O$	000055-48-1		T+		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)		
Ätzbaryt	-> siehe: Bariumhydroxid																													
Ätzkali	-> siehe: Kaliumhydroxid																													
Ätzkalk	-> siehe: Calciumoxid																													
Ätznatron	-> siehe: Natriumhydroxid																													
Azafluoren, 9-	-> siehe: Carbazol																													
Baldriantropfen	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	1/1	1/1	(1)	(3)	(3)	(2)	0/0	(2)	(1)	(1)		
Bariumbromid	$BaBr_2$	010553-31-8		Xn		1/1	1/1	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	1/1	0/0	(2)	(2L)	(2L)		
Bariumcarbonat	$BaCO_3$	000513-77-9	gesättigt	Xn		1/1	1/1	1/1	(1)	1/1	1/1	(1)	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	wegen geringer Löslichkeit keine chemische Einwirkung zu erwarten
Bariumchlorid	$BaCl_2$	010361-37-2	gesättigt	T		1/1	1/1	1/0	1/0	1/0	1/1	(2)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1	
Bariumchlorid	$BaCl_2$	010361-37-2	wässrig	T		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1	
Bariumhydroxid	$Ba(HO)_2$	012230-71-6	gesättigt	Xn		1/1	1/1	1/0	(3)	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/3	
Bariumhydroxid	$Ba(HO)_2$	012230-71-6	wässrig	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	?	
Bariumsulfid	BaS	021109-95-5	gesättigt	(T)		1/1	1/1	1/0	(2)	(2)	1/1	(2)	1/1	0/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	(2)	1/0	1/0	1/1	0/0	(3)	(1)	(1)	1/1	
Baumwollsamenöl	—	008001-29-4	techn. rein	?		0/0	0/0	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	3/0	1/0	1/0	0/0	(1)	1/1	1/1		
Benzaldehyd	C_7H_6O	000100-52-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	künstl. Mandelöl
Benzen	-> siehe: Benzol																													
Benzin	C_5H_{12} - $C_{12}H_{26}$	086290-81-5		F, Xn, N	X	2/3	3/4	1/0	3/3	(2)	2/3	1/2	3/4	4/4	3/3	2/4	0/0	0/4	1/1	1/1	1/1	1/1	1/1	4/4	(1-3)	3/0	0/0	1/1	1/1	1/1	1/1	Kraftstoff, unverbleit

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste														Fluor-Kunststoffe			Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Benzoesäure	$C_7H_6O_2$	000065-85-0	gesättigt	Xn, Xi		1/1	1/1	3/4	4/4	1/0	1/2	2/4	1/3	2/2	3/3	1/2	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1	
Benzoesäure	$C_7H_6O_2$	000065-85-0	wässrig	Xn, Xi		1/1	1/1	3/4	4/4	1/0	0/0	2/4	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1	
Benzoesäure Natriumsalz	-> siehe: Natriumbenzoat																														
Benzoesäurealdehyd	-> siehe: Benzaldehyd																														
Benzoesäurebenzylester	-> siehe: Benzylbenzoat																														
Benzoesäurechlorid	-> siehe: Benzoylchlorid																														
Benzoesäureethylester	$C_9H_{10}O_2$	000093-89-0		Xn		2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Benzol	C_6H_6	000071-43-2		F, T	X	3/4	3/4	2/0	4/4	4/4	2/3	1/2	3/4	4/4	4/4	4/4	0/0	0/4	1/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	1/1	1/1	1/1	0/0	
Benzol-1,2-dicarbonsäure	-> siehe: Phthalsäure																														
Benzolcarbonsäure	-> siehe: Benzoesäure																														
Benzolhexachlorid (BHC)	-> siehe: Hexachlorcyclohexan																														
Benzolsulfonsäure	$C_6H_6SO_3$	000098-11-3	gesättigt	C		1/1	1/1	(4)	(3)	(4)	0/0	(4)	2/4	0/0	1/0	2/0	0/0	0/0	0/0	1/1	1/1	1/4	4/4	1/0	4/4	0/0	3/4	0/0	1/0	0/0	
Benzoylchlorid	C_7H_5ClO	000098-88-4	100 %	C		0/0	3/3	4/4	(4)	0/0	(4)	(3)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	(3)	4/4	0/0	1/0	(2L)	(2L)	0/0	
Benzylacetat	$C_9H_{10}O_2$	000140-11-4		Xn/Xi		1/1	1/2	(2)	3/4	0/0	1/2	(2)	1/2	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	1/0	4/4	0/0	1/1	1/1	1/1		
Benzylalkohol	C_7H_8O	000100-51-6		Xn		3/4	4/4	4/4	4/4	0/0	4/4	1/0	4/4	4/4	4/4	2/3	0/0	4/4	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	1/1	1/1	1/1	3/3	
Benzylbenzoat	$C_{14}H_{12}O_2$	000120-51-4		Xn		0/0	0/0	(2)	(3)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Benzylcarbinol	-> siehe: Phenylethanol																														
Benzylchlorid	C_7H_7Cl	000100-44-7	100 %	T/Xi		0/0	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	(3)	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0	
Benzylether	-> siehe: Dibenzylether																														
Bernsteinsäure	$C_4H_6O_4$	000110-15-6	50 %	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	2/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/0	1/0	1/1	
Bernsteinsäure	$C_4H_6O_4$	000110-15-6	gesättigt	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	?	
Bernsteinsäurediethylester	$C_8H_{14}O_4$	000123-25-1		—		0/0	0/0	(2)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	4/4	4/4	0/0	(1)	(1)	(1)		
Bichromat-Schwefelsäure	-> siehe: Chromschwefelsäure																														
Bienenwachs	—	008012-89-3		—		1/1	1/1	1/1	(1)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	1/1	(1)	(1)		
Bier	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	
Bis(2-Chlor-1-methylethyl)ether	-> siehe: Dichlorisopropylether																														
Bis(2-ethylhexyl)-adipat	-> siehe: Dioctyladipat																														
Bis(2-ethylhexyl)-phthalat	-> siehe: Diisooctylphthalat																														
Bis(2-ethylhexyl)-sebacat, Sebacinsäure-bis(2-ethylhexyl)ester	-> siehe: Dioctylsebacat																														
Bismutchlorid	$BiCl_3$	007787-60-2		Xi		1/1	1/1	(3)	(2)	(2)	0/0	(4)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(4)	0/0	0/0		früher: Wismutchlorid
Bismutsubnitrat	$Bi_5O(HO)_9(NO_3)_4$	001304-85-4		O, Xi		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		früher: Wismutsubnitrat
Bisulfit	-> siehe: Natriumbisulfit																														
Bisulfitlauge	$NaHSO_3$	??		Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	3/0	0/0	(3)	1/1	1/1	1/1	
Bisulfitlauge, $S0_2$-haltig	$NaHSO_3$	??	gesättigt	Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/1	4/4	0/0	(3)	1/1	1/1		
Bittermandelöl	C_7H_6O	090320-35-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1		Hauptbestandteil: Benzaldehyd
Bittersalz	-> siehe: Magnesiumsulfat																														
Bitumen	—	008052-42-4		—		0/0	0/0	1/0	(2)	(2)	0/0	2/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	(3)	0/0	1/1	(1)	(1)		
Blausäure	HCN	000074-90-8	techn. rein	F+, T+	X	1/1	1/1	(3)	4/4	0/0	0/0	4/4	1/1	1/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	1/1	1/0	1/0	1/0	
Blausäure	HCN	000074-90-8	wässrig	F+, T+	X	1/1	1/1	(3)	4/4	0/0	(4)	4/4	1/1	1/0	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(1)	1/0	1/0	?	
Blei-(II)-acetat	$C_4H_6PbO_4$	000301-04-2	wässrig	T, N		1/1	1/1	3/0	1/0	(2)	1/0	1/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	3/0	0/0	4/4	1/1	1/1	1/1	
Blei-(II)-acetat	$C_4H_6PbO_4$	000301-04-2		T, N		1/1	1/1	3/0	1/0	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	2/2	0/0	4/4	1/1	1/1	1/1	
Blei-(II)-nitrat	$Pb(NO_3)_2$	010099-74-8	wässrig	O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Blei-(II)-nitrat	$Pb(NO_3)_2$	010099-74-8		O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Bleisalpeter	-> siehe: Blei-(II)-nitrat																														
Bleistearat	$C_{36}H_{70}PbO_4$	001072-35-1		?		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		wegen geringer Löslichkeit keine chemische Einwirkung zu erwarten
Bleisulfat	$PbSO_4$	007446-14-2		(T, N)		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	0/0	(1)	(1)	(1)	0/0	wegen geringer Löslichkeit keine chemische Einwirkung zu erwarten
Bleitetraethyl	-> siehe: Tetraethylblei																														
Bleizucker	-> siehe: Blei-(II)-acetat																														
Blutlaugensalz gelb	-> siehe: Ferrocyankalium																														
Blutlaugensalz rot	-> siehe: Ferricyankalium																														
Borax	-> siehe: Natriumborat																														
Borsäure	H_3BO_3	010043-35-3	10 %	Xi		1/1	1/1	1/0	1/1	1/0	1/1	2/3	1/1	1/2	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Borsäure	H_3BO_3	010043-35-3	wässrig	Xi		1/1	1/1	3/3	1/1	1/0	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Branntweine	-> siehe: Spirituosen																														

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

							Thermoplaste													Fluor-Kunststoffe				Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Bremsflüssigkeit	—	—		?		1/0	1/0	1/0	4/4	0/0	1/1	(3)	1/1	3/0	0/0	1/0	3/0	4/4	0/0	(1)	1/0	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Brom	Br_2	007726-95-6		T+, C		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	2/4	4/4	4/4	1/2	1/1	1/3	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	4/4	
Brombenzen	-> siehe: Brombenzol																													
Brombenzol	C_6H_5Br	000108-86-1		Xn	X	3/4	4/4	1/0	4/4	(2)	4/4	1/0	4/4	4/4	4/4	4/4	0/0	0/0	2/4	1/1	1/0	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)		
Bromchlormethan	CH_2BrCl	000074-97-5	100 %	Xn		(4)	(4)	4/4	4/4	1/0	(4)	(3)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/0	(3)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	
Bromdämpfe	Br_2	007726-95-6		T		(4)	(4)	4/4	(3)	4/4	(4)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(2-3)	4/4	0/0	(3)	(4)	(4)	4/4	
Bromkalium	-> siehe: Kaliumbromid																													
Brommethan	CH_3Br	000074-83-9	techn. rein	T		3/0	4/4	1/0	(3)	0/0	0/0	1/0	4/4	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0	
Bromoform	$CHBr_3$	000075-25-2		T		4/4	4/4	4/4	4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	0/0	0/0	2/3	1/1	(1)	(2)	4/4	(4)	4/4	0/0	(3)	0/0	0/0	0/0	
Brompentafluorid	BrF_5	007789-30-2		F, T, C		0/0	0/0	4/4	(4)	(4)	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromsäure	$HBrO_3$	007789-31-3	konz.	C		0/0	0/0	(4)	(4)	(4)	0/0	4/4	3/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(4)	(2)	4/4	0/0	(4)	(4)	(4)	0/0	
Bromtrifluorid	BrF_3	007787-71-5		T, C		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromtrifluormethan	$CBrF_3$	000075-63-8		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Bromwasser	Br_2+H_2O	007726-95-6	gesättigt	T		4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	4/4	0/0	3/4	0/0	0/0	0/0	0/0	1/1	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	0/0	
Bromwasserstoffsäure	HBr	010035-10-6	40 %	C		1/0	1/1	4/4	4/4	(4)	4/4	4/4	1/1	4/4	0/0	1/1	3/3	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Bromwasserstoffsäure	HBr	010035-10-6	50 %	C		1/1	1/2	4/4	4/4	(4)	4/4	4/4	1/2	4/4	0/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Bromwasserstoffsäure	HBr	010035-10-6	verdünnt	C		1/1	1/1	4/4	4/4	3/0	4/4	4/4	1/1	4/4	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Butadien, 1,3-	C_4H_6	000106-99-0		F+, T	X	3/4	4/4	1/0	4/4	1/0	4/4	(2)	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)	4/4	
Butan	C_4H_{10}	000106-97-8	techn. rein	F+	X	1/0	1/1	1/0	1/0	1/0	1/0	2/0	1/1	4/4	1/0	1/0	3/0	1/0	0/0	1/1	1/1	1/0	4/4	1/0	1/0	0/0	1/1	(1)	(1)	1/1	
Butanal	-> siehe: Butyraldehyd																													
Butandiol	-> siehe: Butylenglycol																													
Butandisäure	-> siehe: Bernsteinsäure																													
Butanol	$C_4H_{10}O$	000071-36-3	techn. rein	Xn	X	1/1	1/3	1/0	2/3	1/0	1/2	1/2	1/2	1/2	2/3	2/3	4/4	1/3	1/1	1/1	1/1	1/1	2/0	3/4	1/0	0/0	1/1	(1)	(1)	0/0	
Butanol, sek-	-> siehe: Butylalkohol, sekundär																													
Butanol, tert-	-> siehe: Butylalkohol, tertiär																													
Butanol-2	-> siehe: Butylalkohol, sekundär																													
Butanon	-> siehe: Methylethylketon																													
Butansäure	-> siehe: Buttersäure																													
Butantriol	$C_4H_{10}O_3$	—	100 %	—		(4)	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	3/3	4/4	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)		Isomeres in der Quelle nicht angegeben
Buten	C_4H_8	—	techn. rein	F+	X	4/4	0/0	1/0	(1)	1/0	0/0	1/0	4/4	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/0	1/0	3/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0	Isomeres in der Quelle nicht angegeben
Butenal, trans-2-	-> siehe: Crotonaldehyd																													
Butendisäure, cis-	-> siehe: Maleinsäure																													
Butoxyethanol, 2-	-> siehe: Butylglycol																													
Butter	—	—		—		1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	3/0	1/0	1/1	0/0	(1)	(1)	(1)		
Buttersäure	$C_4H_8O_2$	000107-92-6		C		3/4	4/4	3/3	4/4	0/0	4/4	4/4	4/4	4/4	2/2	2/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/2	1/2	1/1	1/1	
Buttersäureethylester	-> siehe: Ethylbutyrat																													
Butylacetat	-> siehe: Essigsäurebutylester																													
Butylacrylat	$C_7H_{12}O_2$	000141-32-2	100 %	Xi	X	1/2	2/3	2/0	4/4	1/3	2/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/0	
Butylalkohol	-> siehe: Butanol																													
Butylalkohol, sekundär	$C_4H_{10}O$	000078-92-2		Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	2/2	2/3	2/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		
Butylalkohol, tertiär	$C_4H_{10}O$	000075-65-0		F, Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		
Butylamin	$C_4H_{11}N$	000109-73-9		F, C	X	0/0	0/0	0/0	(3)	0/0	0/0	3/4	2/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Butylcarbinol	-> siehe: Amylalkohol, n-																													
Butylcellosolve	-> siehe: Butylglycol																													
Butylen	-> siehe: Buten																													
Butylenglycol	$C_4H_{10}O_2$	—	techn. rein	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	4/4	(1)	0/0	1/1	(1)	(1)	0/0	Isomeres in der Quelle nicht angegeben
Butylether	-> siehe: Dibutylether																													
Butylethylen	-> siehe: Hexen, 1-																													
Butylglycol	$C_4H_{14}O_2$	000111-76-2	100 %	Xn	X	0/0	1/0	1/0	(2)	1/0	0/0	1/0	1/0	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	1/1	3/0	3/4	3/4	0/0	1/1	(1)	(1)	0/0	
Butylphenol	$C_{10}H_{14}O$	—	100 %	Xi		0/0	1/1	(3)	(3)	0/0	(3)	(4)	1/1	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Isomeres in der Quelle nicht angegeben
Butylphenol, p-tertiär	$C_{11}H_{15}NO$	000098-54-4	techn. rein	C, Xn		3/0	0/0	(3)	(3)	0/0	(3)	(4)	1/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1		
Butylstearat	-> siehe: Stearinsäurebutylester																													

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

							Thermoplaste													Fluor-Kunststoffe				Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Butyraldehyd	C_4H_8O	000123-72-8		F, Xn	X	0/0	0/0	(3)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Cadmiumbromid	CdBr	007789-42-6		T		1/1	1/1	(3)	(2)	(2)	0/0	(3)	(1)	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	4/4	0/0	0/0		
Calciumacetat	$C_4H_6CaO_4$	000062-54-4	wässrig	—		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(2)	(1)	(1)	0/0	
Calciumbicarbonat	$Ca(HCO_3)_2$	—	gesättigt	—		1/1	1/1	1/1	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	(2)	(1)	(1)	0/0	
Calciumbisulfit	$Ca(HSO_3)_2$	013780-03-5	gesättigt	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1	
Calciumbisulfit	$Ca(HSO_3)_2$	013780-03-5	wässrig	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1	
Calciumbromid	$CaBr_2$	007789-41-5		?		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(3)	0/0	0/0	0/0	
Calciumcarbid	CaC_2	000075-20-7		F	X	1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0	Carbid, reagiert mit Wasser zu Acetylen - hochentzündlich!
Calciumcarbonat	$CaCO_3$	000471-34-1	gesättigt	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	wegen geringer Löslichkeit keine chemische Einwirkung zu erwarten
Calciumchlorat	$Ca(ClO_3)_2$	010137-74-3	gesättigt	O, (T)		0/0	0/0	(3)	(2)	0/0	1/1	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(2)	(1)	(3)	0/0	1/1	(1)	1/0	1/1	
Calciumchlorid	$CaCl_2$	010043-52-4	alkoholisch	F, Xi		1/0	0/0	4/4	(2)	0/0	1/0	(3)	1/1	0/0	0/0	0/0	4/4	0/0	0/0	1/1	1/0	(1)	(2)	(2)	(2)	0/0	(3)	1/2L	1/2L	1/1	
Calciumchlorid	$CaCl_2$	010043-52-4	wässrig	Xi		1/1	1/1	1/0	1/0	1/0	1/1	(3)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/2L	1/2L	1/1	
Calciumhydrat	-> siehe: Calciumhydroxid																														
Calciumhydrogencarbonat	-> siehe: Calciumbicarbonat																														
Calciumhydrogensulfit	-> siehe: Calciumbisulfit																														
Calciumhydroxid	CaH_2O_2	001305-62-0	wässrig	(Xi)		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calciumhydroxid	CaH_2O_2	001305-62-0	konz.	C		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	2/2	2/2	1/1	1/0	0/0	1/1	1/1	1/1	1/3	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calciumhypochlorit	$Ca(OCl)_2$	007778-54-3	gesättigt	O, C		1/1	1/1	1/4	3/4	3/0	1/2	1/0	1/1	2/3	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/3	(2)	2/3	4/4	0/0	4/4	3/0	2/0	1/1	Bleichpulver
Calciumhypochlorit	$Ca(OCl)_2$	007778-54-3	wässrig	O, C/Xi		0/0	0/0	4/4	1/0	3/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	4/4	3/0	2/0	1/1	Bleichpulver
Calciumnitrat	$Ca(NO_3)_2$	010124-37-5	50 %	O		1/1	1/1	(2)	1/0	(2)	1/1	(3)	1/1	1/1	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	1/0	1/1	1/1	1/1	
Calciumnitrat	$Ca(NO_3)_2$	010124-37-5	wässrig	O		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/1	1/1	1/1	
Calciumoxid	CaO	001305-78-8	Pulver	C		1/0	1/1	(2)	(2)	(2)	0/0	0/0	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	1/1	1/1		
Calciumphosphat	$Ca_3(PO_4)_2$	007758-87-4	wässrig	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	wegen geringer Löslichkeit keine chemische Einwirkung zu erwarten
Calciumphosphat	$Ca_3(PO_4)_2$	007758-87-4		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	wegen geringer Löslichkeit keine chemische Einwirkung zu erwarten
Calciumsulfat	$CaSO_4$	007778-18-9	gesättigt	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	Gips
Calciumsulfid	CaS	020548-54-3	wässrig	C		0/0	0/0	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	(1)	(1)	0/0	
Calciumsulfid	CaS	020548-54-3		C		0/0	3/3	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Campher	$C_{10}H_{16}O$	000464-48-2 / -49-2		F, Xn	X	3/4	3/4	(2)	(3)	0/0	0/0	(2)	1/0	1/3	0/0	4/4	4/4	1/1	0/0	(1)	1/0	(3)	4/4	3/4	1/0	0/0	(1)	1/0	1/0	1/0		
Campheröl	—	008008-51-3		Xn		4/4	4/4	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	(3)	4/4	3/0	1/0	0/0	(1)	(1)	(1)	1/0	aus Cinnamomum Camphora
Camphogen	-> siehe: Cymol, p-																														
Capronaldehyd	-> siehe: Hexanal																														
Carbazol	$C_{12}H_9N$	000086-74-8		Xn		1/1	1/1	(2)	4/4	0/0	1/1	(1)	1/1	1/1	4/4	4/4	0/0	4/4	1/1	1/1	(2)	(2)	(2)	(3)	(2)	0/0	(1)	(1)	(1)	0/0	
Carbinol	-> siehe: Methanol																														
Carbolineum	—	008001-58-9	wässrig	(Xn)		1/0	1/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	(2)	3/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Carbolsäure	-> siehe: Phenol																														
Carbondisulfid	-> siehe: Schwefelkohlenstoff																														
Carbonylchlorid	-> siehe: Phosgen																														
Carnaubawachs	—	008015-86-9		—		1/1	1/1	1/1	(1)	1/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(3)	(1)	(1)	0/0	1/1	(1)	(1)		
Cäsiumbromid	CsBr	007787-69-1		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	0/0	0/0		
Cellosolve	-> siehe: Ethylglycol																														
Cellosolveacetat	-> siehe: Ethylenglycolmonoethyletheracetat																														
Cetylalkohol	$C_{16}H_{34}O$	036653-82-4	100 %	Xi		1/1	1/1	4/4	(2)	1/0	0/0	(1)	1/1	0/0	1/0	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(1)	1/1	1/1		
Cetylsäure	-> siehe: Palmitinsäure																														
Chinin	$C_{20}H_{24}N_2O_2$	000130-95-0		Xn		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)	0/0	
Chlor	Cl_2	007782-50-5	10 % nass	T		3/4	3/4	4/4	2/3	4/4	2/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	(2)	2/0	3/0	4/4	0/0	4/4	4/4	4/4	0/0	
Chlor	Cl_2	007782-50-5	97 %	T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0	1/1	
Chlor(o)schwefelsäure	-> siehe: Chlorsulfonsäure																														
Chlor-1-propen, 3-	-> siehe: Allylchlorid																														
Chlor-2-propanon, 1-	-> siehe: Chloraceton																														
Chloraceton	C_3H_5ClO	000078-95-5		(F, Xi)	X	0/0	0/0	(3)	(4)	(4)	(4)	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	0/0	
Chloracetophenon, p-	C_8H_7ClO	000099-91-2		(Xn)		1/1	1/1	(2)	4/4	0/0	1/1	(2)	1/1	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(2)	(2)	(3)	4/4	4/4	0/0	(1)	0/0	0/0		
Chloral	-> siehe: Trichloracetaldehyd																														

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste														Fluor-Kunststoffe			Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Chloralhydrat	$C_2H_3Cl_3O_2$	000302-17-0	techn. rein	T/Xi		3/3	3/3	4/4	(3)	(4)	0/0	(3)	3/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	4/4	3/0	3/4	4/4	0/0	4/4	0/0	0/0	0/0	
Chloramin T	$C_7H_7ClNaNSO_2$	000127-65-1	verdünnt	Xi		1/0	1/0	4/4	1/0	0/0	0/0	(3)	(3)	0/0	0/0	0/0	1/0	0/0	0/0	(1)	1/0	3/4	1/0	4/4	1/0	0/0	3/4	2/2	1/1	0/0	Schwimmbad-Desinfektion
Chlorbenzen	-> siehe: Chlorbenzol																													
Chlorbenzol	C_6H_5Cl	000108-90-7		Xn	X	3/4	3/4	4/4	4/4	1/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/1	(1/1)[1]	(1/1)[1]	1/1	[1] wasserfrei! Wenn durch Feuchtigkeit auch nur Spuren von Salzsäure (HCl) abgespaltet werden, besteht die Gefahr von Lochfraß, Spalt- und Spannungsrisskorrosion.
Chlorbleichlauge	-> siehe: Natriumhypochlorit																													
Chlorbrommethan	-> siehe: Bromchlormethan																													
Chlorbutadien	C_4H_5Cl	000126-99-8		F, Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/4	4/4	0/0	(3)	0/0	0/0		
Chlorcalcium	-> siehe: Calciumchlorid																													
Chlordifluormethan	$CHClF_2$	000075-45-6		N, Xn		0/0	3/0	1/0	3/0	1/0	0/0	1/0	4/4	4/4	4/4	2/0	4/4	0/0	0/0	3/3	1/0	(3)	1/0	4/4	4/4	0/0	(3)	0/0	0/0		
Chlordioxid	ClO_2	010049-04-4		E, T		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/0	(2)	4/4	1/0	4/4	0/0	3/4	3/4	3/4		
Chlordodecan	-> siehe: Laurylchlorid																													
Chloressigsäure	$C_2H_3ClO_2$	000079-11-8	50 %	T, C		1/3	1/3	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/0	0/0	3/4	0/0	(1)	1/1	1/4	2/0	3/0	4/4	0/0	4/4	2/4	2/4	1/4	
Chloressigsäure	$C_2H_3ClO_2$	000079-11-8		T, C		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/2	2/4	4/4	3/4	4/4	3/4	1/1	1/1	1/1	4/4	3/0	3/0	4/4	0/0	4/4	4/4	4/4	4/4	
Chloressigsäureethylester	-> siehe: Ethylchloracetat																													
Chloressigsäuremethylester	-> siehe: Methylchloracetat																													
Chlorethan	C_2H_5Cl	000075-00-3		F+, Xn	X	3/3	3/4	1/0	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/0	4/4	0/0	(3)	(1/1L)[1]	(1/1L)[1]	0/0	[1] wasserfrei! Wenn durch Feuchtigkeit auch nur Spuren von Salzsäure (HCl) abgespaltet werden, besteht die Gefahr von Lochfraß, Spalt- und Spannungsrisskorrosion.
Chlorethanol	C_2H_5ClO	000107-07-3	techn. rein	T+		1/1	0/0	4/4	4/4	0/0	0/0	3/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	1/1	1/0	1/3	3/0	4/4	4/4	0/0	(3)	1/0L	1/0L	1/0	
Chlorethylalkohol, 2-	-> siehe: Chlorethanol																													
Chlorethylen	C_2H_3Cl	000075-01-4	techn. rein	F+, T	X	0/0	0/0	1/1	(4)	1/1	0/0		(3)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	1/1	3/0	3/0	4/4	0/0	(1)	0/0	0/0	0/0	
Chlorfluormethan	CH_2ClF	000593-70-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	4/4	0/0	(3)	0/0	0/0		
Chlorgas	Cl_2	007782-50-5		T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0		
Chlorkalium	-> siehe: Kaliumchlorid																													
Chlorkalk	[3 x CaCl(OCl) + Ca	—	wässrig	?		0/0	0/0	4/4	(2)	3/0	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	"Bleichkalk", engl.: chloride of lime, bleach
Chlorkalk	[3 x CaCl(OCl) + Ca	—		O, C		0/0	0/0	4/4	(2)	3/0	0/0	4/4	1/1	1/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	"Bleichkalk", engl.: chloride of lime, bleach
Chlormethan	CH_3Cl	000074-87-3	techn. rein	F+, T	X	3/0	2/0	4/4	(3)	0/0	0/0	1/0	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/0	1/0	1/1	4/4	4/4	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]		[1] wasserfrei! Wenn durch Feuchtigkeit auch nur Spuren von Salzsäure (HCl) abgespaltet werden, besteht die Gefahr von Lochfraß, Spalt- und Spannungsrisskorrosion.
Chlormethyl	-> siehe: Chlormethan																													
Chlormethylbenzol	-> siehe: Benzylchlorid																													
Chlormethyloxiran	-> siehe: Epichlorhydrin																													
Chlornaphthalin, 1-	$C_{10}H_7Cl$	000090-13-1		Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	4/4	0/0	(2)	1/0	1/0		
Chlornickel	-> siehe: Nickel-(II)-chlorid																													
Chloroform	$CHCl_3$	000067-66-3	100 %	Xn		3/4	4/4	3/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	1/1	4/4	3/4	4/4	0/0	(3)	(1/1)[1]	(1/1)[1]	1/1	[1] wasserfrei! Wenn durch Feuchtigkeit auch nur Spuren von Salzsäure (HCl) abgespaltet werden, besteht die Gefahr von Lochfraß, Spalt- und Spannungsrisskorrosion.
Chloropren	-> siehe: Chlorbutadien																													
Chlorpentafluorethan	C_2ClF_5	000076-15-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Chlorpentan, 1-	-> siehe: Amylchlorid																													
Chlorphenylmethylketon, 4-	-> siehe: Chloracetophenon, -p																													
Chlorpropan, 2-	-> siehe: Isopropylchlorid																													
Chlorpropylen, 3-	-> siehe: Allylchlorid																													
Chlorsäure	$HClO_3$	007790-93-4	1 %	(C)		0/0	1/1	4/4	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/3	1/0	0/0	0/0	0/0	1/1	1/1	3/0	1/1	(3)	0/0	(3)	4/4	4/4	1/1	

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste													Fluor-Kunststoffe			Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZENTRATION	GEFAHRENHINWEIS	ENTZÜNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMERKUNG
Chlorsäure	$HClO_3$	007790-93-4	10 %	(O), C		1/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	3/0	3/0	4/4	0/0	4/4	4/4	4/4	1/1	
Chlorsäure	$HClO_3$	007790-93-4	20 %	(O), C		3/0	1/4	4/4	(3)	(4)	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/0	3/0	3/0	4/4	0/0	4/4	4/4	4/4	?	
Chlorsulfonsäure	$ClHSO_3$	007790-94-5	techn. rein	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	3/0	4/4	4/4	0/0	0/0	1/0	3/4	4/4	4/4	4/4	0/0	3/3	3/4	3/4	1/0	
Chlortoluol	C_7H_7Cl	—		Xn		0/0	0/0	(2)	4/4	0/0	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(3)	1/0	1/0	1/1	Isomeres in der Quelle nicht angegeben
Chlortoluol, alpha-	-> siehe: Benzylchlorid																													
Chlortrifluorid	ClF_3	007790-91-2		(O, T)		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(4)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(4)	4/4	(4)	4/4	0/0	(4)	(4)	(4)		
Chlortrifluormethan	$CClF_3$	000075-72-9		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	0/0	
Chlorwasser	$Cl_2 \times H_2O$	007782-50-5		(T)		3/0	0/4	4/4	4/4	4/4	4/4	4/4	3/4	4/4	0/0	3/3	3/0	3/3	1/1	(1)	1/1	1/1	3/0	1/0	4/4	0/0	4/4	2/0L	2/0L	0/0	
Chlorwasserstoff(gas)	HCl	007647-01-0	wasserfrei	T, C		1/1	0/0	4/4	(3)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	2/2L	2/2L	0/0	
Chlorwasserstoffgas	-> siehe: Chlorwasserstoff																													
Chlorwasserstoffsäure	-> siehe: Salzsäure																													
Chlorzink	-> siehe: Zinkchlorid																													
Chrom-(III)-Kaliumsulfat-Dodecahydrat	-> siehe: Chromalaun																													
Chrom-(VI)-oxid	-> siehe: Chromsäure																													
Chromalaun	$KCr(SO_4)_2 \times 12H_2O$	007788-99-0	gesättigt	Xn		1/1	0/0	(2)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(3)	1/3	1/3	1/1	
Chromsalze	—	—	jede	T/Xn		0/0	0/0	0/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	0/0	K	K	K		
Chromsäure	CrO_3	001333-82-0	10 %	O, T, C, N		1/1	1/1	4/4	2/3	3/0	1/1	4/4	1/1	1/1	4/4	1/2	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	1/2	1/2	1/1	
Chromsäure	CrO_3	001333-82-0	20 %	O, T, C, N		0/0	1/3	4/4	3/4	(4)	0/0	4/4	3/3	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	(2)	(2)	1/1	
Chromsäure	CrO_3	001333-82-0	50 %	O, T, C, N		3/4	3/4	4/4	3/4	(4)	2/3	4/4	3/3	3/3	4/4	1/3	1/0	3/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	(3)	2/3	2/3	1/1	
Chromsäure-Kaliumsalz	-> siehe: Kaliumchromat																													
Chromschwefelsäure	$CrO_3 + H_2SO_4$	065272-71-1	konz.	O, T, C, N		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	4/4	4/4	1/1	0/0	1/1	4/4	4/4	1/0	4/4	4/4	4/4	2/3	2/3	0/0	
Chromtrioxid	-> siehe: Chromsäure																													
Citronensäure	-> siehe: Zitronensäure																													
Citronensäuretributylester	-> siehe: Tributylcitrat																													
Clophen A60	—	011096-82-5		Xn, N		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	0/0	0/0	0/0	0/0	(1)	(2)	4/4	2/3	4/4	0/0	1/0	1/0	1/0	0/0	polychlorierte Biphenyle, PCB; Bayer
Cobalt-(II)-chlorid	$CoCl_2$	007646-79-9	wässrig	Xn		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Cobaltdichlorid	-> siehe: Cobalt-(II)-chlorid																													
Colamin	-> siehe: Ethanolamin																													
Crotonaldehyd	C_4H_6O	004170-30-3	techn. rein	F, T	X	1/0	0/0	(2)	(4)	0/0	(4)	(2)	1/0	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	1/3	1/0	3/0	4/4	0/0	1/0	1/1	1/1	0/0	
Cumen	-> siehe: Cumol																													
Cumol	C_9H_{12}	000098-82-8		Xi	X	2/3	3/4	(2)	4/4	0/0	4/4	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Curry	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	3/3	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		ggf. Verfärbung
Cyanessigsäureethylester	-> siehe: Ethylcyanacetat																													
Cyankali	-> siehe: Kaliumcyanid																													
Cyankalium	-> siehe: Kaliumcyanid																													
Cyannatrium	-> siehe: Natriumcyanid																													
Cyanwasserstoff(säure)	-> siehe: Blausäure																													
Cyclanon	—	—		(Xn, Xi)		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/1	0/0	3/4	(1)	(1)	0/0	polyquaternäre Verbindungen, Färbereihilfsmittel; BASF
Cyclohexan	C_6H_{12}	000110-82-7		F	X	3/4	3/4	1/0	3/3	1/0	4/4	1/1	3/4	4/4	4/4	2/3	1/0	1/3	1/2	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Cyclohexanol	$C_6H_{12}O$	000108-93-0	techn. rein	Xn		1/1	1/1	1/1	3/0	0/0	1/2	1/0	1/3	3/3	1/0	1/1	4/4	1/3	0/0	(1)	1/1	1/3	4/4	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Cyclohexanon	$C_6H_{10}O$	000108-94-1	techn. rein	Xn	X	1/3	3/4	1/0	4/4	(4)	3/4	1/0	2/4	4/4	4/4	4/4	4/4	4/4	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Cyclohexylmethan	-> siehe: Methylcyclohexan																													
Cymol, p-	$C_{10}H_{14}$	000099-87-6		F, Xn/Xi	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Dampf	H_2O	—	bis 150°C	?		4	4	4/4	0/0	0	0	(3)	(3)	0	0	0	0	0	0	0/0	1	0	1	3	4/4	0	(1)	1/1	1/1		
DDT (Emulsion)	$C_{14}H_9Cl_5$	000050-29-3		T		0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(3)	(3)	0/0	(2)	(2)	(2)	0/0	
Decahydronaphtalin	$C_{10}H_{18}$	000091-17-8		Xn		1/3	3/4	1/0	4/4	3/0	4/4	1/0	3/4	4/4	4/4	1/2	3/0	3/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	(1)	(1)	0/0	
Decalin	-> siehe: Decahydronaphtalin																													
Decan	$C_{10}H_{22}$	000124-18-5		Xn	X	0/0	0/0	(1)	(2)	(1)	(3)	1/1	(3)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	(1)	(1)		
Decandisäuredibenzylester	-> siehe: Dibenzylsebacat																													
Decandisäuredibutylester	-> siehe: Dibutylsebacat																													
Decandisäurediethylester	-> siehe: Diethylsebacat																													
Dehydracetsäure	$C_8H_8O_4$	000520-45-6		Xn		0/0	0/0	(3)	(2)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(4)	(1)	(1)		
Densodrin W	—	—	wässrig	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/0	0/0	0/0	1/0	0/0	0/0	0/0	0/0		Hydrophobierungsmittel für Leder, Siliconderivat; BASF

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

							---------- Thermoplaste ----------		Fluor-Kunststoffe		--- Elastomere ---		------- Metalle -------		
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Desmodur 44	$C_{15}H_{10}N_2O_2$	000101-68-8		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	0/0	4/4	0/0	(1)	(1)	(1)		
Dextrin	$(C_6H_{10}O_5)_n$ x H_2O	009004-53-9	wässrig	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Dextrose	-> siehe: Glucose																														
Diacetonalkohol	$C_6H_{12}O_2$	000123-42-2		Xi	X	0/0	0/0	(3)	(3)	0/0	0/0	1/0	2/2	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(2)	(1)	(1)		
Diamid	-> siehe: Hydrazin																														
Diaminoethan	-> siehe: Ethylendiamin																														
Diazan	-> siehe: Hydrazin																														
Dibenzylether	$C_{14}H_{14}O$	000103-50-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Dibenzylsebacat	$C_{24}H_{26}O_4$	??		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	(4)	4/4	0/0	(1)	(1)	(1)		Weichmacher
Dibromethan-1,2	$C_2H_4Br_2$	000106-93-4		T		(4)	(4)	(2)	(4)	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/2	4/4	(3)	4/4	0/0	(3)	1/0L	1/0L	0/0	
Dibromtetrafluormethan	$C_2Br_2F_4$	000124-73-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0		
Dibutylamin	$C_8H_{19}N$	000111-92-2		Xn	X	0/0	0/0	(2)	(3)	0/0	(3)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Dibutylether	$C_8H_{18}O$	000142-96-1	techn. rein	Xi	X	3/4	1/4	(2)	(3)	1/0	(4)	(1)	3/4	0/0	3/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Dibutylphthalat	$C_{16}H_{22}O_4$	000084-74-2	FR, 80°C	T		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	(1)	0	0	0	4/4	0	0	0	0	0/0	Weichmacher
Dibutylphthalat	$C_{16}H_{22}O_4$	000084-74-2		T		1/3	3/3	1/0	4/4	1/0	0/2	1/0	2/2	4/4	1/0	4/4	4/4	0/4	1/1	(1)	1/1	1/3	3/0	2/3	4/4	0/0	(1)	1/1	1/1	0/0	Weichmacher
Dibutylsebacat	$C_{18}H_{34}O_4$	000109-43-3	techn. rein	—		1/0	1/3	1/0	(3)	0/0	0/0	(2)	1/0	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Weichmacher
Dichlorbenzen, 1,2-	-> siehe: Dichlorbenzol, 1,2-																														
Dichlorbenzen, 1,4-	-> siehe: Dichlorbenzol, 1,4-																														
Dichlorbenzol, 1,2-	$C_6H_4Cl_2$	000095-50-1		Xn		3/3	3/4	(1)	4/4	0/0	3/4	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/3	(1)	1/1	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Dichlorbenzol, 1,4-	$C_6H_4Cl_2$	000106-46-7		Xn		2/3	3/4	1/0	4/4	0/0	2/3	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/3	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Dichlorbenzol, o-	-> siehe: Dichlorbenzol, 1,2-																														
Dichlorbenzol, p-	-> siehe: Dichlorbenzol, 1,4-																														
Dichlordifluormethan	CCl_2F_2	000075-71-8	techn. rein	N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0	
Dichlordifluormethan	CCl_2F_2	000075-71-8		N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0	
Dichlordiphenyltrichlorethan	-> siehe: DDT (Emulsion)																														
Dichloressigsäure	$C_2H_2Cl_2O_2$	000079-43-6	50 %	C		1/1	1/1	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1	
Dichloressigsäure	$C_2H_2Cl_2O_2$	000079-43-6	techn. rein	C		1/3	3/3	4/4	(4)	4/4	0/0	4/4	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1	
Dichloressigsäuremethylester	-> siehe: Methyldichloracetat																														
Dichlorethan, 1,2-	-> siehe: Ethylenchlorid																														
Dichlorethen, 1,1-	-> siehe: Vinylidenchlorid																														
Dichlorethylen	$C_2H_2Cl_2$	—	techn. rein	F+, Xn	X	4/4	4/4	3/0	(4)	4/4	(4)	4/4	3/0	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/0	1/1	4/4	3/4	4/4	0/0	(3)	1/1L	1/1L	0/0	Isomeres in der Quelle nicht angegeben
Dichlorethylen, 1,1-	-> siehe: Vinylidenchlorid																														
Dichlorfluormethan	$CHCl_2F$	000075-43-4	100 %	N		0/0	3/0	1/0	3/0	0/0	0/0	1/0	4/4	4/4	3/0	4/4	4/4	3/3	0/0	(3)	1/0	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Dichlor-hexafluorcyclobutan	$C_4Cl_2F_6$	000356-18-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	(3)	1/0	0/0	(3)	0/0	0/0		
Dichlorisopropylether	$C_6H_{12}Cl_2O$	—		(Xn)		(4)	(4)	(2)	(3)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		Isomeres in der Quelle nicht angegeben
Dichlormethan	CH_2Cl_2	000075-09-2		Xn		4/4	4/4	3/4	4/4	4/4	3/4	3/0	3/4	4/4	4/4	4/4	4/4	4/4	2/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]	1/1	[1] wasserfrei! Wenn durch Feuchtigkeit auch nur Spuren von Salzsäure (HCl) abgespaltet werden, besteht die Gefahr von Lochfraß, Spalt- und Spannungsrisskorrosion.
Dichlorpropan	$C_3H_6Cl_2$	—	100 %	F, T/Xn	X	0/0	0/0	(3)	-4	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(3)	0/0	0/0	0/0	Isomeres in der Quelle nicht angegeben
Dichlortetrafluorethan	$C_2Cl_2F_4$	000076-14-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Dicyclohexylamin (DCHA)	$C_{12}H_{23}N$	000101-83-7		C, Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Dicyclohexylphthalat	$C_{20}H_{26}O_4$	000084-61-7	techn. rein	(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	(3)	4/4	4/4	0/0	(1)	(1)	(1)		Weichmacher
Dieselkraftstoff	—	—		Xn, N		1/3	0/0	1/1	3/3	1/1	0/0	1/1	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	(1)	(1)	0/0	
Dieselöl	—	068334-30-5	100 %	(Xn)		1/3	1/4	1/1	3/3	1/1	0/0	1/1	1/3	3/4	0/0	1/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	(1)	(1)	0/0	
Diethanolamin (DEA)	$C_4H_{11}NO_2$	000111-42-2	100 %	Xi		0/0	1/0	(2)	(3)	0/0	0/0	(2)	1/2	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/3	3/0	(3)	4/4	0/0	1/1	(1)	(1)	0/0	
Diethylamin	$C_4H_{11}N$	000109-89-7	techn. rein	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/2	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Diethylbenzol	$C_{10}H_{14}$	000135-01-3		Xi		3/4	4/4	(1)	3/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Diethylenglycol	$C_4H_{10}O_3$	000111-46-6		T		1/1	1/1	3/0	2/3	0/0	1/1	(2)	1/1	2/2	2/2	3/4	0/0	1/1	1/1	1/1	1/1	(2)	1/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0	
Diethylenglycolether	—	—		(Xn)		1/1	1/1	3/0	3/4	0/0	1/1	(2)	1/1	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	3/0	(3)	3/3	0/0	(1)	(1)	(1)		
Diethylether	-> siehe: Ethylether																														
Diethylketon	$C_5H_{10}O$	000096-22-0		F		2/2	2/3	(3)	4/4	(4)	2/3	1/0	2/2	4/4	4/4	4/4	0/0	4/4	2/3	1/1	1/1	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	0/0	

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

							---------- Thermoplaste ----------		Fluor-Kunststoffe		--- Elastomere ---		------- Metalle -------			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Diethylmalonat	$C_7H_{12}O_4$	000105-53-3		Xi		1/1	1/1	(2)	3/4	0/0	1/2	(2)	1/1	4/4	3/3	2/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(4)	(3)	0/0	(1)	(1)	(1)		
Diethylmethan	-> siehe: Pentan																														
Diethylsebacat	$C_{14}H_{26}O_4$	000110-40-7		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		Weichmacher
Diethylsuccinat	-> siehe: Bernsteinsäurediethylester																														
Difluorchlorethan	$C_2H_3ClF_2$	000075-68-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluorethan	$C_2H_2F_2$	000075-37-6		(E), F+		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluormethan	CH_2F_2	000075-10-5		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluortetrachlorethan	$C_2Cl_4F_2$	000076-12-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0		
Diglycol	-> siehe: Diethylenglycol																														
Diglycolsäure	$C_4H_6O_5$	000110-99-6	wässrig	Xn		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/1	4/4	0/0	3/4	1/4	1/4	1/1	
Diglycolsäure	$C_4H_6O_5$	000110-99-6	30 %	Xn, Xi		1/1	1/1	(3)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/0	1/0	1/1	4/4	0/0	3/4	1/4	1/4	1/1	
Dihexylphthalat	-> siehe: Dicyclohexylphthalat																														
Dihydroxybenzol, 1,3-	-> siehe: Resorcin																														
Dihydroxybenzol, 1,4-	-> siehe: Hydrochinon																														
Dihydroxybernsteinsäure	-> siehe: Weinsäure																														
Dihydroxydiethylamin	-> siehe: Diethanolamin																														
Diisobutylen (DIB)	C_8H_{10}	025167-70-8		F	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	1/2	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Diisobutylketon	$C_9H_{18}O$	000108-83-8	techn. rein	Xi	X	1/4	1/3	(3)	(3)	(4)	(4)	1/0	1/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/3	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Diisooctylphthalat (DOP)	$C_{24}H_{38}O_4$	000117-81-7	techn. rein	Xn		4/4	4/4	1/0	4/4	1/0	1/0	(2)	4/4	4/4	1/0	4/4	4/4	0/0	0/0	1/1	1/0	(2)	3/0	2/3	4/4	0/0	(1)	(1)	(1)		Weichmacher
Diisopropylether	-> siehe: Isopropylether																														
Diisopropylketon	$C_7H_{14}O$	000565-80-0		F	X	0/0	0/0	(3)	(3)	(4)	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Dimethylamin	C_2H_7N	000124-40-3	techn. rein	F+, Xn	X	1/3	1/3	1/0	4/4	0/0	0/0	(2)	1/3	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	3/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Dimethylanilin	$C_8H_{11}N$	—		T		0/0	0/0	(3)	4/4	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	Isomeres in der Quelle nicht angegeben
Dimethylbenzol	-> siehe: Xylol																														
Dimethylcarbinol	-> siehe: Isopropanol																														
Dimethylether	C_2H_6O	000115-10-6	Gas	F+	X	0/0	3/0	1/0	(3)	1/0	0/0	(2)	4/4	4/4	0/0	3/0	4/4	0/0	0/0	0/0	1/0	(3)	3/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Dimethylformamid (DMF)	C_3H_7NO	000068-12-2		T, F	X	1/1	1/3	1	4/4	1/0	1/1	1/2	1/1	4/4	4/4	3/4	0/0	4/4	2/2	1/1	1/1	4/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Dimethylketon	-> siehe: Aceton																														
Dimethylpentanon-3, 2,4-	-> siehe: Diisopropylketon																														
Dimethylphthalat (DMP)	$C_{10}H_{10}O_4$	000131-11-3	100 %	(Xn)		4/4	1/3	(2)	4/4	0/0	0/0	(2)	2/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(2)	3/0	2/0	4/4	0/0	(1)	(1)	(1)	0/0	Weichmacher
Dimethylpropan	-> siehe: Pentan																														
Dimethylsulfoxid (DMSO)	C_2H_6SO	000067-68-5		Xi		1/1	1/1	(2)	4/4	0/0	1/1	1/0	1/1	1/2	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(3)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		
Dinatriumhydrogenphosphat	-> siehe: Dinatriumphosphat																														
Dinatriumphosphat	Na_2HPO_4	007558-79-4		(Xi)		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	(1)	1/1	1/1	0/0	
Dinatriumsulfat	-> siehe: Natriumsulfat																														
Dinonylphthalat (DNP)	$C_{26}H_{42}O_4$	000084-76-4	techn. rein	Xn		3/0	0/0	(2)	3/0	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		Weichmacher
Dioctyladipat	$C_{22}H_{42}O_4$	000103-23-1		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		Weichmacher
Dioctylphthalat	-> siehe: Diisooctylphthalat																														
Dioctylsebacat	$C_{26}H_{50}O_4$	002432-87-3		—		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		Weichmacher
Dioxan	$C_4H_8O_2$	000123-91-1		F, Xn	X	2/2	2/3	1/0	4/4	1/0	2/3	1/2	3/3	4/4	2/3	3/4	4/4	4/4	1/3	1/1	1/1	3/3	2/0	4/4	4/4	0/0	1/1	1/0	1/0	0/0	
Dioxan, 1,4-	-> siehe: Dioxan																														
Dipenten	-> siehe: Limonen, DL-																														
Dipentylphthalat	-> siehe: Phthalsäureamylester																														
Diphenylamin	$C_{12}H_{11}N$	000122-39-4		T		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	0/0	
Diphenylenimin	-> siehe: Carbazol																														
Diphenylether	$C_{12}H_{10}O$	000101-84-8		Xn/Xi		0/0	1/0	3/0	(3)	(4)	0/0	1/1	4/4	4/4	0/0	0/0	4/4	4/4	0/0	(1)	1/0	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Diphenylmethandiisocyanat (MDI)	-> siehe: Desmodur 44																														
Diphenyloxid	-> siehe: Diphenylether																														
Diphosphorpentoxid	-> siehe: Phosphorpentoxid																														
Diphyl	—	008004-13-5		?		0/0	0/0	1/1	(3)	4/4	0/0	1/1	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)		Gemisch aus Diphenyl und Diphenylether; Bayer
Dipropylenglycol	$C_6H_{14}O_3$	025265-71-8		Xi		1/1	1/1	(2)	2/3	0/0	1/1	1/0	1/1	1/1	2/2	2/3	0/0	0/0	1/1	1/1	(1)	(2)	4/4	3/0	3/3	0/0	(1)	(1)	(1)		
Dipropylketon	$C_7H_{14}O$	000123-19-3		—	X	0/0	0/0	(3)	(4)	(4)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Dipropylmethan, n-	-> siehe: Heptan, n-																														
Dischwefeldichlorid	-> siehe: Schwefelchlorid																														

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste														Fluor-Kunststoffe				Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZENTRATION	GEFAHRENHINWEIS	ENTZÜNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMERKUNG
Distickstofftetroxid	-> siehe: Stickstofftetroxid																														
Disulfit	-> siehe: Natriumdisulfit																														
Divinylensulfid	-> siehe: Thiophen																														
Dodecanol	-> siehe: Laurylalkohol																														
Dodecylalkohol	-> siehe: Laurylalkohol																														
Dodecylchlorid	-> siehe: Laurylchlorid																														
Dolcymen	-> siehe: Cymol, p-																														
Eau de Labarraque	-> siehe: Natriumhypochlorit																														
Edetinsäure	-> siehe: Ethylendiamintetraessigsäure																														
Eisen-(II)-ammoniumsulfat	-> siehe: Ammoniumeisen-(II)-sulfat																														
Eisen-(II)-chlorid	$FeCl_2$	007758-94-3	gesättigt	Xn		1/1	1/1	3/0	1/0	(2)	1/0	(3)	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	(1)	0/0	4/4	(2)	1/1	1/1	
Eisen-(II)-sulfat	$FeSO_4$	007720-78-7	gesättigt	(Xn)		1/1	1/1	(2)	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1	
Eisen-(II)-sulfat	$FeSO_4$	007720-78-7	wässrig	(Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Eisen-(II)-sulfat	$FeSO_4$	007720-78-7		Xn		1/1	1/1	(2)	1/0	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/0	(1)	0/0	4/4	1/1	1/1	1/1	
Eisen-(III)-chlorid	$FeCl_3$	007705-08-0	gesättigt	Xn		1/1	1/1	3/0	1/0	0/0	1/0	4/4	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	4/4	4/4	4/4	1/1	
Eisen-(III)-nitrat	-> siehe: Eisennitrat																														
Eisen-(III)-sulfat	$Fe_2(SO_4)_3$	010028-22-5	gesättigt	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1	
Eisenalaun	-> siehe: Ammoniumeisen-(III)-sulfat																														
Eisenammoniumalaun	-> siehe: Ammoniumeisen-(III)-sulfat																														
Eisennitrat	$Fe(NO_3)_3$	010421-48-4	wässrig	(O, Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Eisennitrat	$Fe(NO_3)_3$	010421-48-4	gesättigt	O, Xn		1/1	1/1	1/0	1/0	0/0	1/0	(3)	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Eisenvitriol	-> siehe: Eisen-(II)-sulfat																														
Eisessig	-> siehe: Essigsäure																														
Elaol	-> siehe: Dibutylphthalat																														
Emulgatoren	—	—		?		0/0	0/0	(2)	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(3)	0/0	0/0	K	K		
Entwicklerflüssigkeiten	—	—		?		1/1	1/1	4/4	1/0	1/0	0/0	1/0	1/1	0/0	1/0	1/1	1/0	0/0	0/0	0/0	1/1	(1)	2/0	1/0	3/3	0/0	1/1	1/0	1/0	0/0	
Ephetin	—	—	10% in Was	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Epichlorhydrin	C_3H_5ClO	000106-89-8	100 %	F, T	X	1/0	1/0	4/4	(4)	0/0	(4)	1/0	2/2	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(3)	3/0	4/4	4/4	0/0	(3)	0/0	0/0	0/0	
Epoxypropan	-> siehe: Propylenoxid																														
Epsom-Salz	-> siehe: Magnesiumsulfat																														
Erdgas	—	—		F+	X	0/0	0/0	01/0	1/0	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	0/0	hauptsächlich Methan
Erdnußöl	—	008002-03-7		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Erdöl	—	008002-05-9		(Xn)		0/0	0/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/3	0/0	(1)	(1)	(1)	0/0	Kerosin, Lampenöl
Essig	$C_2H_4O_2$	000064-19-7		(Xi)		1/1	1/3	4/4	1/2	1/1	1/0	1/3	1/1	1/0	1/0	1/0	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/2	1/1	Weinessig, Essigsäure
Essigester	-> siehe: Ethylacetat																														
Essigsäure	$C_2H_4O_2$	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1	1/1	
Essigsäure	$C_2H_4O_2$	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Essigsäure	$C_2H_4O_2$	000064-19-7	90%	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Essigsäure	$C_2H_4O_2$	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1	1/1	
Essigsäure	$C_2H_4O_2$	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1	1/1	
Essigsäure Silbersalz	-> siehe: Silberacetat																														
Essigsaure Tonerde	$C_4H_7AlO_5 \times H_2O$	000142-03-0	gesättigt	Xi		1/1	1/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1		
Essigsäureallylester	-> siehe: Allylacetat																														
Essigsäureamid	-> siehe: Acetamid																														
Essigsäureanhydrid	$C_4H_6O_3$	000108-24-7	techn. rein	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1	1/1	
Essigsäurebenzylester	-> siehe: Benzylacetat																														
Essigsäurebutylester	$C_6H_{12}O_2$	000123-86-4	100 %	—	X	2/2	2/3	1/0	4/4	3/0	3/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	3/0	4/4	4/4	0/0	1/1	(1)	(1)	4/4	
Essigsäurechlorid	-> siehe: Acetylchlorid																														
Essigsäureethylester	-> siehe: Ethylacetat																														
Essigsäureisobutylester	-> siehe: Isobutylacetat																														
Essigsäureisopropylester	-> siehe: Isopropylacetat																														
Essigsäuremethylester	$C_3H_6O_2$	000079-20-9	techn. rein	F	X	1/0	1/1	1/0	4/4	3/0	(4)	2/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Essigsäure-n-amylester	-> siehe: Amylacetat, n-																														
Essigsäurepentylester	-> siehe: Amylacetat, n-																														
Essigsäurepropylester	-> siehe: Propylacetat																														
Essigsäurevinylester	-> siehe: Vinylacetat																														

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste														Fluor-Kunststoffe				Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Ethanal	-> siehe: Acetaldehyd																														
Ethancarbonsäure	-> siehe: Propionsäure																														
Ethandiamin	-> siehe: Ethylendiamin																														
Ethandicarbonsäure	-> siehe: Bernsteinsäure																														
Ethandiol	-> siehe: Ethylenglycol																														
Ethandisäure	-> siehe: Oxalsäure																														
Ethanol	C_2H_6O	000064-17-5	40 %	—	X	1/1	1/2	1/0	1/2	1/1	1/2	1/2	1/1	2/3	1/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Ethanol	C_2H_6O	000064-17-5	50 %	—	X	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	
Ethanol	C_2H_6O	000064-17-5	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	
Ethanolamin	C_2H_7NO	000141-43-5		Xn/Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/2	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Ethansäure	-> siehe: Essigsäure																														
Ethanthiol	C_2H_6S	000075-08-1		F, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ethen	-> siehe: Ethylen																														
Ether	-> siehe: Ethylether																														
Ethin	-> siehe: Acetylen																														
Ethinylcarbiol	-> siehe: Propargylalkohol																														
Ethoxyacetanilid, 4-	-> siehe: Phenacetin																														
Ethoxyethanol	-> siehe: Ethylglycol																														
Ethoxyethylacetat, 2-	-> siehe: Ethylenglycolmonoethyletheracetat																														
Ethyl(hydroxymethyl)-propandiol	-> siehe: Trimethylolpropan																														
Ethylacetat	$C_4H_8O_2$	000141-78-6	100 %	F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/1	1/3	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	3/3	3/0	4/4	4/4	0/0	1/1	(1)	(1)	1/0	
Ethylacrylat	$C_5H_8O_2$	000140-88-5	100 %	F, Xn	X	4/4	4/4	1/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	3/0	4/4	4/4	4/4	0/0	(1)	(1)	(1)	1/0	
Ethylalkohol	-> siehe: Ethanol																														
Ethylbenzen	-> siehe: Ethylbenzol																														
Ethylbenzoat	-> siehe: Benzoesäureethylester																														
Ethylbenzol	C_8H_{10}	000100-41-4		F, Xn	X	2/3	3/4	(2)	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	1/1	4/4	(2)	4/4	0/0	(1)	(1)	(1)	0/0	
Ethylbutyrat	$C_6H_{12}O_2$	000105-54-4		F	X	2/3	2/4	(2)	4/4	0/0	3/4	(2)	2/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethylcarbinol	-> siehe: Propanol																														
Ethyl-Cellosolve	-> siehe: Ethylglycol																														
Ethylchloracetat	$C_4H_7ClO_2$	000105-39-5	techn. rein	T/Xi		1/1	1/1	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/4	3/4	0/0	0/0	(1)	1/1	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Ethylchlorid	-> siehe: Chlorethan																														
Ethylcyanacetat	$C_5H_7NO_2$	000105-56-6		Xn/Xi		1/1	1/1	0/0	3/4	0/0	1/1	(2)	1/1	2/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Ethylen	C_2H_4	000074-85-1		F+	X	0/0	0/0	1/0	(2)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	(3)	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Ethylen(di)bromid	-> siehe: Dibromethan-1,2																														
Ethylen(di)chlorid	-> siehe: Dichlorethan-1,2																														
Ethylenchlorhydrin	-> siehe: Chlorethanol																														
Ethylenchlorid	$C_2H_4Cl_2$	—		F, T	X	3/3	2/4	3/0	4/4	4/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/3	1/1L	1/1L	0/0	Isomeres in der Quelle nicht angegeben
Ethylendiamin	$C_2H_8N_2$	000107-15-3	techn. rein	C, Xn	X	1/1	1/3	1/0	(3)	0/0	1/0	1/0	1/1	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/4	1/0	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Ethylendiamintetraessigsäure (EDTA)	$C_{10}H_{16}N_2O_8$	000060-00-4		Xi		1/1	1/1	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(3)	0/0	0/0	0/0	
Ethylendichlorid	-> siehe: Ethylenchlorid																														
Ethylendinitrilotetraessigsäure	-> siehe: Ethylendiamintetraessigsäure																														
Ethylenglycol	$C_2H_6O_2$	000107-21-1		Xn		1/1	1/1	3/3	2/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	1/1	
Ethylenglycolethylether	-> siehe: Ethylglycol																														
Ethylenglycolmonobutylether	-> siehe: Butylglycol																														
Ethylenglycolmonoethylether	-> siehe: Ethylglycol																														
Ethylenglycolmonoethyletheracetat	$C_6H_{12}O_3$	000115-15-9		Xn	X	1/1	1/2	0/0	3/4	0/0	1/2	(2)	1/2	4/4	4/4	3/4	0/0	0/0	1/2	1/1	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Ethylenglycolmonomethylether	-> siehe: Methylglycol																														
Ethylenoxid	C_2H_4O	000075-21-8		F+, T	X	2/3	3/3	3/0	3/4	1/0	3/4	1/0	3/3	4/4	1/1	3/4	0/0	0/0	1/1	1/1	(1)	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Ethylentetrachlorid	-> siehe: Perchlorethylen																														
Ethylentrichlorid	-> siehe: Trichlorethylen																														
Ethylethanamin, N-	-> siehe: Diethylamin																														
Ethylether	$C_4H_{10}O$	000060-29-7	techn. rein	F+, Xn	X	3/4	4/4	1/1	4/4	1/0	4/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Ethylformiat	$C_3H_6O_2$	000109-94-4		F	X	0/0	0/0	0/0	(4)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethylglycol	$C_4H_{10}O_2$	000110-80-5	100 %	T	X	0/0	4/4	(3)	(2)	0/0	0/0	1/0	2/4	4/4	1/0	4/4	4/4	4/4	0/0	1/1	1/0	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Ethylglycolacetat	-> siehe: Ethylenglycolmonoethyletheracetat																														

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste														Fluor-Kunststoffe			Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZENTRATION	GEFAHRENHINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMERKUNG
Ethylhexanol-1	$C_8H_{18}O$	000104-76-7		Xn/Xi		0/0	1/3	(2)	(2)	(1)	1/0	1/0	1/0	3/0	0/0	1/0	4/4	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	
Ethyllactat	$C_5H_{10}O_3$	000097-64-3		—	X	1/1	1/1	(2)	3/4	0/0	1/1	(2)	1/1	3/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	3/0	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Ethylmalonat	-> siehe: Diethylmalonat																													
Ethylmercaptan	-> siehe: Ethanthiol																													
Ethylmethylketon	-> siehe: Methylethylketon																													
Ethylsilicat	-> siehe: Tetraethylorthosilicat																													
Eukalyptusöl	—	008000-48-8		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Exsikkatorfett	—	—		—		0/0	1/3	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(2)	(2)	0/0	(1)	(1)	(1)	0/0	
Ferrichlorid	-> siehe: Eisen-(III)-chlorid																													
Ferricyankalium	$C_6FeK_3N_6$	013746-66-2	jede	Xn		1/1	1/1	1/0	(1)	(1)	0/0	2/0	1/1	1/1	0/0	1/3	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1	1/1	
Ferrochlorid	-> siehe: Eisen-(II)-chlorid																													
Ferrocyankalium	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	gesättigt	—		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(1)	1/1	1/1		
Ferrocyankalium	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	verdünnt	—		1/0	1/1	1/0	(1)	(1)	0/0	2/0	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1		
Fett, mineralisch	—	—		(—)		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	(1)	1/0	0/0	(1)	1/1	1/1		
Fett, pflanzlich	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fett, tierisch	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fettalkoholsulfonate	—	—	wässrig	(Xn, Xi)		1/1	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	1/1	0/0	3/4	1/0	1/0	0/0	Fettalkoholsulfate, Netzmittel/Tenside
Fette, Speiseöle	—	—		—		0/0	1/0	1/0	1/0	1/0	1/0	1/1	3/0	0/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Fettsäure C16	-> siehe: Palmitinsäure																													
Fichtennadelöl	—	008008-80-8		?		1/2	2/4	(2)	2/3	0/0	2/3	(2)	1/2	4/4	3/3	3/4	0/0	3/4	1/2	1/1	(1)	(2)	4/4	1/0	3/3	0/0	(1)	(1)	(1)		Pinus sylvestris
Fischtran	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/4	1/0	1/0	0/0	(1)	(1)	(1)		
Fixiersalz	-> siehe: Natriumthiosulfat																													
Flugmotorenkraftstoffe (JP)	—	—		(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	1/0	1/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	1/0	1/0	0/0	(1)	(1)	(1)		
Fluid 101, 100°C	—	—		?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	3	0	0	0	0		Bremsflüssigkeit, Basis Polyglykole
Fluor	F_2	007782-41-4		O, T+, C+		4/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	4/4	4/4	3/0	4/4	0/0	4/4	(4)	(4)	0/0	
Fluorammonium	-> siehe: Ammoniumfluorid																													
Fluorbenzol	C_6H_5F	000462-06-6		F, (Xn)	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0		
Fluorchloralkane (FCKW)	—	—		N		0/0	0/0	(2)	(3)	0/0	0/0	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(3)	(3)	0/0	(3)	0/0	(3)	0/0	0/0		Beständigkeit je nach Typ unterschiedlich
Fluoride	—	—		T		1/1	1/1	(2)	1/1	(2)	1/1	(1)	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	(1)	0/0	0/0	K	K		
Fluorkalium	-> siehe: Kaliumfluorid																													
Fluorkieselsäure	-> siehe: Kieselfluorwasserstoffsäure																													
Fluorkohlenwasserstoffe (FKW)	—	—		?		0/0	0/4	(2)	(3)	(2)	0/0	(2)	(3)	4/4	0/0	0/0	0/0	0/4	1/1	0/0	1/1	(3)	(3)	(3)	(3)	0/0	(1)	0/0	0/0		Beständigkeit je nach Typ unterschiedlich
Fluorsiliziumsäure	-> siehe: Kieselfluorwasserstoffsäure																													
Fluortrichlormethan	-> siehe: Trichlorfluormethan																													
Fluorwasserstoff	HF	007664-39-3	wasserfrei	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)		Flusssäure, wasserfrei
Fluorwasserstofflösung	-> siehe: Flusssäure																													
Fluorwasserstoffsäure	-> siehe: Flusssäure																													
Flüssigseifen	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(2)	(2)	0/0	(3)	0/0	0/0		
Flusssäure	HF	007664-39-3	4 %	T, C		1/1	1/2	4/4	2/3	4/4	1/2	4/4	1/2	2/3	2/3	2/3	0/0	0/0	1/1	1/1	1/1	1/1	(3)	1/3	(2)	0/0	4/4	0/0	0/0	?	
Flusssäure	HF	007664-39-3	50 %	T+, C		1/1	1/1	4/4	4/4	4/4	1/1	4/4	1/1	4/4	3/4	2/3	2/0	3/3	1/1	1/1	1/1	1/1	3/4	1/3	3/4	0/0	4/4	4/4	4/4	?	
Flusssäure	HF	007664-39-3	70 %	T+, C		0/0	1/3	4/4	4/4	4/4	0/0	4/4	1/3	4/4	4/4	1/4	3/0	0/0	0/0	(1)	1/1	1/1	3/4	(3)	4/4	0/0	4/4	4/4	4/4	?	
Flusssäure	HF	007664-39-3	100 %	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)	?	
Flusssäure, wasserfrei	-> siehe: Fluorwasserstoff																													
Formaldehydlösung	CH_2O	000050-00-0	10 %	Xn		1/1	1/1	3/3	1/2	1/0	1/2	1/2	1/1	3/4	2/3	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/0	3/0	(2)	0/0	1/1	1/1	1/1	1/1	
Formaldehydlösung	CH_2O	000050-00-0	30 %	T		1/1	1/1	3/3	1/2	1/0	0/0	1/2	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	1/1	1/1	
Formaldehydlösung	CH_2O	000050-00-0	40 %	T		1/2	2/3	1/3	1/2	1/0	1/2	1/2	1/2	4/4	2/3	2/3	3/3	0/4	1/1	1/1	1/1	1/1	1/0	3/0	(3)	0/0	1/1	1/1	1/1	1/1	
Formalin	-> siehe: Formaldehydlösung																													
Formamid	CH_3NO	000075-12-7	techn. rein	T/Xi		1/1	1/1	1/0	(3)	0/0	0/0	1/0	1/1	1/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	3/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	
Formin	-> siehe: Hexamethylentetramin																													
Formylsäure	-> siehe: Ameisensäure																													
Fotoemulsionen	—	—		?		1/0	0/0	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(1)	0/0	(2)	0/0	0/0		
Fotoentwickler	—	—		?		1/3	1/1	4/4	(2)	1/0	0/0	1/3	1/2	0/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Fotofixierbäder	—	—		?		1/0	1/1	1/0	(2)	0/0	0/0	1/0	1/1	0/0	0/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/0	1/0		

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

							Thermoplaste												Fluor-Kunststoffe				Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Freon 11	-> siehe: Trichlorfluormethan																													
Freon 112	-> siehe: Difluortetrachlorethan																													
Freon 113	-> siehe: Trichlortrifluorethan																													
Freon 114	-> siehe: Dichlortetrafluorethan																													
Freon 114 B2	-> siehe: Dibromtetrafluormethan																													
Freon 115	-> siehe: Chlorpentafluorethan																													
Freon 12	-> siehe: Dichlordifluormethan																													
Freon 13	-> siehe: Chlortrifluormethan																													
Freon 13 B1	-> siehe: Bromtrifluormethan																													
Freon 14	-> siehe: Tetrafluormethan																													
Freon 142b	-> siehe: Difluorchlorethan																													
Freon 152a	-> siehe: Difluorethan																													
Freon 21	-> siehe: Dichlorfluormethan																													
Freon 218	-> siehe: Perfluorpropan																													
Freon 22	-> siehe: Chlordifluormethan																													
Freon 31	-> siehe: Chlorfluormethan																													
Freon 32	-> siehe: Difluormethan																													
Freon C 318	-> siehe: Octafluor-cyclobutan																													
Freon C316	-> siehe: Dichlor-hexafluorcyclobutan																													
Frigen 12	-> siehe: Dichlordifluormethan																													
Frigen 21	-> siehe: Dichlorfluormethan																													
Frigen 22	-> siehe: Chlordifluormethan																													
Frostschutzmittel (KFZ)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1	1/1	Glykol-Wasser-Mischungen
Fruchtsäfte	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(2)	1/1	1/1	1/1	
Fruchtzucker	-> siehe: Fructose																													
Fructose	$C_6H_{12}O_6$	000057-48-7	jede	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Furan	C_4H_4O	000110-00-9		F+, T+	X	0/0	0/0	(3)	4/4	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Furanal	-> siehe: Furfurol																													
Furancarbinol, 2-	-> siehe: Furfurylalkohol																													
Furanmethanol, 2-	-> siehe: Furfurylalkohol																													
Furfural	-> siehe: Furfurol																													
Furfuralkohol	-> siehe: Furfurylalkohol																													
Furfuran	-> siehe: Furan																													
Furfurol	$C_5H_4O_2$	000098-01-1		T		1/3	3/4	3/3	(3)	1/0	0/0	2/0	4/4	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	1/2	3/0	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Furfurylalkohol	$C_5H_6O_2$	000098-00-0	techn. rein	Xn		1/1	1/3	1/0	(3)	1/0	0/0	1/0	1/3	0/0	4/4	4/4	4/4	3/4	0/0	(1)	1/1	1/3	3/0	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Furylaldehyd, 2-	-> siehe: Furfurol																													
Furylmethanal, 2-	-> siehe: Furfurol																													
Gallotannin	-> siehe: Tannin																													
Gallussäure	$C_7H_6O_5 \times H_2O$	000149-91-7		Xi		1/1	1/1	1/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/4	3/0	1/0	3/0	0/0	1/0	1/1	1/1	1/1	
Gärungsamylalkohol	-> siehe: Isoamylalkohol																													
Gärungsmaische	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(1)	1/0	4/4	0/0	(2)	(1)	(1)	0/0	
Gasöl	—	—		(Xn)		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Gasoline	—	008006-61-9		(F, Xn)	X	0/0	0/0	(1)	3/4	(2)	0/0	1/2	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/0	0/0	1/1	(1)	(1)		
Gaswasser	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(2)	0/0	(2)	0/0	0/0		
Gelatine	—	009000-70-8	jede	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Genantin	—	—		Xn		0/0	0/0	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		Frostschutzmittel, Basis Glykol; Clariant
Gerbeextrakte, pflanzlich	—	—	techn. üblich	?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Gerbextrakte	—	—		?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Gerbsäure	-> siehe: Tannin																													
Getriebeöl, EP (Hypoid), 110°C	—	—		?		0	0	1	1	1	0	4	(3)	0	0	0	0	0	0	0	(2)	0	4/4	0	4/4	0	(1)	1	1		
Gips	-> siehe: Calciumsulfat																													
Glaubersalz	-> siehe: Natriumsulfat																													
Glucarsäure	-> siehe: Zuckersäure																													
Glucose	$C_6H_{12}O_6$	000050-99-7	jede	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Glucosesirup	-> siehe: Stärkesirup																													

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste														Fluor-Kunststoffe			Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Glycerin	$C_3H_8O_3$	000056-81-5	jede	Xi		1/1	1/1	1/0	3/3	1/0	1/1	1/0	1/1	1/1	1/1	1/1	2/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Glycerintrinitrat	-> siehe: Nitroglycerin																														
Glycin	-> siehe: Aminoessigsäure																														
Glycol	-> siehe: Ethylenglycol																														
Glycoldinitrat	-> siehe: Nitroglycol																														
Glycolsäure	$C_2H_4O_3$	000079-14-1	37 %	Xn		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	2/0	1/0	0/0	1/0	1/3	1/3	1/1	
Glycolsäure	$C_2H_4O_3$	000079-14-1	70 %	C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(2)	1/0	3/0	(2)	0/0	(2)	1/3	1/3	1/1	
Glykokoll	-> siehe: Aminoessigsäure																														
Glykolchlorhydrin	-> siehe: Chlorethanol																														
Glysantin	—	—		Xn		1/1	1/1	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		Frostschutzmittel, Basis Glykol; BASF
Glyzerintriacetat	-> siehe: Triacetin																														
Grubengas	—	—		F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		hauptsächlich Methan
Harnsäure	$C_5H_4N_4O_3$	000069-93-2		Xi		1/1	1/1	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	4/4	1/1	1/1	0/0	
Harnstoff	CH_4N_2O	000057-13-6	wässrig	Xi		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, Carbamid u.a.
Harnstoff	CH_4N_2O	000057-13-6		Xi		1/1	1/1	1/0	1/1	1/0	1/2	1/1	1/1	1/2	3/3	2/4	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, Carbamid u.a.
HD-Öl Motorenöl, aromatenfrei	—	—		?		1/0	1/3	1/0	1/1	1/1	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	(1)	3/3	0/0	1/1	1/1	1/1		
Hefe	—	—	jede	—		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	(1)	(1)		
Heizöl	—	—		Xn		3/3	3/4	1/0	3/3	1/0	2/3	1/1	1/3	3/4	1/2	1/1	3/3	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Helium	He	007440-59-7		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	1/0	1/0	1/0	0/0	1/1	1/1	1/1		
Hendecanol	-> siehe: Undecylalkohol																														
Henkel-P3-Lösung	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/0	0/0	0/0	1/1	1/1		Reinigungsmittel
Heptan, n-	C_7H_{16}	000142-82-5		F, Xn	X	2/3	3/4	1/0	1/2	1/0	3/3	1/2	2/4	4/4	1/2	2/3	4/4	1/0	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Heptanol, 1-	$C_7H_{16}O$	000111-70-6		Xn		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	(1)	(1)	(1)		
Heptanon	$C_7H_{14}O$	—		(Xn)	X	0/0	0/0	(3)	(4)	(4)	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(4)	(4)	4/4	0/0	(1)	(1)	(1)		Isomeres in der Quelle nicht angegeben
Heptanon-4	-> siehe: Dipropylketon																														
Heptylalkohol	-> siehe: Heptanol, 1-																														
Hexachlorbenzol (HCB)	C_6Cl_6	000118-74-1		T		0/0	0/0	(3)	(4)	0/0	(4)	1/0	(3)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(2)	0/0	4/4	(3)	4/4	0/0	(1)	0/0	0/0		
Hexachlorbutadien (HCBD)	C_4Cl_6	000087-68-3		T		0/0	0/0	(3)	4/4	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexachlorcyclohexan (HCH)	$C_6H_6Cl_6$	000319-84-6		T		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexadecanol	-> siehe: Cetylalkohol																														
Hexadecansäure	-> siehe: Palmitinsäure																														
Hexadecylalkohol	-> siehe: Cetylalkohol																														
Hexahydrobenzol	-> siehe: Cyclohexan																														
Hexahydrophenol	-> siehe: Cyclohexanol																														
Hexahydropyridin	-> siehe: Piperidin																														
Hexahydrotoluol	-> siehe: Methylcyclohexan																														
Hexaldehyd	-> siehe: Hexanal																														
Hexamethylentetramin	$C_6H_{12}N_4$	000100-97-0		F, Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	1/1	1/1	0/0	
Hexamin	-> siehe: Hexamethylentetramin																														
Hexan, n-	C_6H_{14}	000110-54-3		F, Xn	X	2/3	4/4	1/0	(2)	1/0	3/4	1/1	2/3	4/4	1/2	2/4	4/4	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Hexanal	$C_6H_{12}O$	000066-25-1		F, Xi	X	0/0	0/0	0/0	(4)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Hexandisäure	-> siehe: Adipinsäure																														
Hexanol, (1-)	$C_6H_{14}O$	000111-27-3		Xn		1/0	1/0	(2)	(2)	(1)	0/0	(1)	1/2	0/0	3/0	1/0	3/0	1/3	0/0	(1)	1/0	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Hexanon-2	-> siehe: Methylbutylketon																														
Hexantriol	$C_6H_{14}O_3$	—	100 %	?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	1/1	3/3	1/1	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	0/0	Isomeres in der Quelle nicht angegeben
Hexen, 1-	C_6H_{12}	000592-41-6		F, Xn	X	0/0	0/0	1/0	(2)	(1)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Hexylaldehyd	-> siehe: Hexanal																														
Hexylalkohol	-> siehe: Hexanol, (1-)																														
Hexylen	-> siehe: Hexen, 1-																														
Hirschhornsalz	-> siehe: Ammoniumcarbonat																														
Holzgeist	-> siehe: Methanol																														
Holzöl	—	008001-20-5		—		0/0	0/0	(1)	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	1/1	(1)	(1)		
Holzteeröl	-> siehe: Kreosot																														

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

							Thermoplaste												Fluor-Kunststoffe				Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Honig	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	0/0	(1)	(1)	(1)	0/0	
Hydrargillit	-> siehe: Aluminiumhydroxid																													
Hydraulikflüssigkeiten, HFA	—	—	50°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulikflüssigkeiten, HFB	—	—	50°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulikflüssigkeiten, HFC	—	—	60°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	0	0	1	0	(2)	0	0		
Hydraulikflüssigkeiten, HFD-R	—	—	100°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulikflüssigkeiten, HFD-S	—	—	100°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydrauliköle (Mineralölbasis)	—	—		?		0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	(1)	1/0	0/0	1/1	1/1	1/1		
Hydrazin	N_2H_4	000302-01-2	10 %	T	X	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	1/1	
Hydrazinhydrat	N_2H_6O	010217-52-4	wässrig	(T, C)	(X)	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	0/0	
Hydraziniumhydroxid	-> siehe: Hydrazinhydrat																													
Hydrazinobenzol	-> siehe: Phenylhydrazin																													
Hydrochinon	$C_6H_6O_2$	000123-31-9	gesättigt	Xn		0/0	1/3	4/4	(3)	1/0	0/0	(3)	1/0	4/4	0/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	4/4	4/4	0/0	(1)	1/0	1/0	0/0	
Hydrosulfit	-> siehe: Natriumdithionit																													
Hydroxy-4-methyl-2-pentanon, 4-	-> siehe: Diacetonalkohol																													
Hydroxybenzaldehyd, 2-	-> siehe: Salicylaldehyd																													
Hydroxybenzoesäure, 2-	-> siehe: Salicylsäure																													
Hydroxybenzol	-> siehe: Phenol																													
Hydroxybenzolcarbonsäure, 2-	-> siehe: Salicylsäure																													
Hydroxyessigsäure	-> siehe: Glycolsäure																													
Hydroxylaminsulfat	-> siehe: Hydroxylammoniumsulfat																													
Hydroxylammoniumsulfat	$H_8N_2SO_6$	010039-54-0	12 %	Xn		1/1	1/1	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	1/1	
Hydroxylammoniumsulfat	$H_8N_2SO_6$	010039-54-0	jede	Xn		1/1	0/0	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	1/1	
Hydroxymethoxybutan	-> siehe: Methoxybutanol																													
Hydroxymethylfuran, 2-	-> siehe: Furfurylalkohol																													
Hydroxymethylfurfural, 5-	-> siehe: Oxymethylfurfurol, 5-																													
Hydroxymethyltetrahydrofuran, 2-	-> siehe: Tetrahydrofurfurylalkohol																													
Hydroxypropan	-> siehe: Propanol																													
Hydroxypropan, 2-	-> siehe: Isopropanol																													
Hydroxypropionsäure, 2-	-> siehe: Milchsäure																													
Hydroxypropionsäure-ethylester, 2-	-> siehe: Ethyllactat																													
Hydroxytoluol	-> siehe: Kresol (-Gemische)																													
Iminodiethanol	-> siehe: Diethanolamin																													
Ingwer	—	—	gemahlen	?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Isoamylalkohol	$C_5H_{12}O$	000123-51-3		Xn	X	0/0	0/0	(2)	3/0	1/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	1/3	0/0	(1)	!/1	1/1	3/0	2/4	3/3	0/0	(1)	(1)	(1)		
Isobutanol	$C_4H_{10}O$	000078-83-1		Xn	X	1/1	1/1	(2)	1/2	(2)	1/2	1/0	1/1	2/2	1/2	1/2	0/0	3/4	1/1	1/1	(1)	1/1	1/0	1/0	3/4	0/0	1/0	(1)	(1)	0/0	
Isobutylacetat	$C_6H_{12}O_2$	000110-19-0		F	X	0/0	0/0	(2)	(4)	0/0	(4)	1/0	(3)	4/4	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Isobutylalkohol	-> siehe: Isobutanol																													
Isobutylketon	-> siehe: Diisobutylketon																													
Isobutylmethylketon	$C_6H_{12}O$	000108-10-1		F	X	1/2	2/3	1/0	4/4	(4)	3/3	(2)	2/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Isobutyltrimethylmethan	-> siehe: Isooctan																													
Isooctan	C_8H_{18}	000540-84-1	techn. rein	F, Xn	X	1/3	1/3	1/0	(2)	1/0	(4)	1/0	1/3	3/4	1/0	1/0	4/4	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Isooctanol	-> siehe: Ethylhexanol-1																													
Isooctylalkohol	-> siehe: Ethylhexanol-1																													
Isopropanol	C_3H_8O	000067-63-0	techn. rein	F	X	1/1	1/1	1/0	1/2	1/0	1/2	1/0	1/1	2/2	1/2	1/2	4/4	1/4	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	(2)	(1)	(1)	0/0	
Isopropyl-4-methylbenzol, 1-	-> siehe: Cymol, p-																													
Isopropyl-5-methylcyclohexanol, 2-	-> siehe: Menthol																													
Isopropyl-5-methylphenol, 2-	-> siehe: Thymol																													
Isopropylacetat	$C_5H_{10}O_2$	000108-21-4		F, Xi	X	1/2	2/3	1/0	4/4	(3)	2/3	1/0	2/3	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/1	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Isopropylaceton	-> siehe: Isobutylmethylketon																													
Isopropylalkohol	-> siehe: Isopropanol																													
Isopropylbenzen	-> siehe: Cumol																													
Isopropylbenzol	-> siehe: Cumol																													
Isopropylchlorid	C_3H_7Cl	000075-29-6		F, Xn	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Isopropylether	$C_6H_{14}O$	000108-20-3	techn. rein	F	X	3/4	3/4	4/4	(4)	1/0	(4)	(1)	3/4	4/4	1/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Isopropylidenaceton	-> siehe: Mesityloxid																													

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste														Fluor-Kunststoffe			Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Isopropylmethylketon	$C_5H_{10}O$	000563-80-4		F	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Jasminaldehyd	-> siehe: Amylzimtaldehyd																													
Jodkalium	-> siehe: Kaliumjodid																													
Jodoform	CHJ_3	000075-47-8	100 %	Xn		3/0	3/0	(3)	3/0	0/0	0/0	(2)	3/0	3/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(2)	1/0	1/0	(3)	0/0	(3)	(1)[1)]	(1)[1)]	1/1	[1)] wasserfrei! Wenn durch Feuchtigkeit auch nur Spuren von Salzsäure (HCl) abgespaltet werden, besteht die Gefahr von Lochfraß, Spalt- und Spannungsrisskorrosion.
Jodpentafluorid	JF_5	007783-66-6		(T, C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Jodtinktur	I_2	007553-56-2		Xn	(X)	1/3	1/3	4/4	3/4	0/0	1/1	1/1	1/2	3/3	0/0	4/4	4/4	3/3	1/1	0/0	1/1	1/1	2/0	1/1	3/3	0/0	1/0	2/0L	1/0L	1/1	
Kakao	—	—		(—)		1/1	1/1	(2)	(1)	(2)	0/0	1/1	(2)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Kakaobutter	—	008002-31-1		—		0/0	0/0	1/0	(1)	1/0	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1		
Kalialaune	-> siehe: Kaliumaluminiumsulfat																													
Kalilauge	-> siehe: Kaliumhydroxid																													
Kaliumperoxodisulfat	-> siehe: Kaliumpersulfat																													
Kalisalpeter	-> siehe: Kaliumnitrat																													
Kalium(hexa)cyanoferrat-(II)	-> siehe: Ferrocyankalium																													
Kalium(hexa)cyanoferrat-(III)	-> siehe: Ferricyankalium																													
Kaliumacetat	$C_2H_3KO_2$	000127-08-2	wässrig	Xi		1/1	1/1	1/0	(1)	(2)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/0	1/1	1/1	3/0	3/3	0/0	1/3	1/1	1/1	0/0	
Kaliumaluminiumsulfat	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	verdünnt	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Kaliumaluminiumsulfat	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	gesättigt	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Kaliumbicarbonat	-> siehe: Kaliumhydrogencarbonat																													
Kaliumbichromat	-> siehe: Kaliumdichromat																													
Kaliumbisulfat	-> siehe: Kaliumhydrogensulfat																													
Kaliumbitartrat	-> siehe: Kaliumhydrogentartat																													
Kaliumborat	KBO_2	012228-88-5	10 %	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0	
Kaliumborat	KBO_2	012228-88-5	wässrig	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0	
Kaliumbromat	$KBrO_3$	007758-01-2	gesättigt	O, T		1/3	1/3	(2)	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Kaliumbromat	$KBrO_3$	007758-01-2	wässrig	O, T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Kaliumbromid	KBr	007758-02-3	jede	Xn		1/1	1/1	3/0	1/0	(1)	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/0L	1/0L	1/1	
Kaliumcarbonat	K_2CO_3	000584-08-7	gesättigt	Xn		1/1	1/1	1/1	3/3	(2)	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1	
Kaliumcarbonat	K_2CO_3	000584-08-7	wässrig	Xn		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1	
Kaliumchlorat	$KClO_3$	003811-04-9	gesättigt	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Kaliumchlorat	$KClO_3$	003811-04-9	wässrig	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Kaliumchlorid	KCl	007447-40-7	wässrig	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/3	1/1L	1/1L	1/1	
Kaliumchromat	K_2CrO_4	007789-00-6	gesättigt	T		1/0	1/1	2/0	(2)	0/0	1/0	(2)	1/1	1/1	0/0	1/1	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Kaliumchromat	K_2CrO_4	007789-00-6	wässrig	T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Kaliumcyanid	KCN	000151-50-8	gesättigt	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	4/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Kaliumcyanid	KCN	000151-50-8	wässrig	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	1/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Kaliumdichromat	$K_2Cr_2O_7$	007778-50-9	gesättigt	T		1/1	1/0	4/4	3/0	3/0	1/0	3/0	1/1	1/3	0/0	1/3	1/0	1/3	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Kaliumdichromat	$K_2Cr_2O_7$	007778-50-9	wässrig	T		0/0	0/0	3/0	1/0	3/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Kaliumeisen-(II)-cyanid	-> siehe: Ferrocyankalium																													
Kaliumeisen-(III)-cyanid	-> siehe: Ferricyankalium																													
Kaliumfluorid	KF	007789-23-3		T		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	(1)	0/0	1/1	1/1	1/1	0/0	
Kaliumhydrogencarbonat	$CHKO_3$	000298-14-6	gesättigt	—		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	4/4	(1)	(1)	1/1	
Kaliumhydrogensulfat	$KHSO_4$	007646-93-7	wässrig	(C)		1/1	1/1	4/4	1/0	(2)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	1/1	
Kaliumhydrogensulfat	$KHSO_4$	007646-93-7		C		1/1	1/1	4/4	1/0	0/0	0/0	2/0	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	?	
Kaliumhydrogentartat	$C_4H_5KO_6$	000868-14-4	gesättigt	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(4)	1/3	1/2	0/0	
Kaliumhydroxid	KHO	001310-58-3	10 %	C+		1/1	1/1	1/0	4/4	4/4	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	
Kaliumhydroxid	KHO	001310-58-3	30 %	C+		1/1	1/1	1/3	4/4	4/4	1/0	(3)	1/1	1/0	1/0	1/3	1/0	0/0	0/0	0/0	1/0	(2)	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	
Kaliumhydroxid	KHO	001310-58-3	50 %	C+		1/1	1/1	1/3	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/3	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Kaliumhydroxid	KHO	001310-58-3	konz.	C+		1/1	1/1	1/0	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/2	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Kaliumhydroxid	KHO	001310-58-3	1 %	Xi		1/1	1/1	1/0	3/4	(4)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/3	3/3	0/0	4/4	1/1	1/1	1/1	
Kaliumhypochlorit	KClO	007778-66-7	verdünnt	(O, C)		1/0	1/3	3/0	(3)	(3)	1/0	4/4	1/3	3/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	4/4	3/3L	2/2L	1/1	Javellewasser, urspr.
Kaliumjodat	KJO_3	007758-05-6		O		0/0	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/1	(1)	(1)	(2)	0/0	1/1	1/1	1/1	0/0	
Kaliumjodid	KJ	007681-11-0	gesättigt	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	1/1	

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste													Fluor-Kunststoffe				Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZENTRATION	GEFAHRENHINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMERKUNG
Kaliumjodid	KJ	007681-11-0	wässrig	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	1/1	
Kaliumnitrat	KNO_3	007757-79-1	50 %	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Kaliumnitrat	KNO_3	007757-79-1	wässrig	O, Xn		1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Kaliumperchlorat	$KClO_4$	007778-74-7	gesättigt	O, Xn		1/1	1/1	(1)	1/0	(1)	1/0	1/1	1/1	0/0	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	
Kaliumperchlorat	$KClO_4$	007778-74-7	wässrig	O, Xn		1/1	1/1	(1)	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Kaliumpermanganat	$KMnO_4$	007722-64-7	wässrig	O, Xn		0/0	0/0	4/4	1/0	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	übermangansaures Kali
Kaliumpermanganat	$KMnO_4$	007722-64-7		O, Xn		1/3	1/1	4/4	1/0	(2)	1/1	1/1	1/1	1/3	0/0	1/3	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	übermangansaures Kali
Kaliumpersulfat	$K_2(SO_4)_2$	007727-21-1	jede	O, Xn		1/1	1/1	4/4	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/0	1/0	1/1	
Kaliumsulfat	K_2SO_4	007778-80-5	wässrig	Xn		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Kaliumsulfid	K_2S	001312-73-8	verdünnt	(C)		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	(1)	(1)	2/0	0/0	3/4	1/1	1/1	0/0	
Kaliumsulfit	K_2SO_3	010117-38-1	gesättigt	(Xi)		1/1	1/1	(1)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/0	1/0	0/0	
Kaliumthiosulfat	$K_2S_2O_3$	010233-00-8	gesättigt	Xi		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	3/3	0/0	(1)	(1)	(1)		
Kalk, gebrannt	-> siehe: Calciumoxid																													
Kalkhydrat	-> siehe: Calciumhydroxid																													
Kalksalpeter	-> siehe: Calciumnitrat																													
Kalkwasser	-> siehe: Calciumhydroxid																													
Kardamom	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Kautschukdispersion	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(1)	(2)	0/0	(3)	(1)	(1)		Latex
Kerosin	—	008008-20-6		(Xn)		2/2	3/4	(1)	4/4	1/1	2/3	1/1	3/3	4/4	2/3	1/1	0/0	0/0	2/3	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	Lampenöl, Leichtpetroleum
Kiefernadelöl	—	008023-99-2		?		0/0	0/0	1/0	(3)	0/0	(4)	(2)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	0/0	Pinus sylvestris
Kieselfluorwasserstoffsäure	H_2SiF_6	016961-83-4	32 %	C		1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	3/0	2/2	3/4	0/0	4/4	(2)	1/1	1/1	
Kieselsäure	SiO_2	001343-98-2	jede	—		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Kieselsäuretetraethylester	-> siehe: Tetraethylorthosilicat																													
Knochenöl	—	008001-85-2		—		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Kochsalz	-> siehe: Natriumchlorid																													
Kohlen(stoff)disulfid	-> siehe: Schwefelkohlenstoff																													
Kohlendioxid	CO_2	000124-38-9	gesättigt	?		1/3	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Kohlendioxid, feucht	CO_2	000124-38-9	techn. rein	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Kohlendioxid, trocken	CO_2	000124-38-9	techn. rein	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Kohlensäure	-> siehe: Kohlendioxid																													
Kohlensäuredichlorid	-> siehe: Phosgen																													
Kohlenstofftetrabromid	-> siehe: Tetrabromkohlenstoff																													
Kohlenstofftetrachlorid	-> siehe: Tetrachlorkohlenstoff																													
Kokosfett	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1		
Kokosfettalkohol	—	068425-37-6	techn. rein	(Xi)		1/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1		
Kokosnussöl	—	008001-31-8	techn. rein	—		1/3	1/3	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Königswasser	HNO_3 + HCl	008007-56-5		C		4/4	4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	4/4	0/0	4/4	4/4	4/4	4/4	Aqua regia = Salpeter- + Salzsäure
Kraftstoff + 20% Ethanol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	1/1	1/1		
Kraftstoff + 20% Methanol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	1/1	1/1		
Kraftstoff, Normal	—	—		F, T	X	0/0	0/0	1/0	3/0	1/1	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Kraftstoff, Super	—	—		F, T	X	0/0	0/0	1/0	4/4	(2)	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Kreide	$CaCO_3$	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Calciumcarbonat
Kreosot	—	—		(T)		1/1	1/1	3/0	(3)	0/0	0/0	(3)	3/4	0/0	1/0	3/0	4/4	0/0	0/0	(1)	1/1	(3)	4/4	(3)	1/0	0/0	(2)	1/1	1/1	0/0	
Kresol (-Gemische)	C_7H_8O	001319-77-3		T, C		3/4	4/4	4/4	4/4	4/4	4/4	4/4	2/3	4/4	4/4	4/4	4/4	3/4	1/2	1/1	1/1	1/1	4/4	1/0	4/4	0/0	1/1	1/0	1/0	1/1	
Kümmel	—	—	gemahlen	?		0/0	0/0	(2)	(2)	(1)	0/0	1/1	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	4/4	(1)	(1)		
Kupfer-(I)-chlorid	CuCl	007758-89-6	wässrig	Xn		0/0	0/0	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1	
Kupfer-(I)-cyanid	-> siehe: Kupfercyanid																													
Kupfer-(II)-chlorid	$CuCl_2$	007447-39-4	gesättigt	Xn		1/3	1/1	(3)	1/0	(2)	1/0	(2)	1/3	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1	
Kupfer-(II)-nitrat	$Cu(NO_3)_2$	003251-23-8	gesättigt	O, Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/0	1/1	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/1	1/1	1/1	
Kupfer-(II)-nitrat	$Cu(NO_3)_2$	003251-23-8	wässrig	O, Xn		0/0	0/0	(3)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	1/1	1/1	1/1	
Kupfer-(II)-sulfat	-> siehe: Kupfersulfat																													
Kupferacetat	$C_4H_6CuO_4$	004180-12-5	wässrig	Xn		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	(3)	3/3	0/0	4/4	1/1	1/1	1/1	Cupriacetat, Grünspan
Kupfercyanid	CCuN	000544-92-3	gesättigt	T		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/3	0/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	(3)	1/1	1/1		
Kupfercyanür	-> siehe: Kupfercyanid																													
Kupfersulfat, wässrig	-> siehe: Kupfervitriol																													
Kupfervitriol	$CuSO_4 \times 5H_2O$	007758-99-8	wässrig	Xn		1/1	1/1	1/0	1/0	(2)	1/0	1/0	1/1	1/1	1/0	1/3	1/0	1/1	1/1	(1)	1/1	1/1	1/0	1/1	2/0	0/0	4/4	1/1	1/1	1/1	

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste													Fluor-Kunststoffe			Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Lachgas	N_2O	010024-97-2		(O)		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	2/0	1/0	1/0	0/0	1/1	(1)	(1)		Distickstoffoxid, "Stickoxydul"
Lactame	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	4/4	4/4	0/0	(2)	(1)	(1)		cyclische Carbonsäureamide
Lactobiose	-> siehe: Lactose																													
Lactose	$C_{12}H_{22}O_{11}$	000063-42-3	wässrig	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	
Lanolin	—	008006-54-0	techn. rein	—		3/3	3/3	1/0	1/0	1/0	0/0	(2)	3/3	1/1	0/0	3/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Latex	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(1)	(2)	0/0	(2)	(1)	(1)	1/1	Kautschukdispersion
Laurylalkohol	$C_{12}H_{26}O$	000112-53-8	100 %	Xi		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	(1)	(1)	0/0	
Laurylchlorid	$C_{12}H_{25}Cl$	000112-52-7	100 %	(Xi)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(1)	(3)	0/0	(3)	0/0	0/0		
Lavendelöl	—	008000-28-0		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	(1)	(1)	(1)		
Lebertran	—	008001-69-2		—		1/3	1/3	(2)	1/0	(2)	0/0	(2)	1/3	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/0	(1)	(1)	1/1	
Leim (Knochenleim)	—	—	jede	—		1/0	1/1	(1)	(1)	1/1	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(1)	(1)	1/0	1/0	0/0	(3)	1/1	1/1	0/0	
Leinöl	—	008001-26-1	techn. rein	—		1/1	1/3	1/0	1/0	1/0	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Lemongrasöl	—	008007-02-1		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Leuchtgas, benzolfrei	—	—		F+, T	X	1/0	1/0	1/0	1/0	(2)	1/0	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/0	1/0	4/4	1/0	3/0	0/0	1/1	1/1	1/1	0/0	
Ligroin	—	008032-32-4		F, Xn	X	0/0	0/0	(2)	1/0	(2)	(4)	(2)	(3)	3/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		Leichtbenzin
Liköre	—	—		—		1/0	0/0	(2)	1/0	1/0	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Limonen, DL-	$C_{10}H_{16}$	000138-86-3		Xn	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Lindan	-> siehe: Hexachlorcyclohexan																													
Lithiumbromid	LiBr	007550-35-8		Xn		1/1	1/1	(3)	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Lorbeer	—	—	gemahlen	?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Lysol	—	—		T		0/0	0/0	(4)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(3)	1/1	1/1		Desinfektionsmittel, Kresol + Seife
Magnesit	-> siehe: Magnesiumcarbonat																													
Magnesiumbromid	$MgBr_2$	007789-48-2		Xi		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	(3)	0/0	0/0		
Magnesiumcarbonat	$MgCO_3$	000546-93-0	gesättigt	—		1/1	1/1	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Magnesiumchlorid	$MgCl_2$	007786-30-3	wässrig	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/2	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0L	1/0L	1/1	
Magnesiumchlorit	$Mg(ClO_2)_2$	??		O		0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0		
Magnesiumhydroxid	$Mg(HO)_2$	001309-42-8	gesättigt	—		1/1	1/1	1/0	(2)	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	1/1	1/1	1/1	1/1	0/0	
Magnesiumjodid	MgJ_2	010377-58-9		(Xn)		1/1	1/1	(2)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/1	(1)	(2)	0/0	(2)	0/0	0/0		
Magnesiumnitrat	$Mg(NO_3)_2$	010377-60-3	gesättigt	O, Xi		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	1/0	1/0	1/0	1/1	
Magnesiumsulfat	$MgSO_4$	007487-88-9	jede	—		1/1	1/1	1/0	1/0	1/0	1/0	1/0	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	0/0	1/1	1/1	1/1	1/1	
Magnesiumsulfat-Heptahydrat	-> siehe: Bittersalz																														
Maiskeimöl	—	008001-30-7	techn. rein	—		1/3	0/0	(2)	(1)	1/0	0/0	(2)	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	1/1	Maisöl
Maleinsäure	$C_4H_4O_4$	000110-16-7	gesättigt	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Maleinsäure	$C_4H_4O_4$	000110-16-7	wässrig	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Malonester	-> siehe: Diethylmalonat																														
Malonsäurediethylester	-> siehe: Diethylmalonat																														
Mandelöl	—	008007-69-0		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	3/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(1)	(2)	0/0	(1)	1/1	1/1		
Margarine	—	—		—		0/0	0/0	(2)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Marmelade	—	—		—		1/1	1/1	(1)	1/1	1/1	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(2)	1/1	1/1	1/1	
Maschinenöl	—	—	100 %	?		0/0	1/4	(1)	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Matriummetabisulfit	-> siehe: Natriumdisulfit																														
Matriumpyrochromat	-> siehe: Natriumdichromat																														
Meerwasser	-> siehe: Salzwasser, Meerwasser																														
Melasse	—	—		—		1/1	1/1	1/0	(1)	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/0	1/0	3/4	
Melassewürze	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Menthadien-1,8, p-	-> siehe: Limonen, DL-																														
Menthol	$C_{10}H_{20}O$	000089-78-1	fest	Xi		1/3	3/4	3/0	3/4	0/0	0/0	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	1/0	1/0		
Mercaptoessigsäure	-> siehe: Thioglycolsäure																														
Mercaptoethansäure, 2-	-> siehe: Thioglycolsäure																														
Mesityloxid	$C_6H_{10}O$	000141-79-7		Xn	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	0/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methacrylsäure	$C_4H_6O_2$	000079-41-4		C		1/0	1/1	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	3/0	4/4	4/4	0/0	(4)	0/0	0/0		
Methacrylsäuremethylester	-> siehe: Methylmethacrylat																														
Methan	CH_4	000074-82-8	techn. rein	F+	X	1/0	0/0	1/0	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Methanallösung	-> siehe: Formaldehydlösung																														
Methanamin	-> siehe: Methylamin, (Mono-)																														
Methancarbonsäure	-> siehe: Essigsäure																														

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste														Fluor-Kunststoffe			Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Methanol	CH_4O	000067-56-1		F, T	X	1/1	1/1	2/0	4/4	1/0	1/1	1/1	1/1	3/4	3/3	1/3	3/3	3/4	1/1	1/1	1/1	1/1	1/0	3/4	3/3	0/0	1/0	1/1	1/1	0/0	
Methansäure	-> siehe: Ameisensäure																													
Methenamin	-> siehe: Hexamethylentetramin																													
Methoxybenzol	-> siehe: Anisol																													
Methoxybutanol	$C_5H_{12}O_2$	—	100 %	?	X	0/0	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	3/0	1/0	!/0	0/0	(1)	(1)	(1)		Isomeres in der Quelle nicht angegeben
Methoxyethanol	-> siehe: Methylglycol																													
Methoxyethylacetat	-> siehe: Methylglycolacetat																													
Methoxyethyloleat	$C_{21}H_{40}O_3$	000111-10-4		?		1/1	1/2	(2)	3/4	(2)	1/2	(2)	1/2	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(1)	(1)	4/4	(2)	4/4	0/0	(1)	(1)	(1)		Weichmacher
Methoxypropanol	-> siehe: Propylenglycolmethylether																													
Methyethylether	C_3H_8O	000540-67-0	100 %	(F+)	X	0/0	3/0	(1)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(2)	4/4	4/4	4/4	0/0	1/1	(1)	(1)		
Methyl-2-hydroxybenzoat	-> siehe: Methylsalicylat																													
Methyl-2-methylpropionat	-> siehe: Methylmethacrylat																													
Methylacetat	-> siehe: Essigsäuremethylester																													
Methylacrolein	-> siehe: Crotonaldehyd																													
Methylacrylat	$C_4H_6O_2$	000096-33-3		F, Xn	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Methylacrylsäure	-> siehe: Methacrylsäure																													
Methylalkohol	-> siehe: Methanol																													
Methylamin, (Mono-)	CH_5N	000074-89-5	32 %	F+, C	X	1/0	1/0	4/4	4/4	0/0	0/0	1/0	1/0	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	3/0	1/0	4/4	4/4	0/0	1/0	1/0	1/0	0/0	
Methylbenzol	C_7H_8	000108-88-3		F, Xn	X	3/4	3/4	1/0	4/4	1/0	3/3	1/3	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/3	4/4	0/0	1/1	1/1	1/1	1/1	
Methylbromid	-> siehe: Brommethan																													
Methylbutanol	$C_5H_{12}O$	—		Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	1/3	0/0	(1)	1/1	1/1	3/0	2/2	3/3	0/0	(1)	(1)	(1)		Isomeres in der Quelle nicht angegeben
Methylbutanol, 3-	-> siehe: Isoamylalkohol																													
Methylbutanon-2, 3-	-> siehe: Isopropylmethylketon																													
Methylbutylalkohol	-> siehe: Methylbutanol																													
Methylbutylketon	$C_6H_{12}O$	000591-78-6		F, T	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methylcellosolve	-> siehe: Methylglycol																													
Methylchloracetat	$C_3H_5ClO_2$	000096-34-4	techn. rein	T/Xi	X	1/1	0/0	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/0	0/0	0/0	0/0	(1)	(1)	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Methylchlorid	-> siehe: Chlormethan																													
Methylchloroform	-> siehe: Trichlorethan-1,1,1																													
Methylcyanid	-> siehe: Acetonitril																													
Methylcyclohexan	C_7H_{14}	000108-87-2		F, Xn	X	3/0	3/0	(2)	(2)	1/0	(4)	(2)	3/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	(1)	4/4	(1)	4/4	0/0	1/1	1/1	1/1	0/0	
Methylcyclopentan	C_6H_{12}	000096-37-7		F	X	0/0	0/0	(2)	(2)	1/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Methyldichloracetat	$C_3H_4Cl_2O_2$	000116-54-1		(Xn)		1/1	0/0	(3)	(4)		(4)	(3)	1/1	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	3/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Methylen(di)chlorid	-> siehe: Dichlormethan																													
Methylenchlorbromid	-> siehe: Bromchlormethan																													
Methylether	-> siehe: Dimethylether																													
Methylethylketon (MEK)	C_4H_8O	000078-93-3		F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/2	1/3	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	3/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methylformiat	$C_2H_4O_2$	000107-31-3		F+	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methylglycol	$C_3H_8O_2$	000109-86-4	100 %	T	X	1/0	1/1	1/0	3/4	0/0	1/1	1/0	1/1	4/4	3/3	3/4	4/4	0/0	1/1	1/1	1/1	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methylglycolacetat	$C_5H_{10}O_3$	000110-49-6		T		0/0	0/0	1/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methylisobutenylketon	-> siehe: Mesityloxid																													
Methylisobutylketon (MIBK)	-> siehe: Isobutylmethylketon																													
Methylisopropylketon	-> siehe: Isopropylmethylketon																													
Methylmethacrylat	$C_5H_8O_2$	000080-62-6	100 %	F, Xi	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Methylmethanoat	-> siehe: Methylformiat																													
Methyloleat	$C_{19}H_{36}O_2$	000112-62-9		—		0/0	0/0	(2)	(3)	(2)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	4/4	0/0	(1)	(1)	(1)		
Methyloxiran	-> siehe: Propylenoxid																													
Methylpent-4-en-2-on, 5-	-> siehe: Mesityloxid																													
Methylpentan-2-on, 4-	-> siehe: Isobutylmethylketon																													
Methylphenol	-> siehe: Kresol (-Gemische)																													
Methylphenylether	-> siehe: Anisol																													
Methylphenylketon	-> siehe: Acetophenon																													
Methylpropanol-1, 2-	-> siehe: Isobutanol																													
Methylpropanol-2, 2-	-> siehe: Butylalkohol, tertiär																													

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

							---------- Thermoplaste ----------		Fluor-Kunststoffe		--- Elastomere ---		------- Metalle -------		
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZÜNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Methylpropenoat	-> siehe: Methylacrylat																														
Methylpropensäure, 2-	-> siehe: Methacrylsäure																														
Methylpropylketon	$C_5H_{10}O$	000107-87-9		(F)	X	1/2	2/3	(2)	4/4	(4)	3/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	(1)	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		
Methylsalicylat	$C_8H_8O_3$	000119-36-8		Xn, Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/0	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	2/0	(3)	4/4	0/0	(2)	(1)	(1)	0/0	synthetisches Wintergrünöl/Gaultheriaöl
Methylschwefelsäure	CH_4SO_4	000077-78-1	50 %	(C)		0/0	1/1	4/4	(4)	(4)	0/0	4/4	2/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4	
Methylschwefelsäure	CH_4SO_4	000077-78-1	wässrig	(C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4	
Milch	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Milchsäure	$C_3H_6O_3$	000050-21-5	3 %	?		1/1	1/2	(3)	1/2	1/0	1/2	2/4	1/2	2/2	1/1	2/3	0/0	1/1	1/1	1/1	1/1	1/1	3/4	1/1	(2)	0/0	(1)	1/1	1/1	1/1	Lactol
Milchsäure	$C_3H_6O_3$	000050-21-5	80 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/1	1/1	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1	Lactol
Milchsäure	$C_3H_6O_3$	000050-21-5	85 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/2	2/2	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1	Lactol
Milchsäure-ethylester	-> siehe: Ethyllactat																														
Milchzucker	-> siehe: Lactose																														
Mineralöl	—	008012-95-1		(Xn)		1/1	2/4	(1)	1/2	1/1	1/2	1/1	1/3	1/1	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	2/2	0/0	1/1	1/1	1/1	0/0	
Mineralwasser	—	—		—		1/1	1/1	(1)	1/0	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	(1)	(1)	1/1	
Mohrsches Salz	-> siehe: Ammoniumeisen-(II)-sulfat																														
Molke	—	—		—		1/1	0/0	(2)	(1)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(2)	1/1	1/1		
Monobrombenzol	-> siehe: Brombenzol																														
Monochlorbenzol	-> siehe: Chlorbenzol																														
Monochloressigsäure	-> siehe: Chloressigsäure																														
Monochloressigsäureethylester	-> siehe: Ethylchloracetat																														
Monochloressigsäuremethylester	-> siehe: Methylchloracetat																														
Monoethanolamin	-> siehe: Ethanolamin																														
Monofluordichlormethan	-> siehe: Dichlorfluormethan																														
Monokaliumtartrat	-> siehe: Kaliumhydrogentartat																														
Monopentylphthalat	-> siehe: Phthalsäuremonoamylester																														
Morpholin	C_4H_9NO	000110-91-8	techn. rein	C, Xn	X	1/1	1/1	(3)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	3/0	2/3	4/4	0/0	1/0	(1)	(1)	0/0	
Motorenöl	—	—		?		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Mowilith D	—	—		?		1/0	0/0	(2)	0/0	(2)	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(2)	(2)	(2)	0/0	(2)	(1)	(1)	0/0	Polyvinylacetatdispersion; Clariant
Muskat	—	—	gemahlen	?		0/0	0/0	(2)	4/4	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Muskatnussöl	—	008008-45-5		(Xn)		0/0	0/0	(2)	4/4	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/4	0/0	(1)	(1)	(2)	(4)	(3)	(3)	0/0	(1)	(1)	(1)		
Nagellackentferner	—	—		?	(X)	0/0	0/0	(2)	4/4	0/0	(4)	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Naphtha	—	008032-32-4		(Xn)		1/3	3/4	1/0	(2)	(1)	1/0	1/0	1/3	3/0	1/0	1/0	4/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	Petreoleumbenzin
Naphthalin	$C_{10}H_8$	000091-20-3	100 %	F, Xn	X	0/0	1/3	1/0	(3)	0/0	0/0	1/2	1/3	3/4	1/0	4/4	4/4	1/4	0/0	(1)	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	
Naphthalin (in Alkohol)	—	—		F, Xn	X	1/4	1/4	(2)	(3)	0/0	0/0	1/2	1/3	3/4	0/0	0/0	0/0	3/4	0/0	(1)	1/1	(2)	4/4	(3)	(3)	0/0	(1)	(1)	(1)	0/0	
Naphthen	-> siehe: Cyclohexan																														
Natriumacetat	$C_2H_3NaO_2$	000127-09-3	jede	—		1/1	1/1	1/0	1/2	(1)	1/1	1/1	1/1	2/2	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	1/1	1/1	1/1	
Natriumaluminiumsulfat	$NaAl(SO_4)_2$	010102-71-3		?		1/1	1/1	(3)	(2)	(1)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)		
Natriumbenzoat	$C_7H_5NaO_2$	000532-32-1	36 %	Xn		1/1	1/1	1/0	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	1/1	0/0	(1)	(1)	(1)	1/1	
Natriumbenzoat	$C_7H_5NaO_2$	000532-32-1	wässrig	Xn		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1	
Natriumbenzoat	$C_7H_5NaO_2$	000532-32-1		Xn		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1	
Natriumbicarbonat	$NaHCO_3$	000144-55-8	wässrig	—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Natriumbichromat	-> siehe: Natriumdichromat																														
Natriumbisulfat	$NaHSO_4$	007681-38-1	10 %	(C)		1/1	1/1	4/4	1/0	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	1/2	1/1	1/1	
Natriumbisulfat	$NaHSO_4$	007681-38-1	jede	(C)		1/1	1/1	1/0	1/0	0/0	0/0	(3)	1/1	1/3	0/0	1/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	(2)	1/1	1/1	
Natriumbisulfit	$NaHSO_3$	007631-90-5	wässrig	Xn		1/1	1/1	1/0	(2)	1/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1	1/1	
Natriumborat	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	gesättigt	Xi		1/1	1/1	1/0	1/0	(2)	1/0	1/1	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/3	1/1	1/1	1/1	
Natriumborat	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	wässrig	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/3	1/1	1/1	1/1	
Natriumbromat	$NaBrO_3$	007789-38-0	jede	O, T		1/0	1/3	(3)	(2)	0/0	0/0	1/1	1/1	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	(2)	(1)	1/3	0/0	1/1	1/1L	1/1L	0/0	
Natriumbromid	NaBr	007647-15-6	jede	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/3	0/0	4/4	0/0	0/0	0/0	
Natriumcarbonat	Na_2CO_3	000497-19-8	gesättigt	Xi		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Natriumcarbonat	Na_2CO_3	000497-19-8	wässrig	Xi		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Natriumcarbonat	Na_2CO_3	000497-19-8		Xi		1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	2/0	0/0	1/1	0/0	1/2	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Natriumchlorat	$NaClO_3$	007775-09-9	jede	O, Xn		1/1	1/0	1/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1L	1/1L	1/1	
Natriumchlorat	$NaClO_3$	007775-09-9	wässrig	O, Xn		0/0	0/0	3/0	1/0	1/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/0	1/1L	1/1L	1/1	
Natriumchlorid	NaCl	007647-14-5	jede	—		1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/2	1/2	1/1	

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste												Fluor-Kunststoffe				Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Natriumchlorid	NaCl	007647-14-5	wässrig	—		1/1	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/4	1/2	1/2	1/1	
Natriumchlorit	$NaClO_2$	007758-19-2	verdünnt	(O, Xn)		1/0	1/3	1/4	(2)	0/0	0/0	(2)	1/3	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	3/4	3/4	3/3	0/0	
Natriumchromat	$NaCrO_4$	007775-11-3	verdünnt	T		1/0	1/0	1/1	(2)	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	1/1	1/1	1/1	0/0	
Natriumcyanid	CNNa	000143-33-9	gesättigt	T		1/1	1/1	1/0	(3)	0/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	4/4	(2)	(2)	0/0	
Natriumcyanid	CNNa	000143-33-9	wässrig	T		1/1	1/1	1/0	(3)	1/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	(2)	(2)	0/0	
Natriumdichromat	$Na_2Cr_2O_7$	010588-01-9		T		0/0	1/1	1/0	1/0	3/0	1/1	(3)	1/1	1/1	0/0	1/0	0/0	0/0	1/1	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Natriumdisulfit	$Na_2S_2O_5$	007681-57-4	jede	Xn		1/1	1/1	1/0	(2)	(2)	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1		
Natriumdithionit	$Na_2S_2O_4$	007775-14-6	10 %	Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		
Natriumdithionit	$Na_2S_2O_4$	007775-14-6		Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		
Natriumdodecylbenzolsulfonat	$C_{18}H_{29}NaSO_3$	025155-30-0		Xn		1/1	1/1	(2)	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(1)	(2)	0/0	(2)	(1)	(1)		
Natriumeisencyanid	-> siehe: Natriumhexacyanoferrat(II)																														
Natriumferrocyanid	-> siehe: Natriumhexacyanoferrat(II)																														
Natriumfluorid	NaF	007681-49-4	gesättigt	T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/0	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	1/1	
Natriumhexacyanoferrat-(II)	$C_6FeNa_4N_6$	013601-19-9		Xn		1/1	1/1	(1)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(1)	(1)	(1)		
Natriumhexametaphosphat	$(NaPO_3)_6$	068915-31-1	gesättigt	—		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Natriumhydrogencarbonat	-> siehe: Natriumbicarbonat																														
Natriumhydrogensulfat	-> siehe: Natriumbisulfat																														
Natriumhydrogensulfit	-> siehe: Natriumbisulfit																														
Natriumhydrosulfit	-> siehe: Natriumdithionit																														
Natriumhydroxid	NaOH	001310-73-2	konz.	C		1/1	1/1	1/3	4/4	4/4	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/4	0/0	4/4	(2)	(2)	?	
Natriumhydroxid	NaOH	001310-73-2	30 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/0	1/0	1/3	1/3	0/0	0/0	1/1	1/1	(2)	1/0	(3)	2/3	0/0	4/4	1/3	1/3	1/1	
Natriumhydroxid	NaOH	001310-73-2	45 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/1	1/0	1/3	1/3	1/1	0/0	0/0	1/1	(2)	1/0	2/4	2/3	0/0	4/4	1/3	1/3	1/1	
Natriumhydroxid	NaOH	001310-73-2	50 %	C+		1/1	1/1	1/0	4/4	4/4	1/1	1/3	1/1	2/2	1/1	1/2	0/0	0/3	1/1	1/1	1/1	3/3	1/0	3/4	3/3	0/0	4/4	1/3	1/3	1/1	
Natriumhydroxid	NaOH	001310-73-2	60 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	(3)	1/1	1/0	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	3/4	2/3	0/0	4/4	1/3	1/3	1/1	
Natriumhydroxid	NaOH	001310-73-2	1 %	Xi		1/1	1/1	1/0	3/4	(3)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	(4)	1/1	1/1	1/1	
Natriumhypochlorit	NaClO	007681-52-9	verdünnt	(O, C)		2/3	2/3	4/4	(3)	3/0	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javellewasser, neu
Natriumhypochlorit	NaClO	007681-52-9	15 %	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/1	0/0	1/1	1/1	1/1	1/1	3/4	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javellewasser, neu
Natriumhypochlorit	NaClO	007681-52-9	gesättigt	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	0/0	1/1	0/0	(1)	1/1	(3)	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javellewasser, neu
Natriumhypochlorit	NaClO	007681-52-9	12,5 % Cl	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javellewasser, neu
Natriumhypodisulfit	-> siehe: Natriumdithionit																														
Natriumjodid	NaJ	007681-82-5	jede	Xi		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/0	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	(1)	1/1	0/0	1/1	3/4	3/4	0/0	
Natriummetaboratperoxid	-> siehe: Natriumperborat																														
Natriumnitrat	$NaNO_3$	007631-99-4	gesättigt	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	
Natriumnitrat	$NaNO_3$	007631-99-4	wässrig	O, Xn		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Natriumnitrit	$NaNO_2$	007632-00-0	gesättigt	O, T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1	1/1	1/1	
Natriumnitrit	$NaNO_2$	007632-00-0	wässrig	O, T		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	1/0	1/1	1/1	1/1	
Natriumoxalat	$C_2Na_2O_4$	000062-76-0	gesättigt	Xn		1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	1/0	1/0	0/0	1/1	(2)	(2)		
Natriumperborat	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	gesättigt	(O, Xn)		1/1	1/1	4/4	(2)	0/0	0/0	2/0	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Natriumperborat	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	wässrig	(O, Xn)		1/1	1/1	4/4	(2)	3/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Natriumperchlorat	$NaClO_4$	007601-89-0	gesättigt	O, Xn		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	1/1	1/1	
Natriumperoxid	Na_2O_2	001313-60-6	10 %	O, C+		0/0	1/3	4/4	(3)	(4)	0/0	4/4	272	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	3/0	0/0	4/4	1/1	1/1	0/0	
Natriumperoxid	Na_2O_2	001313-60-6	gesättigt	O, C+		0/0	3/3	4/4	(3)	(4)	0/0	4/4	2/2	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	(4)	0/0	4/4	(2)	(2)	0/0	
Natriumperoxodisulfat	-> siehe: Natriumpersulfat																														
Natriumpersulfat	$Na_2S_2O_8$	007775-27-1	gesättigt	O, Xi		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(3)	0/0	4/4	0/0	1/0	0/0	
Natriumphosphat	$Na_3PO_4 \times 12H_2O$	010101-89-0	gesättigt	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Natriumphosphat	$Na_3PO_4 \times 12H_2O$	010101-89-0	wässrig	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Natriumphosphat, sekundär	-> siehe: Dinatriumphosphat																														
Natriumphosphat, tertiär	-> siehe: Trinatriumphosphat																														
Natriumphosphat-Dodecahydrat	-> siehe: Natriumphosphat																														
Natriumpyrosulfit	-> siehe: Natriumdisulfit																														
Natriumsilicat	$Na_2Si_3O_7$	001344-09-8	jede	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Natriumstearat	$C_{18}H_{35}NaO_2$	000822-16-2	wässrig	(Xi)		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(1)	1/0	0/0	(1)	1/1	1/1		
Natriumsulfat	Na_2SO_4	007757-82-6	gesättigt	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/3	0/0	1/1	1/1	1/1	1/1	
Natriumsulfat	Na_2SO_4	007757-82-6	wässrig	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	0/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Natriumsulfat	Na_2SO_4	007757-82-6		—		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	1/1	1/1	1/1	1/1	
Natriumsulfid	Na_2S	001313-82-2	gesättigt	C		1/1	1/1	1/0	3/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	0/0	1/1	1/1	3/3	1/0	1/1	2/3	0/0	3/4	(1)	(1)	1/1	

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste													Fluor-Kunststoffe			Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Natriumsulfid	Na_2S	001313-82-2	wässrig	C		1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/2	1/2	1/1	
Natriumsulfit	Na_2SO_3	007757-83-7	gesättigt	Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/3	1/1	1/1	1/1	
Natriumtetraborat	-> siehe: Natriumborat																														
Natriumthiosulfat	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	jede	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/1	1/1	1/1	1/1	Fixiernatron, "Natriumhyposulfit"
Natriumthiosulfat	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	gesättigt	Xi		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	Fixiernatron, "Natriumhyposulfit"
Natriumthiosulfat	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	wässrig	Xi		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	Fixiernatron, "Natriumhyposulfit"
Natriumthiosulfat-5-hydrat	-> siehe: Natriumthiosulfat																														
Natronbleichlauge	-> siehe: Natriumhypochlorit																														
Natronlauge	-> siehe: Natriumhydroxid																														
Natronsalpeter	-> siehe: Natriumnitrat																														
Natronwasserglas	-> siehe: Natriumsilicat																														
Nelken	—	—	gemahlen	?		0/0	0/0	(2)	4/4	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	0/0	
Neon	Ne	007440-01-9		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(1)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1		
Netzmittel	—	—	5 %	?		1/0	0/0	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(2)	0/0	0/0	K	K		Tenside
Niacin	-> siehe: Nicotinsäure																														
Nickel-(II)-chlorid	$NiCl_2$	007718-54-9	gesättigt	T		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1	
Nickel-(II)-chlorid	$NiCl_2$	007718-54-9	wässrig	T		1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1	
Nickelacetat	$C_4H_6NiO_4$	000373-02-4	wässrig	(T, N)		1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/0	0/0	4/4	0/0	0/0		
Nickelnitrat	$Ni(NO_3)_2$	013138-45-9	gesättigt	(O, Xn)		1/1	1/1	(3)	(2)	(1)	1/0	(2)	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Nickelsulfat	$NiSO_4$	007786-81-4	gesättigt	Xn		1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nickelsulfat	$NiSO_4$	007786-81-4	wässrig	Xn		1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nicotin	$C_{10}H_{14}N_2$	000054-11-5		T+		1/0	1/0	(3)	(3)	0/0	0/0	(2)	1/0	1/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/1	0/0	(1)	(1)	(1)	0/0	
Nicotinsäure	$C_6H_5NO_2$	000059-67-6	verdünnt	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/0	0/0	0/0	1/1	0/0	0/0	0/0	1/1	(1)	(2)	(2)	(3)	(2)	0/0	(3)	0/0	0/0	0/0	
Nitrobenzoesäure	$C_7H_5NO_4$	—		(Xn)		1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	(3)	(2)	0/0	(3)	0/0	0/0		Isomeres in der Quelle nicht angegeben
Nitrobenzol	$C_6H_5NO_2$	000098-95-3		T		3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitroethan	$C_2H_5NO_2$	000079-24-3		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Nitroglycerin	$C_3H_5(NO_3)_3$	000055-63-0	verdünnt	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(3)	1/0	1/0	4/4	0/0	0/0	0/0	0/0	0/0	
Nitroglycol	$C_2H_4(NO_3)_2$	000628-96-6	verdünnt	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(3)	1/0	1/0	4/4	0/0	0/0	(1)	(1)	0/0	
Nitropropan	$C_3H_7NO_2$	—		(T)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Isomeres in der Quelle nicht angegeben
Nitrose Gase	—	—	verdünnt	T		1/1	0/0	3/0	4/4	0/0	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	3/0	4/4	0/0	(2)	(1)	(1)	0/0	Stickstoffmonoxid + Stickstoffdioxid
Nitrotoluole	$C_7H_7NO_2$	001321-12-6	techn. rein	T		1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitroverdünnung	—	—		?	X	0/0	0/0	3/0	(4)	0/0	(4)	(3)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		Lösemittelgemisch
Nonanol	$C_9H_{20}O$	000143-08-8	100 %	Xn, Xi		0/0	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Nonylalkohol	-> siehe: Nonanol																														
Obstpulp	—	—		—		1/1	1/1	(2)	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	
Obstwein	—	—		—		1/1	1/1	(2)	(1)	1/1	0/0	1/1	1/0	0/0	0/0	1/0	0/0	0/0	1/1	1/1	(1)	1/1	1/0	(1)	1/0	0/0	(2)	1/1	1/1	0/0	
Octadec-9-ensäure, cis-	-> siehe: Ölsäure																														
Octadecansäure	-> siehe: Stearinsäure																														
Octafluor-cyclobutan	C_4F_8	000115-25-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Octal	-> siehe: Diisooctylphthalat																														
Octan, n-	C_8H_{18}	000111-65-9		F, Xn	X	1/1	1/1	1/0	2/3	(1)	1/1	1/0	1/1	4/4	2/3	3/4	3/3	1/1	1/1	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	0/0	
Octanol, 1-	-> siehe: Octylalkohol, -n																														
Octylalkohol, -n	$C_8H_{18}O$	000111-87-5		Xi		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Octylkresol	$C_{15}H_{24}O$	—	100 %	?		3/0	3/0	(3)	(4)	0/0	0/0	(3)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	(1)	(1)	0/0	Isomeres in der Quelle nicht angegeben
Öle und Fette, pflanzlich	—	—		—		1/3	1/3	(2)	(2)	1/0	0/0	(2)	1/3	3/0	0/0	1/1	3/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	(2)	0/0	(1)	1/1	1/1	0/0	
Öle, ätherisch	—	—		?		4/4	3/4	(2)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	(1-3)	(3)	0/0	1/1	(1)	(1)	0/0	
Olein	-> siehe: Ölsäure																														
Oleum	$H_2SO_4 \times SO_3$	008014-95-7	10 % SO_3	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/0	4/4	4/4	1/0	4/4	0/0	1/3	1/2	1/1	0/0	rauchende Schwefelsäure
Oleumdämpfe	—	—	gering	?		4/4	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	1/0	(3)	1/0	(3)	0/0	(3)	(1)	(1)	0/0	Schwefeltrioxid
Olivenöl	—	008001-25-0		—		1/3	0/0	(2)	(2)	1/0	0/0	1/1	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Ölsäure	$C_{18}H_{34}O_2$	000112-80-1	techn. rein	Xi		1/3	1/3	1/0	1/0	1/0	0/0	2/0	1/3	1/3	0/0	1/1	0/0	1/3	0/0	(1)	1/1	1/1	4/4	2/2	3/0	0/0	1/1	1/1	1/1	0/0	
Ölsäuremethoxyethylester	-> siehe: Methoxyethyloleat																														
Ölsäuremethylester	-> siehe: Methyloleat																														

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste													Fluor-Kunststoffe			Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZENTRATION	GEFAHRENHINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMERKUNG
Orangensaft	-> siehe: Apfelsinensaft																													
Orangenschalenöl	-> siehe: Apfelsinenschalenöl																													
Ortho-Kieselsäuretetraethylester	-> siehe: Tetraethylorthosilicat																													
Orthophosphorsäure	-> siehe: Phosphorsäure																													
Oxabutylacetat	-> siehe: Methylglycolacetat																													
Oxalsäure	$C_2H_2O_4 \times 2H_2O$	000144-62-7	wässrig	Xn		1/1	1/1	4/4	(2)	(2)	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/2	
Oxalsäure	$C_2H_2O_4 \times 2H_2O$	000144-62-7		Xn		1/1	1/1	3/4	1/0	0/0	1/1	4/4	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/3	
Oxalsäure Natriumsalz	-> siehe: Natriumoxalat																													
Oxalsäure-Ammoniumsalz	-> siehe: Ammoniumoxalat																													
Oxiran	-> siehe: Ethylenoxid																													
Oxolan	-> siehe: Tetrahydrofuran																													
Oxydiessigsäure	-> siehe: Diglycolsäure																													
Oxymethylfurfurol, 5-	$C_6H_6O_3$	000067-47-0		Xi		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ozon	O_3	010028-15-6		(O, T)		3/4	3/4	4/4	1/2	0/0	1/1	4/4	3/4	2/2	1/1	1/2	0/0	1/1	1/1	1/1	(1)	1/3	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Ozon-Luft-Gemisch	—	—		(O, T)		0/0	0/0	4/4	(2)	0/0	0/0	4/4	3/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Palmitinsäure	$C_{16}H_{32}O_2$	000057-10-3	techn. rein	Xi		3/3	2/2	1/1	(2)	1/0	0/0	1/0	3/4	1/1	0/0	1/1	3/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
Palmitylalkohol	-> siehe: Cetylalkohol																													
Palmkernöl	—	008023-79-8		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/3	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Palmöl	—	008002-75-3		—		1/3	0/0	1/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1		
Paraffine	C_nH_{2n+2}	—	100 %	?		1/0	1/1	1/0	1/0	1/0	1/1	1/1	1/0	1/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/3	0/0	1/1	1/1	1/1	
Paraffinemulsion	—	—		?		1/3	0/0	1/0	(2)	(2)	0/0	(2)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/0	1/1	0/0	(2)	(1)	(1)	0/0	
Paraffinwachs	—	008002-74-2	geschmolzer	(—)		0	0	0	(2)	0	0	(2)	(2)	0	0	0	0	0	0	(1)	1	0	4	(2)	1	0	1	1	1		
Paraform	-> siehe: Paraformaldehyd																													
Paraformaldehyd	$(CH_2O)_nH_2O$	030525-89-4		F, T	X	0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	1/0	3/3	0/0	(1)	(1)	(1)		
Parfüms	—	—		?		3/0	3/0	1/0	(3)	1/0	0/0	(2)	1/0	4/4	0/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Pectin	—	009000-69-5	wässrig	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Pektin
Pectin	—	009000-69-5		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Pektin
Penicillin	—	—		Xn		(1)	(1)	(2)	(1)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		Antibiotikum
Pentachlordiphenyl	$C_{12}H_5Cl_5$	—		Xn		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0		ein PCB
Pentamethylenimin	-> siehe: Piperidin																													
Pentan	C_5H_{12}	000109-66-0		F	X	1/3	1/3	1/0	1/0	1/1	(3)	1/0	(3)	3/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(1)	4/4	1/0	1/2	0/0	1/1	1/1	1/1		
Pentanon, 2-	-> siehe: Methylpropylketon																													
Pentanon, 3-	-> siehe: Diethylketon																													
Pentanthiol, 1-	$C_5H_{12}S$	000110-66-7		Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(2)	(1)	(1)		
Pentylacetat, n-	-> siehe: Amylacetat, n-																													
Pentylalkohol	-> siehe: Amylalkohol, n-																													
Pentylchlorid	-> siehe: Amylchlorid																													
Pentylzimtaldehyd, a-	-> siehe: Amylzimtaldehyd																													
Perchlorbutadien	-> siehe: Hexachlorbutadien																													
Perchlorethen	-> siehe: Perchlorethylen																													
Perchlorethylen (PER)	C_2Cl_4	000127-18-4		Xn		4/4	4/4	4/4	4/4	3/4	4/4	1/3	4/4	4/4	4/4	4/4	4/4	3/3	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	(3)	0/0	0/0	0/0	
Perchlorsäure	$HClO_4$	007601-90-3	70 %	E, O, C+		2/4	3/4	4/4	4/4	(4)	2/4	4/4	4/4	2/3	4/4	3/4	4/4	0/0	1/2	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	0/0	0/0	?	
Perchlorsäure	$HClO_4$	007601-90-3	20 %	Xi		0/0	1/3	4/4	3/0	0/0	0/0	4/4	1/3	0/0	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	2/0	1/1	4/4	0/0	4/4	0/0	0/0	1/1	
Perfluorpropan	C_3F_8	000076-19-7		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Perhydrol	-> siehe: Wasserstoffperoxid 30 %																													
Petrolatum	-> siehe: Vaseline																													
Petrolether	—	008032-32-4	techn. rein	(F, Xn)	X	1/3	1/3	1/0	3/0	1/0	1/0	1/1	1/3	4/4	1/0	1/1	3/3	3/3	0/0	(1)	1/1	1/1	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	
Petroleum	—	—	techn. rein	Xn, N	X	1/3	3/4	1/0	3/0	(1)	0/0	1/1	1/3	4/4	1/0	1/0	3/0	3/4	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Pfeffer	—	—	gemahlen	?		0/0	0/0	(2)	1/0	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Pflanzliche Öle	—	—		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Phenacetin	$C_{10}H_{13}NO_2$	000062-44-2		Xn		0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)		
Phenetol	-> siehe: Phenylethylether																													
Phenol	C_6H_6O	000108-95-2	10 %	T		1/1	1/1	4/4	4/4	4/4	1/0	4/4	1/1	4/4	4/4	1/3	3/3	3/3	0/0	1/0	1/1	1/1	4/4	2/3	4/4	0/0	1/1	1/2	1/1	0/0	
Phenol	C_6H_6O	000108-95-2	100 %	T, C		2/3	3/3	4/4	4/4	4/4	1/1	4/4	1/2	4/4	3/3	4/4	3/0	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	0/0	
Phenolharzformmasse	—	—		?		1/1	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(4)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Phenyethylen	-> siehe: Styrol																													

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste													Fluor-Kunststoffe				Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZÜNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Phenyl-2-propenal, trans-3-	-> siehe: Zimtaldehyd																													
Phenylamin	-> siehe: Anilin																													
Phenylanilin, N-	-> siehe: Diphenylamin																													
Phenylbromid	-> siehe: Brombenzol																													
Phenylcarbinol	-> siehe: Benzylalkohol																													
Phenylchlorid	-> siehe: Chlorbenzol																													
Phenylethanol	$C_8H_{10}O$	000060-12-8		Xn		0/0	0/0	3/0	4/4	0/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(1)	(1)	(1)		
Phenylether	-> siehe: Diphenylether																													
Phenylethylalkohol	-> siehe: Phenylethanol																													
Phenylethylether	$C_8H_{10}O$	000103-73-1		?		0/0	0/0	(2)	(4)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Phenylhydrazin	$C_6H_8N_2$	000100-63-0	techn. rein	T		3/0	0/0	(3)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/3	4/4	0/0	(2)	0/0	0/0	0/0	
Phenylhydrazinchlorhydrat	-> siehe: Phenylhydrazin-HCl																													
Phenylhydrazin-HCl	$C_6H_8N_2$-HCl	000059-88-1		T		0/0	0/0	(3)	(2)	0/0	0/0	(3)	1/3	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/3	1/3	0/0	(4)	(4L)	(4L)		
Phenylpropan	-> siehe: Cumol																													
Phenylsulfonat	—	70528-83-5		?		0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Phenylsulfonsäure	-> siehe: Benzolsulfonsäure																													
Phosgen	$COCl_2$	000075-44-5	flüssig	T+, C		0/0	0/0	1/0	(3)	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	1/0	3/0	0/0	(3)	3/4	3/4	0/0	
Phosgen	$COCl_2$	000075-44-5	gasförmig	T+, C		0/0	3/0	1/0	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	3/0	0/0	(3)	3/4	3/4	0/0	
Phosphate	—	—	wässrig	?		1/1	1/1	0/0	0/0	(1)	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	0/0	(1)	(1)		Salze der Phosphorsäure
Phosphin	PH_3	007803-51-2	konz.	F+, T+	X	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Phosphor-(III)-chlorid	-> siehe: Phosphortrichlorid																													
Phosphoroxychlorid	PCl_3O	010025-87-3	100 %	T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	
Phosphoroxychlorid	PCl_3O	010025-87-3		T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	
Phosphorpentachlorid	PCl_5	010026-13-8		T+, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	1/1	(3)	(3)	4/4	0/0	1/1	1/3L	1/3L		
Phosphorpentoxid	P_4O_{10}	001314-56-3	techn. rein	C		1/0	0/0	(4)	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	(3)	(2)	3/4	0/0	1/1	1/0	1/0	0/0	
Phosphorperchlorid	-> siehe: Phosphorpentachlorid																													
Phosphorsäure	H_3PO_4	007664-38-2	30 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphorsäure	H_3PO_4	007664-38-2	85 %	C		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	1/1	1/2	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	2/4	1/3	1/1	
Phosphorsäure	H_3PO_4	007664-38-2	1-5 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	3/4	1/1	2/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	(4)	1/1	1/1	1/1	
Phosphorsäure	H_3PO_4	007664-38-2	20%	Xi		1/1	1/1	4/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphorsäureanhydrid	-> siehe: Phosphorpentoxid																													
Phosphorsäurechlorid	-> siehe: Phosphorpentachlorid																													
Phosphorsäuretritolyester	-> siehe: Trikresylphosphat																													
Phosphortrichlorid	PCl_3	007719-12-2		T, C		3/3	3/3	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/1	1/0	3/4	4/4	0/0	1/1	0/0	0/0	1/1	
Phosphorwasserstoff	-> siehe: Phosphin																													
Phosphorylchlorid	-> siehe: Phosphoroxychlorid																													
Phthalsäure	$C_8H_6O_4$	000088-99-3	gesättigt	Xi		1/1	1/1	3/3	(3)	1/0	0/0	1/0	1/1	1/0	0/0	1/4	0/0	1/1	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	
Phthalsäureamylester	$C_{18}H_{26}O_4$	000131-18-0	100 %	(T)		0/0	1/3	(1)	(4)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Phthalsäuredibutylester	-> siehe: Dibutylphthalat																													
Phthalsäuredicyclohexylester	-> siehe: Dicyclohexylphthalat																													
Phthalsäuredimethylester	-> siehe: Dimethylphthalat																													
Phthalsäuredinonylester	-> siehe: Dinonylphthalat																													
Phthalsäuremonoamylester	$C_{13}H_{16}O_4$	??		(Xn)		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	(1)	(1)		
Pikrinsäure	$C_6H_3N_3O_7$	000088-89-1	1 % wässrig	T		1/0	1/0	3/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	4/4	0/0	0/0	1/0	1/0	1/1	3/0	1/0	3/4	0/0	1/0	1/0	1/0	1/0	
Piment	—	—	gemahlen	?		0/0	0/0	(2)	4/4		0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Piperidin	$C_5H_{11}N$	000110-89-4		F, T, C		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Polyesterharze	—	—		(Xn)	(X)	3/4	3/4	1/0	4/4	1/0	0/0	(2)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Polyethylenglycol	HO-$(C_2H_4O)_n$-H	025322-68-3	100 %	(—)		1/1	1/1	(3)	0/0	0/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2-3)	(2)	(3)	0/0	(1)	(1)	(1)	0/0	
Polyglycol	-> siehe: Polyethylenglycol																													
Polyoxyethylen	-> siehe: Polyethylenglycol																													
Polyoxymethylen	-> siehe: Paraformaldehyd																													
Polyran M25 N	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	3	0	0	(1)	(1)		Schmieröl
Polyran M400	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	(3)	0	0	(1)	(1)		Schmieröl
Polysiloxan	-> siehe: Siliconöl																													
Polysolvan O	$C_6H_{12}O_3$	007397-62-8	100 %	Xi		0/0	1/1	(2)	(3)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	(3)	0/0	(1)	(1)	(1)		Lösemittel, Glykolsäurebutylester; Celanese AG

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste													Fluor-Kunststoffe			Elastomere			Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZENTRATION	GEFAHRENHINWEIS	ENTZÜNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMERKUNG
Pomeranzenöl	—	068916-04-1		?		2/3	3/4	(2)	3/3	1/0	3/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	4/4	(2)	(4)	0/0	(1)	(1)	(1)		
Pottasche	-> siehe: Kaliumcarbonat																													
Pressluft	—	—	ölhaltig	—		1/0	0/0	(2)	(2)	(1)	0/0	(1)	3/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	1/1	1/1	1/1		
Prontosil	—	—		(Xn)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	0/0	0/0		Chemotherapeutikum; Bayer - nicht mehr im Handel
Prop-2-enylacetat	-> siehe: Allylacetat																													
Propan	C_3H_8	000074-98-6	flüssig	F+	X	1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/0	0/0	1/0	1/0	3/0	1/0	0/0	(1)	1/1	1/1	4/4	1/0	(2)	0/0	1/1	1/1	1/1	0/0	
Propan	C_3H_8	000074-98-6	gasförmig	F+	X	3/4	4/4	1/0	3/4	1/0	4/4	1/1	2/4	4/4	3/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Propandiol, 1,2-	-> siehe: Propylenglycol																													
Propanol	C_3H_8O	000071-23-8		F	X	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	3/0	0/0	2/2	3/3	1/4	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/1	(1)	(1)	0/0	
Propanol, 2-	-> siehe: Isopropanol																													
Propanon, 2-	-> siehe: Aceton																													
Propansäure	-> siehe: Propionsäure																													
Propantriol	-> siehe: Glycerin																													
Propargylalkohol	C_3H_4O	000107-19-7	7 %	Xn		1/1	1/1	(3)	1/0	0/0	0/0	(2)	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/3	1/0	1/1	1/1	0/0	1/0	(1)	(1)	0/0	
Propen	C_3H_6	000115-07-1		F+	X	1/1	1/1	1/0	(3)	1/0	0/0	1/0	1/1	4/4	0/0	3/4	4/4	0/0	0/0	(1)	1/1	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Propen-1-ol, 2-	-> siehe: Allylalkohol																													
Propensäureethylester	-> siehe: Ethylacrylat																													
Propin-1-ol, 2-	-> siehe: Propargylalkohol																													
Propionsäure	$C_3H_6O_2$	000079-09-4	50 %	C, F	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/1	4/4	4/4	1/3	3/3	0/0	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	1/1	(1)	(1)	1/1	
Propionsäure	$C_3H_6O_2$	000079-09-4		C, F+	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	1/1	
Propylacetat	$C_5H_{10}O_2$	000109-60-4		F	X	0/0	0/0	(1)	4/4	0/0	(4)	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Propylalkohol	-> siehe: Propanol																													
Propylamin, n-	C_3H_9N	000107-10-8		F, C, Xn	X	0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Propylen	-> siehe: Propen																													
Propylen(di)chlorid	-> siehe: Dichlorpropan																													
Propylenglycol	$C_3H_8O_2$	000057-55-6		—		1/1	1/1	4/4	2/3	(2)	1/1	1/0	1/1	1/1	2/2	3/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	(1)	(1)	1/1	
Propylenglycolmethylether	$C_4H_{10}O_2$	—		—	X	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		Isomeres in der Quelle nicht angegeben
Propylenoxid	C_3H_6O	000075-56-9		F+, T	X	1/1	1/2	(3)	2/3	0/0	1/2	(2)	1/2	4/4	2/2	3/4	0/0	4/4	3/4	1/1	1/0	1/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Propylidintris(methanol)	-> siehe: Trimethylolpropan																													
Propylnitrat	$C_3H_7NO_3$	000627-13-4		(E, Xn)	(X)	0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(2)	(1)	(1)		
Pseudocumol	C_9H_{12}	000095-63-6		Xn	X	0/0	0/0	(1)	(4)	0/0	0/0	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(2)	4/4	0/0	1/1	1/1	1/1		
Pydraul C (312, 540)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	1/0	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Monsanto
Pydraul E (29, 30, 50, 65, 90, 11)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Monsanto
Pyridin	C_5H_5N	000110-86-1		F, Xn	X	1/3	0/2	1/0	4/4	0/0	0/2	1/1	3/3	4/4	4/4	4/4	4/4	4/4	1/1	(2)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Pyridin-3-carbonsäure	-> siehe: Nicotinsäure																													
Pyrogallol	$C_6H_6O_3$	000087-66-1		Xn		0/0	0/0	1/0	(3)	0/0	0/0	3/4	1/0	3/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	1/1	(3)	(3)	(3)	0/0	1/1	1/1	1/1	1/1	
Pyrosulfit	-> siehe: Natriumdisulfit																													
Pyrrol	C_4H_5N	000109-97-7		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Quecksilber	Hg	007439-97-6	rein	T		1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(3)	1/1	1/1		
Quecksilber-(II)-chlorid	$HgCl_2$	007487-94-7	wässrig	T+, C		1/1	1/1	4/4	1/0	(2)	1/1	3/0	1/1	1/3	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	(4)	(4)	1/1	Sublimat
Quecksilber-(II)-cyanid	C_2HgN_2	000592-04-1	gesättigt	T+		1/1	1/1	(3)	(2)	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	1/1	(1)	1/1	(2)	0/0	4/4	1/0	1/0	1/1	
Quecksilber-(II)-nitrat	-> siehe: Quecksilbernitrat																													
Quecksilbernitrat	$Hg(NO_3)_2$	010045-94-0	gesättigt	(T+)		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	1/0	0/0	1/3	1/0	0/0	(1)	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	1/1	1/1	1/1	
Quecksilberpernitrat	-> siehe: Quecksilbernitrat																													
Ramasit	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	Hydrophobierungsmittel für Textilien; BASF
Resorcin	$C_6H_6O_2$	000108-46-3	5 %	—		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	2/4	0/0	3/3	1/3	1/1	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Resorcin	$C_6H_6O_2$	000108-46-3	gesättigt	Xn		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	3/4	0/0	0/0	1/1	(1)	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Rindertalg	—	061789-97-7		—		0/0	0/0	1/0	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Rindertalg-Emulsion	—	—	sulfuriert	(—)		1/0	0/0	(2)	(2)	0/0	0/0	0/0	1/0	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(2)	(2)	0/0	(2)	(1)	(1)	0/0	
Rizinusöl	—	008001-79-4	100 %	Xi		1/1	1/1	1/0	1/0	(1)	1/0	(2)	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Rohöl	—	—	100 %	(N)		0/0	1/3	1/0	(3)	1/0	0/0	1/0	1/3	3/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/3	0/0	(2)	(1)	(1)		

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste													Fluor-Kunststoffe			Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Rosenöl	—	008007-01-0		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Röstgase	—	—	jede	(T)		0/0	0/0	(2)	0/0	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(4)	(2)	(2)	0/0	
Rüböl	—	008002-13-9		—		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	(1)	1/1	1/1		
Rumaroma	—	008030-89-5		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(3)	(3)	(4)	(3)	0/0	(1)	(1)	(1)		
Sagrotan	—	—	flüssig	?		1/2	1/3	0/0	3/0	0/0	0/0	(3)	1/3	3/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	3/0	0/0	(2)	(1)	(1)		Desinfektionsmittel; Schülke & Mayr
Salicylaldehyd	$C_7H_6O_2$	000090-02-8		Xn, Xi		1/1	1/2	(3)	2/3	0/0	1/2	(3)	1/2	4/4	3/3	3/4	0/0	0/0	1/4	1/1	(1)	(3)	(3)	(3)	4/4	0/0	(2)	(1)	(1)		
Salicylsäure	$C_7H_6O_3$	000069-72-7	gesättigt	(Xn, Xi)		1/1	1/1	1/0	1/2	1/0	1/1	4/4	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1	
Salicylsäure	$C_7H_6O_3$	000069-72-7	Pulver	Xn, Xi		1/1	1/1	1/0	1/2	(1)	1/2	(3)	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1	
Salicylsäuremethylester	-> siehe: Methylsalicylat																													
Salmiak	-> siehe: Ammoniumchlorid																													
Salmiakgeist	-> siehe: Ammoniumhydroxid																													
Salpetersäure	HNO_3	007697-37-2	1-10 %	C		1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1	1/1	
Salpetersäure	HNO_3	007697-37-2	50 %	C+		2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Salpetersäure	HNO_3	007697-37-2	66 %	C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Salpetersäure	HNO_3	007697-37-2	100 %	O, C+		4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	0/0	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	?	
Salpetersäure	HNO_3	007697-37-2	70 %	O, C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2	1/2	
Salzsäure	HCl	007647-01-0	1-5 %	—		1/1	1/1	4/4	1/1	(2)	1/2	4/4	1/1	1/1	1/1	1/1	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	3/4	0/0	4/4	4/4	4/4	1/1	
Salzsäure	HCl	007647-01-0	35 %	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	1/1	
Salzsäure	HCl	007647-01-0	konz.	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	1/1	
Salzsäure	HCl	007647-01-0	20 %	Xi		1/1	1/1	4/4	2/3	3/0	1/2	4/4	1/1	1/1	1/1	1/3	0/0	0/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	4/4	4/4	4/4	1/1	Chlorwasserstoffsäure
Salzsäure-Aluminiumsalz, wasserfrei	-> siehe: Aluminiumchlorid																													
Salzsole	NaCl	007647-14-5	gesättigt	—		1/1	1/1	1/0	(1)	(1)	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3	1/2	0/0	
Salzwasser, Meerwasser	—	—		—		1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	
Sattdampfkondensat	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(2)	1/1	1/1		
Sauerstoff	O_2	007782-44-7	techn. rein	O		1/3	1/3	2/0	1/0	(1)	0/0	1/0	1/3	1/0	0/0	1/1	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Schmieröle	—	—		?		1/3	2/3	(2-3)	(1)	(2)	0/0	(2)	3/0	0/0	0/0	1/1	1/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0	
Schmierseife	—	—	verdünnt	?		1/3	1/1	(2-3)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(1)	1/1	0/0	(2)	(1)	(1)	0/0	
Schwefel	S_8	007704-34-9	techn. rein	Xi		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	3/0	3/4	1/1	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	(1)	1/1	1/1	1/1	Sulfur, Netzschwefel, Schwefelblüte
Schwefel, geschmolzen, 121 °C	S_8	007704-34-9		?		0	0	(4)	(3)	0	4	4	4	4	0	0	0	4	0	0	(1)	0	4	1	4	0	(3)	1	1	0/0	
Schwefelchlorid	S_2Cl_2	010025-67-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	4/4	1/0	4/4	0/0	3/4	(1/1L)[1]	(1/1L)[1]	0/0	[1] wasserfrei! Wenn durch Feuchtigkeit auch nur Spuren von Salzsäure (HCl) abgespaltet werden, besteht die Gefahr von Lochfraß, Spalt- und Spannungsrisskorrosion.
Schwefeldioxid	SO_2	007446-09-5	feucht	T, C		1/1	1/1	(3)	(3)	0/0	1/1	4/4	1/3	3/4	2/2	1/2	0/0	0/0	1/1	1/1	1/1	1/4	1/0	4/4	4/4	0/0	3/4	1/1	1/1	1/0	mit H2O -> Schweflige Säure
Schwefeldioxid	SO_2	007446-09-5	flüssig	T, C		3/4	4/4	(3)	3/4	0/0	4/4	4/4	4/4	4/4	2/2	3/4	0/0	0/0	1/2	1/1	1/1	4/4	1/0	4/4	4/4	0/0	(3)	(1)	(1)	1/0	mit H2O -> Schweflige Säure
Schwefeldioxid, wässrige Lösung	-> siehe: Schweflige Säure																													
Schwefelether	-> siehe: Ethylether																													
Schwefelhexafluorid	SF_6	002551-62-4		—		0/0	0/0	1/0	(2)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	1/0	0/0	0/0	(1)	(2)	1/0	3/0	1/0	0/0	(1)	(1)	(1)		
Schwefelkohlenstoff	CS_2	000075-15-0		F+, T	X	4/4	4/4	3/0	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/3	1/1	1/0	1/1	4/4	1/0	4/4	0/0	1/1	1/1	1/1	1/0	
Schwefelmonochlorid	-> siehe: Schwefelchlorid																													
Schwefelnatrium	-> siehe: Natriumsulfid																													
Schwefelsäure	H_2SO_4	007664-93-9	40 %	C+		1/1	1/1	4/4	2/0	(4)	1/2	4/4	1/1	2/0	3/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	(3)	1/1	4/4	0/0	3/4	2/3	2/3	0/0	
Schwefelsäure	H_2SO_4	007664-93-9	60 %	C+		1/3	1/3	4/4	3/3	(4)	1/2	4/4	1/3	2/4	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	4/4	3/4	0/0	
Schwefelsäure	H_2SO_4	007664-93-9	80 %	C+		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/1	3/4	3/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	2/4	2/3	0/0	
Schwefelsäure	H_2SO_4	007664-93-9	95 %	C+		3/4	3/4	4/4	4/4	4/4	2/2	4/4	3/4	4/4	4/4	2/4	0/0	4/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	1/3	1/3	0/0	
Schwefelsäure	H_2SO_4	007664-93-9	rauchend	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	4/4	4/4	1/0	4/4	0/0	(3)	1/2	1/1	0/0	Oleum
Schwefelsäure	H_2SO_4	007664-93-9	1-6 %	Xi		1/1	1/1	4/4	1/1	0/0	1/1	4/4	1/1	1/2	1/1	1/2	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/0	0/0	(3)	2/2	1/2	0/0	
Schwefelsäure	H_2SO_4	007664-93-9	20 %	Xi		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	(3)	2/3	2/3		
Schwefelsäure Kupfer-(II)-Salz	-> siehe: Kupfersulfat																													
Schwefelsäuremonomethylester	-> siehe: Methylschwefelsäure																													
Schwefeltrioxid	SO_3	007446-11-9		C+		4/4	4/4	4/4	(4)	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	(2)	(2)	3/4	3/0	1/0	4/4	0/0	(3)	(1)	(1)	0/0	
Schwefelwasserstoff	H_2S	007783-06-4	gesättigt	F+, T+	X	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	3/0	1/0	1/3	3/3	1/0	0/0	1/0	1/1	1/1	1/0	(3)	4/4	0/0	1/1	1/1	1/1	0/0	
Schweflige Säure	H_2SO_3	007782-99-2	gesättigt	(C)		1/1	1/1	4/4	4/4	1/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	3/0	(3)	3/4	0/0	3/4	1/1	1/1	1/1	
Schwefligsäuredichlorid	-> siehe: Thionylchlorid																													
Schweinefett	—	—		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	2/0	1/0	1/0	0/0	(1)	1/1	1/1		

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

							---------- Thermoplaste ----------		Fluor-Kunststoffe		--- Elastomere ---		------- Metalle -------		
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Sebacinsäuredibenzylester	-> siehe: Dibenzylsebacat																																			
Sebacinsäuredibutylester	-> siehe: Dibutylsebacat																																			
Sebacinsäurediethylester	-> siehe: Diethylsebacat																																			
Seewasser, Meerwasser	-> siehe: Salzwasser, Meerwasser																																			
Seifenlösung	—	—	jede	(—)		1/1	0/0	4/4	(2)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/1						
Senf	—	—		—		0/0	0/0	(2)	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	1/0	1/0	0/0	(2)	1/0L	1/0L						
Senföl	-> siehe: Allylsenföl																																			
Silberacetat	$C_2H_3AgO_2$	000563-63-3		Xi		1/1	1/1	(2)	1/2	(2)	1/1	(2)	1/1	2/2	1/1	2/2	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	(3)	0/0	(4)	0/0	0/0	0/0						
Silbercyanid	CAgN	000506-64-9		T		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	(1)	(1)	(3)	0/0	(4)	0/0	0/0	0/0						
Silbernitrat	$AgNO_3$	007761-88-8	wässrig	C		1/1	0/0	1/0	1/1	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	1/1	Höllenstein					
Silbernitrat	$AgNO_3$	007761-88-8		C		1/1	1/2	1/0	1/1	(2)	1/1	1/0	1/2	2/3	1/1	1/2	1/3	1/2	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	1/1	Höllenstein					
Siliciumdioxid	-> siehe: Kieselsäure																																			
Siliconfette	—	—		(—)		0/0	0/0	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	1/0	1/0	1/1	0/0	1/1	1/1	1/1						
Siliconöl	—	—		?		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	3/3	1/0	1/4	0/0	1/1	0/0	1/1	1/1	(1)	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	Polysiloxan					
Skydrol 500 (B4)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	0/0	1/0	4/4	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Solutia				
Skydrol 7000	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	1/0	2/0	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Solutia				
Soda	-> siehe: Natriumcarbonat																																			
Sojaöl	—	008001-22-7		—		0/0	0/0	(2)	(1)	1/0	0/0	2/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	1/1						
Spindelöl	—	—		?		3/3	2/3	(2)	(2)	1/0	0/0	(2)	1/4	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/1	1/1	0/0	1/1	1/1	1/1	1/1						
Spinnbadsäuren	—	—	100mg CS_2/l	?		1/0	0/0	4/4	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(3)	(2)	4/4	0/0	(4)	3/4	2/4	0/0						
Spinnlösung, viskose ~	—	—		(Xn, Xi)		1/1	1/1	4/4	(3)	0/0	0/0		1/1	0/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	(3)	(2)	4/4	0/0	(3)	3/4	2/4	0/0						
Spirituosen	C_2H_6O	—		—		1/1	1/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	1/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	0/0	Ethanol 40 %					
Spiritus	C_2H_6O	—		F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1		Ethanol					
Spülmittel	—	—	wässrig	?		1/1	1/1	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0						
Stärkegummi	-> siehe: Dextrin																																			
Stärkelösung	$(C_6H_{10}O_5)_n$	—	jede	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0						
Stärkesirup	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0						
Staufferfett	—	—		(—)		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	1/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	(1)	(2)	0/0	(1)	1/1	1/1	0/0						
Stearinsäure	$C_{18}H_{36}O_2$	000057-11-4	Kristalle	Xi		1/3	1/3	1/0	1/2	1/0	1/1	1/0	1/3	1/2	2/2	1/2	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1						
Stearinsäure Zinksalz	-> siehe: Zinkstearat																																			
Stearinsäurebutylester	$C_{22}H_{44}O_2$	000123-95-5	100 %	Xi		0/0	0/0	(1)	(3)	1/0	0/0	(2)	(2)	0/0	0/0	1/0	1/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1	0/0						
Steinkohlenteeröl	—	092045-38-0	100 %	T		1/0	1/3	1/0	(3)	0/0	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	1/1	1/1							
Stickstoff	N_2	007727-37-9		—		0/0	0/0	1/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1							
Stickstofftetroxid	N_2O_4	010544-72-6		(O), T+, C		0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(2)	(1)	(1)							
Strontiumbromid	$SrBr_2$	010476-81-0		Xi		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(3)	0/0	0/0							
Strychnin	$C_{21}H_{22}N_2O_2$	000057-24-9		T+		1/1	1/1	(1)	(1)	(2)	0/0	(2)	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)							
Styrol	C_8H_8	000100-42-5	100 %	Xn, Xi	X	4/4	3/4	1/1	4/4	1/1	(4)	1/1	3/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(2)	4/4	3/0	4/4	0/0	1/1	1/1	1/1	0/0						
Sulfitlauge	-> siehe: Calciumbisulfit																																			
Sulfurylchlorid	Cl_2SO_2	007791-25-5	techn. rein	C		4/4	4/4	4/4	1/0	0/0	0/0	4/4	4/4	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/0	3/0	3/0	1/0	4/4	0/0	3/4	0/0	0/0							
Talg	—	—	techn. rein	—		1/1	1/1	1/0	(1)	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1	0/0						
Tannin	$C_{76}H_{52}O_{46}$	001401-55-4	10 %	Xi		1/1	1/1	1/0	3/3	0/0	1/1	4/4	1/1	3/3	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	1/1						
Tannin	$C_{76}H_{52}O_{46}$	001401-55-4		Xi		1/1	1/1	1/0	4/4	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	1/1						
Teer	—	—		T		0/0	1/0	1/0	(3)	1/0	0/0	1/0	(2)	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(1)	(1)	(1)							
Tenside	-> siehe: Netzmittel																																			
Terpentinersatz	—	—		Xn, N	X	0/0	0/0	1/0	(3)	1/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	(3)	0/0	1/1	1/1	1/1	1/1						
Terpentinöl	—	008006-64-2		Xn	X	2/2	3/4	1/0	4/4	1/0	3/3	1/1	4/4	4/4	4/4	2/3	4/4	3/3	1/1	1/1	1/0	1/3	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1						
Testbenzin	—	—	flüssig	Xn, N	X	0/0	2/3	(1)	(3)	1/0	(4)	1/0	3/4	4/4	0/0	1/3	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0						
Testkraftstoff A (ISO-Fluid A)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	1/0	0/0	(1)	(1)	(1)							
Testkraftstoff B (ISO-Fluid B)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)							
Testkraftstoff C (ISO-Fluid C)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)							
Testkraftstoff D (ISO-Fluid D)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	4/4	0/0	(1)	(1)	(1)							
Tetrabromethan (TBE)	$C_2H_2Br_4$	—	100 %	T+		4/4	3/4	(3)	4/4	(4)	(4)	(3)	3/4	4/4	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	0/0	Isomeres in der Quelle nicht angegeben					
Tetrabromkohlenstoff	CBr_4	000558-13-4		Xn, Xi		0/0	0/0	(3)	4/4	0/0	0/0	(3)	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0							
Tetrabrommethan	-> siehe: Tetrabromkohlenstoff																																			

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

						Thermoplaste														Fluor-Kunststoffe				Elastomere				Metalle			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Tetrachlorethan	$C_2H_2Cl_4$	—	techn. rein	T+		3/0	3/4	3/0	4/4	(4)	(4)	1/1	3/4	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0	0/0	Isomeres in der Quelle nicht angegeben
Tetrachlorethen	-> siehe: Perchlorethylen																														
Tetrachlorethylen	-> siehe: Perchlorethylen																														
Tetrachlorkohlenstoff (TETRA)	CCl_4	000056-23-5		T		4/4	4/4	4/4	4/4	1/4	4/4	2/3	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	1/1	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]	1/1	[1] wasserfrei! Wenn durch Feuchtigkeit auch nur Spuren von Salzsäure (HCl) abgespaltet werden, besteht die Gefahr von Lochfraß, Spalt- und Spannungsrisskorrosion.
Tetrachlormethan	-> siehe: Tetrachlorkohlenstoff																														
Tetrachlortitan	-> siehe: Titantetrachlorid																														
Tetraethylblei (TEL)	$C_8H_{20}Pb$	000078-00-2	techn. rein	T+	X	1/0	1/0	1/4	3/0	(2)	(4)	(2)	2/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/0	0/0	(2)	(1)	(1)	1/1	
Tetraethylorthosilicat	$C_8H_{20}SiO_4$	000078-10-4		Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	1/0	0/0	(1)	(1)	(1)		
Tetrafluormethan	CF_4	000075-73-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Tetrahydro-1,4-oxazin	-> siehe: Morpholin																														
Tetrahydrofuran (THF)	C_4H_8O	000109-99-9		F, Xi	X	3/4	4/4	1/0	4/4	1/0	3/4	1/3	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	1/1	
Tetrahydrofurfurylalkohol	$C_5H_{10}O_2$	000097-99-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(2)	(1)	(1)		
Tetrahydronaphthalin	$C_{10}H_{12}$	000119-64-2	techn. rein	Xi		3/4	4/4	1/0	4/4	1/0	(4)	1/0	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	1/0	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Tetralin	-> siehe: Tetrahydronaphthalin																														
Tetramethylenoxid	-> siehe: Tetrahydrofuran																														
Tetraphosphordecaoxid	-> siehe: Phosphorpentoxid																														
Thiacyclopentadien	-> siehe: Thiophen																														
Thiofuran	-> siehe: Thiophen																														
Thioglycolsäure	$C_2H_4SO_2$	000068-11-1		T, C		0/0	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	(4)	0/0	3/4	0/0	1/1	0/0	
Thionylchlorid	Cl_2SO	007719-09-7	techn. rein	C		4/4	4/4	4/4	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	(3)	3/0	1/0	4/4	0/0	3/4	0/0	0/0	0/0	
Thiophen	C_2H_4S	000110-02-1		F, Xn	X	3/3	3/3	(2)	4/4	0/0	(4)	(2)	3/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	4/4	3/0	0/0	(1)	(1)	(1)	0/0	
Thymol	$C_{10}H_{14}O$	000089-83-8		C, Xn		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(3)	3/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	1/0	4/4	0/0	(1)	(1)	(1)		
Titanchlorid	-> siehe: Titantetrachlorid																														
Titantetrachlorid	$TiCl_4$	007550-45-0		C		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(4)	0/0	0/0		
Toluen	-> siehe: Methylbenzol																														
Toluol	-> siehe: Methylbenzol																														
Toluolsulfonchloramid-Natrium, p-	-> siehe: Chloramin T																														
Traganth	—	009000-65-1		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1		
Transformatorenöl	—	—		?		1/3	3/3	1/0	(3)	1/1	1/0	3/3	1/3	1/3	1/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	2/3	3/3	0/0	1/1	(1)	(1)	0/0	
Traubenzucker	-> siehe: Glucose																														
Triacetin	$C_9H_{14}O_6$	000102-76-1		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	3/3	0/0	(1)	(1)	(1)		
Tribrommethan	-> siehe: Bromoform																														
Tributylcitrat	$C_{18}H_{32}O_7$	000077-94-1		—		1/2	2/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Tributylphosphat (TBP)	$C_{12}H_{27}PO_4$	000126-73-8	techn. rein	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Trichloracetaldehyd	C_2HCl_3O	000075-87-6	100 %	T/Xi		1/1	1/1	4/4	(3)	(4)	0/0	(3)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	0/0	(4)	3/0	(4)	4/4	0/0	4/4	0/0	0/0	0/0	
Trichloracetaldehyd-hydrat	-> siehe: Chloralhydrat																														
Trichloraldehydhydrat	-> siehe: Chloralhydrat																														
Trichlorbenzol	$C_6H_3Cl_3$	—	100 %	(Xn)		4/4	4/4	(3)	(3)	0/0	(4)	(2)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	(2)	(3)	(4)	(3)	4/4	0/0	(2)	0/0	0/0	0/0	Isomeres in der Quelle nicht angegeben
Trichloressigsäure (TCA)	$C_2HCl_3O_2$	000076-03-9		C+		1/4	3/4	4/4	4/4	4/4	0/0	4/4	1/1	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	1/3	3/0L	2/0L	1/1	
Trichlorethan	$C_2H_3Cl_3$	—		Xn		3/4	4/4	3/0	4/4	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	(1)	1/3	4/4	1/0	4/4	0/0	4/4	0/0	0/0	0/0	Isomeres in der Quelle nicht angegeben
Trichlorethen	-> siehe: Trichlorethylen																														
Trichlorethylen (TRI)	C_2HCl_3	000079-01-6	100 %	Xn		3/4	4/4	3/0	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/4	1/2	1/1	1/0	1/1	4/4	1/3	4/4	0/0	1/3	(1/1L)[1]	(1/1L)[1]	1/0	[1] wasserfrei! Wenn durch Feuchtigkeit auch nur Spuren von Salzsäure (HCl) abgespaltet werden, besteht die Gefahr von Lochfraß, Spalt- und Spannungsrisskorrosion.
Trichlorfluormethan	CCl_3F	000075-69-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(3)	(1)	0/0	4/4	2/0	1/0	0/0	(3)	0/0	0/0	0/0	
Trichlormethan	-> siehe: Chloroform																														
Trichlormonofluormethan	-> siehe: Trichlorfluormethan																														

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

							---------- Thermoplaste ----------		Fluor-Kunststoffe		--- Elastomere ---		------- Metalle -------		
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Trichlorphenol	$C_6H_3Cl_3O$	—		(Xn, Xi)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(4)	(3)	(4)	0/0	(3)	0/0	0/0		Isomeres in der Quelle nicht angegeben
Trichlorphosphin	-> siehe: Phosphortrichlorid																														
Trichlorphosphinoxid	-> siehe: Phosphoroxychlorid																														
Trichlorphosphoroxid	-> siehe: Phosphoroxychlorid																														
Trichlortrifluorethan	$C_2Cl_3F_3$	000076-13-1		?		0/0	0/0	1/0	(3)	1/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		
Triethanolamin (TEA)	$C_6H_{15}NO_3$	000102-71-6	techn. rein	Xi		1/1	1/2	(2)	(2)	1/0	0/0	2/2	1/1	1/1	0/0	3/0	4/4	1/1	0/0	1/1	1/0	1/0	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Triethylamin (TEA)	$C_6H_{15}N$	000121-44-8	techn. rein	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	1/1	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	3/4	4/4	3/0	3/4	0/0	(1)	(1)	(1)	0/0	
Triethylenglycol	-> siehe: Triglycol																														
Triethylenglykoldiacetat	-> siehe: Triglycolacetat																														
Trifluortrichlorethan	$C_2Cl_3F_3$	—	100 %	?		4/4	3/4	1/0	3/0	0/0	0/0	1/0	4/4	4/4	1/0	3/4	4/4	3/3	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		Isomeres in der Quelle nicht angegeben
Triglycol	$C_6H_{14}O_4$	000112-27-6		Xi		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	(3)	0/0	(1)	(1)	(1)	0/0	
Triglycolacetat	$C_{10}H_{18}O_6$	000111-21-7		?		0/0	0/0	(3)	(3)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)		
Trihydroxybenzoesäure, 3,4,5-	-> siehe: Gallussäure																														
Trihydroxybenzol, 1,2,3-	-> siehe: Pyrogallol																														
Trihydroxybutan	-> siehe: Butantriol																														
Trihydroxypurin, 2,6,8-	-> siehe: Harnsäure																														
Trihydroxytriethylamin	-> siehe: Triethanolamin																														
Triiodmethan	-> siehe: Jodoform																														
Triisopropylbenzol	$C_{15}H_{24}$	000717-74-8		—		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Trikresylphosphat (TCF)	$C_{21}H_{21}PO_4$	—	techn. rein	T/Xn, N		1/1	1/1	1/0	4/4	1/0	0/0	1/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	1/1	1/1	1/1	1/1	Isomeres in der Quelle nicht angegeben
Trimethylbenzol, 1,3,4-	-> siehe: Pseudocumol																														
Trimethylolpropan	$C_6H_{14}O_3$	000077-99-6	wässrig	—		0/0	0/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	0/0	(1)	(1)	(1)		
Trimethylpentan, 2,2,4-	-> siehe: Isooctan																														
Trinatriumphosphat	Na_3PO_4	007601-54-9		Xi		1/1	1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(4)	1/1	1/1		
Trinatriumphosphat, tribasisch	-> siehe: Natriumphosphat																														
Trinitrophenol, 2,4,6-	-> siehe: Pikrinsäure																														
Trioctylphosphat	$C_{24}H_{54}PO_4$	000078-42-2	techn. rein	(Xn)		3/0	1/0	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	(1)	(1)	(1)	0/0	
Tripen	-> siehe: Hexachlorbutadien																														
Tripropylenglycol (TPG)	$C_9H_{20}O_4$	024800-44-0		(—)		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/1	(2)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Tris(2-ethylhexyl)-phosphat	-> siehe: Trioctylphosphat																														
Tris(hydroxyethyl)-amin	-> siehe: Triethanolamin																														
Tris(hydroxymethyl)-propan	-> siehe: Trimethylolpropan																														
Tropasäure-tropylester-sulfat	-> siehe: Atropinsulfat																														
Tungöl	-> siehe: Holzöl																														
Turbinenöl (Mineralölbasis)	—	—		?		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	(2)	1/0	0/0	1/1	1/1	1/1		
Überchlorsäure	-> siehe: Perchlorsäure																														
Undecanol	-> siehe: Undecylalkohol																														
Undecylalkohol	$C_{11}H_{24}O$	000112-42-5		Xi		1/2	1/3	(1)	2/3	(1)	1/2	1/0	1/2	2/2	3/3	1/3	0/0	1/1	1/2	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(1)	(1)	(1)		
Urin	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	3/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	
Urotropin	-> siehe: Hexamethylentetramin																														
Vaseline	—	008009-03-8	techn. rein	(—)		3/4	2/3	1/0	1/0	1/0	0/0		1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Vaselinöl	—	008012-95-1	100 %	?		0/0	1/3	1/0	(2)	1/0	1/0		1/3	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	Paraffinöl
Vaselinöl	—	008012-95-1		?		1/1	1/3	1/0	1/0	1/0	0/0	1/1	1/3	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/3	0/0	1/1	1/1	1/1	1/1	Paraffinöl
Vinylacetat	$C_4H_6O_2$	000108-05-4	techn. rein	F	X	0/0	1/1	1/0	4/4	(3)	(4)		1/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	1/0	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Vinylbenzol	-> siehe: Styrol																														
Vinylcarbinol	-> siehe: Allylalkohol																														
Vinylchlorid	-> siehe: Chlorethylen																														
Vinylcyanid	-> siehe: Acrylnitril																														
Vinylethylen	-> siehe: Butadien, 1,3-																														
Vinylidenchlorid	$C_2H_2Cl_2$	000075-35-4		F+, Xn	X	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	2/3	1/1	(1)	(2)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	
Vitamin C	$C_6H_8O_6$	000050-81-7	flüssig	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	(1)	(1)		
Wachsalkohol	—	—	techn. rein	(—)		3/4	3/4	(2)	(2)	1/0	0/0		3/4	0/0	0/0	1/1	3/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	(1)	(1)	0/0	
Wachse	—	—		—		0/0	1/3	1/1	1/1	1/1	0/0		1/3	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	(4)	1/0	(1)	0/0	1/1	1/1	1/1		

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

| | | | | | | |---------- Thermoplaste ----------| | Fluor-Kunststoffe | |--- Elastomere ---| |------- Metalle -------| | | |
|---|---|---

							-------- Thermoplaste --------		Fluor-Kunststoffe		--- Elastomere ---		------- Metalle -------			
MEDIUM	FORMEL	CAS-NR.	KONZEN-TRATION	GEFAHREN-HINWEIS	ENTZUNDL.	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	ANMER-KUNG
Zuckerrübensaft	—	—		—		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Zuckersäure	—	—	gesättigt	(Xi)		1/1	1/1	(3)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		
Zuckersirup	—	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Zweitaktöl	—	—	100 %	—		0/0	1/3	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		

Je Medium sind zwei Werte angegeben:
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C

Beständigkeit

Je Medium sind zwei Werte angegeben.
linke Zahl = Wert bei +20°C / rechte Zahl = Wert bei +50°C.

0	keine Angabe vorhanden/keine Aussage möglich
1	sehr gut beständig/geeignet
2	gut beständig/geeignet
3	eingeschränkt beständig
4	nicht beständig
K	keine allgemeinen Angaben möglich
L	Gefahr von Lochfraß oder Spannungsrißkorrosion
( )	Schätzwert

Gefahrenhinweise

E	explosiv
O	brandfördernd
F	entzündlich
F+	hochentzündlich
T	giftig
T+	sehr giftig
C	ätzend
Xn	gesundheitsschädlich
Xi	reizend
N	umweltgefährlich

Bezeichnung der Materialien

Thermoplaste

HDPE	Polyethylen hoher Dichte
LDPE	Polyethylen niedriger Dichte
PA	Polyamid (Nylon)
PC	Polycarbonat
PETG	Polyethylenterephthalatglycol (Co-Polyester)
PMP	Polymethylpenten (TPX)
POM	Polyoxymethylen
PP	Polypropylen
PS	Polystyrol
PSU	Polysulfon
PVC	Polyvinylchlorid
SAN	Styrol-Acrylnitril

Fluorkunststoffe

E-CTFE	Ethylen-Chlortrifluorethylen (Halar)
ETFE	Ethylen-Tetrafluorethylen
FEP	Tetrafluorethylen-Perfluorpropylen (Teflon, FEP)
PTFE	Polytetrafluorethylen (Teflon)
PVDF	Polyvinylidenfluorid

Elastomere

EPDM	Ethylen-Propylen-Terpolymer-Kautschuk
FPM/FKM	Fluor-Polymer (Viton)
NBR	Nitril-Kautschuk
SI	Silikon-Kautschuk

Metalle

Al	Aluminium
V2A	Edelstahl 1.4301 (AISI 304)
V4A	Edelstahl 1.4401 (AISI 316)
Hastelloy C	Nickel-Chrom-Molybdän-Legierung

SEZNAM CHEMICKÝCH LÁTEK MACH I

DŮLEŽITÁ POZNÁMKA

Tabulka „Chemická odolnost plastů“ byla uvedena na základě informací od různých výrobců surovin. Hodnoty se týkají výhradně laboratorních testů se surovinami. Plastové díly z nich vyrobené často podléhají vlivům, které nelze zjistit při laboratorních zkouškách (teplota, tlak, namáhání materiálu, působení chemických látek, konstrukční vlastnosti atd.). Z těchto důvodů mohou uvedené hodnoty sloužit pouze jako směrnice. V případě pochybností důrazně doporučujeme provést test. Z těchto informací nelze vyvozovat žádné právní nároky, vylučujeme jakoukoli záruku a odpovědnost. Samotná chemická a mechanická odolnost není pro posouzení použitelnosti výrobku dostačující. Zejména je třeba zohlednit předpisy pro hořlavé kapaliny (ochrana proti výbuchu).

AUTORSKÁ PRÁVA

Děkujeme společnosti Bürkle GmbH za umožnění použití této tabulky.
Tuto tabulku vydává a spravuje společnost Bürkle GmbH, D-79415 Bad Bellingen jako referenční dílo. Toto upozornění na autorská práva nesmí být odstraněno. Tabulka může být volně šířena a kopírována, pokud zůstane zachována poznámka o autorských právech.

Jazyk seznamu chemických látek: Angličtina

SEZNAM MATERIÁLŮ MACH I

Nádrž:	PP	Sací hadice:	PP, EVA
Čerpadla na špinavou vodu:	PP + GF20	Výpustná hadice:	PP, EVA
Zpětný ventil:	PP	Podlahová hubice:	PP
Šroubové spojení:	PP	Sací trubice:	PP
Spojky C:	PA6 + GF30	Sací hlavice:	ABS

LIST OF CHEMICALS MACH I

IMPORTANT NOTICE

The table „Chemical resistance of plastics“ was listed based on information from various raw material manufacturers. The values refer exclusively to laboratory tests with raw materials. Plastic parts made from them are often subject to influences that cannot be detected in laboratory tests (temperature, pressure, material stresses, exposure to chemical substances, design features, etc.). For these reasons, the values given can only serve as a guideline. In cases of doubt, we strongly recommend carrying out a test. No legal claim can be derived from this information, we exclude any warranty and liability. Chemical and mechanical resistance alone is not sufficient for assessing the serviceability of a product. In particular, the regulations for flammable liquids (explosion protection) must be taken into account.

COPYRIGHT

We would like to thank Bürkle GmbH for granting us the right to use this table.
This table is published and maintained by Bürkle GmbH, D-79415 Bad Bellingen, Germany, as a referral guide. This copyright notice may not be removed. The table may be freely distributed and copied as long as the copyright notice remains intact.

LIST OF MATERIALS MACH I

Tank:	PP	Suction hose:	PP, EVA
Sewage pump:	PP + GF20	Drain hose:	PP, EVA
Check valve:	PP	Floor nozzle:	PP
Screw connections:	PP	Suction tube:	PP
C-couplings:	PA6 + GF30	Suction head:	ABS

Version 3.11 (11.01.2021); Subject to technical changes, © Bürkle GmbH 2021.

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Exhaust gases, alkaline	—	—		?		1/1	0/0	(2)	0/0	0/0	0/0	(1)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/4	1/0	1/0	1/0	0/0	(2)	(1)	(1)		
Exhaust gases, containing hydrogen fluoride	—	—	low	?		1/1	0/0	(3)	(3)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	(2)	(2)	1/1	
Exhaust gases, carbon dioxide-containing	—	—	low	?		1/1	0/0	(1)	(1)	(1)	(1)	(1)	1/1	(1)	(1)	1/1	(1)	(1)	1/1	1/1	1/1	1/1	1/0	1/0	(1)	(1)	(1)	(1)	(1)	0/0	
Exhaust gases, nitrous	—	—	low	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	(3)	0/0	(2)	(1)	(1)		
Exhaust gases containing hydrochloric acid	—	—	any	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	2/2L	2/2L	3/3	
Exhaust gases containing sulphur dioxide	—	—	low	?		1/1	0/0	(2)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	1/1	1/1	0/0	
Exhaust gases containing sulphuric acid	—	—	any	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0	
Exhaust gases, containing sulphur trioxide	—	—	low	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	4/4	0/0	0/0	1/1	0/0	0/0	(2)	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0	
Acetaldehyde	C_2H_4O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	3/4	
Acetaldehyde	C_2H_4O	000075-07-0	tech. pure	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Acetamide	C_2H_5NO	000060-35-5	saturated	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)	1/1	
Acetamino-4-ethoxybenzene, 1-	-> see: Phenacetin																														
Acetic anhydride	-> see: Acetic anhydride																														
Acetone	C_3H_6O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	1/1	
Acetonitrile	C_2H_3N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Acetophenone	C_8H_8O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Acetoxybenzoic acid, 2-	-> see: Acetylsalicylic acid																														
Acetyl-5-methyl-2,3-dihydropyran-2,4-dione, -2	-> see: PDehydroacetic acid																														
Acetyl chloride	C_2H_3ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	0/0	
Acetylene	C_2H_2	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	1/1	0/0	1/0	1/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	
Acetylene tetrabromide	-> see: Tetrabromomethane, 1,1,2,2-																														
Acetylene tetrachloride	-> see: Tetrachloroethane-1,1,2,2																														
Acetylsalicylic acid	$C_9H_8O_4$	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	1/0	
Acrylonitrile	C_3H_3N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	1/1	
Acrylic acid butyl ester	-> see: Butyl acrylate																														
Acrylic acid ethyl ester	-> see: Ethyl acrylate																														
Acrylic acid methyl ester	-> see: Methyl acrylate																														
Acrylic acid nitrile	-> see: Acrylonitrile																														
Adipic acid	$C_6H_{10}O_4$	000124-04-9	saturated	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	1/0	(2)	(2)	1/1	
Adipic acid dioctyl ester	-> see: Dioctyladipate																														
Acrylic acid	H_2SO_4	007664-93-9	38 %	C		1/1	1/1	4/4	1/1	(4)	1/1	4/4	1/1	1/1	1/1	1/3	3/4	0/0	(1)	1/1	1/1	1/1	1/0	1/1	4/4	0/0	3/4	2/3	2/3	1/1	"Battery acid"
Alanine	$C_3H_7NO_2$	000056-41-7		—		1/1	1/1	1/1	4/4	(2)	1/1	(1)	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(2)	(2)	(2)		
Alum	-> see: Potassium aluminium sulphate																														
Alcohol	-> see: Ethanol																														
Allyl acetate	$C_5H_8O_2$	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		
Allyl alcohol	C_3H_6O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	1/1	(2)	1/0	4/4	3/0	0/0	1/1	1/1	1/1	1/1	
Allyl chloride	C_3H_5Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)	0/0	
Allyl isothiocyanate	-> see: Allyl mustard oil																														
Allyl mustard oil	C_4H_5NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		Oleum Sinapis
Aluminium (hydroxide) acetate	$C_4H_7AlO_5$	000139-12-8	aqueous	Xn		1/1	1/1	1/1	(1)	1/0	1/1	1/0	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	(1)	1/0	(3)	3/0	0/0	1/1	1/1	1/1	0/0	"Acetic acid alumina"
Aluminium ammonium sulphate	$(NH_4)Al(SO_4)_2$	007784-26-1	saturated	Xi		1/1	1/1	3/4	(2)	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3	0/0	
Aluminium chloride	$AlCl_3$	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	1/1	0/0	1/1	0/0	1/1	2/2	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	4/4	3/4	1/1	
Aluminium chloride	$AlCl_3$	007784-13-6	solid	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	(3)	0/0	4/4	4/4	3/4	1/1	Hydrochloric acid aluminium salt, anhydrous
Aluminium chloride	$AlCl_3$	007784-13-6	saturated	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	(1)	1/1	(2)	1/0	1/1	0/0	4/4	4/4	3/4	1/1	Hydrochloric acid aluminium salt, anhydrous
Aluminium fluoride	AlF_3	007789-18-1	aqueous	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	0/0	
Aluminium hydroxide	$Al(HO)_3$	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1/1	1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	0/0	No chemical effect expected due to low solubility
Aluminium hydroxide diacetate	-> see: Acetic clay																														
Aluminium nitrate	$Al(NO_3)_3$	013473-90-0	aqueous	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Aluminium oxide	Al_2O_3	001344-28-1	solid	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	No chemical effect expected due to low solubility
Aluminium sulphate	$Al_2(SO_4)_3$	010043-01-3	10 %	?		1/1	1/1	1/0	1/0	(2)	1/1	3/4	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/2	1/1	1/1	
Aluminium sulphate	$Al_2(SO_4)_3$	010043-01-3	saturated	Xn		1/1	1/1	3/4	1/0	0/0	1/1	3/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	2/2	1/2	1/1	
Aluminium trifluoride	-> see: Aluminium fluoride																														
Formic acid	CH_2O_2	000064-18-6	50 %	C, F	X	1/1	1/2	4/4	3/3	0/0	1/2	4/4	1/2	3/3	2/2	2/3	0/0	1/3	1/1	1/1	1/1	1/1	3/4	4/4	4/4	0/0	(3)	1/3	1/2	1/1	
Formic acid	CH_2O_2	000064-18-6	98-100 %	C, F+, T	X	1/1	1/2	4/4	3/4	0/0	1/3	4/4	1/3	3/4	3/3	3/4	1/3	3/4	1/1	(1)	1/1	1/1	3/4	4/4	4/4	0/0	1/0	1/3	1/2	1/0	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Formic acid	CH_2O_2	000064-18-6	3 %	Xi		1/1	1/2	3/4	1/2	1/0	1/2	2/4	1/2	1/2	2/2	2/3	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(3)	4/4	0/0	(3)	1/2	1/1	1/1	
Formic acid amide	-> see: Formamide																													
Formic acid ethyl ester	-> see: Ethyl formate																													
Formic acid methyl ester	-> see: Methylformia																													
Aminobenzene	-> see: Aniline																													
Aminobutane	-> see: Buylamine																													
Aminoacetic acid	$C_2H_5NO_2$	000056-40-6	10 %	—		1/1	1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	(2)	(2)	(2)	0/0	
Aminoethanol, 2-	-> see: Ethanolamine																													
Aminoethanoic acid	-> see: Aminoacetic acid																													
Amonimethane	-> see: Methylamine, (mono-)																													
Aminopropane	-> see: Propylamine, n-																													
Aminopropionic acid, L-2-	-> see: Alanine, (L-)																													
Ammonia	-> see: Ammonium hydroxide																													
Ammonia, sulphuric acid	-> see: Ammonium sulphate																													
Ammonia water	-> see: Ammonium hydroxide																													
Ammonium 2-hydroxyacetate	-> see: Ammonium glycolate																													
Ammonium acetate	$C_2H_7NO_2$	000631-61-8	saturated	Xi		1/1	1/1	1/0	1/1	(2)	1/1	(1)	1/1	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(3)	2/2	0/0	1/1	(2)	(2)	1/1	
Ammonium alum	-> see: Aluminium ammonium sulphate																													
Ammonium aluminium sulphate	-> see: Aluminium ammonium sulphate																													
Ammonium bicarbonate	-> see: Ammonium hydrogen carbonate																													
Ammonium bifluoride	-> see: Ammoinium hydrogen difluoride																													
Ammonium carbonate	$(NH_4)_2CO_3$	010361-29-2	50 %	Xn		1/1	1/1	1/0	3/0	0/0	1/0	(2)	1/1	1/1	1/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Hartshorn salt
Ammonium carbonate	$(NH_4)_2CO_3$	010361-29-2	aqueous	Xn		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Hartshorn salt
Ammonium chloride	$(NH_4)Cl$	012125-02-9	solid	Xn		1/1	1/1	1/0	1/0	(2)	0/0	2/3	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	3/4	1/3L	1/2L	1/1	Ammonia
Ammonium chloride	$(NH_4)Cl$	012125-02-9	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	Ammonia
Ammonium dihydrogen phosphate	$(NH_4)H_2PO_4$	007722-76-1	any	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	3/0	1/1	0/0	4/4	(1)	(1)	1/1	
Ammonium iron(II) sulfate	$(NH_4)_2Fe(SO_4)_2$	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	(1)	(1)		
Ammonium iron(III) sulfate	$(NH_4)Fe(SO_4)_2$	007783-83-7	saturated	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0		
Ammonium fluoride	$(NH_4)F$	012125-01-8	saturated	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)	?	
Ammonium fluoride	$(NH_4)F$	012125-01-8	aqueous	T. C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3	1/1	
Ammonium glycolate	$C_2H_7NO_3$	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)		
Ammonium heptamolybdate	$(NH_4)_6Mo_7O_{24}$	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/0	(3)	(1)	0/0		(1)	(1)	0/0	
Ammonium hydrogen carbonate	CH_5NO_3	001066-33-7	saturated	Xi		1/1	1/1	1/0	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	(3)	0/0	1/1	1/1	1/1	1/1	
Ammonium hydrogen difluoride	F_2H_5N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0		
Ammonium hydrogen sulphide	-> see: Ammonium hydrosulphide																													
Ammonium hydrosulphide	$(NH_4)HS$	012124-99-1	any	T, C		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	(2)	0/0	(2)	(1)	(1)	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	1/2	2/3	2/3	1/2	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1	1/1	
Ammonium metaphosphate	$(NH_4PO_3)_n$	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)		
Ammonium molybdate	-> see: Ammonium heptamolybdate																													
Ammonium monophosphate, monobasic	-> see: Ammonium dihydrogen phosphate																													
Ammonium nitrate	$(NH_4)NO_3$	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	1/1	
Ammonium nitrate	$(NH_4)NO_3$	006484-52-2	saturated	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1	1/1	
Ammonium nitrite	$(NH_4)NO_2$	013446-48-5	aqueous	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/0	0/0	(2)	(1)	(1)		
Ammonium oxalate	$C_2H_8N_2O_4$	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1	0/0	
Ammoniumperoxodisulfat	$(NH_4)_2S_2O_8$	007727-54-0	saturated	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0	
Ammoniumperoxodisulfat	$(NH_4)_2S_2O_8$	007727-54-0	aqueous	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0	
Ammonium persulphate	-> see: Ammonium peroxodisulphate																													
Ammonium phosphate, primary	-> see: Ammonium dihydrogen phosphate																													
Ammoniumpolyphosphat	-> see: Ammonium metaphosphate																													
Ammonium rhodanide	-> see: Ammonium thiocyanate																													
Ammonium sulphate	$(NH_4)_2SO_4$	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	1/1	sulphuric acid ammonia
Ammonium sulphate	$(NH_4)_2SO_4$	007783-20-2	saturated	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2	1/1	sulphuric acid ammonia
Ammonium sulphide	$(NH_4)_2S$	012135-76-1	any	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	?	
Ammonium sulphide	$(NH_4)_2S$	012135-76-1	aqueous	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ammonium sulphocyanide	-> see: Ammonium thiocyanate																													
Ammonium thiocyanate	CH_4N_2S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)		
Ammonium nitrate	-> see: Ammonium nitrate																													
Amylacetate, n-	$C_7H_{11}O_2$	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Amyl alcohol, n-	$C_5H_{12}O$	000071-41-0		Xn	X	1/1	1/2	1/0	1/0	1/0	2/3	1/0	1/1	1/3	3/0	2/3	3/0	0/4	1/1	1/1	1/1	1/1	3/0	2/4	3/0	0/0	1/2	1/1	1/1	0/0	
Anym chloride	$C_5H_{11}Cl$	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L	0/0	
Amyl hydrosulphide	-> see: Pentanthiol, 1-																													
Amyl mercaptan	-> see: Pentanthiol, 1-																													
α-pentylcinnamaldehyde	$C_{14}H_{18}O$	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)	(1)		Fragrance
Pineapple juice	—	—		—		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	(1)	(1)		
Aniline	C_6H_7N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0	1/1	
Aniline chlorohydrate	$C_6H_3ClN_6$	000142-04-1	saturated	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4		
Aniline hydrochloride	-> see: Aniline chlorohydrate																													
Anilinium chloride	-> see: Aniline chlorohydrate																													
Anise	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Anise oil	C_7H_8O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Anise oil	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Anon	-> see: Cyclohexanone																													
Antimony (III) chloride	-> see: Antimony trichloride																													
Antimony (V) chloride	-> see: Antimony pentachloride																													
Antimony pentachloride	$SbCl_5$	007647-18-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	(4)	0/0	
Antimony trichloride	$SbCl_3$	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4	0/0	
Antimony trichloride	$SbCl_3$	010025-91-9	anhydrous	C		0/0	0/0	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	1/0	1/0	1/0	0/0	1/1	4/4	4/4		
Antimony trichloride	$SbCl_3$	010025-91-9	aqueous	C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4		
Apple juice	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	(2)	(1)	(1)		
Orange juice	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(2)	1/1	1/1		
Orange peel oil	—	008028-48-6		Xn		(3)	(3)	1/0	(3)	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	4/4	(2)	(3)	0/0	(1)	(1)	(1)		mainly +-Limes
Arcton 12	-> see: Dichlorodifluoromethane																													
Arcton 21	-> see: Dichlorofluoromethane																													
Arcton 22	-> see: Chlorodifluoromethane																													
Arsenic anhydride	-> see: Arsenic pentoxide																													
Arsenic pentoxide	As_2O_5	001303-28-2		T, N		1/1	1/1	(3)	(2)	0/0	0/0	(4)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	(2)	(3)	(3)	0/0	(3)	(1)	(1)		
Arsenic acid	H_3AsO_4	022538-92-7	aqueous	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	1/1	
Arsenic acid	H_3AsO_4	022538-92-7	80 %	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	0/0	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	1/1	
Arsenic anhydride	-> see: Arsenic pentoxide																													
Ascorbic acid	$C_6H_8O_6$	000050-81-7	aqueous	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	1/1	(1)	(1)	0/0	
Ether	-> siehe: Ethylether																													
Atropine sulphate	$C_{34}H_{48}N_2SO_{10}\cdot H_2O$	000055-48-1		T+		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)		
Caustic baryte	-> see: Barium hydroxide																													
Caustic potash	-> see: Potassium hydroxide																													
Caustic lime	-> see: Calcium oxide																													
Caustic soda	-> see: Sodium hydroxide																													
Azafluorene, 9-	-> siehe: Carbazole																													
Valerian drops	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	1/1	1/1	(1)	(3)	(3)	(2)	0/0	(2)	(1)	(1)		
Barium bromide	$BaBr_2$	010553-31-8		Xn		1/1	1/1	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	1/1	0/0	(2)	(2L)	(2L)		
Barium carbonate	$BaCO_3$	000513-77-9	saturated	Xn		1/1	1/1	1/1	(1)	1/1	1/1	(1)	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	No chemical effect expected due to low solubility
Barium chloride	$BaCl_2$	010361-37-2	saturated	T		1/1	1/1	1/0	1/0	1/0	1/1	(2)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1	
Barium chloride	$BaCl_2$	010361-37-2	aqueous	T		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1	
Barium hydroxide	$Ba(HO)_2$	012230-71-6	saturated	Xn		1/1	1/1	1/0	(3)	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/3	
Barium hydroxide	$Ba(HO)_2$	012230-71-6	aqueous	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	?	
Barium sulphide	BaS	021109-95-5	saturated	(T)		1/1	1/1	1/0	(2)	(2)	1/1	(2)	1/1	0/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	(2)	1/0	1/0	1/1	0/0	(3)	(1)	(1)	1/1	
Cottonseed oil	—	008001-29-4	tech. pure	?		0/0	0/0	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	3/0	1/0	1/0	0/0	(1)	1/1	1/1		
Benzaldehyde	C_7H_6O	000100-52-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	artificial almond oil
Benzene	-> see: Benzene (page 5)																													
Petrol	C_5H_{12} - $C_{12}H_{26}$	086290-81-5		F, Xn, N	X	2/3	3/4	1/0	3/3	(2)	2/3	1/2	3/4	4/4	3/3	2/4	0/0	0/4	1/1	1/1	1/1	1/1	4/4	(1-3)	3/0	0/0	1/1	1/1	1/1	1/1	Fuel, unleaded

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Benzoic acid	$C_7H_6O_2$	000065-85-0	saturated	Xn, Xi		1/1	1/1	3/4	4/4	1/0	1/2	2/4	1/3	2/2	3/3	1/2	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1	
Benzoic acid	$C_7H_6O_2$	000065-85-0	aqueous	Xn, Xi		1/1	1/1	3/4	4/4	1/0	0/0	2/4	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1	
Benzoic acid sodium salt	-> see: Sodium benzoate																														
Benzoic acid aldehyde	-> see: Benzaldehyde																														
Benzoic acid benzyl ester	-> see: Benzyl benzoate																														
Benzoic acid chloride	-> see: Benzoyl chloride																														
Benzoic acid ethyl ester	$C_9H_{10}O_2$	000093-89-0		Xn		2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Benzene	C_6H_6	000071-43-2		F, T	X	3/4	3/4	2/0	4/4	4/4	2/3	1/2	3/4	4/4	4/4	4/4	0/0	0/4	1/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	1/1	1/1	1/1	0/0	
Benzene-1,2-dicarboxylic acid	-> see: Phthalic acid																														
Benzene carboxylic acid	-> see: Benzoic acid																														
Benzene hexachloride (BHC)	-> see: Hexachlorocyclohexane																														
Benzenesulfonic acid	$C_6H_6SO_3$	000098-11-3	saturated	C		1/1	1/1	(4)	(3)	(4)	0/0	(4)	2/4	0/0	1/0	2/0	0/0	0/0	0/0	1/1	1/1	1/4	4/4	1/0	4/4	0/0	3/4	0/0	1/0	0/0	
Benzoyl chloride	C_7H_5ClO	000098-88-4	100 %	C		0/0	3/3	4/4	(4)	0/0	(4)	(3)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	(3)	4/4	0/0	1/0	(2L)	(2L)	0/0	
Benzyl acetate	$C_9H_{10}O_2$	000140-11-4		Xn/Xi		1/1	1/2	(2)	3/4	0/0	1/2	(2)	1/2	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	1/0	4/4	0/0	1/1	1/1	1/1		
Benzyl alcohol	C_7H_8O	000100-51-6		Xn		3/4	4/4	4/4	4/4	0/0	4/4	1/0	4/4	4/4	4/4	2/3	0/0	4/4	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	1/1	1/1	1/1	3/3	
Benzyl benzoate	$C_{14}H_{12}O_2$	000120-51-4		Xn		0/0	0/0	(2)	(3)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Benzylcarbinol	-> see: Phenylethanol																														
Benzyl chloride	C_7H_7Cl	000100-44-7	100 %	T/Xi		0/0	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	(3)	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0	
Benzylether	-> see: Dibenzyl ether																														
Succinic acid	$C_4H_6O_4$	000110-15-6	50 %	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	2/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/0	1/0	1/1	
Succinic acid	$C_4H_6O_4$	000110-15-6	saturated	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	?	
Succinic acid diethyl ester	$C_8H_{14}O_4$	000123-25-1		—		0/0	0/0	(2)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	4/4	4/4	0/0	(1)	(1)	(1)		
Bichromate sulphuric acid	-> see: Chromosulphuric acid																														
Beeswax	—	008012-89-3		—		1/1	1/1	1/1	(1)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	1/1	(1)	(1)		
Beer	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	
Bis(2-chloro-1-methylethyl)-ether	-> ssee: Dichloroisopropyl ether																														
Bis(2-ethylhexyl)-dipate	-> see: Dioctyladipate																														
Bis(2-ethylhexyl)-phthalate	-> see: Diisooctyl phthalate																														
Bis(2-ethylhexyl)-sebacate, sebacic acid bis(2-ethylhexyl)-ester	-> see: Dioctylsebacate																														
Bismuth chloride	$BiCl_3$	007787-60-2		Xi		1/1	1/1	(3)	(2)	(2)	0/0	(4)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(4)	0/0	0/0		
Bismuth subnitrate	$Bi_5O(HO)_9(NO_3)_4$	001304-85-4		O, Xi		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		
Bisulphite	-> see: Sodium bisulphite																														
Bisulphite lye	$NaHSO_3$	??		Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	3/0	0/0	(3)	1/1	1/1	1/1	
Bisulphite lye, containing $S0_2$	$NaHSO_3$	??	saturated	Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/1	4/4	0/0	(3)	1/1	1/1		
Bitter almond oil	C_7H_6O	090320-35-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1		Main ingredient: Benzaldehyde
Epsom salt	-> see: Magnesium sulphate																														
Bitumen	—	008052-42-4		—		0/0	0/0	1/0	(2)	(2)	0/0	2/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	(3)	0/0	1/1	(1)	(1)		
Hydrogen cyanide	HCN	000074-90-8	tech. pure	F+, T+	X	1/1	1/1	(3)	4/4	0/0	0/0	4/4	1/1	1/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	1/1	1/0	1/0	1/0	
Hydrogen cyanide	HCN	000074-90-8	aqueous	F+, T+	X	1/1	1/1	(3)	4/4	0/0	(4)	4/4	1/1	1/0	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(1)	1/0	1/0	?	
Lead (II) acetate	$C_4H_6PbO_4$	000301-04-2	aqueous	T, N		1/1	1/1	3/0	1/0	(2)	1/0	1/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	3/0	0/0	4/4	1/1	1/1	1/1	
Lead (II) acetate	$C_4H_6PbO_4$	000301-04-2		T, N		1/1	1/1	3/0	1/0	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	2/2	0/0	4/4	1/1	1/1	1/1	
Lead(II) nitrate	$Pb(NO_3)_2$	010099-74-8	aqueous	O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Lead(II) nitrate	$Pb(NO_3)_2$	010099-74-8		O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Lead nitrate	-> see: Lead (II) nitrate																														
Lead stearate	$C_{36}H_{70}PbO_4$	001072-35-1		?		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		No chemical effect expected due to low solubility
Lead sulphate	$PbSO_4$	007446-14-2		(T, N)		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	0/0	(1)	(1)	(1)	0/0	No chemical effect expected due to low solubility
Tetraethyllead	-> see: Tetraethyl lead																														
Lead sugar	-> see: Lead (II) acetate																														
Yellow prussiate of Potash	-> see: Potassium hexacyanoferrate(II)																														
Red prussiate of Potash	-> see: Potassium hexacyanoferrate(III)																														
Borax	-> see: Sodium borate																														
Boric acid	H_3BO_3	010043-35-3	10 %	Xi		1/1	1/1	1/0	1/1	1/0	1/1	2/3	1/1	1/2	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Boric acid	H_3BO_3	010043-35-3	aqueous	Xi		1/1	1/1	3/3	1/1	1/0	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Spirits	-> see: Spirits																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Brake fluid	—	—		?		1/0	1/0	1/0	4/4	0/0	1/1	(3)	1/1	3/0	0/0	1/0	3/0	4/4	0/0	(1)	1/0	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Bromine	Br_2	007726-95-6		T+, C		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	2/4	4/4	4/4	1/2	1/1	1/3	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	4/4	
Bromine benzene	-> see: Bromobenzene																													
Bromobenzene	C_6H_5Br	000108-86-1		Xn	X	3/4	4/4	1/0	4/4	(2)	4/4	1/0	4/4	4/4	4/4	4/4	0/0	0/0	2/4	1/1	1/0	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)		
Bromochloromethane	CH_2BrCl	000074-97-5	100 %	Xn		(4)	(4)	4/4	4/4	1/0	(4)	(3)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/0	(3)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	
Bromine vapours	Br_2	007726-95-6		T		(4)	(4)	4/4	(3)	4/4	(4)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(2-3)	4/4	0/0	(3)	(4)	(4)	4/4	
Bromine potassium	-> see: Potassium bromide																													
Bromomethane	CH_3Br	000074-83-9	tech. pure	T		3/0	4/4	1/0	(3)	0/0	0/0	1/0	4/4	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0	
Bromoform	$CHBr_3$	000075-25-2		T		4/4	4/4	4/4	4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	0/0	0/0	2/3	1/1	(1)	(2)	4/4	(4)	4/4	0/0	(3)	0/0	0/0	0/0	
Bromopental fluoride	BrF_5	007789-30-2		F, T, C		0/0	0/0	4/4	(4)	(4)	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromic acid	$HBrO_3$	007789-31-3	concentrated.	C		0/0	0/0	(4)	(4)	(4)	0/0	4/4	3/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(4)	(2)	4/4	0/0	(4)	(4)	(4)	0/0	
Bromine trifluoride	BrF_3	007787-71-5		T, C		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromotrifluoromethane	$CBrF_3$	000075-63-8		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Bromine water	Br_2+H_2O	007726-95-6	saturated	T		4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	4/4	0/0	3/4	0/0	0/0	0/0	0/0	1/1	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	0/0	
Hydrobromic acid	HBr	010035-10-6	40 %	C		1/0	1/1	4/4	4/4	(4)	4/4	4/4	1/1	4/4	0/0	1/1	3/3	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Hydrobromic acid	HBr	010035-10-6	50 %	C		1/1	1/2	4/4	4/4	(4)	4/4	4/4	1/2	4/4	0/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Hydrobromic acid	HBr	010035-10-6	diluted	C		1/1	1/1	4/4	4/4	3/0	4/4	4/4	1/1	4/4	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Butadiene, 1,3-	C_4H_6	000106-99-0		F+, T	X	3/4	4/4	1/0	4/4	1/0	4/4	(2)	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)	4/4	
Butane	C_4H_{10}	000106-97-8	tech. pure	F+	X	1/0	1/1	1/0	1/0	1/0	1/0	2/0	1/1	4/4	1/0	1/0	3/0	1/0	0/0	1/1	1/1	1/0	4/4	1/0	1/0	0/0	1/1	(1)	(1)	1/1	
Butanal	-> see: Butyraldehyde																													
Butanediol	-> see: Butylene glycol																													
Butanedioic acid	-> see: Succinic acid																													
Butanol	$C_4H_{10}O$	000071-36-3	techn. pure	Xn	X	1/1	1/3	1/0	2/3	1/0	1/2	1/2	1/2	1/2	2/3	2/3	4/4	1/3	1/1	1/1	1/1	1/1	2/0	3/4	1/0	0/0	1/1	(1)	(1)	0/0	
Butanol, secondary	-> see: Butyl alcohol, secondary																													
Butanol, tertiary	-> see: Butyl alcohol, tertiary																													
Butanol-2	-> see: Butyl alcohol, secondary																													
Butanone	-> see: Methyl ethyl ketone																													
Butanoic acid	-> see: Butyric acid																													
Butanetriol	$C_4H_{10}O_3$	—	100 %	—		(4)	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	3/3	4/4	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)		Isomer not specified in the source
Butene	C_4H_8	—	tech. pure	F+	X	4/4	0/0	1/0	(1)	1/0	0/0	1/0	4/4	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/0	1/0	3/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0	Isomer not specified in the source
Butenal, trans-2-	-> see: Crotonaldehyde																													
Butenedioic acid, cis-	-> see: Maleic acid																													
Butoxyethanol, 2-	-> see: Butyl glycol																													
Butter	—	—		—		1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	3/0	1/0	1/1	0/0	(1)	(1)	(1)		
Buttersäure	$C_4H_8O_2$	000107-92-6		C		3/4	4/4	3/3	4/4	0/0	4/4	4/4	4/4	4/4	2/2	2/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/2	1/2	1/1	1/1	
Butyric acid ethyl ester	-> see: Ethyl butyrate																													
Butyl acetate	-> see: Acetic acid butyl ester																													
Butyl acrylate	$C_7H_{12}O_2$	000141-32-2	100 %	Xi	X	1/2	2/3	2/0	4/4	1/3	2/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/0	
Butyl alcohol	-> see: Butanol																													
Butyl alcohol, secondary	$C_4H_{10}O$	000078-92-2		Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	2/2	2/3	2/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		
Butyl alcohol, tertiary	$C_4H_{10}O$	000075-65-0		F, Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		
Butylamine	$C_4H_{11}N$	000109-73-9		F, C	X	0/0	0/0	0/0	(3)	0/0	0/0	3/4	2/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Butyl carbinol	-> see: Amyl alcohol, n-																													
Butyl cellosolve	-> see: Butyl glycol																													
Butylene	-> see: Butene																													
Butylen glycol	$C_4H_{10}O_2$	—	tech. pure	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	4/4	(1)	0/0	1/1	(1)	(1)	0/0	Isomer not specified in the source
Butyl ether	-> see: Dibutyl ether																													
Butyl ethylene	-> see: Hexene, 1-																													
Butyl glycol	$C_4H_{14}O_2$	000111-76-2	100 %	Xn	X	0/0	1/0	1/0	(2)	1/0	0/0	1/0	1/0	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	1/1	3/0	3/4	3/4	0/0	1/1	(1)	(1)	0/0	
Butylphenol	$C_{10}H_{14}O$	—	100 %	Xi		0/0	1/1	(3)	(3)	0/0	(3)	(4)	1/1	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Isomer not specified in the source
Para tertiary butylphenol	$C_{11}H_{15}NO$	000098-54-4	tech. pure	C, Xn		3/0	0/0	(3)	(3)	0/0	(3)	(4)	1/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1		
Butyl stearate	-> see: Stearic acid butyl ester																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Butyraldehyde	C_4H_8O	000123-72-8		F, Xn	X	0/0	0/0	(3)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Cadmium bromide	CdBr	007789-42-6		T		1/1	1/1	(3)	(2)	(2)	0/0	(3)	(1)	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	4/4	0/0	0/0		
Calcium acetate	$C_4H_6CaO_4$	000062-54-4	aqueous	—		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(2)	(1)	(1)	0/0	
Calcium bicarbonate	$Ca(HCO_3)_2$	—	saturated	—		1/1	1/1	1/1	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	(2)	(1)	(1)	0/0	
Calcium bisulphite	$Ca(HSO_3)_2$	013780-03-5	saturated	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1	
Calcium bisulphite	$Ca(HSO_3)_2$	013780-03-5	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1	
Calcium bromide	$CaBr_2$	007789-41-5		?		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(3)	0/0	0/0	0/0	
Calcium carbide	CaC_2	000075-20-7		F	X	1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0	Carbide, reacts with water to form acetylene - highly flammable!
Calcium carbonate	$CaCO_3$	000471-34-1	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium chlorate	$Ca(ClO_3)_2$	010137-74-3	saturated	O, (T)		0/0	0/0	(3)	(2)	0/0	1/1	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(2)	(1)	(3)	0/0	1/1	(1)	1/0	1/1	
Calcium chloride	$CaCl_2$	010043-52-4	alcoholic	F, Xi		1/0	0/0	4/4	(2)	0/0	1/0	(3)	1/1	0/0	0/0	0/0	4/4	0/0	0/0	1/1	1/0	(1)	(2)	(2)	(2)	0/0	(3)	1/2L	1/2L	1/1	
Calcium chloride	$CaCl_2$	010043-52-4	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/1	(3)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/2L	1/2L	1/1	
Calcium hydrate	-> see: Calcium hydroxide																														
Calcium hydrogen carbonate	-> see: Calcium bicarbonate																														
Calcium hydrogen sulphite	-> see: Calcium bisulphite																														
Calcium hydroxide	CaH_2O_2	001305-62-0	aqueous	(Xi)		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calcium hydroxide	CaH_2O_2	001305-62-0	concentrated.	C		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	2/2	2/2	1/1	1/0	0/0	1/1	1/1	1/1	1/3	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calcium hypochlorite	$Ca(OCl)_2$	007778-54-3	saturated	O, C		1/1	1/1	1/4	3/4	3/0	1/2	1/0	1/1	2/3	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/3	(2)	2/3	4/4	0/0	4/4	3/0	2/0	1/1	Bleaching powder
Calcium hypochlorite	$Ca(OCl)_2$	007778-54-3	aqueous	O, C/Xi		0/0	0/0	4/4	1/0	3/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	4/4	3/0	2/0	1/1	Bleaching powder
Calcium nitrate	$Ca(NO_3)_2$	010124-37-5	50 %	O		1/1	1/1	(2)	1/0	(2)	1/1	(3)	1/1	1/1	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	1/0	1/1	1/1	1/1	
Calcium nitrate	$Ca(NO_3)_2$	010124-37-5	aqueous	O		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/1	1/1	1/1	
Calcium oxide	CaO	001305-78-8	Powder	C		1/0	1/1	(2)	(2)	(2)	0/0	0/0	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	1/1	1/1		
Calcium phosphate	$Ca_3(PO_4)_2$	007758-87-4	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium phosphate	$Ca_3(PO_4)_2$	007758-87-4		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium sulphate	$CaSO_4$	007778-18-9	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	Plaster
Calcium sulphide	CaS	020548-54-3	aqueous	C		0/0	0/0	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	(1)	(1)	0/0	
Calcium sulphide	CaS	020548-54-3		C		0/0	3/3	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Camphor	$C_{10}H_{16}O$	000464-48-2 / -49-2		F, Xn	X	3/4	3/4	(2)	(3)	0/0	0/0	(2)	1/0	1/3	0/0	4/4	4/4	1/1	0/0	(1)	1/0	(3)	4/4	3/4	1/0	0/0	(1)	1/0	1/0	1/0		
Camphor oil	—	008008-51-3		Xn		4/4	4/4	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	(3)	4/4	3/0	1/0	0/0	(1)	(1)	(1)	1/0	made from Cinnamomum Camphora
Paracymene	-> see: Cymene, p-																														
Capronaldehyde	-> see: Hexanal																														
Carbazole	$C_{12}H_9N$	000086-74-8		Xn		1/1	1/1	(2)	4/4	0/0	1/1	(1)	1/1	1/1	4/4	4/4	0/0	4/4	1/1	1/1	(2)	(2)	(2)	(3)	(2)	0/0	(1)	(1)	(1)	0/0	
Carbinol	-> see: Methanol																														
Carbolineum	—	008001-58-9	aqueous	(Xn)		1/0	1/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	(2)	3/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Carbolic acid	-> see: Phenol																														
Carbon disulfide	-> see: Carbon disulphide																														
Carbonyl chloride	-> see: Phosgene																														
Carnauba wax	—	008015-86-9		—		1/1	1/1	1/1	(1)	1/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(3)	(1)	(1)	0/0	1/1	(1)	(1)		
Caesium bromide	CsBr	007787-69-1		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	0/0	0/0		
Cellosolve	-> see: Ethyl glycol																														
Cellosolve acetate	-> see: Ethylene glycol monoethyl ether acetate																														
Cetyl alcohol	$C_{16}H_{34}O$	036653-82-4	100 %	Xi		1/1	1/1	4/4	(2)	1/0	0/0	(1)	1/1	0/0	1/0	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(1)	1/1	1/1		
Cetylic acid	-> see: Palmitic acid																														
Quinine	$C_{20}H_{24}N_2O_2$	000130-95-0		Xn		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)	0/0	
Chlorine	Cl_2	007782-50-5	10 % wet	T		3/4	3/4	4/4	2/3	4/4	2/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	(2)	2/0	3/0	4/4	0/0	4/4	4/4	4/4	0/0	
Chlorine	Cl_2	007782-50-5	97 %	T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0	1/1	
Chlorosulfonic acid	-> see: Chlorosulfunic acid																														
Chlorine-1-propene, 3-	-> see: Allyl chloride																														
Chlor-2-propanone, 1-	-> see: Chloroacetone																														
Chloroacetone	C_3H_5ClO	000078-95-5		(F, Xi)	X	0/0	0/0	(3)	(4)	(4)	(4)	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	0/0	
Chloroacetophenone, p-	C_8H_7ClO	000099-91-2		(Xn)		1/1	1/1	(2)	4/4	0/0	1/1	(2)	1/1	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(2)	(2)	(3)	4/4	4/4	0/0	(1)	0/0	0/0		
Chloral	-> see: Trichloroacetaldehyde																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Chloral hydrate	$C_2H_3Cl_3O_2$	000302-17-0	tech. pure	T/Xi		3/3	3/3	4/4	(3)	(4)	0/0	(3)	3/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	4/4	3/0	3/4	4/4	0/0	4/4	0/0	0/0	0/0	
Chloramine T	$C_7H_7ClNaNSO_2$	000127-65-1	diluted	Xi		1/0	1/0	4/4	1/0	0/0	0/0	(3)	(3)	0/0	0/0	0/0	1/0	0/0	0/0	(1)	1/0	3/4	1/0	4/4	1/0	0/0	3/4	2/2	1/1	0/0	Swimming pool disinfection
Phenyl chloride	-> see: Chlorobenzene																													
Chlorobenzene	C_6H_5Cl	000108-90-7		Xn	X	3/4	3/4	4/4	4/4	1/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/1	(1/1)[1]	(1/1)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chlorine bleach	-> see: Sodium hypochlorite																													
Bromochloromethane	-> see: Bromochloromethane																													
Chlorobutadiene	C_4H_5Cl	000126-99-8		F, Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/4	4/4	0/0	(3)	0/0	0/0		
Chlorobutadiene	-> see: Calcium chloride																													
Chlorodifluoromethane	$CHClF_2$	000075-45-6		N, Xn		0/0	3/0	1/0	3/0	1/0	0/0	1/0	4/4	4/4	4/4	2/0	4/4	0/0	0/0	3/3	1/0	(3)	1/0	4/4	4/4	0/0	(3)	0/0	0/0		
Chlorine dioxide	ClO_2	010049-04-4		E, T		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/0	(2)	4/4	1/0	4/4	0/0	3/4	3/4	3/4		
Chlordodecane	-> see: Lauryl chloride																													
Chloroacetic acid	$C_2H_3ClO_2$	000079-11-8	50 %	T, C		1/3	1/3	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/0	0/0	3/4	0/0	(1)	1/1	1/4	2/0	3/0	4/4	0/0	4/4	2/4	2/4	1/4	
Chloroacetic acid	$C_2H_3ClO_2$	000079-11-8		T, C		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/2	2/4	4/4	3/4	4/4	3/4	1/1	1/1	1/1	4/4	3/0	3/0	4/4	0/0	4/4	4/4	4/4	4/4	
Ethyl monochloroacetate	-> see: Ethyl chloroacetate																													
Chloroethanoic acid methyl ester	-> see: Methyl chloroacetate																													
Chlorethane	C_2H_5Cl	000075-00-3		F+, Xn	X	3/3	3/4	1/0	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/0	4/4	0/0	(3)	(1/1L)[1]	(1/1L)[1]	0/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloroethanol	C_2H_5ClO	000107-07-3	tech. pure	T+		1/1	0/0	4/4	4/4	0/0	0/0	3/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	1/1	1/0	1/3	3/0	4/4	4/4	0/0	(3)	1/0L	1/0L	1/0	
Chloroethyl alcohol, 2-	-> see: Chloroethanol																													
Chloroethylene	C_2H_3Cl	000075-01-4	tech. pure	F+, T	X	0/0	0/0	1/1	(4)	1/1	0/0		(3)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	1/1	3/0	3/0	4/4	0/0	(1)	0/0	0/0	0/0	
Chlorofluoromethane	CH_2ClF	000593-70-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	4/4	0/0	(3)	0/0	0/0		
Chlorine gas	Cl_2	007782-50-5		T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0		
Chlorinated potassium	-> see: Potassium chloride																													
Chlorinated lime	[3 x CaCl(OCl) + Ca(—		aqueous	?		0/0	0/0	4/4	(2)	3/0	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach
Chlorinated lime	[3 x CaCl(OCl) + Ca —			O, C		0/0	0/0	4/4	(2)	3/0	0/0	4/4	1/1	1/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach
Chloromethane	CH_3Cl	000074-87-3	tech. pure	F+, T	X	3/0	2/0	4/4	(3)	0/0	0/0	1/0	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/0	1/0	1/1	4/4	4/4	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]		[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloromethyl	-> see: Chloromethane																													
Chloromethylbenzene	-> see: Benzyl chloride																													
Chloromethyloxirane	-> see: Epichlorohydrin																													
Chloronaphthalene, 1-	$C_{10}H_7Cl$	000090-13-1		Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	4/4	0/0	(2)	1/0	1/0		
Nickel chloride	-> see: Nickel (II) chloride																													
Chloroform	$CHCl_3$	000067-66-3	100 %	Xn		3/4	4/4	3/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	1/1	4/4	3/4	4/4	0/0	(3)	(1/1)[1]	(1/1)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloroprene	-> see: Chlorobutadiene																													
Chloropentafluoroethane	C_2ClF_5	000076-15-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Chloropentane, 1-	-> see: Amyl chloride																													
Chlorophenyl methyl ketone, 4-	-> see: Chloroacetophenone, -p																													
Chloropropane, 2-	-> see: Isopropyl chloride																													
Chloropropylene, 3-	-> see: Allyl chloride																													
Chloric acid	$HClO_3$	007790-93-4	1 %	(C)		0/0	1/1	4/4	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/3	1/0	0/0	0/0	0/0	1/1	1/1	3/0	1/1	(3)	0/0	(3)	4/4	4/4	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Chloric acid	$HClO_3$	007790-93-4	10 %	(O), C		1/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	3/0	3/0	4/4	0/0	4/4	4/4	4/4	1/1	
Chloric acid	$HClO_3$	007790-93-4	20 %	(O), C		3/0	1/4	4/4	(3)	(4)	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/0	3/0	3/0	4/4	0/0	4/4	4/4	4/4	?	
Chlorosulfonic acid	$ClHSO_3$	007790-94-5	tech. pure	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	3/0	4/4	4/4	0/0	0/0	1/0	3/4	4/4	4/4	4/4	0/0	3/3	3/4	3/4	1/0	
Chlorotoluene	C_7H_7Cl	—		Xn		0/0	0/0	(2)	4/4	0/0	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(3)	1/0	1/0	1/1	Isomer not specified in the source
Chlorotoluene, alpha-	-> see: Benzyl chloride																													
Chlorine trifluoride	ClF_3	007790-91-2		(O, T)		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(4)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(4)	4/4	(4)	4/4	0/0	(4)	(4)	(4)		
Chlorotrifluoromethane	$CClF_3$	000075-72-9		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	0/0	
Chlorinated water	$Cl_2 \times H_2O$	007782-50-5		(T)		3/0	0/4	4/4	4/4	4/4	4/4	4/4	3/4	4/4	0/0	3/3	3/0	3/3	1/1	(1)	1/1	1/1	3/0	1/0	4/4	0/0	4/4	2/0L	2/0L	0/0	
Hydrochloric acid gas	HCl	007647-01-0	anhydrous	T, C		1/1	0/0	4/4	(3)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	2/2L	2/2L	0/0	
Hydrochloric gas	-> see: Hydrogen acid																													
Hydronium chloride	-> see: Hydrochloric acid																													
Chlorozinc	-> see: Zinc chloride																													
Chromium (III) potassium sulphate dodecahydrate	-> see: Chrome alum																													
Chromium (VI) oxide	-> see: Chromic acid																													
Chrome alum	$KCr(SO_4)_2 \times 12H_2O$	007788-99-0	saturated	Xn		1/1	0/0	(2)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(3)	1/3	1/3	1/1	
Chromium salts	—	—	any	T/Xn		0/0	0/0	0/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	0/0	K	K	K		
Chromic acid	CrO_3	001333-82-0	10 %	O, T, C, N		1/1	1/1	4/4	2/3	3/0	1/1	4/4	1/1	1/1	4/4	1/2	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	1/2	1/2	1/1	
Chromic acid	CrO_3	001333-82-0	20 %	O, T, C, N		0/0	1/3	4/4	3/4	(4)	0/0	4/4	3/3	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	(2)	(2)	1/1	
Chromic acid	CrO_3	001333-82-0	50 %	O, T, C, N		3/4	3/4	4/4	3/4	(4)	2/3	4/4	3/3	3/3	4/4	1/3	1/0	3/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	(3)	2/3	2/3	1/1	
Chromic acid potassium salt	-> see: Potassium chromate																													
Chromosulphuric acid	$CrO_3 + H_2SO_4$	065272-71-1	concentrated	O, T, C, N		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	4/4	4/4	1/1	0/0	1/1	4/4	4/4	1/0	4/4	4/4	4/4	2/3	2/3	0/0	
Chromium trioxide	-> see: Chromic acid																													
2-Hydroxypropane-1,2,3-tricarboxylic acid	-> see: Citric acid																													
Citric acid tributyl ester	-> see: Tributyl citrate																													
Clophen A60	—	011096-82-5		Xn, N		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	0/0	0/0	0/0	0/0	(1)	(2)	4/4	2/3	4/4	0/0	1/0	1/0	1/0	0/0	ppolychlorinated biphenyls, PCBs; Bayer
Cobalt (II) chloride	$CoCl_2$	007646-79-9	aqueous	Xn		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Cobalt dichloride	-> see: Cobalt (II) chloride																													
Colamine	-> see: Ethanolamine																													
Crotonaldehyde	C_4H_6O	004170-30-3	tech. pure	F, T	X	1/0	0/0	(2)	(4)	0/0	(4)	(2)	1/0	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	1/3	1/0	3/0	4/4	0/0	1/0	1/1	1/1	0/0	
Cumol	-> see: Cumene																													
Cumene	C_9H_{12}	000098-82-8		Xi	X	2/3	3/4	(2)	4/4	0/0	4/4	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Curry	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	3/3	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		could lead to discolouration
Ethyl cyanoacetate	-> see: Ethyl cyanoacetate																													
Cyanide	-> see: Potassium cyanide																													
Cyan potassium	-> see: Potassium cyanide																													
Cyannosodium	-> see: Sodium cyanide																													
Prussic acid	-> see: Hydrogen cyanide																													
Cyclanon	—	—		(Xn, Xi)		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/1	0/0	3/4	(1)	(1)	0/0	Polyquaternary compounds, dyeing auxiliaries; BASF
Cyclohexane	C_6H_{12}	000110-82-7		F	X	3/4	3/4	1/0	3/3	1/0	4/4	1/1	3/4	4/4	4/4	2/3	1/0	1/3	1/2	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Cyclohexanol	$C_6H_{12}O$	000108-93-0	tech. pure	Xn		1/1	1/1	1/1	3/0	0/0	1/2	1/0	1/3	3/3	1/0	1/1	4/4	1/3	0/0	(1)	1/1	1/3	4/4	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Cyclohexanone	$C_6H_{10}O$	000108-94-1	tech. pure	Xn	X	1/3	3/4	1/0	4/4	(4)	3/4	1/0	2/4	4/4	4/4	4/4	4/4	4/4	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Cyclohexylmethane	-> see: Methylcyclohexane																													
Cymene, p-	$C_{10}H_{14}$	000099-87-6		F, Xn/Xi	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Steam	H_2O	—	up to 150°C	?		4	4	4/4	0/0	0	0	(3)	(3)	0	0	0	0	0	0	0/0	1	0	1	3	4/4	0	(1)	1/1	1/1		
DDT (emulsion)	$C_{14}H_9Cl_5$	000050-29-3		T		0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(3)	(3)	0/0	(2)	(2)	(2)	0/0	
Decahydronaphthalene	$C_{10}H_{18}$	000091-17-8		Xn		1/3	3/4	1/0	4/4	3/0	4/4	1/0	3/4	4/4	4/4	1/2	3/0	3/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	(1)	(1)	0/0	
Decalin	-> see: Decahydronaphthalene																													
Decane	$C_{10}H_{22}$	000124-18-5		Xn	X	0/0	0/0	(1)	(2)	(1)	(3)	1/1	(3)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	(1)	(1)		
Decanedioic acid dibenzyl ester	-> see: Dibenzyl sebacate																													
Decanedioic acid dibutyl ester	-> see: Dibutyl sebacate																													
Decanedioic acid diethyl ester	-> see: Diethyl sebacate																													
Dehydroacetic acid	$C_8H_8O_4$	000520-45-6		Xn		0/0	0/0	(3)	(2)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(4)	(1)	(1)		
Densodrin W	—	—	aqueous	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/0	0/0	0/0	1/0	0/0	0/0	0/0	0/0		Hydrophobing agent for leather, silicone derivative; BASF

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Desmodur 44	$C_{15}H_{10}N_2O_2$	000101-68-8		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	0/0	4/4	0/0	(1)	(1)	(1)		
Dextrin	$(C_6H_{10}O_5)_n$ x H_2O	009004-53-9	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Dextrose	-> see: Glucose																														
Diacetone alcohol	$C_6H_{12}O_2$	000123-42-2		Xi	X	0/0	0/0	(3)	(3)	0/0	0/0	1/0	2/2	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(2)	(1)	(1)		
Diamide	-> see: Hydrazine																														
Diaminoethane	-> see: Ethylenediamine																														
Diazane	-> see: Hydrazine																														
Dibenzyl ether	$C_{14}H_{14}O$	000103-50-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Dibenzyl sebacate	$C_{24}H_{26}O_4$	??		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	(4)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dibromoethane-1,2	$C_2H_4Br_2$	000106-93-4		T		(4)	(4)	(2)	(4)	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/2	4/4	(3)	4/4	0/0	(3)	1/0L	1/0L	0/0	
Dibromotetrafluoromethane	$C_2Br_2F_4$	000124-73-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0		
Dibutylamine	$C_8H_{19}N$	000111-92-2		Xn	X	0/0	0/0	(2)	(3)	0/0	(3)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Dibutyl ether	$C_8H_{18}O$	000142-96-1	tech. pure	Xi	X	3/4	1/4	(2)	(3)	1/0	(4)	(1)	3/4	0/0	3/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Dibutyl phthalate	$C_{16}H_{22}O_4$	000084-74-2	FR, 80°C	T		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	(1)	0	0	0	4/4	0	0	0	0	0/0	Plasticiser
Dibutyl phthalate	$C_{16}H_{22}O_4$	000084-74-2		T		1/3	3/3	1/0	4/4	1/0	0/2	1/0	2/2	4/4	1/0	4/4	4/4	0/4	1/1	(1)	1/1	1/3	3/0	2/3	4/4	0/0	(1)	1/1	1/1	0/0	Plasticiser
Dibutyl sebacate	$C_{18}H_{34}O_4$	000109-43-3	tech. pure	—		1/0	1/3	1/0	(3)	0/0	0/0	(2)	1/0	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dichlorocide, 1,2-	-> see: Dichlorobenzene, 1,2-																														
Dichlorocide, 1,4-	-> see: Dichlorobenzene, 1,4-																														
Dichlorobenzene, 1,2-	$C_6H_4Cl_2$	000095-50-1		Xn		3/3	3/4	(1)	4/4	0/0	3/4	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/3	(1)	1/1	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Dichlorobenzene, 1,4-	$C_6H_4Cl_2$	000106-46-7		Xn		2/3	3/4	1/0	4/4	0/0	2/3	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/3	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
DCB, o-	-> see: Dichlorobenzene, 1,2-																														
DCB, p-	-> see: Dichlorobenzene, 1,4-																														
Dichlorodifluoromethane	CCl_2F_2	000075-71-8	tech. pure	N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0	
Dichlorodifluoromethane	CCl_2F_2	000075-71-8		N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0	
Dichlorodiphenyltrichloroethane	-> see: DDT (emulsion)																														
Dichloroacetic acid	$C_2H_2Cl_2O_2$	000079-43-6	50 %	C		1/1	1/1	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1	
Dichloroacetic acid	$C_2H_2Cl_2O_2$	000079-43-6	tech. pure	C		1/3	3/3	4/4	(4)	4/4	0/0	4/4	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1	
Dichloroacetic acid methyl ester	-> see: Methyl dichloroacetate																														
Dichlorethane, 1,2-	-> see: Ethylene chloride																														
Dichlorethene, 1,1-	-> see: Vinylidene chloride																														
Dichloroethylene	$C_2H_2Cl_2$	—	tech. pure	F+, Xn	X	4/4	4/4	3/0	(4)	4/4	(4)	4/4	3/0	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/0	1/1	4/4	3/4	4/4	0/0	(3)	1/1L	1/1L	0/0	Isomer not specified in the source
Dichloroethylene, 1,1-	-> see: Vinylidene chloride																														
Dichlorofluoromethane	$CHCl_2F$	000075-43-4	100 %	N		0/0	3/0	1/0	3/0	0/0	0/0	1/0	4/4	4/4	3/0	4/4	4/4	3/3	0/0	(3)	1/0	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Dichlorohexafluorocyclobutane	$C_4Cl_2F_6$	000356-18-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	(3)	1/0	0/0	(3)	0/0	0/0		
Dichloroisopropyl ether	$C_6H_{12}Cl_2O$	—		(Xn)		(4)	(4)	(2)	(3)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		Isomer not specified in the source
Dichlormethane	CH_2Cl_2	000075-09-2		Xn		4/4	4/4	3/4	4/4	4/4	3/4	3/0	3/4	4/4	4/4	4/4	4/4	4/4	2/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	4/4	(1/1L)[1)]	(1/1L)[1)]	1/1	[1)] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Dichlorpropane	$C_3H_6Cl_2$	—	100 %	F, T/Xn	X	0/0	0/0	(3)	-4	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Dichlorotetrafluoroethane	$C_2Cl_2F_4$	000076-14-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Dicyclohexylamine (DCHA)	$C_{12}H_{23}N$	000101-83-7		C, Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Dicyclohexyl phthalate	$C_{20}H_{26}O_4$	000084-61-7	tech. pure	(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	(3)	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diesel fuel	—	—		Xn, N		1/3	0/0	1/1	3/3	1/1	0/0	1/1	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	(1)	(1)	0/0	
Diesel oil	—	068334-30-5	100 %	(Xn)		1/3	1/4	1/1	3/3	1/1	0/0	1/1	1/3	3/4	0/0	1/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	(1)	(1)	0/0	
Diethanolamine (DEA)	$C_4H_{11}NO_2$	000111-42-2	100 %	Xi		0/0	1/0	(2)	(3)	0/0	0/0	(2)	1/2	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/3	3/0	(3)	4/4	0/0	1/1	(1)	(1)	0/0	
Diethylamine	$C_4H_{11}N$	000109-89-7	tech. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/2	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Diethylbenzene	$C_{10}H_{14}$	000135-01-3		Xi		3/4	4/4	(1)	3/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Diethylene glycol	$C_4H_{10}O_3$	000111-46-6		T		1/1	1/1	3/0	2/3	0/0	1/1	(2)	1/1	2/2	2/2	3/4	0/0	1/1	1/1	1/1	1/1	(2)	1/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0	
Diethylene glycol ether	—	—		(Xn)		1/1	1/1	3/0	3/4	0/0	1/1	(2)	1/1	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	3/0	(3)	3/3	0/0	(1)	(1)	(1)		
Diethyl ether	-> see: Ethyl ether																														
Diethyl ketone	$C_5H_{10}O$	000096-22-0		F		2/2	2/3	(3)	4/4	(4)	2/3	1/0	2/2	4/4	4/4	4/4	0/0	4/4	2/3	1/1	1/1	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	0/0	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Diethylmalonate	$C_7H_{12}O_4$	000105-53-3		Xi		1/1	1/1	(2)	3/4	0/0	1/2	(2)	1/1	4/4	3/3	2/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(4)	(3)	0/0	(1)	(1)	(1)		
Diethylmethane	-> see: Pentane																													
Diethyl sebacate	$C_{14}H_{26}O_4$	000110-40-7		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diethyl succinate	-> see: Succinic acid diethyl ester																													
Difluorochloroethane	$C_2H_3ClF_2$	000075-68-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluoroethane	$C_2H_2F_2$	000075-37-6		(E), F+		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluoromethane	CH_2F_2	000075-10-5		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluorotetrachloroethane	$C_2Cl_4F_2$	000076-12-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0		
Diglycol	-> see: Diethylene glycol																													
Diglycolic acid	$C_4H_6O_5$	000110-99-6	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/1	4/4	0/0	3/4	1/4	1/4	1/1	
Diglycolic acid	$C_4H_6O_5$	000110-99-6	30 %	Xn, Xi		1/1	1/1	(3)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/0	1/0	1/1	4/4	0/0	3/4	1/4	1/4	1/1	
Dihexyl phthalate	-> see: Dicyclohexyl phthalate																													
Dihydroxybenzene, 1,3-	-> see: Resorcinol																													
Dihydroxybenzene, 1,4-	-> see: Hydroquinone																													
Dihydroxysuccinic acid	-> see: Tartaric acid																													
Dihydroxydiethylamine	-> see: Diethanolamine																													
Diisobutylene (DIB)	C_8H_{16}	025167-70-8		F	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	1/2	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Diisobutylketone	$C_9H_{18}O$	000108-83-8	tech. pure	Xi	X	1/4	1/3	(3)	(3)	(4)	(4)	1/0	1/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/3	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Diisooctyl phthalate (DOP)	$C_{24}H_{38}O_4$	000117-81-7	tech. pure	Xn		4/4	4/4	1/0	4/4	1/0	1/0	(2)	4/4	4/4	1/0	4/4	4/4	0/0	0/0	1/1	1/0	(2)	3/0	2/3	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diisopropyl ether	-> see: Isopropyl ether																													
Diisopropyl ketone	$C_7H_{14}O$	000565-80-0		F	X	0/0	0/0	(3)	(3)	(4)	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Dimethylamine	C_2H_7N	000124-40-3	tech. pure	F+, Xn	X	1/3	1/3	1/0	4/4	0/0	0/0	(2)	1/3	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	3/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Dimethylaniline	$C_8H_{11}N$	—		T		0/0	0/0	(3)	4/4	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Dimethylbenzene	-> see: Xylene																													
Dimethylcarbinol	-> see: Isopropyl																													
Dimethyl ether	C_2H_6O	000115-10-6	Gas	F+	X	0/0	3/0	1/0	(3)	1/0	0/0	(2)	4/4	4/4	0/0	3/0	4/4	0/0	0/0	0/0	1/0	(3)	3/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Dimethylformamide (DMF)	C_3H_7NO	000068-12-2		T, F	X	1/1	1/3	1	4/4	1/0	1/1	1/2	1/1	4/4	4/4	3/4	0/0	4/4	2/2	1/1	1/1	4/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Dimethyl ketone	-> see: Acetone																													
Dimethylpentanone-3, 2,4-	-> see: Diisopropyl ketone																													
Dimethyl phthalate (DMP)	$C_{10}H_{10}O_4$	000131-11-3	100 %	(Xn)		4/4	1/3	(2)	4/4	0/0	0/0	(2)	2/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(2)	3/0	2/0	4/4	0/0	(1)	(1)	(1)	0/0	Plasticiser
Dimethylpropane	-> see: Pentane																													
Dimethyl sulphoxide (DMSO)	C_2H_6SO	000067-68-5		Xi		1/1	1/1	(2)	4/4	0/0	1/1	1/0	1/1	1/2	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(3)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		
Disodium hydrogen phosphate	-> see: Disodium phosphate																													
Disodium phosphate	Na_2HPO_4	007558-79-4		(Xi)		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	(1)	1/1	1/1	0/0	
Disodium sulphate	-> see: Sodium sulphate																													
Dinonyl phthalate (DNP)	$C_{26}H_{42}O_4$	000084-76-4	tech. pure	Xn		3/0	0/0	(2)	3/0	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioctyladipate	$C_{22}H_{42}O_4$	000103-23-1		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioctyl phthalate	-> see: Diisooctyl phthalate																													
Dioctyl sebacate	$C_{26}H_{50}O_4$	002432-87-3		—		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioxane	$C_4H_8O_2$	000123-91-1		F, Xn	X	2/2	2/3	1/0	4/4	1/0	2/3	1/2	3/3	4/4	2/3	3/4	4/4	4/4	1/3	1/1	1/1	3/3	2/0	4/4	4/4	0/0	1/1	1/0	1/0	0/0	
Dioxane, 1,4-	-> see: Dioxane																													
Dipentene	-> see: Limonene, DL-																													
Dipentyl phthalate	-> see: Phthalic acid amyl ester																													
Diphenylamine	$C_{12}H_{11}N$	000122-39-4		T		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	0/0	
Diphenyleneimine	-> see: Carbazole																													
Diphenyl ether	$C_{12}H_{10}O$	000101-84-8		Xn/Xi		0/0	1/0	3/0	(3)	(4)	0/0	1/1	4/4	4/4	0/0	0/0	4/4	4/4	0/0	(1)	1/0	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Diphenylmethane diisocyanate (MDI)	-> see: Desmodur 44																													
Diphenyl oxide	-> see: Diphenyl ether																													
Diphosphorus pentoxide	-> see: Phosphorus pentoxide																													
Diphyl	—	008004-13-5		?		0/0	0/0	1/1	(3)	4/4	0/0	1/1	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)		Mixture of diphenyl and diphenyl ether; Bayer
Dipropylene glycol	$C_6H_{14}O_3$	025265-71-8		Xi		1/1	1/1	(2)	2/3	0/0	1/1	1/0	1/1	1/1	2/2	2/3	0/0	0/0	1/1	1/1	(1)	(2)	4/4	3/0	3/3	0/0	(1)	(1)	(1)		
Dipropyl ketone	$C_7H_{14}O$	000123-19-3		—	X	0/0	0/0	(3)	(4)	(4)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Dipropylmethane, n-	-> see: Heptane, n-																													
Di-sulphur dichloride	-> see: Sulphur chloride																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals		
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Dinitrogen tetroxide	-> see: Nitrogen tetroxide																													
Disulphite	-> see: Sodium disulphite																													
Divinylensulphide	-> see: Thiophene																													
Dodecanol	-> see: Lauryl alcohol																													
Dodecyl alcohol	-> see: Lauryl alcohol																													
Dodecyl chloride	-> see: Lauryl chloride																													
Dolcymene	-> see: Cymene, p-																													
Eau de Labarraque	-> see: Sodium hypochlorite																													
Edetic acid	-> see: Ethylenediaminetetraacetic acid																													
Iron (II) ammonium sulphate	-> see: Ammonium iron (II) sulphate																													
Iron (II) chloride	$FeCl_2$	007758-94-3	saturated	Xn		1/1	1/1	3/0	1/0	(2)	1/0	(3)	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	(1)	0/0	4/4	(2)	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7	saturated	(Xn)		1/1	1/1	(2)	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7	aqueous	(Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7		Xn		1/1	1/1	(2)	1/0	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/0	(1)	0/0	4/4	1/1	1/1	1/1	
Iron (III) chloride	$FeCl_3$	007705-08-0	saturated	Xn		1/1	1/1	3/0	1/0	0/0	1/0	4/4	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	4/4	4/4	4/4	1/1	
Iron (III) nitrate	-> see: Ferric nitrate																													
Iron (III) sulphate	$Fe_2(SO_4)_3$	010028-22-5	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1	
Iron alum	-> see: Ammonium iron (III) sulphate																													
Iron ammonium alum	-> see: Ammonium iron (III) sulphate																													
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	aqueous	(O, Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	saturated	O, Xn		1/1	1/1	1/0	1/0	0/0	1/0	(3)	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Iron vitriol	-> see: Iron (II) sulphate																													
Glacial acetic acid	-> see: Acetic acid																													
Elaol	-> see: Dibutyl phthalate																													
Emulsifiers	—	—		?		0/0	0/0	(2)	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(3)	0/0	0/0	K	K		
Developer fluids	—	—		?		1/1	1/1	4/4	1/0	1/0	0/0	1/0	1/1	0/0	1/0	1/1	1/0	0/0	0/0	0/0	1/1	(1)	2/0	1/0	3/3	0/0	1/1	1/0	1/0	0/0	
Limescale	—	—	10% in Water	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Epichlorohydrin	C_3H_5ClO	000106-89-8	100 %	F, T	X	1/0	1/0	4/4	(4)	0/0	(4)	1/0	2/2	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(3)	3/0	4/4	4/4	0/0	(3)	0/0	0/0	0/0	
Epoxypropane	-> see: Propylene oxide																													
Epsom salt	-> see: Magnesium sulphate																													
Natural gas	—	—		F+	X	0/0	0/0	01/0	1/0	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	0/0	mainly methane
Peanut oil	—	008002-03-7		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Crude oil / petroleum	—	008002-05-9		(Xn)		0/0	0/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/3	0/0	(1)	(1)	(1)	0/0	Kerosene, lamp oil
Vinegar	$C_2H_4O_2$	000064-19-7		(Xi)		1/1	1/3	4/4	1/2	1/1	1/0	1/3	1/1	1/0	1/0	1/0	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/2	1/1	Wine vinegar, acetic acid
Acetic ester	-> see: Ethyl acetate																													
Acetic acid	$C_2H_4O_2$	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	90%	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1	1/1	
Acetic acid Silver salt	-> see: Silver acetate																													
Acetic alumina	$C_4H_7AlO_5 \times H_2O$	000142-03-0	saturated	Xi		1/1	1/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1		
Acetic acid allyl ester	-> see: Allyl acetate																													
Acetic acid amide	-> see: Acetamide																													
Acetic anhydride	$C_4H_6O_3$	000108-24-7	tech.pure	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1	1/1	
Acetic acid benzyl ester	-> see: Benzyl acetate																													
Acetic acid butyl ester	$C_6H_{12}O_2$	000123-86-4	100 %	—	X	2/2	2/3	1/0	4/4	3/0	3/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	3/0	4/4	4/4	0/0	1/1	(1)	(1)	4/4	
Acetic acid chloride	-> see: Acetyl chloride																													
Acetic acid ethyl ester	-> see: Ethyl acetate																													
Acetic acid isobutyl ester	-> see: Isobutyl acetate																													
Acetic acid isopropyl ester	-> see: Isopropyl acetate																													
Acetic acid methyl ester	$C_3H_6O_2$	000079-20-9	tech. pure	F	X	1/0	1/1	1/0	4/4	3/0	(4)	2/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Acetic acid-n-amyl ester	-> see: Amyl acetate, n-																													
Acetic acid pentyl ester	-> see: Amyl acetate, n-																													
Acetic acid propyl ester	-> see: Propyl acetate																													
Acetic acid vinyl ester	-> see: Vinyl acetate																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ethanal	-> see: Acetaldehyde																													
Ethane carboxylic acid	-> see: Propionic acid																													
Ethanediamine	-> see: Ethylenediamine																													
Ethanedicarboxylic acid	-> see: Succinic acid																													
Ethanediol	-> see: Ethylene glycol																													
Ethanedioic acid	-> see: Oxalic acid																													
Ethanol	C_2H_6O	000064-17-5	40 %	—	X	1/1	1/2	1/0	1/2	1/1	1/2	1/2	1/1	2/3	1/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Ethanol	C_2H_6O	000064-17-5	50 %	—	X	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	
Ethanol	C_2H_6O	000064-17-5	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	
Ethanolamine	C_2H_7NO	000141-43-5		Xn/Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/2	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Ethanoic acid	-> see: Acetic acid																													
Ethanethiol	C_2H_6S	000075-08-1		F, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ethene	-> see: Ethylene																													
Ether	-> see: Ethyl ether																													
Ethyne	-> see: Acetylene																													
Ethinylcarbiol	-> see: Propargyl alcohol																													
Ethoxyacetanilide, 4-	-> see: Phenacetin																													
Ethoxyethanol	-> see: Ethyl glycol																													
Ethoxyethyl acetate, 2-	-> see: Ethylene glycol monoethyl ether acetate																													
Ethyl(hydroxymethyl)-propanediol	-> see: Trimethylolpropane																													
Ethyl acetate	$C_4H_8O_2$	000141-78-6	100 %	F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/1	1/3	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	3/3	3/0	4/4	4/4	0/0	1/1	(1)	(1)	1/0	
Ethyl acrylate	$C_5H_8O_2$	000140-88-5	100 %	F, Xn	X	4/4	4/4	1/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	3/0	4/4	4/4	4/4	0/0	(1)	(1)	(1)	1/0	
Ethyl alcohol	-> see: Ethanol																													
Ethylbenzol	-> see: Ethylbenzene																													
Ethyl benzoate	-> see: Benzoic acid ethyl ester																													
Ethylbenzene	C_8H_{10}	000100-41-4		F, Xn	X	2/3	3/4	(2)	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	1/1	4/4	(2)	4/4	0/0	(1)	(1)	(1)	0/0	
Ethyl butyrate	$C_6H_{12}O_2$	000105-54-4		F	X	2/3	2/4	(2)	4/4	0/0	3/4	(2)	2/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethylcarbinol	-> see: Propanol																													
Ethyl cellosolve	-> see: Ethyl glycol																													
Ethyl chloroacetate	$C_4H_7ClO_2$	000105-39-5	tech. pure	T/Xi		1/1	1/1	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/4	3/4	0/0	0/0	(1)	1/1	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Ethyl chloride	-> see: Chlorethane																													
Ethyl cyanoacetate	$C_5H_7NO_2$	000105-56-6		Xn/Xi		1/1	1/1	0/0	3/4	0/0	1/1	(2)	1/1	2/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Ethylene	C_2H_4	000074-85-1		F+	X	0/0	0/0	1/0	(2)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	(3)	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Ethylene(di)bromide	-> see: Dibromoethane-1,2																													
Ethylene(di)chloride	-> see: Dichloroethane-1,2																													
Ethylene chlorohydrin	-> see: Chloroethanol																													
Ethylene chloride	$C_2H_4Cl_2$	—		F, T	X	3/3	2/4	3/0	4/4	4/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/3	1/1L	1/1L	0/0	Isomer not specified in the source
Ethylenediamine	$C_2H_8N_2$	000107-15-3	tech. pure	C, Xn	X	1/1	1/3	1/0	(3)	0/0	1/0	1/0	1/1	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/4	1/0	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Ethylenediaminetetraacetic acid (EDTA)	$C_{10}H_{16}N_2O_8$	000060-00-4		Xi		1/1	1/1	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(3)	0/0	0/0	0/0	
Ethylene dichloride	-> see: Ethylene chloride																													
Ethylenedinitrilotetraacetic acid	-> see: Ethylenediaminetetraacetic acid																													
Ethylene glycol	$C_2H_6O_2$	000107-21-1		Xn		1/1	1/1	3/3	2/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	1/1	
Ethylene glycol ethyl ether	-> see: Ethyl glycol																													
Ethylene glycol monobutyl ether	-> see: Butyl glycol																													
Ethylene glycol monobutyl ether	-> see: Ethyl glycol																													
Ethylene glycol monoethyl ether acetate	$C_6H_{12}O_3$	000115-15-9		Xn	X	1/1	1/2	0/0	3/4	0/0	1/2	(2)	1/2	4/4	4/4	3/4	0/0	0/0	1/2	1/1	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Ethylene glycol monomethyl ether	-> see: Methyl glycol																													
Ethylene oxide	C_2H_4O	000075-21-8		F+, T	X	2/3	3/3	3/0	3/4	1/0	3/4	1/0	3/3	4/4	1/1	3/4	0/0	0/0	1/1	1/1	(1)	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Ethylene tetrachloride	-> see: Perchloroethylene																													
Ethylene trichloride	-> see: Trichloroethylene																													
Ethylethanamine, N-	-> see: Diethylamine																													
Ethyl ether	$C_4H_{10}O$	000060-29-7	tech. pure	F+, Xn	X	3/4	4/4	1/1	4/4	1/0	4/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Ethyl formate	$C_3H_6O_2$	000109-94-4		F	X	0/0	0/0	0/0	(4)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethyl glycol	$C_4H_{10}O_2$	000110-80-5	100 %	T	X	0/0	4/4	(3)	(2)	0/0	0/0	1/0	2/4	4/4	1/0	4/4	4/4	4/4	0/0	1/1	1/0	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Ethyl glycol acetate	-> see: Ethylene glycol monoethyl ether acetate																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ethylhexanol-1	$C_8H_{18}O$	000104-76-7		Xn/Xi		0/0	1/3	(2)	(2)	(1)	1/0	1/0	1/0	3/0	0/0	1/0	4/4	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	
Ethyl lactate	$C_5H_{10}O_3$	000097-64-3		—	X	1/1	1/1	(2)	3/4	0/0	1/1	(2)	1/1	3/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	3/0	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Ethyl malonate	-> see: Diethylmalonate																													
Ethyl mercaptan	-> see: Ethanethiol																													
Ethyl methyl ketone	-> see: Methyl ethyl ketone																													
Ethyl silicate	-> see: Tetraethylorthosilicate																													
Eucalyptus oil	—	008000-48-8		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Desiccator grease	—	—		—		0/0	1/3	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(2)	(2)	0/0	(1)	(1)	(1)	0/0	
Ferrichloride	-> see: Iron (III) chloride																													
Potassium hexacyanoferrate(III)	$C_6FeK_3N_6$	013746-66-2	any	Xn		1/1	1/1	1/0	(1)	(1)	0/0	2/0	1/1	1/1	0/0	1/3	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1	1/1	
Ferrous chloride	-> see: Iron (II) chloride																													
Potassium hexacyanoferrate(II)	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	saturated	—		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(1)	1/1	1/1		
Potassium hexacyanoferrate(II)	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	diluted	—		1/0	1/1	1/0	(1)	(1)	0/0	2/0	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1		
Fat/Grease, mineral	—	—		(—)		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	(1)	1/0	0/0	(1)	1/1	1/1		
Fat/Grease, vegetable	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fat/Grease, animal	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fatty/Greasy alcohol sulphonates	—	—	aqueous	(Xn, Xi)		1/1	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	1/1	0/0	3/4	1/0	1/0	0/0	Fatty alcohol sulphates, wetting agents/surfactants
Fat/Grease, edible oil	—	—		—		0/0	1/0	1/0	1/0	1/0	1/0	1/1	3/0	0/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Fatty acid C16	-> see: Palmitic acid																													
Spruce needle oil	—	008008-80-8		?		1/2	2/4	(2)	2/3	0/0	2/3	(2)	1/2	4/4	3/3	3/4	0/0	3/4	1/2	1/1	(1)	(2)	4/4	1/0	3/3	0/0	(1)	(1)	(1)		Pinus sylvestris
Fish oil	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/4	1/0	1/0	0/0	(1)	(1)	(1)		
Fixing salt	-> see: Sodium thiosulphate																													
Aircraft engine fuels (JP)	—	—		(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	1/0	1/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	1/0	1/0	0/0	(1)	(1)	(1)		
Fluid 101, 100°C	—	—		?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	3	0	0	0	0		Brake fluid, polyglycol base
Fluorine	F_2	007782-41-4		O, T+, C+		4/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	4/4	4/4	3/0	4/4	0/0	4/4	(4)	(4)	0/0	
Fluorammonium	-> see: Ammonium fluoride																													
Fluorobenzene	C_6H_5F	000462-06-6		F, (Xn)	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0		
Fluorochloroalkanes (FCKW)	—	—		N		0/0	0/0	(2)	(3)	0/0	0/0	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(3)	(3)	0/0	(3)	0/0	(3)	0/0	0/0		Resistance varies depending on type
Fluorides	—	—		T		1/1	1/1	(2)	1/1	(2)	1/1	(1)	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	(1)	0/0	0/0	K	K		
Fluoropotassium	-> see: Potassium fluoride																													
Fluorosilicic acid	-> see: Silicofluoric acid																													
Fluorocarbons (FKW)	—	—		?		0/0	0/4	(2)	(3)	(2)	0/0	(2)	(3)	4/4	0/0	0/0	0/0	0/4	1/1	0/0	1/1	(3)	(3)	(3)	(3)	0/0	(1)	0/0	0/0		Resistance varies depending on type
Fluorosilicic acid	-> see: Silicofluoric acid																													
Fluorotrichloromethane	-> see: Trichlorofluoromethane																													
Hydrogen fluoride	HF	007664-39-3	anhydrous	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)		Hydrofluoric acid, anhydrous
Hydrogen fluoride solution	-> see: Hydrofluoric acid																													
Hydrofluoric acid	-> see: Hydrofluoric acid																													
Liquid soaps	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(2)	(2)	0/0	(3)	0/0	0/0		
Hydrofluoric acid	HF	007664-39-3	4 %	T, C		1/1	1/2	4/4	2/3	4/4	1/2	4/4	1/2	2/3	2/3	2/3	0/0	0/0	1/1	1/1	1/1	1/1	(3)	1/3	(2)	0/0	4/4	0/0	0/0	?	
Hydrofluoric acid	HF	007664-39-3	50 %	T+, C		1/1	1/1	4/4	4/4	4/4	1/1	4/4	1/1	4/4	3/4	2/3	2/0	3/3	1/1	1/1	1/1	1/1	3/4	1/3	3/4	0/0	4/4	4/4	4/4	?	
Hydrofluoric acid	HF	007664-39-3	70 %	T+, C		0/0	1/3	4/4	4/4	4/4	0/0	4/4	1/3	4/4	4/4	1/4	3/0	0/0	0/0	(1)	1/1	1/1	3/4	(3)	4/4	0/0	4/4	4/4	4/4	?	
Hydrofluoric acid	HF	007664-39-3	100 %	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)	?	
Hydrofluoric acid, anhydrous	-> see: Hydrogen fluoride																													
Formaldehyde solution	CH_2O	000050-00-0	10 %	Xn		1/1	1/1	3/3	1/2	1/0	1/2	1/2	1/1	3/4	2/3	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/0	3/0	(2)	0/0	1/1	1/1	1/1	1/1	
Formaldehyde solution	CH_2O	000050-00-0	30 %	T		1/1	1/1	3/3	1/2	1/0	0/0	1/2	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	1/1	1/1	
Formaldehyde solution	CH_2O	000050-00-0	40 %	T		1/2	2/3	1/3	1/2	1/0	1/2	1/2	1/2	4/4	2/3	2/3	3/3	0/4	1/1	1/1	1/1	1/1	1/0	3/0	(3)	0/0	1/1	1/1	1/1	1/1	
Formalin	-> see: Formaldehyde solution																													
Formamide	CH_3NO	000075-12-7	tech. pure	T/Xi		1/1	1/1	1/0	(3)	0/0	0/0	1/0	1/1	1/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	3/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	
Formin	-> see: Hexamethylenetetramine																													
Formylic acid	-> see: Formic acid																													
Photo emulsions	—	—		?		1/0	0/0	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(1)	0/0	(2)	0/0	0/0		
Photo developers	—	—		?		1/3	1/1	4/4	(2)	1/0	0/0	1/3	1/2	0/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Photo fixing baths	—	—		?		1/0	1/1	1/0	(2)	0/0	0/0	1/0	1/1	0/0	0/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/0	1/0		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Freon 11	-> see: Trichlorofluoromethane																													
Freon 112	-> see: Difluorotetrachloroethane																													
Freon 113	-> see: Trichlorotrifluoroethane																													
Freon 114	-> see: Dichlorotetrafluoroethane																													
Freon 114 B2	-> see: Dibromotetrafluoromethane																													
Freon 115	-> see: Chloropentafluoroethane																													
Freon 12	-> see: Dichlorodifluoromethane																													
Freon 13	-> see: Chlorotrifluoromethane																													
Freon 13 B1	-> see: Bromotrifluoromethane																													
Freon 14	-> see: Tetrafluoromethane																													
Freon 142b	-> see: Difluorochloroethane																													
Freon 152a	-> see: Difluoroethane																													
Freon 21	-> see: Dichlorofluoromethane																													
Freon 218	-> see: Perfluoropropane																													
Freon 22	-> see: Chlorodifluoromethane																													
Freon 31	-> see: Chlorofluoromethane																													
Freon 32	-> see: Difluoromethane																													
Freon C 318	-> see: Octafluorocyclobutane																													
Freon C316	-> see: Dichlorohexafluorocyclobutane																													
Frigen 12	-> see: Dichlorodifluoromethane																													
Frigen 21	-> see: Dichlorofluoromethane																													
Frigen 22	-> see: Chlorodifluoromethane																													
Antifreeze (KFZ)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1	1/1	Glycol-water mixtures
Fruit juices	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(2)	1/1	1/1	1/1	
Fruit sugar	-> see: Fructose																													
Fructose	$C_6H_{12}O_6$	000057-48-7	any	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Furan	C_4H_4O	000110-00-9		F+, T+	X	0/0	0/0	(3)	4/4	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Furanal	-> see: Furfural																													
Furancarbinol, 2-	-> see: Furfuryl alcohol																													
Furanmethanol, 2-	-> see: Furfuryl alcohol																													
Furfurol	-> see: Furfural																													
Furfural alcohol	-> see: Furfuryl alcohol																													
Furfuran	-> see: Furan																													
Furfural	$C_5H_4O_2$	000098-01-1		T		1/3	3/4	3/3	(3)	1/0	0/0	2/0	4/4	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	1/2	3/0	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Furfuryl alcohol	$C_5H_6O_2$	000098-00-0	tech. pure	Xn		1/1	1/3	1/0	(3)	1/0	0/0	1/0	1/3	0/0	4/4	4/4	4/4	3/4	0/0	(1)	1/1	1/3	3/0	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Furylaldehyde, 2-	-> see: Furfural																													
Furylmethanal, 2-	-> see: Furfural																													
Gallotannin	-> see: Tannin																													
Gallic acid	$C_7H_6O_5 \times H_2O$	000149-91-7		Xi		1/1	1/1	1/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/4	3/0	1/0	3/0	0/0	1/0	1/1	1/1	1/1	
Fermentation amyl alcohol	-> see: Isoamyl alcohol																													
Fermentation mash	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(1)	1/0	4/4	0/0	(2)	(1)	(1)	0/0	
Gas oil (straight-run)	—	—		(Xn)		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Gasoline	—	008006-61-9		(F, Xn)	X	0/0	0/0	(1)	3/4	(2)	0/0	1/2	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/0	0/0	1/1	(1)	(1)		
Gas water	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(2)	0/0	(2)	0/0	0/0		
Gelatine	—	009000-70-8	any	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Genantin	—	—		Xn		0/0	0/0	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		Antifreeze, basis glycol; Clariant
Tanning extracts, vegetable	—	—	tech. common	?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Tanning extracts	—	—		?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Tannic acid	-> see: Tannin																													
Gear oil, EP (hypoid), 110°C	—	—		?		0	0	1	1	1	0	4	(3)	0	0	0	0	0	0	0	(2)	0	4/4	0	4/4	0	(1)	1	1		
Plaster	-> see: Calcium sulphate																													
Glauber's salt	-> see: Sodium sulphate																													
Glucaric acid	-> see: Sugar acid																													
Glucose	$C_6H_{12}O_6$	000050-99-7	any	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Glucose syrup	-> see: Starch syrup																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Glycerine	$C_3H_8O_3$	000056-81-5	any	Xi		1/1	1/1	1/0	3/3	1/0	1/1	1/0	1/1	1/1	1/1	1/1	2/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Glycerol trinitrate	-> see: Nitroglycerin																													
Glycine	-> see: Aminoacetic acid																													
Glycol	-> see: Ethylene glycol																													
Glycol dinitrate	-> see: Nitroglycol																													
Glycolic acid	$C_2H_4O_3$	000079-14-1	37 %	Xn		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	2/0	1/0	0/0	1/0	1/3	1/3	1/1	
Glycolic acid	$C_2H_4O_3$	000079-14-1	70 %	C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(2)	1/0	3/0	(2)	0/0	(2)	1/3	1/3	1/1	
Glycocoll	-> see: Aminoacetic acid																													
Glycol chlorohydrin	-> see: Chloroethanol																													
Glysantin	—	—		Xn		1/1	1/1	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		Antifreeze, basis glycol; BASF
Glycerol triacetate	-> see: Triacetin																													
Firedamp	—	—		F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		mainly methane
Uric acid	$C_5H_4N_4O_3$	000069-93-2		Xi		1/1	1/1	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	4/4	1/1	1/1	0/0	
Urea	CH_4N_2O	000057-13-6	aqueous	Xi		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, carbamide, etc.
Urea	CH_4N_2O	000057-13-6		Xi		1/1	1/1	1/0	1/1	1/0	1/2	1/1	1/1	1/2	3/3	2/4	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, carbamide, etc.
HD oil engine oil, aromatics-free	—	—		?		1/0	1/3	1/0	1/1	1/1	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	(1)	3/3	0/0	1/1	1/1	1/1		
Yeast	—	—	any	—		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	(1)	(1)		
Heating oil	—	—		Xn		3/3	3/4	1/0	3/3	1/0	2/3	1/1	1/3	3/4	1/2	1/1	3/3	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Helium	He	007440-59-7		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	1/0	1/0	1/0	0/0	1/1	1/1	1/1		
Hendecanol	-> see: Undecyl alcohol																													
Henkel-P3-solution	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/0	0/0	0/0	1/1	1/1		Cleaning agents
Heptan, n-	C_7H_{16}	000142-82-5		F, Xn	X	2/3	3/4	1/0	1/2	1/0	3/3	1/2	2/4	4/4	1/2	2/3	4/4	1/0	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Heptanol, 1-	$C_7H_{16}O$	000111-70-6		Xn		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	(1)	(1)	(1)		
Heptanon	$C_7H_{14}O$	—		(Xn)	X	0/0	0/0	(3)	(4)	(4)	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(4)	(4)	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Heptanon-4	-> see: Dipropylketone																													
Heptyl alcohol	-> see: Heptanol, 1-																													
Hexachlorobenzene (HCB)	C_6Cl_6	000118-74-1		T		0/0	0/0	(3)	(4)	0/0	(4)	1/0	(3)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(2)	0/0	4/4	(3)	4/4	0/0	(1)	0/0	0/0		
Hexachlorobutadiene (HCBD)	C_4Cl_6	000087-68-3		T		0/0	0/0	(3)	4/4	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexachlorocyclohexane (HCH)	$C_6H_6Cl_6$	000319-84-6		T		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexadecanol	-> see: Cetyl alcohol																													
Hexadecanoic acid	-> see: Palmitic acid																													
Hexadecyl alcohol	-> see: Cetyl alcohol																													
Hexahydrobenzene	-> see: Cyclohexan																													
Hexahydrophenol	-> see: Cyclohexanol																													
Hexahydropyridine	-> see: Piperidine																													
Hexahydrotoluene	-> see: Methylcyclohexane																													
Hexaldehyde	-> see: Hexanal																													
Hexamethylenetetramine	$C_6H_{12}N_4$	000100-97-0		F, Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	1/1	1/1	0/0	
Hexamine	-> see: Hexamethylenetetramine																													
Hexane, n-	C_6H_{14}	000110-54-3		F, Xn	X	2/3	4/4	1/0	(2)	1/0	3/4	1/1	2/3	4/4	1/2	2/4	4/4	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Hexanal	$C_6H_{12}O$	000066-25-1		F, Xi	X	0/0	0/0	0/0	(4)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Hexanedioic acid	-> see: Adipic acid																													
Hexanol, (1-)	$C_6H_{14}O$	000111-27-3		Xn		1/0	1/0	(2)	(2)	(1)	0/0	(1)	1/2	0/0	3/0	1/0	3/0	1/3	0/0	(1)	1/0	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Hexanone-2	-> see: Methyl butyl ketone																													
Hexanetriol	$C_6H_{14}O_3$	—	100 %	?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	1/1	3/3	1/1	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Hexen, 1-	C_6H_{12}	000592-41-6		F, Xn	X	0/0	0/0	1/0	(2)	(1)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Hexylaldehyde	-> see: Hexanal																													
Hexyl alcohol	-> see: Hexanol, (1-)																													
Hexylene	-> see: Hexen, 1-																													
Staghorn salt	-> see: Ammonium carbonate																													
Wood alcohol	-> see: Methanol																													
Wood oil	—	008001-20-5		—		0/0	0/0	(1)	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	1/1	(1)	(1)		
Wood tar oil	-> see: Creosote																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Honey	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	0/0	(1)	(1)	(1)	0/0	
Gibbsite	-> see: Aluminium hydroxide																													
Hydraulic fluids, HFA	—	—	50°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFB	—	—	50°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFC	—	—	60°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	0	0	1	0	(2)	0	0		
Hydraulic fluids, HFD-R	—	—	100°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic fluids, HFD-S	—	—	100°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic oils (mineral oil based)	—	—		?		0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	(1)	1/0	0/0	1/1	1/1	1/1		
Hydrazine	N_2H_4	000302-01-2	10 %	T	X	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	1/1	
Hydrazine hydrate	N_2H_6O	010217-52-4	aqueous	(T, C)	(X)	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	0/0	
Hydrazinium hydroxide	-> see: Hydrazine hydrate																													
Hydrazinobenzene	-> see: Phenylhydrazine																													
Hydroquinone	$C_6H_6O_2$	000123-31-9	saturated	Xn		0/0	1/3	4/4	(3)	1/0	0/0	(3)	1/0	4/4	0/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	4/4	4/4	0/0	(1)	1/0	1/0	0/0	
Hydrosulphite	-> see: Sodium dithionite																													
Hydroxy-4-methyl-2-pentanone, 4-	-> see: Diacetone alcohol																													
Hydroxybenzaldehyde, 2-	-> see: Salicylaldehyde																													
Hydroxybenzoic acid, 2-	-> see: Salicylic acid																													
Hydroxybenzene	-> see: Phenol																													
Hydroxybenzenecarboxylic acid, 2-	-> see: Salicylic acid																													
Hydroxyacetic acid	-> see: Glycolic acid																													
Hydroxylamine sulphate	-> see: Hydroxylammonium sulphate																													
Hydroxylammonium sulphate	$H_8N_2SO_6$	010039-54-0	12 %	Xn		1/1	1/1	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	1/1	
Hydroxylammonium sulphate	$H_8N_2SO_6$	010039-54-0	any	Xn		1/1	0/0	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	1/1	
Hydroxymethoxybutane	-> see: Methoxybutanol																													
Hydroxymethylfuran, 2-	-> see: Furfuryl alcohol																													
Hydroxymethylfurfural, 5-	-> see: Oxymethylfurfurol, 5-																													
Hydroxymethyl tetrahydrofuran, 2-	-> see: Tetrahydrofurfuryl alcohol																													
Hydroxypropane	-> see: Propanol																													
Hydroxypropane, 2-	-> see: Isopropyl																													
Hydroxypropionic acid, 2-	-> see: Lactic acid																													
Hydroxypropionic acid ethyl ester, 2-	-> see: Ethyl lactate																													
Hydroxytoluene	-> see: Cresol (-mixtures)																													
Iminodiethanol	-> see: Diethanolamine																													
Ginger	—	—	grinded	?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Isoamyl alcohol	$C_5H_{12}O$	000123-51-3		Xn	X	0/0	0/0	(2)	3/0	1/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	1/3	0/0	(1)	!/1	1/1	3/0	2/4	3/3	0/0	(1)	(1)	(1)		
Isobutanol	$C_4H_{10}O$	000078-83-1		Xn	X	1/1	1/1	(2)	1/2	(2)	1/2	1/0	1/1	2/2	1/2	1/2	0/0	3/4	1/1	1/1	(1)	1/1	1/0	1/0	3/4	0/0	1/0	(1)	(1)	0/0	
Isobutyl acetate	$C_6H_{12}O_2$	000110-19-0		F	X	0/0	0/0	(2)	(4)	0/0	(4)	1/0	(3)	4/4	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Isobutyl alcohol	-> see: Isobutanol																													
Isobutyl ketone	-> see: Diisobutyl ketone																													
Isobutyl methyl ketone	$C_6H_{12}O$	000108-10-1		F	X	1/2	2/3	1/0	4/4	(4)	3/3	(2)	2/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Isobutyltrimethylmethane	-> see: Iso-octane																													
Iso-octane	C_8H_{18}	000540-84-1	tech. pure	F, Xn	X	1/3	1/3	1/0	(2)	1/0	(4)	1/0	1/3	3/4	1/0	1/0	4/4	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Isooctanol	-> see: Ethylhexanol-1																													
Isooctyl alcohol	-> see: Ethylhexanol-1																													
Isopropyl	C_3H_8O	000067-63-0	tech. pure	F	X	1/1	1/1	1/0	1/2	1/0	1/2	1/0	1/1	2/2	1/2	1/2	4/4	1/4	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	(2)	(1)	(1)	0/0	
Isopropyl-4-methylbenzene, 1-	-> see: Cymene, p-																													
Isopropyl-5-methylcyclohexanol, 2-	-> see: Menthol																													
Isopropyl-5-methylphenol, 2-	-> see: Thymol																													
Isopropyl acetate	$C_5H_{10}O_2$	000108-21-4		F, Xi	X	1/2	2/3	1/0	4/4	(3)	2/3	1/0	2/3	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/1	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Isopropyl acetone	-> see: Isobutyl methyl ketone																													
Isopropyl alcohol	-> see: Isopropyl																													
Isopropylbenzene	-> see: Cumene																													
Isopropylbenzol	-> see: Cumene																													
Isopropyl chloride	C_3H_7Cl	000075-29-6		F, Xn	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Isopropyl ether	$C_6H_{14}O$	000108-20-3	tech. pure	F	X	3/4	3/4	4/4	(4)	1/0	(4)	(1)	3/4	4/4	1/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Isopropylidene acetone	-> see: Mesityl oxide																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Isopropyl methyl ketone	$C_5H_{10}O$	000563-80-4		F	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Jasminaldehyde	-> see: α-pentylcinnamaldehyde																													
Iodine potassium	-> see: Potassium iodide																													
Iodoform	CHJ_3	000075-47-8	100 %	Xn		3/0	3/0	(3)	3/0	0/0	0/0	(2)	3/0	3/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(2)	1/0	1/0	(3)	0/0	(3)	(1)[1)]	(1)[1)]	1/1	[1)] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Iodine pentafluoride	JF_5	007783-66-6		(T, C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Tincture of iodine	I_2	007553-56-2		Xn	(X)	1/3	1/3	4/4	3/4	0/0	1/1	1/1	1/2	3/3	0/0	4/4	4/4	3/3	1/1	0/0	1/1	1/1	2/0	1/1	3/3	0/0	1/0	2/0L	1/0L	1/1		
Cocoa	—	—		(—)		1/1	1/1	(2)	(1)	(2)	0/0	1/1	(2)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Cocoa butter	—	008002-31-1		—		0/0	0/0	1/0	(1)	1/0	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1		
Potash alum	-> see: Potassium aluminium sulphate																													
Potash lye	-> see: Potassium hydroxide																													
Potassium peroxodisulphate	-> see: Potassium persulphate																													
Potassium nitrate	-> see: Potassium nitrate																													
Potassium (hexa)cyanoferrate-(II)	-> see: Potassium hexacyanoferrate (II)																													
Potassium (hexa)cyanoferrate-(III)	-> see: Potassium hexacyanoferrate (III)																													
Potassium acetate	$C_2H_3KO_2$	000127-08-2	aqueous	Xi		1/1	1/1	1/0	(1)	(2)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/0	1/1	1/1	3/0	3/3	0/0	1/3	1/1	1/1	0/0	
Potassium aluminium sulphate	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	diluted	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Potassium aluminium sulphate	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	saturated	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Potassium bicarbonate	-> see: Potassium hydrogen carbonate																													
Potassium bichromate	-> see: Potassium dichromate																													
Potassium bisulphate	-> see: Potassium hydrogen sulphate																													
Potassium bitartrate	-> see: Potassium hydrogentartate																													
Potassium borate	KBO_2	012228-88-5	10 %	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0	
Potassium borate	KBO_2	012228-88-5	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0	
Potassium bromate	$KBrO_3$	007758-01-2	saturated	O, T		1/3	1/3	(2)	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Potassium bromate	$KBrO_3$	007758-01-2	aqueous	O, T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Potassium bromide	KBr	007758-02-3	any	Xn		1/1	1/1	3/0	1/0	(1)	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/0L	1/0L	1/1	
Potassium carbonate	K_2CO_3	000584-08-7	saturated	Xn		1/1	1/1	1/1	3/3	(2)	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1	
Potassium carbonate	K_2CO_3	000584-08-7	aqueous	Xn		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1	
Potassium chlorate	$KClO_3$	003811-04-9	saturated	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium chlorate	$KClO_3$	003811-04-9	aqueous	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium chloride	KCl	007447-40-7	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/3	1/1L	1/1L	1/1	
Potassium chromate	K_2CrO_4	007789-00-6	saturated	T		1/0	1/1	2/0	(2)	0/0	1/0	(2)	1/1	1/1	0/0	1/1	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Potassium chromate	K_2CrO_4	007789-00-6	aqueous	T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Potassium cyanide	KCN	000151-50-8	saturated	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	4/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Potassium cyanide	KCN	000151-50-8	aqueous	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	1/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Potassium dichromate	$K_2Cr_2O_7$	007778-50-9	saturated	T		1/1	1/0	4/4	3/0	3/0	1/0	3/0	1/1	1/3	0/0	1/3	1/0	1/3	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Potassium dichromate	$K_2Cr_2O_7$	007778-50-9	aqueous	T		0/0	0/0	3/0	1/0	3/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Potassium iron (II) cyanide	-> see: Potassium hexacyanoferrate (III)																													
Potassium iron (III) cyanide	-> see: Potassium hexacyanoferrate (II)																													
Potassium fluoride	KF	007789-23-3		T		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	(1)	0/0	1/1	1/1	1/1	0/0	
Potassium hydrogen carbonate	$CHKO_3$	000298-14-6	saturated	—		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	4/4	(1)	(1)	1/1	
Potassium hydrogen sulphate	$KHSO_4$	007646-93-7	aqueous	(C)		1/1	1/1	4/4	1/0	(2)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	1/1	
Potassium hydrogen sulphate	$KHSO_4$	007646-93-7		C		1/1	1/1	4/4	1/0	0/0	0/0	2/0	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	?	
Potassium hydrogentartate	$C_4H_5KO_6$	000868-14-4	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(4)	1/3	1/2	0/0	
Potassium hydroxide	KHO	001310-58-3	10 %	C+		1/1	1/1	1/0	4/4	4/4	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	30 %	C+		1/1	1/1	1/3	4/4	4/4	1/0	(3)	1/1	1/0	1/0	1/3	1/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	50 %	C+		1/1	1/1	1/3	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/3	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	concentrated	C+		1/1	1/1	1/0	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/2	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	1 %	Xi		1/1	1/1	1/0	3/4	(4)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/3	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hypochlorite	KClO	007778-66-7	diluted	(O, C)		1/0	1/3	3/0	(3)	(3)	1/0	4/4	1/3	3/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	4/4	3/3L	2/2L	1/1	Javelle water, originally
Potassium iodate	KJO_3	007758-05-6		O		0/0	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/1	(1)	(1)	(2)	0/0	1/1	1/1	1/1	0/0	
Potassium iodide	KJ	007681-11-0	saturated	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Potassium iodide	KJ	007681-11-0	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	1/1	
Potassium nitrate	KNO_3	007757-79-1	50 %	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium nitrate	KNO_3	007757-79-1	aqueous	O, Xn		1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium perchlorate	$KClO_4$	007778-74-7	saturated	O, Xn		1/1	1/1	(1)	1/0	(1)	1/0	1/1	1/1	0/0	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	
Potassium perchlorate	$KClO_4$	007778-74-7	aqueous	O, Xn		1/1	1/1	(1)	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium permanganate	$KMnO_4$	007722-64-7	aqueous	O, Xn		0/0	0/0	4/4	1/0	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	hypermanganic potash
Potassium permanganate	$KMnO_4$	007722-64-7		O, Xn		1/3	1/1	4/4	1/0	(2)	1/1	1/1	1/1	1/3	0/0	1/3	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	hypermanganic potash
Potassium persulphate	$K_2(SO_4)_2$	007727-21-1	any	O, Xn		1/1	1/1	4/4	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/0	1/0	1/1	
Potassium sulphate	K_2SO_4	007778-80-5	aqueous	Xn		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium sulphide	K_2S	001312-73-8	diluted	(C)		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	(1)	(1)	2/0	0/0	3/4	1/1	1/1	0/0	
Potassium sulphite	K_2SO_3	010117-38-1	saturated	(Xi)		1/1	1/1	(1)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/0	1/0	0/0	
Potassium thiosulphate	$K_2S_2O_3$	010233-00-8	saturated	Xi		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	3/3	0/0	(1)	(1)	(1)		
Lime, burnt	-> see: Calcium oxide																													
Hydrated lime	-> see: Calcium hydroxide																													
Lime nitrate	-> see: Calcium nitrate																													
Lime water	-> see: Calcium hydroxide																													
Cardamom	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Rubber (caoutchouc) dispersion	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(1)	(2)	0/0	(3)	(1)	(1)		Latex
Kerosene	—	008008-20-6		(Xn)		2/2	3/4	(1)	4/4	1/1	2/3	1/1	3/3	4/4	2/3	1/1	0/0	0/0	2/3	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	Lamp oil, light petroleum
Pine needle oil	—	008023-99-2		?		0/0	0/0	1/0	(3)	0/0	(4)	(2)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	0/0	Pinus sylvestris
Silicofluoric acid	H_2SiF_6	016961-83-4	32 %	C		1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	3/0	2/2	3/4	0/0	4/4	(2)	1/1	1/1	
Silicic acid	SiO_2	001343-98-2	any	—		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Silicic acid tetraethylester	-> see: Tetraethylorthosilicate																													
Bone oil	—	008001-85-2		—		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Common salt	-> see: Sodium chloride																													
Carbon (substance) disulphide	-> see: Carbon disulphide																													
Carbon dioxide	CO_2	000124-38-9	saturated	?		1/3	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbon dioxide, moist	CO_2	000124-38-9	tech. pure	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbon dioxide, dry	CO_2	000124-38-9	tech. pure	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbonic acid	-> see: Carbon dioxide																													
Carbonic acid dichloride	-> see: Phosgene																													
Carbon tetrabromide	-> see: Carbon tetrabromide																													
Carbon tetrachloride	-> see: Carbon tetrachloride																													
Coconut fat	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1		
Coconut oil alcohol	—	068425-37-6	tech. pure	(Xi)		1/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1		
Coconut oil	—	008001-31-8	tech. pure	—		1/3	1/3	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Aqua regia	HNO_3 + HCl	008007-56-5		C		4/4	4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	4/4	0/0	4/4	4/4	4/4	4/4	Aqua regia = Nitric acid + hydrochloric acid
Fuel + 20% ethanol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	1/1	1/1		
Fuel + 20% methanol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	1/1	1/1		
Fuel, Normal	—	—		F, T	X	0/0	0/0	1/0	3/0	1/1	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Fuel, Super	—	—		F, T	X	0/0	0/0	1/0	4/4	(2)	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Chalk	$CaCO_3$	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	Calcium carbonate
Creosote	—	—		(T)		1/1	1/1	3/0	(3)	0/0	0/0	(3)	3/4	0/0	1/0	3/0	4/4	0/0	0/0	(1)	1/1	(3)	4/4	(3)	1/0	0/0	(2)	1/1	1/1	0/0	
Cresol (-mixtures)	C_7H_8O	001319-77-3		T, C		3/4	4/4	4/4	4/4	4/4	4/4	4/4	2/3	4/4	4/4	4/4	4/4	3/4	1/2	1/1	1/1	1/1	4/4	1/0	4/4	0/0	1/1	1/0	1/0	1/1	
Carum	—	—	grinded	?		0/0	0/0	(2)	(2)	(1)	0/0	1/1	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	4/4	(1)	(1)		
Kupfer-(I)-chlorid	CuCl	007758-89-6	aqueous	Xn		0/0	0/0	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1	
Kupfer-(I)-cyanid	-> see: Copper cyanide																													
Kupfer-(II)-chlorid	$CuCl_2$	007447-39-4	saturated	Xn		1/3	1/1	(3)	1/0	(2)	1/0	(2)	1/3	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1	
Kupfer-(II)-nitrat	$Cu(NO_3)_2$	003251-23-8	saturated	O, Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/0	1/1	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/1	1/1	1/1	
Kupfer-(II)-nitrat	$Cu(NO_3)_2$	003251-23-8	aqueous	O, Xn		0/0	0/0	(3)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	1/1	1/1	1/1	
Kupfer-(II)-sulfat	-> see: Copper sulphate																													
Copper acetate	$C_4H_6CuO_4$	004180-12-5	aqueous	Xn		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	(3)	3/3	0/0	4/4	1/1	1/1	1/1	Cupriacetate, verdigris
Copper cyanide	CCuN	000544-92-3	saturated	T		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/3	0/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	(3)	1/1	1/1		
Copper cyanuric	-> see: Copper cyanide																													
Copper sulphate, aqueous	-> see: Copper vitriol																													
Copper vitriol	$CuSO_4 \times 5H_2O$	007758-99-8	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/0	1/0	1/1	1/1	1/0	1/3	1/0	1/1	1/1	(1)	1/1	1/1	1/0	1/1	2/0	0/0	4/4	1/1	1/1	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Nitrous oxide	N_2O	010024-97-2		(O)		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	2/0	1/0	1/0	0/0	1/1	(1)	(1)		Nitrous oxide, "nitrogen oxydul"
Lactam	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	4/4	4/4	0/0	(2)	(1)	(1)		cyclic carboxylic acid amides
Lactobiosis	-> see: Lactose																													
Lactose	$C_{12}H_{22}O_{11}$	000063-42-3	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	
Lanolin	—	008006-54-0	tech. pure	—		3/3	3/3	1/0	1/0	1/0	0/0	(2)	3/3	1/1	0/0	3/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Latex	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(1)	(2)	0/0	(2)	(1)	(1)	1/1	Rubber dispersion
Lauryl alcohol	$C_{12}H_{26}O$	000112-53-8	100 %	Xi		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	(1)	(1)	0/0	
Lauryl chloride	$C_{12}H_{25}Cl$	000112-52-7	100 %	(Xi)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(1)	(3)	0/0	(3)	0/0	0/0		
Lavender oil	—	008000-28-0		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	(1)	(1)	(1)		
Cod liver oil	—	008001-69-2		—		1/3	1/3	(2)	1/0	(2)	0/0	(2)	1/3	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/0	(1)	(1)	1/1	
Glue (bone glue)	—	—	any	—		1/0	1/1	(1)	(1)	1/1	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(1)	(1)	1/0	1/0	0/0	(3)	1/1	1/1	0/0	
Linseed oil	—	008001-26-1	tech. pure	—		1/1	1/3	1/0	1/0	1/0	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Lemongrass oil	—	008007-02-1		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Luminous gas, benzene-free	—	—		F+, T	X	1/0	1/0	1/0	1/0	(2)	1/0	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/0	1/0	4/4	1/0	3/0	0/0	1/1	1/1	1/1	0/0	
Ligroin	—	008032-32-4		F, Xn	X	0/0	0/0	(2)	1/0	(2)	(4)	(2)	(3)	3/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		Light petrol
Liqueurs	—	—		—		1/0	0/0	(2)	1/0	1/0	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Limonene, DL-	$C_{10}H_{16}$	000138-86-3		Xn	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Lindane	-> see: Hexachlorocyclohexane																													
Lithium bromide	LiBr	007550-35-8		Xn		1/1	1/1	(3)	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Laurel	—	—	grinded	?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Lysol	—	—		T		0/0	0/0	(4)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(3)	1/1	1/1		Disinfectant, cresol + soap
Magnesite	-> see: Magnesium carbonate																													
Magnesium bromide	$MgBr_2$	007789-48-2		Xi		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	(3)	0/0	0/0		
Magnesium carbonate	$MgCO_3$	000546-93-0	saturated	—		1/1	1/1	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Magnesium chloride	$MgCl_2$	007786-30-3	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/2	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0L	1/0L	1/1	
Magnesium chlorite	$Mg(ClO_2)_2$	??		O		0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0		
Magnesium hydroxide	$Mg(HO)_2$	001309-42-8	saturated	—		1/1	1/1	1/0	(2)	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	1/1	1/1	1/1	1/1	0/0	
Magnesium iodide	MgJ_2	010377-58-9		(Xn)		1/1	1/1	(2)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/1	(1)	(2)	0/0	(2)	0/0	0/0		
Magnesium nitrate	$Mg(NO_3)_2$	010377-60-3	saturated	O, Xi		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	1/0	1/0	1/0	1/1	
Magnesium sulphate	$MgSO_4$	007487-88-9	any	—		1/1	1/1	1/0	1/0	1/0	1/0	1/0	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	0/0	1/1	1/1	1/1	1/1	
Magnesium sulphate heptahydrate	-> see: Epsom salt																													
Maize germ oil	—	008001-30-7	tech. pure	—		1/3	0/0	(2)	(1)	1/0	0/0	(2)	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	1/1	Maize oil
Maleic acid	$C_4H_4O_4$	000110-16-7	saturated	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Maleic acid	$C_4H_4O_4$	000110-16-7	aqueous	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Malonic ester	-> see: Diethylmalonate																													
Malonic acid diethyl ester	-> see: Diethylmalonate																													
Almond oil	—	008007-69-0		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	3/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(1)	(2)	0/0	(1)	1/1	1/1		
Margarine	—	—		—		0/0	0/0	(2)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Marmalade	—	—		—		1/1	1/1	(1)	1/1	1/1	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(2)	1/1	1/1	1/1	
Machine oil	—	—	100 %	?		0/0	1/4	(1)	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Matrium metabisulphite	-> see: Sodium disulphite																													
Matrium pyrochromate	-> see: Sodium dichromate																													
Marine water	-> see: Salt water, seawater																													
Molasses	—	—		—		1/1	1/1	1/0	(1)	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/0	1/0	3/4	
Molasses seasoning	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Menthadiene-1,8, p-	-> see: Limonene, DL-																													
Menthol	$C_{10}H_{20}O$	000089-78-1	solid	Xi		1/3	3/4	3/0	3/4	0/0	0/0	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	1/0	1/0		
Mercaptoacetic acid	-> see: Thioglycolic acid																													
Mercaptoethanoic acid, 2-	-> see: Thioglycolic acid																													
Mesityl oxide	$C_6H_{10}O$	000141-79-7		Xn	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	0/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methacrylic acid	$C_4H_6O_2$	000079-41-4		C		1/0	1/1	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	3/0	4/4	4/4	0/0	(4)	0/0	0/0		
Methacrylic acid methyl ester	-> see: Methyl methacrylate																													
Methane	CH_4	000074-82-8	tech. pure	F+	X	1/0	0/0	1/0	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Methanol solution	-> see: Formaldehyde solution																													
Methanamine	-> see: Methylamine, (mono)																													
Methane carboxylic acid	-> see: Acetic acid																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Methanol	CH_4O	000067-56-1		F, T	X	1/1	1/1	2/0	4/4	1/0	1/1	1/1	1/1	3/4	3/3	1/3	3/3	3/4	1/1	1/1	1/1	1/1	1/0	3/4	3/3	0/0	1/0	1/1	1/1	0/0	
Methanoic acid	-> see: Formic acid																													
Methenamine	-> see: Hexamethylenetetramine																													
Methoxybenzene	-> see: Anisole																													
Methoxybutanol	$C_5H_{12}O_2$	—	100 %	?	X	0/0	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	3/0	1/0	!/0	0/0	(1)	(1)	(1)		Isomer not specified in the source
Methoxyethanol	-> see: Methyl glycol																													
Methoxyethyl acetate	-> see: Methyl glycol acetate																													
Methoxyethyl oleate	$C_{21}H_{40}O_3$	000111-10-4		?		1/1	1/2	(2)	3/4	(2)	1/2	(2)	1/2	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(1)	(1)	4/4	(2)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Methoxypropanol	-> see: Propylene glycol methyl ether																													
Methyl ethyl ether	C_3H_8O	000540-67-0	100 %	(F+)	X	0/0	3/0	(1)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(2)	4/4	4/4	4/4	0/0	1/1	(1)	(1)		
Methyl 2-hydroxybenzoate	-> see: Methyl salicylate																													
Methyl 2-methyl propionate	-> see: Methyl methacrylate																													
Methyl acetate	-> see: Acetic acid methyl ester																													
Methacrolein	-> see: Crotonaldehyde																													
Methyl acrylate	$C_4H_6O_2$	000096-33-3		F, Xn	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Methylacrylic acid	-> see: Methacrylic acid																													
Methyl alcohol	-> see: Methanol																													
Methylamine, (Mono-)	CH_5N	000074-89-5	32 %	F+, C	X	1/0	1/0	4/4	4/4	0/0	0/0	1/0	1/0	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	3/0	1/0	4/4	4/4	0/0	1/0	1/0	1/0	0/0	
Methylbenzene	C_7H_8	000108-88-3		F, Xn	X	3/4	3/4	1/0	4/4	1/0	3/3	1/3	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/3	4/4	0/0	1/1	1/1	1/1	1/1	
Methyl bromide	-> see: Bromomethane																													
Methylbutanol	$C_5H_{12}O$	—		Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	1/3	0/0	(1)	1/1	1/1	3/0	2/2	3/3	0/0	(1)	(1)	(1)		Isomer not specified in the source
Methylbutanol, 3-	-> see: Isoamyl alcohol																													
Methylbutanone-2, 3-	-> see: Isopropyl methyl ketone																													
Methyl butyl alcohol	-> see: Methylbutanol																													
Methyl butyl ketone	$C_6H_{12}O$	000591-78-6		F, T	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl cellosolve	-> see: Methyl glycol																													
Methyl chloroacetate	$C_3H_5ClO_2$	000096-34-4	tech. pure	T/Xi	X	1/1	0/0	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/0	0/0	0/0	0/0	(1)	(1)	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Methyl chloride	-> see: Chloromethane																													
Methyl chloroform	-> see: Trichloroethane-1,1,1																													
Methyl cyanide	-> see: Acetonitrile																													
Methylcyclohexane	C_7H_{14}	000108-87-2		F, Xn	X	3/0	3/0	(2)	(2)	1/0	(4)	(2)	3/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	(1)	4/4	(1)	4/4	0/0	1/1	1/1	1/1	0/0	
Methylcyclopentane	C_6H_{12}	000096-37-7		F	X	0/0	0/0	(2)	(2)	1/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Methyl dichloroacetate	$C_3H_4Cl_2O_2$	000116-54-1		(Xn)		1/1	0/0	(3)	(4)		(4)	(3)	1/1	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	3/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Methylene(di)chloride	-> see: Dichloromethane																													
Methylene chlorobromide	-> see: Bromochloromethane																													
Methyl ether	-> see: Dimethyl ether																													
Methyl ethyl ketone (MEK)	C_4H_8O	000078-93-3		F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/2	1/3	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	3/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl formate	$C_2H_4O_2$	000107-31-3		F+	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl glycol	$C_3H_8O_2$	000109-86-4	100 %	T	X	1/0	1/1	1/0	3/4	0/0	1/1	1/0	1/1	4/4	3/3	3/4	4/4	0/0	1/1	1/1	1/1	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl glycol acetate	$C_5H_{10}O_3$	000110-49-6		T		0/0	0/0	1/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl isobutenyl ketone	-> see: Mesityl oxide																													
Methyl isobutyl ketone(MIBK)	-> see: Isobutyl methyl ketone																													
Methyl isopropyl ketone	-> see: Isopropyl methyl ketone																													
Methyl methacrylate	$C_5H_8O_2$	000080-62-6	100 %	F, Xi	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Methyl methanoate	-> see: Methyl formate																													
Methyl oleate	$C_{19}H_{36}O_2$	000112-62-9		—		0/0	0/0	(2)	(3)	(2)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	4/4	0/0	(1)	(1)	(1)		
Methyl oxirane	-> see: Propylene oxide																													
Methylpent-4-en-2-one, 5-	-> see: Mesityl oxide																													
Methylpentan-2-one, 4-	-> see: Isobutyl methyl ketone																													
Methylphenol	-> see: Cresol (-mixtures)																													
Methylphenyl ether	-> see: Anisole																													
Methylphenyl ketone	-> see: Acetophenone																													
Methylpropanol-1, 2-	-> see: Isobutanol																													
Methylpropanol-2, 2-	-> see: Butyl alcohol, tertiary																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Methyl propenoate	-> see: Methyl acrylate																													
Methylpropenoic acid, 2-	-> see: Methacrylic acid																													
Methyl propyl ketone	$C_5H_{10}O$	000107-87-9		(F)	X	1/2	2/3	(2)	4/4	(4)	3/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	(1)	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl salicylate	$C_8H_8O_3$	000119-36-8		Xn, Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/0	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	2/0	(3)	4/4	0/0	(2)	(1)	(1)	0/0	Synthetic Wintergreen Oil/Gaultheria Oil
Methyl sulphuric acid	CH_4SO_4	000077-78-1	50 %	(C)		0/0	1/1	4/4	(4)	(4)	0/0	4/4	2/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4	
Methyl sulphuric acid	CH_4SO_4	000077-78-1	aqueous	(C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4	
Milk	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Lactic acid	$C_3H_6O_3$	000050-21-5	3 %	?		1/1	1/2	(3)	1/2	1/0	1/2	2/4	1/2	2/2	1/1	2/3	0/0	1/1	1/1	1/1	1/1	1/1	3/4	1/1	(2)	0/0	(1)	1/1	1/1	1/1	Lactol
Lactic acid	$C_3H_6O_3$	000050-21-5	80 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/1	1/1	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1	Lactol
Lactic acid	$C_3H_6O_3$	000050-21-5	85 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/2	2/2	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1	Lactol
Lactic acid ethyl ester	-> see: Ethyl lactate																													
Milk sugar	-> see: Lactose																													
Mineral oil	—	008012-95-1		(Xn)		1/1	2/4	(1)	1/2	1/1	1/2	1/1	1/3	1/1	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	2/2	0/0	1/1	1/1	1/1	0/0	
Mineral water	—	—		—		1/1	1/1	(1)	1/0	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	(1)	(1)	1/1	
Mohr's salt	-> see: Ammonium iron (II) sulphate																													
Whey	—	—		—		1/1	0/0	(2)	(1)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(2)	1/1	1/1		
Monobromobenzene	-> see: Bromobenzene																													
Monochlorobenzene	-> see: Chlorobenzene																													
Monochloroacetic acid	-> see: Chloroacetic acid																													
Monochloroacetic acid ethyl ester	-> see: Ethyl chloroacetate																													
Monochloroacetic acid methyl ester	-> see: Methyl chloroacetate																													
Monoethanolamine	-> see: Ethanolamine																													
Monofluorodichloromethane	-> see: Dichlorofluoromethane																													
Monopotassium tartrate	-> see: Potassium hydrogentartate																													
Monopentyl phthalate	-> see: Phthalic acid monoamyl ester																													
Morpholine	C_4H_9NO	000110-91-8	tech. pure	C, Xn	X	1/1	1/1	(3)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	3/0	2/3	4/4	0/0	1/0	(1)	(1)	0/0	
Engine oil	—	—		?		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Mowilith D	—	—		?		1/0	0/0	(2)	0/0	(2)	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(2)	(2)	(2)	0/0	(2)	(1)	(1)	0/0	Polyvinylacetatdispersion; Clariant
Nutmeg	—	—	grinded	?		0/0	0/0	(2)	4/4	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Nutmeg oil	—	008008-45-5		(Xn)		0/0	0/0	(2)	4/4	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/4	0/0	(1)	(1)	(2)	(4)	(3)	(3)	0/0	(1)	(1)	(1)		
Nail varnish remover	—	—		?	(X)	0/0	0/0	(2)	4/4	0/0	(4)	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Naphtha	—	008032-32-4		(Xn)		1/3	3/4	1/0	(2)	(1)	1/0	1/0	1/3	3/0	1/0	1/0	4/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	Petroleum gasoline
Naphthalene	$C_{10}H_8$	000091-20-3	100 %	F, Xn	X	0/0	1/3	1/0	(3)	0/0	0/0	1/2	1/3	3/4	1/0	4/4	4/4	1/4	0/0	(1)	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	
Naphthalene (in alcohol)	—	—		F, Xn	X	1/4	1/4	(2)	(3)	0/0	0/0	1/2	1/3	3/4	0/0	0/0	0/0	3/4	0/0	(1)	1/1	(2)	4/4	(3)	(3)	0/0	(1)	(1)	(1)	0/0	
Naphthene	-> see: Cyclohexane																													
Sodium acetate	$C_2H_3NaO_2$	000127-09-3	any	—		1/1	1/1	1/0	1/2	(1)	1/1	1/1	1/1	2/2	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	1/1	1/1	1/1	
Sodium aluminium sulphate	$NaAl(SO_4)_2$	010102-71-3		?		1/1	1/1	(3)	(2)	(1)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)		
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1	36 %	Xn		1/1	1/1	1/0	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	1/1	0/0	(1)	(1)	(1)	1/1	
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1	aqueous	Xn		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1	
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1		Xn		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1	
Sodium bicarbonate	$NaHCO_3$	000144-55-8	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium bichromate	-> see: Sodium dichromate																													
Sodium bisulphate	$NaHSO_4$	007681-38-1	10 %	(C)		1/1	1/1	4/4	1/0	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	1/2	1/1	1/1	
Sodium bisulphate	$NaHSO_4$	007681-38-1	any	(C)		1/1	1/1	1/0	1/0	0/0	0/0	(3)	1/1	1/3	0/0	1/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	(2)	1/1	1/1	
Sodium bisulphite	$NaHSO_3$	007631-90-5	aqueous	Xn		1/1	1/1	1/0	(2)	1/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1	1/1	
Sodium borate	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	saturated	Xi		1/1	1/1	1/0	1/0	(2)	1/0	1/1	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/3	1/1	1/1	1/1	
Sodium borate	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/3	1/1	1/1	1/1	
Sodium bromate	$NaBrO_3$	007789-38-0	any	O, T		1/0	1/3	(3)	(2)	0/0	0/0	1/1	1/1	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	(2)	(1)	1/3	0/0	1/1	1/1L	1/1L	0/0	
Sodium bromide	NaBr	007647-15-6	any	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/3	0/0	4/4	0/0	0/0	0/0	
Sodium carbonate	Na_2CO_3	000497-19-8	saturated	Xi		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium carbonate	Na_2CO_3	000497-19-8	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium carbonate	Na_2CO_3	000497-19-8		Xi		1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	2/0	0/0	1/1	0/0	1/2	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium chlorate	$NaClO_3$	007775-09-9	any	O, Xn		1/1	1/0	1/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1L	1/1L	1/1	
Sodium chlorate	$NaClO_3$	007775-09-9	aqueous	O, Xn		0/0	0/0	3/0	1/0	1/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/0	1/1L	1/1L	1/1	
Sodium chloride	NaCl	007647-14-5	any	—		1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/2	1/2	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sodium chloride	NaCl	007647-14-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/4	1/2	1/2	1/1	
Sodium chlorite	$NaClO_2$	007758-19-2	diluted	(O, Xn)		1/0	1/3	1/4	(2)	0/0	0/0	(2)	1/3	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	3/4	3/4	3/3	0/0	
Sodium chromate	$NaCrO_4$	007775-11-3	diluted	T		1/0	1/0	1/1	(2)	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	1/1	1/1	1/1	0/0	
Sodium cyanide	CNNa	000143-33-9	saturated	T		1/1	1/1	1/0	(3)	0/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	4/4	(2)	(2)	0/0	
Sodium cyanide	CNNa	000143-33-9	aqueous	T		1/1	1/1	1/0	(3)	1/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	(2)	(2)	0/0	
Sodium dichromate	$Na_2Cr_2O_7$	010588-01-9		T		0/0	1/1	1/0	1/0	3/0	1/1	(3)	1/1	1/1	0/0	1/0	0/0	0/0	1/1	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Sodium disulphite	$Na_2S_2O_5$	007681-57-4	any	Xn		1/1	1/1	1/0	(2)	(2)	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1		
Sodium dithionite	$Na_2S_2O_4$	007775-14-6	10 %	Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		
Sodium dithionite	$Na_2S_2O_4$	007775-14-6		Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		
Sodium dodecylbenzene sulphonate	$C_{18}H_{29}NaSO_3$	025155-30-0		Xn		1/1	1/1	(2)	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(1)	(2)	0/0	(2)	(1)	(1)		
Sodium iron cyanide	-> see: Sodium hexacyanoferrate(II)																													
Sodium ferrocyanide	-> see: Sodium hexacyanoferrate(II)																													
Sodium fluoride	NaF	007681-49-4	saturated	T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/0	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	1/1	
Sodium hexacyanoferrate-(II)	$C_6FeNa_4N_6$	013601-19-9		Xn		1/1	1/1	(1)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(1)	(1)	(1)		
Sodium hexametaphosphate	$(NaPO_3)_6$	068915-31-1	saturated	—		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Sodium hydrogen carbonate	-> see: Sodium bicarbonate																													
Sodium hydrogen sulphate	-> see: Sodium bisulphate																													
Sodium hydrogen sulphite	-> see: Sodium bisulphite																													
Sodium hydrosulphite	-> see: Sodium dithionite																													
Sodium hydroxide	NaOH	001310-73-2	concentrated	C		1/1	1/1	1/3	4/4	4/4	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/4	0/0	4/4	(2)	(2)	?	
Sodium hydroxide	NaOH	001310-73-2	30 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/0	1/0	1/3	1/3	0/0	0/0	1/1	1/1	(2)	1/0	(3)	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	45 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/1	1/0	1/3	1/3	1/1	0/0	0/0	1/1	(2)	1/0	2/4	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	50 %	C+		1/1	1/1	1/0	4/4	4/4	1/1	1/3	1/1	2/2	1/1	1/2	0/0	0/3	1/1	1/1	1/1	3/3	1/0	3/4	3/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	60 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	(3)	1/1	1/0	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	3/4	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	1 %	Xi		1/1	1/1	1/0	3/4	(3)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	(4)	1/1	1/1	1/1	
Sodium hypochlorite	NaClO	007681-52-9	diluted	(O, C)		2/3	2/3	4/4	(3)	3/0	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	15 %	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/1	0/0	1/1	1/1	1/1	1/1	3/4	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	saturated	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	0/0	1/1	0/0	(1)	1/1	(3)	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	12,5 % Cl	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypodisulphite	-> see: Sodium dithionite																													
Sodium iodide	NaJ	007681-82-5	any	Xi		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/0	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	(1)	1/1	0/0	1/1	3/4	3/4	0/0	
Sodium metaborate peroxide	-> see: Sodium perborate																													
Sodium nitrate	$NaNO_3$	007631-99-4	saturated	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	
Sodium nitrate	$NaNO_3$	007631-99-4	aqueous	O, Xn		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Sodium nitrite	$NaNO_2$	007632-00-0	saturated	O, T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1	1/1	1/1	
Sodium nitrite	$NaNO_2$	007632-00-0	aqueous	O, T		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	1/0	1/1	1/1	1/1	
Sodium oxalate	$C_2Na_2O_4$	000062-76-0	saturated	Xn		1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	1/0	1/0	0/0	1/1	(2)	(2)		
Sodium perborate	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	saturated	(O, Xn)		1/1	1/1	4/4	(2)	0/0	0/0	2/0	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Sodium perborate	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	aqueous	(O, Xn)		1/1	1/1	4/4	(2)	3/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Sodium perchlorate	$NaClO_4$	007601-89-0	saturated	O, Xn		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	1/1	1/1	
Sodium peroxide	Na_2O_2	001313-60-6	10 %	O, C+		0/0	1/3	4/4	(3)	(4)	0/0	4/4	272	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	3/0	0/0	4/4	1/1	1/1	0/0	
Sodium peroxide	Na_2O_2	001313-60-6	saturated	O, C+		0/0	3/3	4/4	(3)	(4)	0/0	4/4	2/2	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	(4)	0/0	4/4	(2)	(2)	0/0	
Sodium peroxodisulphate	-> see: Sodium persulphate																													
Sodium persulphate	$Na_2S_2O_8$	007775-27-1	saturated	O, Xi		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(3)	0/0	4/4	0/0	1/0	0/0	
Sodium phosphate	$Na_3PO_4 \times 12H_2O$	010101-89-0	saturated	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium phosphate	$Na_3PO_4 \times 12H_2O$	010101-89-0	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium phosphate, secondary	-> see: Disodium phosphate																													
Sodium phosphate, tertiary	-> see: Trisodium phosphate																													
Sodium phosphate dodecahydrate	-> see: Sodium phosphate																													
Sodium pyrosulphite	-> see: Sodium disulphite																													
Sodium silicate	$Na_2Si_2O_7$	001344-09-8	any	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium stearate	$C_{18}H_{35}NaO_2$	000822-16-2	aqueous	(Xi)		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(1)	1/0	0/0	(1)	1/1	1/1		
Sodium sulphate	Na_2SO_4	007757-82-6	saturated	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/3	0/0	1/1	1/1	1/1	1/1	
Sodium sulphate	Na_2SO_4	007757-82-6	aqueous	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	0/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium sulphate	Na_2SO_4	007757-82-6		—		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	1/1	1/1	1/1	1/1	
Sodium sulphide	Na_2S	001313-82-2	saturated	C		1/1	1/1	1/0	3/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	0/0	1/1	1/1	3/3	1/0	1/1	2/3	0/0	3/4	(1)	(1)	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics					Elastomers		Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sodium sulphide	Na_2S	001313-82-2	aqueous	C		1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/2	1/2	1/1	
Sodium sulphite	Na_2SO_3	007757-83-7	saturated	Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/3	1/1	1/1	1/1	
Sodium tetraborate	-> see: Sodium borate																														
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	any	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	saturated	Xi		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	aqueous	Xi		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate-5-hydrate	-> see: Sodium thiosulphate																														
Sodium hypochlorite	-> see: Sodium hypochlorite																														
Caustic soda	-> see: Sodium hydroxide																														
Sodium nitrate	-> see: Sodium nitrate																														
Sodium liquid glass	-> see: Sodium silicate																														
Cloves	—	—	grinded	?		0/0	0/0	(2)	4/4	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	0/0	
Neon	Ne	007440-01-9		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(1)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1		
Wetting agent	—	—	5 %	?		1/0	0/0	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(2)	0/0	0/0	K	K		Surfactants
Niacin	-> see: Nicotinic acid																														
Nickel (II) chloride	$NiCl_2$	007718-54-9	saturated	T		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1	
Nickel (II) chloride	$NiCl_2$	007718-54-9	aqueous	T		1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1	
Nickel acetate	$C_4H_6NiO_4$	000373-02-4	aqueous	(T, N)		1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/0	0/0	4/4	0/0	0/0		
Nickel nitrate	$Ni(NO_3)_2$	013138-45-9	saturated	(O, Xn)		1/1	1/1	(3)	(2)	(1)	1/0	(2)	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Nickel sulphate	$NiSO_4$	007786-81-4	saturated	Xn		1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nickel sulphate	$NiSO_4$	007786-81-4	aqueous	Xn		1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nicotine	$C_{10}H_{14}N_2$	000054-11-5		T+		1/0	1/0	(3)	(3)	0/0	0/0	(2)	1/0	1/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/1	0/0	(1)	(1)	(1)	0/0	
Nicotinic acid	$C_6H_5NO_2$	000059-67-6	diluted	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/0	0/0	0/0	1/1	0/0	0/0	0/0	1/1	(1)	(2)	(2)	(3)	(2)	0/0	(3)	0/0	0/0	0/0	
Nitrobenzoic acid	$C_7H_5NO_4$	—		(Xn)		1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	(3)	(2)	0/0	(3)	0/0	0/0		Isomer not specified in the source
Nitrobenzene	$C_6H_5NO_2$	000098-95-3		T		3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitroethane	$C_2H_5NO_2$	000079-24-3		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Nitroglycerin	$C_3H_5(NO_3)_3$	000055-63-0	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(3)	1/0	1/0	4/4	0/0	0/0	0/0	0/0	0/0	
Nitro glycol	$C_2H_4(NO_3)_2$	000628-96-6	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(3)	1/0	1/0	4/4	0/0	0/0	(1)	(1)	0/0	
Nitropropane	$C_3H_7NO_2$	—		(T)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Nitrous gases	—	—	diluted	T		1/1	0/0	3/0	4/4	0/0	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	3/0	4/4	0/0	(2)	(1)	(1)	0/0	Nitrogen monoxide + nitrogen dioxide
Nitrotoluene	$C_7H_7NO_2$	001321-12-6	tech. pure	T		1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitro thinner	—	—		?	X	0/0	0/0	3/0	(4)	0/0	(4)	(3)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		Solvent mixture
Nonanol	$C_9H_{20}O$	000143-08-8	100 %	Xn, Xi		0/0	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Nonyl alcohol	-> see: Nonanol																														
Fruit pulp	—	—		—		1/1	1/1	(2)	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	
Fruit wine	—	—		—		1/1	1/1	(2)	(1)	1/1	0/0	1/1	1/0	0/0	0/0	1/0	0/0	0/0	1/1	1/1	(1)	1/1	1/0	(1)	1/0	0/0	(2)	1/1	1/1	0/0	
Octadec-9-enoic acid, cis-	-> see: Oleic acid																														
Octadecanoic acid	-> see: Stearic acid																														
Octafluorocyclobutane	C_4F_8	000115-25-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Octal	-> see: Diisooctyl phthalate																														
Octane, n-	C_8H_{18}	000111-65-9		F, Xn	X	1/1	1/1	1/0	2/3	(1)	1/1	1/0	1/1	4/4	2/3	3/4	3/3	1/1	1/1	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	0/0	
Octanol, 1-	-> see: Octyl alcohol, -n																														
Octyl alcohol, -n	$C_8H_{18}O$	000111-87-5		Xi		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Octylcresol	$C_{15}H_{24}O$	—	100 %	?		3/0	3/0	(3)	(4)	0/0	0/0	(3)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Oils and fats, vegetable	—	—		—		1/3	1/3	(2)	(2)	1/0	0/0	(2)	1/3	3/0	0/0	1/1	3/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	(2)	0/0	(1)	1/1	1/1	0/0	
Öle, Oils, ethereal	—	—		?		4/4	3/4	(2)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	(1-3)	(3)	0/0	1/1	(1)	(1)	0/0	
Olein	-> see: Oleic acid																														
Oleum	$H_2SO_4 \times SO_3$	008014-95-7	10 % SO_3	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/0	4/4	4/4	1/0	4/4	0/0	1/3	1/2	1/1	0/0	Fuming sulphuric acid
Oleum vapours	—	—	low	?		4/4	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	1/0	(3)	1/0	(3)	0/0	(3)	(1)	(1)	0/0	Sulphur trioxide
Olive oil	—	008001-25-0		—		1/3	0/0	(2)	(2)	1/0	0/0	1/1	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Oleic acid	$C_{18}H_{34}O_2$	000112-80-1	tech. pure	Xi		1/3	1/3	1/0	1/0	1/0	0/0	2/0	1/3	1/3	0/0	1/1	0/0	1/3	0/0	(1)	1/1	1/1	4/4	2/2	3/0	0/0	1/1	1/1	1/1	0/0	
Oleic acid methoxyethyl ester	-> see: Methoxyethyl oleate																														
Oleic acid methyl ester	-> see: Methyl oleate																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sweet orange juice	-> see: Orange juice																													
Sweet orange peel oil	-> see: Orange peel oil																													
Ortho-silicic acid tetraethyl ester	-> see: Tetraethylorthosilicate																													
Orthophosphoric acid	-> see: Phosphoric acid																													
Oxabutyl acetate	-> see: Methyl glycol acetate																													
Oxalic acid	$C_2H_2O_4 \times 2H_2O$	000144-62-7	aqueous	Xn		1/1	1/1	4/4	(2)	(2)	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/2	
Oxalic acid	$C_2H_2O_4 \times 2H_2O$	000144-62-7		Xn		1/1	1/1	3/4	1/0	0/0	1/1	4/4	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/3	
Oxalic acid sodium salt	-> see: Sodium oxalate																													
Oxalic acid ammonium salt	-> see: Ammonium oxalate																													
Oxirane	-> see: Ethylene oxide																													
Oxolane	-> see: Tetrahydrofuran																													
Oxydiacetic acid	-> see: Diglycolic acid																													
Oxymethylfurfurol, 5-	$C_6H_6O_3$	000067-47-0		Xi		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ozone	O_3	010028-15-6		(O, T)		3/4	3/4	4/4	1/2	0/0	1/1	4/4	3/4	2/2	1/1	1/2	0/0	1/1	1/1	1/1	(1)	1/3	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Ozone-air mixture-Luft-Gemisch	—	—		(O, T)		0/0	0/0	4/4	(2)	0/0	0/0	4/4	3/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Palmitic acid	$C_{16}H_{32}O_2$	000057-10-3	tech. pure	Xi		3/3	2/2	1/1	(2)	1/0	0/0	1/0	3/4	1/1	0/0	1/1	3/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
Palmityl alcohol	-> see: Cetyl alcohol																													
Palm seed oil	—	008023-79-8		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/3	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Palm oil	—	008002-75-3		—		1/3	0/0	1/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1		
Paraffins	C_nH_{2n+2}	—	100 %	?		1/0	1/1	1/0	1/0	1/0	1/1	1/1	1/0	1/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	
Paraffin emulsion	—	—		?		1/3	0/0	1/0	(2)	(2)	0/0	(2)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/0	1/1	0/0	(2)	(1)	(1)	0/0	
Paraffin wax	—	008002-74-2	melted	(—)		0	0	0	(2)	0	0	(2)	(2)	0	0	0	0	0	0	(1)	1	0	4	(2)	1	0	1	1	1		
Paraform	-> see: Paraformaldehyde																													
Paraformaldehyde	$(CH_2O)_nH_2O$	030525-89-4		F, T	X	0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	1/0	3/3	0/0	(1)	(1)	(1)		
Perfumes	—	—		?		3/0	3/0	1/0	(3)	1/0	0/0	(2)	1/0	4/4	0/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Pectin	—	009000-69-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Pectin
Pectin	—	009000-69-5		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Pectin
Penicillin	—	—		Xn		(1)	(1)	(2)	(1)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		Antibiotic
Pentaclorodiphenyl	$C_{12}H_5Cl_5$	—		Xn		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0		a PCB
Pentamethyleneimine	-> see: Piperidine																													
Pentane	C_5H_{12}	000109-66-0		F	X	1/3	1/3	1/0	1/0	1/1	(3)	1/0	(3)	3/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(1)	4/4	1/0	1/2	0/0	1/1	1/1	1/1		
Pentanone, 2-	-> see: Methyl propyl ketone																													
Pentanone, 3-	-> see: Diethyl ketone																													
Pentanethiol, 1-	$C_5H_{12}S$	000110-66-7		Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(2)	(1)	(1)		
Pentylacetate, n-	-> see: Amylacetate, n-																													
Pentyl alcohol	-> see: Amyl alcohol, n-																													
Pentyl chloride	-> see: Amyl chloride																													
Pentylcinnamaldehyde, a-	-> see: α-pentylcinnamaldehyde																													
Perchlorobutadiene	-> see: Hexachlorobutadiene																													
Perchlorethene	-> see: Perchloroethylene																													
Perchloroethylene (PER)	C_2Cl_4	000127-18-4		Xn		4/4	4/4	4/4	4/4	3/4	4/4	1/3	4/4	4/4	4/4	4/4	4/4	3/3	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	(3)	0/0	0/0	0/0	
Perchloric acid	$HClO_4$	007601-90-3	70 %	E, O, C+		2/4	3/4	4/4	4/4	(4)	2/4	4/4	4/4	2/3	4/4	3/4	4/4	0/0	1/2	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	0/0	0/0	?	
Perchloric acid	$HClO_4$	007601-90-3	20 %	Xi		0/0	1/3	4/4	3/0	0/0	0/0	4/4	1/3	0/0	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	2/0	1/1	4/4	0/0	4/4	0/0	0/0	1/1	
Perfluoropropane	C_3F_8	000076-19-7		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Perhydroxic acid	-> see: Hydrogen peroxide 30 %																													
Petrolatum, petroleum jelly	-> see: Vaseline																													
Petroleum ether	—	008032-32-4	tech. pure	(F, Xn)	X	1/3	1/3	1/0	3/0	1/0	1/0	1/1	1/3	4/4	1/0	1/1	3/3	3/3	0/0	(1)	1/1	1/1	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	
Petroleum	—	—	tech. pure	Xn, N	X	1/3	3/4	1/0	3/0	(1)	0/0	1/1	1/3	4/4	1/0	1/0	3/0	3/4	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Pepper	—	—	grinded	?		0/0	0/0	(2)	1/0	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Vegetable oils	—	—		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Phenacetin	$C_{10}H_{13}NO_2$	000062-44-2		Xn		0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)		
Phenetole	-> see: Phenylethylether																													
Phenol	C_6H_6O	000108-95-2	10 %	T		1/1	1/1	4/4	4/4	4/4	1/0	4/4	1/1	4/4	4/4	1/3	3/3	3/3	0/0	1/0	1/1	1/1	4/4	2/3	4/4	0/0	1/1	1/2	1/1	0/0	
Phenol	C_6H_6O	000108-95-2	100 %	T, C		2/3	3/3	4/4	4/4	4/4	1/1	4/4	1/2	4/4	3/3	4/4	3/0	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	0/0	
Phenolic resin moulding compound	—	—		?		1/1	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(4)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Phenyethylene	-> see: Styrene																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Phenyl-2-propenal, trans-3-	-> see: Cinnamaldehyde																													
Phenylamine	-> see: Aniline																													
Phenylaniline, N-	-> see: Diphenylamine																													
Phenyl bromide	-> see: Bromobenzene																													
Phenylcarbinol	-> see: Benzyl alcohol																													
Phenyl chloride	-> see: Chlorobenzene																													
Phenylethanol	$C_8H_{10}O$	000060-12-8		Xn		0/0	0/0	3/0	4/4	0/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(1)	(1)	(1)		
Phenyl ether	-> see: Diphenyl ether																													
Phenylethyl alcohol	-> see: Phenylethanol																													
Phenyl ethyl ether	$C_8H_{10}O$	000103-73-1		?		0/0	0/0	(2)	(4)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Phenylhydrazine	$C_6H_8N_2$	000100-63-0	tech. pure	T		3/0	0/0	(3)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/3	4/4	0/0	(2)	0/0	0/0	0/0	
Phenylhydrazine chlorohydrate	-> see: Phenylhydrazine-HCl																													
Phenylhydrazine-HCl	$C_6H_8N_2$-HCl	000059-88-1		T		0/0	0/0	(3)	(2)	0/0	0/0	(3)	1/3	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/3	1/3	0/0	(4)	(4L)	(4L)		
Phenylpropane	-> see: Cumene																													
Phenyl sulphonate	—	70528-83-5		?		0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Phenylsulfonic acid	-> see: Benzenesulfonic acid																													
Phosgene	$COCl_2$	000075-44-5	liquid	T+, C		0/0	0/0	1/0	(3)	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	1/0	3/0	0/0	(3)	3/4	3/4	0/0	
Phosgene	$COCl_2$	000075-44-5	gaseous	T+, C		0/0	3/0	1/0	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	3/0	0/0	(3)	3/4	3/4	0/0	
Phosphates	—	—	aqueous	?		1/1	1/1	0/0	0/0	(1)	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	0/0	(1)	(1)		Salts of phosphoric acid
Phosphine	PH_3	007803-51-2	concentrated	F+, T+	X	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Phosphorus (III) chloride	-> see: Phosphorus trichloride																													
Phosphorus oxychloride	PCl_3O	010025-87-3	100 %	T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	
Phosphorus oxychloride	PCl_3O	010025-87-3		T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	
Phosphorus pentachloride	PCl_5	010026-13-8		T+, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	1/1	(3)	(3)	4/4	0/0	1/1	1/3L	1/3L		
Phosphorus pentoxide	P_4O_{10}	001314-56-3	tech. rein	C		1/0	0/0	(4)	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	(3)	(2)	3/4	0/0	1/1	1/0	1/0	0/0	
Phosphorus perchloride	-> see: Phosphorus pentachloride																													
Phosphoric acid	H_3PO_4	007664-38-2	30 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	85 %	C		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	1/1	1/2	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	2/4	1/3	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	1-5 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	3/4	1/1	2/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	(4)	1/1	1/1	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	20%	Xi		1/1	1/1	4/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphoric anhydride	-> see: Phosphorus pentoxide																													
Phosphoric acid chloride	-> see: Phosphorus pentachloride																													
Phosphoric acid tritolyester	-> see: Tricresyl phosphate																													
Phosphorus trichloride	PCl_3	007719-12-2		T, C		3/3	3/3	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/1	1/0	3/4	4/4	0/0	1/1	0/0	0/0	1/1	
Hydrogen phosphide	-> see: Phosphine																													
Phosphoryl chloride	-> see: Phosphorus oxychloride																													
Phthalic acid	$C_8H_6O_4$	000088-99-3	saturated	Xi		1/1	1/1	3/3	(3)	1/0	0/0	1/0	1/1	1/0	0/0	1/4	0/0	1/1	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	
Phthalic acid amyl ester	$C_{18}H_{26}O_4$	000131-18-0	100 %	(T)		0/0	1/3	(1)	(4)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Phthalic acid dibutyl ester	-> see: Dibutyl phthalate																													
Phthalic acid dicyclohexyl ester	-> see: Dicyclohexyl phthalate																													
Phthalic acid dimethyl ester	-> see: Dimethyl phthalate																													
Phthalic acid dinonyl ester	-> see: Dinonyl phthalate																													
Phthalic acid monoamyl ester	$C_{13}H_{16}O_4$	??		(Xn)		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	(1)	(1)		
Picric acid	$C_6H_3N_3O_7$	000088-89-1	1 % aqueous	T		1/0	1/0	3/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	4/4	0/0	0/0	1/0	1/0	1/1	3/0	1/0	3/4	0/0	1/0	1/0	1/0	1/0	
Pimenta, allspice	—	—	grinded	?		0/0	0/0	(2)	4/4		0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Piperidine	$C_5H_{11}N$	000110-89-4		F, T, C		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Polyester resins	—	—		(Xn)	(X)	3/4	3/4	1/0	4/4	1/0	0/0	(2)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Polyethylene glycol	HO-$(C_2H_4O)_n$-H	025322-68-3	100 %	(—)		1/1	1/1	(3)	0/0	0/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2-3)	(2)	(3)	0/0	(1)	(1)	(1)	0/0	
Polyglycol	-> see: Polyethylene glycol																													
Polyoxyethylene	-> see: Polyethylene glycol																													
Polyoxymethylene	-> see: Paraformaldehyde																													
Polyran M25 N	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	3	0	0	(1)	(1)		Lubricating oil
Polyran M400	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	(3)	0	0	(1)	(1)		Lubricating oil
Polysiloxane	-> see: Silicone oil																													
Polysolvan O	$C_6H_{12}O_3$	007397-62-8	100 %	Xi		0/0	1/1	(2)	(3)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	(3)	0/0	(1)	(1)	(1)		Solvent, glycolic acid butyl ester; Celanese AG

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							---------- Thermoplastics ----------		---- Fluoroplastics ----		--- Elastomers ---		-------- Metals ---------			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Bitter orange oil	—	068916-04-1		?		2/3	3/4	(2)	3/3	1/0	3/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	4/4	(2)	(4)	0/0	(1)	(1)	(1)		
Potash	-> see: Potassium carbonate																													
Compressed air	—	—	oily	—		1/0	0/0	(2)	(2)	(1)	0/0	(1)	3/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	1/1	1/1	1/1		
Prontosil	—	—		(Xn)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	0/0	0/0		Chemotherapeutic agent; Bayer - no longer on the market
Prop-2-enyl acetate	-> see: Allyl acetate																													
Propane	C_3H_8	000074-98-6	liquid	F+	X	1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/0	0/0	1/0	1/0	3/0	1/0	0/0	(1)	1/1	1/1	4/4	1/0	(2)	0/0	1/1	1/1	1/1	0/0	
Propane	C_3H_8	000074-98-6	gaseous	F+	X	3/4	4/4	1/0	3/4	1/0	4/4	1/1	2/4	4/4	3/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Propandiol, 1,2-	-> see: Propylene glycol																													
Propanol	C_3H_8O	000071-23-8		F	X	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	3/0	0/0	2/2	3/3	1/4	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/1	(1)	(1)	0/0	
Propanol, 2-	-> see: Isopropyl																													
Propanone, 2-	-> see: Acetone																													
Propanoic acid	-> see: Propionic acid																													
Propanetriol	-> see: Glycerine																													
Propargyl alcohol	C_3H_4O	000107-19-7	7 %	Xn		1/1	1/1	(3)	1/0	0/0	0/0	(2)	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/3	1/0	1/1	1/1	0/0	1/0	(1)	(1)	0/0	
Propene	C_3H_6	000115-07-1		F+	X	1/1	1/1	1/0	(3)	1/0	0/0	1/0	1/1	4/4	0/0	3/4	4/4	0/0	0/0	(1)	1/1	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Propene-1-ol, 2-	-> see: Allyl alcohol																													
Propene acid ethyl ester	-> see: Ethyl acrylate																													
Propyn-1-ol, 2-	-> see: Propargyl alcohol																													
Propionic acid	$C_3H_6O_2$	000079-09-4	50 %	C, F	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/1	4/4	4/4	1/3	3/3	0/0	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	1/1	(1)	(1)	1/1	
Propionic acid	$C_3H_6O_2$	000079-09-4		C, F+	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	1/1	
Propyl acetate	$C_5H_{10}O_2$	000109-60-4		F	X	0/0	0/0	(1)	4/4	0/0	(4)	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Propyl alcohol	-> see: Propanol																													
Propylamine, n-	C_3H_9N	000107-10-8		F, C, Xn	X	0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Propylene	-> see: Propene																													
Propylene(di)chloride	-> see: Dichloropropane																													
Propylene glycol	$C_3H_8O_2$	000057-55-6		—		1/1	1/1	4/4	2/3	(2)	1/1	1/0	1/1	1/1	2/2	3/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	(1)	(1)	1/1	
Propylene glycol methyl ether	$C_4H_{10}O_2$	—		—	X	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Propylene oxide	C_3H_6O	000075-56-9		F+, T	X	1/1	1/2	(3)	2/3	0/0	1/2	(2)	1/2	4/4	2/2	3/4	0/0	4/4	3/4	1/1	1/0	1/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Propylidintris(methanol)	-> see: Trimethylol propane																													
Propyl nitrate	$C_3H_7NO_3$	000627-13-4		(E, Xn)	(X)	0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(2)	(1)	(1)		
Pseudocumene	C_9H_{12}	000095-63-6		Xn	X	0/0	0/0	(1)	(4)	0/0	0/0	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(2)	4/4	0/0	1/1	1/1	1/1		
Pydraul C (312, 540)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	1/0	4/4	0/0	0/0	(1)	(1)		Base phosphoric acid ester; Monsanto
Pydraul E (29, 30, 50, 65, 90, 11)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	4/4	0/0	0/0	(1)	(1)		Base phosphoric acid ester; Monsanto
Pyridine	C_5H_5N	000110-86-1		F, Xn	X	1/3	0/2	1/0	4/4	0/0	0/2	1/1	3/3	4/4	4/4	4/4	4/4	4/4	1/1	(2)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Pyridine-3-carboxylic acid	-> see: Nicotinic acid																													
Pyrogallol	$C_6H_6O_3$	000087-66-1		Xn		0/0	0/0	1/0	(3)	0/0	0/0	3/4	1/0	3/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	1/1	(3)	(3)	(3)	0/0	1/1	1/1	1/1	1/1	
Pyrosulphite	-> see: Sodium disulphite																													
Pyrrole	C_4H_5N	000109-97-7		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Mercury	Hg	007439-97-6	pure	T		1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(3)	1/1	1/1		
Mercury (II) chloride	$HgCl_2$	007487-94-7	aqueous	T+, C		1/1	1/1	4/4	1/0	(2)	1/1	3/0	1/1	1/3	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	(4)	(4)	1/1	Sublimate
Mercury (II) cyanide	C_2HgN_2	000592-04-1	saturated	T+		1/1	1/1	(3)	(2)	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	1/1	(1)	1/1	(2)	0/0	4/4	1/0	1/0	1/1	
Mercury (II) nitrate	-> see: Mercury nitrate																													
Mercury nitrate	$Hg(NO_3)_2$	010045-94-0	saturated	(T+)		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	1/0	0/0	1/3	1/0	0/0	(1)	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	1/1	1/1	1/1	
Mercuric nitrate	-> see: Mercury nitrate																													
Ramasit	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	Hydrophobing agent for textiles; BASF
Resorcinol	$C_6H_6O_2$	000108-46-3	5 %	—		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	2/4	0/0	3/3	1/3	1/1	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Resorcinol	$C_6H_6O_2$	000108-46-3	saturated	Xn		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	3/4	0/0	0/0	1/1	(1)	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Beef tallow	—	061789-97-7		—		0/0	0/0	1/0	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Beef tallow emulsion	—	—	sulphurised	(—)		1/0	0/0	(2)	(2)	0/0	0/0	0/0	1/0	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(2)	(2)	0/0	(2)	(1)	(1)	0/0	
Castor oil	—	008001-79-4	100 %	Xi		1/1	1/1	1/0	1/0	(1)	1/0	(2)	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Crude oil	—	—	100 %	(N)		0/0	1/3	1/0	(3)	1/0	0/0	1/0	1/3	3/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/3	0/0	(2)	(1)	(1)		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Rose oil	—	008007-01-0		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Roasting gases	—	—	any	(T)		0/0	0/0	(2)	0/0	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(4)	(2)	(2)	0/0	
Colza oil	—	008002-13-9		—		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	(1)	1/1	1/1		
Rum flavouring	—	008030-89-5		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(3)	(3)	(4)	(3)	0/0	(1)	(1)	(1)		
Sagrotan	—	—	liquid	?		1/2	1/3	0/0	3/0	0/0	0/0	(3)	1/3	3/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	3/0	0/0	(2)	(1)	(1)		Disinfectants; Schülke & Mayr
Salicylaldehyde	$C_7H_6O_2$	000090-02-8		Xn, Xi		1/1	1/2	(3)	2/3	0/0	1/2	(3)	1/2	4/4	3/3	3/4	0/0	0/0	1/4	1/1	(1)	(3)	(3)	(3)	4/4	0/0	(2)	(1)	(1)		
Salicylic acid	$C_7H_6O_3$	000069-72-7	saturated	(Xn, Xi)		1/1	1/1	1/0	1/2	1/0	1/1	4/4	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1	
Salicylic acid	$C_7H_6O_3$	000069-72-7	Powder	Xn, Xi		1/1	1/1	1/0	1/2	(1)	1/2	(3)	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1	
Salicylic acid methyl ester	-> see: Methyl salicylate																													
Salammoniac	-> see: Ammonium chloride																													
Ammonia solution	-> see: Ammonium hydroxide																													
Nitric acid	HNO_3	007697-37-2	1-10 %	C		1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1	1/1	
Nitric acid	HNO_3	007697-37-2	50 %	C+		2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO_3	007697-37-2	66 %	C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO_3	007697-37-2	100 %	O, C+		4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	0/0	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	?	
Nitric acid	HNO_3	007697-37-2	70 %	O, C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2	1/2	
Hydrochloric acid	HCl	007647-01-0	1-5 %	—		1/1	1/1	4/4	1/1	(2)	1/2	4/4	1/1	1/1	1/1	1/1	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	3/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	35 %	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	konz.	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	20 %	Xi		1/1	1/1	4/4	2/3	3/0	1/2	4/4	1/1	1/1	1/1	1/3	0/0	0/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	4/4	4/4	4/4	1/1	Hydrochloric acid
Hydrochloric acid aluminium salt, anhydrous	-> see: Aluminium chloride																													
Salt brine	NaCl	007647-14-5	saturated	—		1/1	1/1	1/0	(1)	(1)	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3	1/2	0/0	
Salt water, seawater	—	—		—		1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	
Saturated steam condensate	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(2)	1/1	1/1		
Oxygen	O_2	007782-44-7	tech. pure	O		1/3	1/3	2/0	1/0	(1)	0/0	1/0	1/3	1/0	0/0	1/1	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Lubricating oils	—	—		?		1/3	2/3	(2-3)	(1)	(2)	0/0	(2)	3/0	0/0	0/0	1/1	1/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0	
Lubricating soap	—	—	diluted	?		1/3	1/1	(2-3)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(1)	1/1	0/0	(2)	(1)	(1)	0/0	
Sulphur	S_8	007704-34-9	tech. pure	Xi		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	3/0	3/4	1/1	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	(1)	1/1	1/1	1/1	Sulphur, net sulphur, sulphur bloom
Sulphur, melted, 121 °C	S_8	007704-34-9		?		0	0	(4)	(3)	0	4	4	4	4	0	0	0	4	0	0	(1)	0	4	1	4	0	(3)	1	1	0/0	
Sulphur chloride	S_2Cl_2	010025-67-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	4/4	1/0	4/4	0/0	3/4	(1/1L)[1]	(1/1L)[1]	0/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Sulphur dioxide	SO_2	007446-09-5	moist	T, C		1/1	1/1	(3)	(3)	0/0	1/1	4/4	1/3	3/4	2/2	1/2	0/0	0/0	1/1	1/1	1/1	1/4	1/0	4/4	4/4	0/0	3/4	1/1	1/1	1/0	with H2O -> Sulphurous acid
Sulphur dioxide	SO_2	007446-09-5	liquid	T, C		3/4	4/4	(3)	3/4	0/0	4/4	4/4	4/4	4/4	2/2	3/4	0/0	0/0	1/2	1/1	1/1	4/4	1/0	4/4	4/4	0/0	(3)	(1)	(1)	1/0	with H2O -> Sulphurous acid
Sulphur dioxide, aqueous solution	-> see: Sulphurous acid																													
Sulphur ether	-> see: Ethyl ether																													
Sulphur hexaflurod	SF_6	002551-62-4		—		0/0	0/0	1/0	(2)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	1/0	0/0	0/0	(1)	(2)	1/0	3/0	1/0	0/0	(1)	(1)	(1)		
Carbon disulfide	CS_2	000075-15-0		F+, T	X	4/4	4/4	3/0	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/3	1/1	1/0	1/1	4/4	1/0	4/4	0/0	1/1	1/1	1/1	1/0	
Sulphur monochloride	-> see: Sulphur chloride																													
Sulphur sodium	-> see: Sodium sulphide																													
Sulphuric acid	H_2SO_4	007664-93-9	40 %	C+		1/1	1/1	4/4	2/0	(4)	1/2	4/4	1/1	2/0	3/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	(3)	1/1	4/4	0/0	3/4	2/3	2/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	60 %	C+		1/3	1/3	4/4	3/3	(4)	1/2	4/4	1/3	2/4	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	4/4	3/4	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	80 %	C+		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/1	3/4	3/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	2/4	2/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	95 %	C+		3/4	3/4	4/4	4/4	4/4	2/2	4/4	3/4	4/4	4/4	2/4	0/0	4/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	1/3	1/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	fuming	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	4/4	4/4	1/0	4/4	0/0	(3)	1/2	1/1	0/0	Oleum
Sulphuric acid	H_2SO_4	007664-93-9	1-6 %	Xi		1/1	1/1	4/4	1/1	0/0	1/1	4/4	1/1	1/2	1/1	1/2	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/0	0/0	(3)	2/2	1/2	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	20 %	Xi		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	(3)	2/3	2/3		
Sulphuric acid copper (II) salt	-> see: Copper sulphate																													
Sulphuric acid monomethyl ester	-> see: Methyl sulphuric acid																													
Sulphur trioxide	SO_3	007446-11-9		C+		4/4	4/4	4/4	(4)	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	(2)	(2)	3/4	3/0	1/0	4/4	0/0	(3)	(1)	(1)	0/0	
Hydrogen sulphide	H_2S	007783-06-4	saturated	F+, T+	X	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	3/0	1/0	1/3	3/3	1/0	0/0	1/0	1/1	1/1	1/0	(3)	4/4	0/0	1/1	1/1	1/1	0/0	
Sulphurous acid	H_2SO_3	007782-99-2	saturated	(C)		1/1	1/1	4/4	4/4	1/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	3/0	(3)	3/4	0/0	3/4	1/1	1/1	1/1	
Sulphuric acid dichloride	-> see: Thionyl chloride																													
Pork fat	—	—		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	2/0	1/0	1/0	0/0	(1)	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sebacic acid dibenzyl ester	-> see: Dibenzyl sebacate																													
Sebacic acid dibutyl ester	-> see: Dibutylsebacat																													
Sebacic acid diethyl ester	-> see: Diethylsebacate																													
Ocean water, seawater	-> see: Salt water, seawater																													
Soap solution	—	—	any	(—)		1/1	0/0	4/4	(2)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/1	
Mustard	—	—		—		0/0	0/0	(2)	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	1/0	1/0	0/0	(2)	1/0L	1/0L		
Mustard oil	-> see: Allyl mustard oil																													
Silver acetate	$C_2H_3AgO_2$	000563-63-3		Xi		1/1	1/1	(2)	1/2	(2)	1/1	(2)	1/1	2/2	1/1	2/2	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	(3)	0/0	(4)	0/0	0/0	0/0	
Silver cyanide	CAgN	000506-64-9		T		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	(1)	(1)	(3)	0/0	(4)	0/0	0/0	0/0	
Silver nitrate	$AgNO_3$	007761-88-8	aqueous	C		1/1	0/0	1/0	1/1	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	1/1	
Silver nitrate	$AgNO_3$	007761-88-8		C		1/1	1/2	1/0	1/1	(2)	1/1	1/0	1/2	2/3	1/1	1/2	1/3	1/2	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	1/1	
Silicon dioxide	-> see: Silicic acid																													
Silicone fats	—	—		(—)		0/0	0/0	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	1/0	1/0	1/1	0/0	1/1	1/1	1/1		
Silicone oil	—	—		?		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	3/3	1/0	1/4	0/0	1/1	0/0	1/1	1/1	(1)	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	Polysiloxan
Skydrol 500 (B4)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	0/0	1/0	4/4	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Solutia
Skydrol 7000	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	1/0	2/0	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Solutia
Soda	-> see: Sodium carbonate																													
Soya oil	—	008001-22-7		—		0/0	0/0	(2)	(1)	1/0	0/0	2/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	1/1	
Spindle oil	—	—		?		3/3	2/3	(2)	(2)	1/0	0/0	(2)	1/4	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Spinning bath acids	—	—	100mg CS_2/l	?		1/0	0/0	4/4	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(3)	(2)	4/4	0/0	(4)	3/4	2/4	0/0	
Spinning solution, viscous -	—	—		(Xn, Xi)		1/1	1/1	4/4	(3)	0/0	0/0		1/1	0/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	(3)	(2)	4/4	0/0	(3)	3/4	2/4	0/0	
Spirits	C_2H_6O	—		—		1/1	1/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	1/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	0/0	Ethanol 40 %
Spirit	C_2H_6O	—		F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1		Ethanol
Rinsing agent	—	—	aqueous	?		1/1	1/1	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0	
Starch gum	-> see: Dextrin																													
Starch solution	$(C_6H_{10}O_5)_n$	—	any	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Starch syrup	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Stauffer's grease	—	—		(—)		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	1/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	(1)	(2)	0/0	(1)	1/1	1/1	0/0	
Stearic acid	$C_{18}H_{36}O_2$	000057-11-4	fuming	Xi		1/3	1/3	1/0	1/2	1/0	1/1	1/0	1/3	1/2	2/2	1/2	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
Stearic acid zinc salt	-> see: Zinc stearate		crystals																											
Stearic acid butyl ester	$C_{22}H_{44}O_2$	000123-95-5	100 %	Xi		0/0	0/0	(1)	(3)	1/0	0/0	(2)	(2)	0/0	0/0	1/0	1/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1	0/0	
Coal tar oil	—	092045-38-0	100 %	T		1/0	1/3	1/0	(3)	0/0	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	1/1	1/1		
Nitrogen	N_2	007727-37-9		—		0/0	0/0	1/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1		
Nitrogen tetroxide	N_2O_4	010544-72-6		(O), T+, C		0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(2)	(1)	(1)		
Strontium bromide	$SrBr_2$	010476-81-0		Xi		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(3)	0/0	0/0		
Strychnine	$C_{21}H_{22}N_2O_2$	000057-24-9		T+		1/1	1/1	(1)	(1)	(2)	0/0	(2)	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)		
Styrene	C_8H_8	000100-42-5	100 %	Xn, Xi	X	4/4	3/4	1/1	4/4	1/1	(4)	1/1	3/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(2)	4/4	3/0	4/4	0/0	1/1	1/1	1/1	0/0	
Sulphite lye	-> see: Calcium bisulphite																													
Sulphuryl chloride	Cl_2SO_2	007791-25-5	tech. pure	C		4/4	4/4	4/4	1/0	0/0	0/0	4/4	4/4	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/0	3/0	3/0	1/0	4/4	0/0	3/4	0/0	0/0		
Tallow	—	—	tech. pure	—		1/1	1/1	1/0	(1)	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1	0/0	
Tannin	$C_{76}H_{52}O_{46}$	001401-55-4	10 %	Xi		1/1	1/1	1/0	3/3	0/0	1/1	4/4	1/1	3/3	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	1/1	
Tannin	$C_{76}H_{52}O_{46}$	001401-55-4		Xi		1/1	1/1	1/0	4/4	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	1/1	
Tar	—	—		T		0/0	1/0	1/0	(3)	1/0	0/0	1/0	(2)	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(1)	(1)	(1)		
Surfactants	-> see: Wetting agent																													
Turpentine substitute	—	—		Xn, N	X	0/0	0/0	1/0	(3)	1/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	(3)	0/0	1/1	1/1	1/1	1/1	
Turpentine oil	—	008006-64-2		Xn	X	2/2	3/4	1/0	4/4	1/0	3/3	1/1	4/4	4/4	4/4	2/3	4/4	3/3	1/1	1/1	1/0	1/3	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
White spirit	—	—	liquid	Xn, N	X	0/0	2/3	(1)	(3)	1/0	(4)	1/0	3/4	4/4	0/0	1/3	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0	
Test fuel A (ISO-Fluid A)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	1/0	0/0	(1)	(1)	(1)		
Test fuel B (ISO-Fluid B)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)		
Test fuel C (ISO-Fluid C)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)		
Test fuel D (ISO-Fluid D)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	4/4	0/0	(1)	(1)	(1)		
Tetrabromomethane (TBE)	$C_2H_2Br_4$	—	100 %	T+		4/4	3/4	(3)	4/4	(4)	(4)	(3)	3/4	4/4	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Carbon tetrabromide	CBr_4	000558-13-4		Xn, Xi		0/0	0/0	(3)	4/4	0/0	0/0	(3)	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Tetrabromomethane	-> see: Carbon tetrabromide																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Tetrachloroethane	$C_2H_2Cl_4$	—	tech. pure	T+		3/0	3/4	3/0	4/4	(4)	(4)	1/1	3/4	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Tetrachloroethene	-> see: Perchloroethylene																													
Tetrachloroethylene	-> see: Perchloroethylene																													
Carbon tetrachloride (TETRA)	CCl_4	000056-23-5		T		4/4	4/4	4/4	4/4	1/4	4/4	2/3	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	1/1	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Methane tetrachloride	-> see: Carbon tetrachloride																													
Tetrachlorotitanium	-> see: Titanium tetrachloride																													
Tetraethyl lead (TEL)	$C_8H_{20}Pb$	000078-00-2	techn. rein	T+	X	1/0	1/0	1/4	3/0	(2)	(4)	(2)	2/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/0	0/0	(2)	(1)	(1)	1/1	
Tetraethylorthosilicate	$C_8H_{20}SiO_4$	000078-10-4		Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	1/0	0/0	(1)	(1)	(1)		
Tetrafluoromethane	CF_4	000075-73-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Tetrahydro-1,4-oxazine	-> see: Morpholine																													
Tetrahydrofuran (THF)	C_4H_8O	000109-99-9		F, Xi	X	3/4	4/4	1/0	4/4	1/0	3/4	1/3	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	1/1	
Tetrahydrofurfuryl alcohol	$C_5H_{10}O_2$	000097-99-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(2)	(1)	(1)		
Tetrahydronaphthalene	$C_{10}H_{12}$	000119-64-2	tech. pure	Xi		3/4	4/4	1/0	4/4	1/0	(4)	1/0	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	1/0	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Tetralin	-> see: Tetrahydronaphthalene																													
Tetramethylene oxide	-> see: Tetrahydrofuran																													
Tetraphosphorus decaoxide	-> see: Phosphorus pentoxide																													
Thiacyclopentadiene	-> see: Thiophene																													
Thiofuran	-> see: Thiophene																													
Thioglycolic acid	$C_2H_4SO_2$	000068-11-1		T, C		0/0	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	(4)	0/0	3/4	0/0	1/1	0/0	
Thionyl chloride	Cl_2SO	007719-09-7	tech. pure	C		4/4	4/4	4/4	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	(3)	3/0	1/0	4/4	0/0	3/4	0/0	0/0	0/0	
Thiophene	C_2H_4S	000110-02-1		F, Xn	X	3/3	3/3	(2)	4/4	0/0	(4)	(2)	3/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	4/4	3/0	0/0	(1)	(1)	(1)	0/0	
Thymol	$C_{10}H_{14}O$	000089-83-8		C, Xn		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(3)	3/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	1/0	4/4	0/0	(1)	(1)	(1)		
Titanium chloride	-> see: Titanium tetrachloride																													
Titanium tetrachloride	$TiCl_4$	007550-45-0		C		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(4)	0/0	0/0		
Toluene	-> see: Methylbenzene																													
Toluol	-> see: Methylbenzene																													
Toluenesulphone chloramide sodium, p-	-> see: Chloramine T																													
Tragacanth	—	009000-65-1		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1		
Transformer oil	—	—		?		1/3	3/3	1/0	(3)	1/1	1/0	3/3	1/3	1/3	1/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	2/3	3/3	0/0	1/1	(1)	(1)	0/0	
Grape sugar	-> see: Glucose																													
Triacetin	$C_9H_{14}O_6$	000102-76-1		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	3/3	0/0	(1)	(1)	(1)		
Tribromomethane	-> see: Bromoform																													
Tributyl citrate	$C_{18}H_{32}O_7$	000077-94-1		—		1/2	2/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Tributyl phosphate (TBP)	$C_{12}H_{27}PO_4$	000126-73-8	tech. pure	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Trichloroacetaldehyde	C_2HCl_3O	000075-87-6	100 %	T/Xi		1/1	1/1	4/4	(3)	(4)	0/0	(3)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	0/0	(4)	3/0	(4)	4/4	0/0	4/4	0/0	0/0	0/0	
Trichloroacetaldehyde hydrate	-> see: Chloral hydrate																													
Trichloraldehyde hydrate	-> see: Chloral hydrate																													
Trichlorobenzene	$C_6H_3Cl_3$	—	100 %	(Xn)		4/4	4/4	(3)	(3)	0/0	(4)	(2)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	(2)	(3)	(4)	(3)	4/4	0/0	(2)	0/0	0/0	0/0	Isomer not specified in the source
Trichloroacetic acid (TCA)	$C_2HCl_3O_2$	000076-03-9		C+		1/4	3/4	4/4	4/4	4/4	0/0	4/4	1/1	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	1/3	3/0L	2/0L	1/1	
Trichloroethane	$C_2H_3Cl_3$	—		Xn		3/4	4/4	3/0	4/4	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	(1)	1/3	4/4	1/0	4/4	0/0	4/4	0/0	0/0	0/0	Isomer not specified in the source
Trichloroethene	-> see: Trichloroethylene																													
Trichloroethylene (TRI)	C_2HCl_3	000079-01-6	100 %	Xn		3/4	4/4	3/0	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/4	1/2	1/1	1/0	1/1	4/4	1/3	4/4	0/0	1/3	(1/1L)[1]	(1/1L)[1]	1/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Trichlorofluoromethane	CCl_3F	000075-69-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(3)	(1)	0/0	4/4	2/0	1/0	0/0	(3)	0/0	0/0	0/0	
Trichloromethane	-> siehe: Chloroform																													
Trichloromonofluoromethane	-> siehe: Trichlorfluormethan																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Trichlorophenol	$C_6H_3Cl_3O$	—		(Xn, Xi)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(4)	(3)	(4)	0/0	(3)	0/0	0/0		Isomer not specified in the source
Trichlorophosphine	-> see: Phosphorus trichloride																													
Trichlorophosphine oxide	-> see: Phosphorus oxychloride																													
Trichlorophosphorus oxide	-> see: Phosphorus oxychloride																													
Trichlorotrifluoroethane	$C_2Cl_3F_3$	000076-13-1		?		0/0	0/0	1/0	(3)	1/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		
Triethanolamine (TEA)	$C_6H_{15}NO_3$	000102-71-6	tech. pure	Xi		1/1	1/2	(2)	(2)	1/0	0/0	2/2	1/1	1/1	0/0	3/0	4/4	1/1	0/0	1/1	1/0	1/0	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Triethylamine (TEA)	$C_6H_{15}N$	000121-44-8	tech. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	1/1	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	3/4	4/4	3/0	3/4	0/0	(1)	(1)	(1)	0/0	
Triethylene glycol	-> see: Triglycol																													
Triethylene glycol diacetate	-> see: Triglycol acetate																													
Trifluorotrichloroethane	$C_2Cl_3F_3$	—	100 %	?		4/4	3/4	1/0	3/0	0/0	0/0	1/0	4/4	4/4	1/0	3/4	4/4	3/3	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		Isomer not specified in the source
Triglycol	$C_6H_{14}O_4$	000112-27-6		Xi		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	(3)	0/0	(1)	(1)	(1)	0/0	
Triglycol acetate	$C_{10}H_{18}O_6$	000111-21-7		?		0/0	0/0	(3)	(3)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)		
Trihydroxybenzoic acid, 3,4,5-	-> see: Gallic acid																													
Trihydroxybenzene, 1,2,3-	-> see: Pyrogallol																													
Trihydroxybutane	-> see: Butanetriol																													
Trihydroxypurine, 2,6,8-	-> see: Uric acid																													
Trihydroxytriethylamine	-> see: Triethanolamine																													
Triiodomethane	-> see: Iodoform																													
Triisopropylbenzene	$C_{15}H_{24}$	000717-74-8		—		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Tricresyl phosphate (TCF)	$C_{21}H_{21}PO_4$	—	tech. pure	T/Xn, N		1/1	1/1	1/0	4/4	1/0	0/0	1/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	1/1	1/1	1/1	1/1	Isomer not specified in the source
Trimethylbenzene, 1,3,4-	-> see: Pseudocumene																													
Trimethylolpropane	$C_6H_{14}O_3$	000077-99-6	aqueous	—		0/0	0/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	0/0	(1)	(1)	(1)		
Trimethylpentane, 2,2,4-	-> see: Iso-octan																													
Trisodium phosphate	Na_3PO_4	007601-54-9		Xi		1/1	1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(4)	1/1	1/1		
Trisodium phosphate, tribasic	-> see: Sodium phosphate																													
Trinitrophenol, 2,4,6-	-> see: Picric acid																													
Trioctyl phosphate	$C_{24}H_{54}PO_4$	000078-42-2	tech. pure	(Xn)		3/0	1/0	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	(1)	(1)	(1)	0/0	
Tripen	-> see: Hexachlorobutadiene																													
Tripropylene glycol (TPG)	$C_9H_{20}O_4$	024800-44-0		(—)		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/1	(2)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Tris(2-ethylhexyl) phosphate	-> see: Trioctyl phosphate																													
Tris(hydroxyethyl)-amine	-> see: Triethanolamine																													
Tris(hydroxymethyl)propane	-> see: Trimethylolpropane																													
Tropic acid tropylester sulphate	-> see: Atropine sulphate																													
Tung oil	-> see: Wood oil																													
Turbine oil (mineral oil base)	—	—		?		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	(2)	1/0	0/0	1/1	1/1	1/1		
Superchloric acid	-> see: Perchloric acid																													
Undecanol	-> see: Undecyl alcohol																													
Undecyl alcohol	$C_{11}H_{24}O$	000112-42-5		Xi		1/2	1/3	(1)	2/3	(1)	1/2	1/0	1/2	2/2	3/3	1/3	0/0	1/1	1/2	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(1)	(1)	(1)		
Urine	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	3/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	
Urotropine	-> see: Hexamethylenetetramine																													
Vaseline	—	008009-03-8	tech. pure	(—)		3/4	2/3	1/0	1/0	1/0	0/0		1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Vaseline oil	—	008012-95-1	100 %	?		0/0	1/3	1/0	(2)	1/0	1/0		1/3	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	Paraffin oil
Vaseline oil	—	008012-95-1		?		1/1	1/3	1/0	1/0	1/0	0/0	1/1	1/3	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/3	0/0	1/1	1/1	1/1	1/1	Paraffin oil
Vinyl acetate	$C_4H_6O_2$	000108-05-4	tech. pure	F	X	0/0	1/1	1/0	4/4	(3)	(4)		1/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	1/0	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Vinylbenzene	-> see: Styrene																													
Vinylcarbinol	-> see: Allyl alcohol																													
Vinyl chloride	-> see: Chlorethylene																													
Vinyl cyanide	-> see: Acrylonitrile																													
Vinyl ethylene	-> see: Butadiene, 1,3-																													
Vinylidene chloride	$C_2H_2Cl_2$	000075-35-4		F+, Xn	X	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	2/3	1/1	(1)	(2)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	
Vitamin C	$C_6H_8O_6$	000050-81-7	liquid	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	(1)	(1)		
Wax alcohol	—	—	tech. pure	(—)		3/4	3/4	(2)	(2)	1/0	0/0		3/4	0/0	0/0	1/1	3/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	(1)	(1)	0/0	
Waxes	—	—		—		0/0	1/3	1/1	1/1	1/1	0/0		1/3	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	(4)	1/0	(1)	0/0	1/1	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Walnut oil	—	008024-09-7		—		0/0	0/0	(2)	(2)	1/0	0/0		1/3	3/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	(1)	1/1	1/1		
Spermaceti	—	008002-23-1		—		0/0	1/3	(1)	1/1	1/0	0/0		1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Detergent	—	—		?		1/1	1/1	1/0	1/1	1/1	0/0		1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	(2)	0/0	1/1	1/1	1/1	1/1	
Water	H_2O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Water, distilled ~	H_2O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Water glass	$Na_2Si_3O_7$	001344-09-8	saturated	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	0/0	1/1	1/1	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	Aqueous solution of alkali silicates
Hydrogen	H_2	001333-74-0	tech. pure	F+	X	1/1	1/1	1/0	1/0	0/0	0/0		1/1	1/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Hydrogen peroxide	H_2O_2	007722-84-1	30 %	C		1/1	1/2	4/4	1/1	1/0	1/2	4/4	1/3	1/2	1/1	1/1	0/0	1/0	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	(3)	1/1	1/1	1/1	
Hydrogen peroxide	H_2O_2	007722-84-1	100 %	O, C		1/4	1/4	4/4	0/0	0/0	0/0	4/4	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(3)	(1)	(1)	?	
Hydrogen peroxide	H_2O_2	007722-84-1	90 %	O, C		1/1	1/2	4/4	1/1	0/0	1/2	4/4	1/3	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/3	4/4	0/0	(3)	1/1	1/1	?	
Hydrogen peroxide	H_2O_2	007722-84-1	3 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	1/0	1/1	1/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	3/4	0/0	(3)	1/1	1/1	1/1	
Oxygenated water	-> see: Hydrogen peroxide																														
Plasticiser	—	—		?		1/3	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	3/3	0/0	(1)	(1)	0/0	(2-3)	0/0	4/4	0/0	(1)	(1)	(1)		
Wines	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	(2)	1/1	1/1	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	1/1	1/1	1/1	
Spirit of wine	C_2H_6O	—	50 %	(F)	X	1/0	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	Ethanol
Spirit of wine	C_2H_6O	—	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	Ethanol
Tartaric acid	$C_4H_6O_6$	000087-69-4	aqueous	Xi		1/1	1/1	3/3	1/2	0/0	0/0	(3)	1/1	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2	1/1	
Tartaric acid	$C_4H_6O_6$	000087-69-4		Xi		1/1	1/1	4/4	1/2	0/0	1/1	(3)	1/1	2/2	1/1	1/2	1/3	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2	1/1	
Cream of tartar	-> see: Potassium hydrogentartate																														
Whiskey	—	—		—		0/0	0/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1		Whisky, Scotch, Bourbon
White spirit	—	008042-47-5		Xn		1/0	1/0	(1)	(3)	1/0	(4)	1/0	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	1/0	(2)	0/0	1/1	1/1	1/1		
Wool grease	-> see: Lanolin																														
Xenon	Xe	007440-63-3		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1		
Xylol	-> see: Xylene																														
Xylene	C_8H_{10}	001330-20-7		(F), Xn	X	3/4	3/4	1/0	4/4	0/0	3/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/0	1/3	4/4	1/3	4/4	0/0	1/1	1/1	1/1	1/1	
Cedar oil	—	008000-27-9		?		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(4)	(2)	(3)	0/0	(1)	(1)	(1)		
Cinnamon	—	—	grinded	?		0/0	0/0	(2)	1/0	(2)	0/0	(2)	(2)	3/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Cinnamaldehyde	C_9H_8O	000104-55-2		Xn, Xi		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(1)	(1)	(1)		
Cinnamon oil	—	008007-80-5		Xn, Xi		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Zinc acetate	$C_4H_6ZnO_4$	000557-34-6	aqueous	Xn, Xi		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/3	0/0	(3)	(1)	(1)		
Zinc bromide	$ZnBr_2$	007699-45-8		C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(3)	0/0	0/0		
Zinc carbonate	$ZnCO_3$	003486-35-9	saturated	?		1/1	1/1	(1)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	No chemical effect expected due to low solubility
Zinc chloride	$ZnCl_2$	007646-85-7	aqueous	(C, Xn)		1/1	1/1	3/4	(2)	0/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1	
Zinc chloride	$ZnCl_2$	007646-85-7	10 %	C, Xn		1/1	1/1	3/4	1/0	0/0	1/1	2/0	1/1	1/3	0/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1	
Zinc nitrate	$Zn(NO_3)_2$	007779-88-6		O, C, Xn		1/1	1/1	1/4	(2)	0/0	0/0	(2)	1/1	1/0	1/0	1/0	1/0	1/1	0/0	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(3)	(1)	(1)	0/0	
Zinc oxide	ZnO	001314-13-2	solid	Xn, Xi		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		No chemical effect expected due to low solubility
Zinc phosphate	$Zn_3(PO_4)_2$	007779-90-0	saturated	?		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	
Zinc ointment	—	—		?		0/0	0/0	(1)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	(4)	(2)	(2)	0/0	(2)	(1)	(1)		
Zinc sludge	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	(3)	0/0	0/0		
Zinc stearate	$C_{36}H_{70}ZnO_4$	000557-05-1		Xi		1/1	1/1	(1)	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	(2)	0/0	(2)	(1)	(1)		
Zinc sulphate	$ZnSO_4$	007733-02-0	10 %	—		1/1	1/1	(3)	1/0	(2)	1/0	2/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	1/1	
Zinc vitriol	-> see: Zinc sulphate																														
Tin (II) chloride	$SnCl_2$	007772-99-8	aqueous	(C, Xn)		1/1	1/1	(4)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	1/1	
Tin (II) chloride	$SnCl_2$	007772-99-8	saturated	C, Xn		1/1	1/1	4/4	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	1/1	
Tin (IV) chloride	$SnCl_4$	007646-78-8	aqueous	C		1/1	1/1	4/4	(3)	0/0	0/0	(4)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	4/4	3/4		
Tin dichloride	-> see: Tin (II) chloride																														
Tin protochloride	-> see: Tin (II) chloride																														
Tin tetrachloride	-> see: Tin (IV) chloride																														
Lemon juice	—	—		—		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	1/0	1/1	0/0	(1)	1/1	1/1		
Citric acid	$C_6H_8O_7$	000077-92-9	10 %	Xi		1/1	1/1	1/1	1/2	1/3	1/1	2/4	1/1	1/2	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/1	1/1	1/1	
Citric acid	$C_6H_8O_7$	000077-92-9	50 %	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1	
Citric acid	$C_6H_8O_7$	000077-92-9	saturated	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1	
Lemon peel oil	—	084929-31-7		Xi	(X)	0/0	0/0	(2)	(3)	1/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	3/3	0/0	1/0	(1)	(2)	4/4	(2)	3/3	0/0	1/1	(1)	(1)		mainly limes
Citrus juices	—	—	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	1/1	0/0	(2)	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers				Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sugar beet juice	—	—		—		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Sugar acid	—	—	saturated	(Xi)		1/1	1/1	(3)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		
Sugar syrup	—	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Two-stroke oil	—	—	100 %	—		0/0	1/3	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

Resistance

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

0	no information available/no statement possible
1	very good resistance/suitable
2	good resistance/suitable
3	limited resistance
4	not resistant
K	no general information possible
L	Risk of pitting or stress corrosion cracking
( )	Estimated value

Hazard preventions

E	explosive
O	oxidising
F	inflammatory
F+	extremely inflammable
T	toxic
T+	very toxic
C	caustic
Xn	harmful to health
Xi	irritant
N	environmentally hazardous

Name of materials

Thermoplastics

HDPE	High density polyethylene
LDPE	Low density polyethylene
PA	Polyamide (nylon)
PC	Polycarbonate
PETG	Polyethylene terephthalate glycol (co-
PMP	polyester) Polymethylpentene (TPX)
POM	Polyoxymethylene
PP	Polypropylene
PS	Polystyrene
PSU	Polysulfone
PVC	Polyvinyl chloride
SAN	Styrene acrylonitrile

Fluoroplastics

E-CTFE	Ethylene-chlorotrifluoroethylene (Halar)
ETFE	Ethylene tetrafluoroethylene
FEP	Tetrafluoroethylene-perfluoropropylene (Teflon,
PTFE	FEP) Polytetrafluoroethylene (Teflon)
PVDF	Polyvinylidene fluoride

Elastomers

EPDM	Ethylene propylene terpolymer rubber
FPM/FKM	Fluoropolymer (Viton)
NBR	Nitrile rubber
SI	Silicone rubber

Metals

Al	Aluminium
V2A	Stainless steel 1.4301 (AISI 304)
V4A	Stainless steel 1.4401 (AISI 316)
Hastelloy C	Nickel-chromium-molybdenum alloy

LISTA DE PRODUCTOS QUÍMICOS MACH I

AVISO IMPORTANTE

La tabla „Resistencia química de los plásticos“ se ha elaborado a partir de la información facilitada por diversos fabricantes de materias primas. Los valores se refieren exclusivamente a ensayos de laboratorio con materias primas. A menudo, las piezas de plástico fabricadas con ellas están sometidas a influencias que no pueden detectarse en los ensayos de laboratorio (temperatura, presión, tensiones del material, exposición a sustancias químicas, características de diseño, etc.). Por estas razones, los valores indicados sólo pueden servir de orientación. En caso de duda, recomendamos encarecidamente realizar una prueba. No se puede derivar ninguna reclamación legal de esta información, excluimos cualquier garantía y responsabilidad. La resistencia química y mecánica por sí sola no es suficiente para evaluar la utilidad de un producto. En particular, debe tenerse en cuenta la normativa sobre líquidos inflamables (protección contra explosiones).

DERECHOS DE AUTOR

Agradecemos a Bürkle GmbH que nos haya concedido el derecho a utilizar esta tabla.
Esta tabla es publicada y mantenida por Bürkle GmbH, D-79415 Bad Bellingen, Alemania, como guía de referencia. Este aviso de copyright no puede ser eliminado. La tabla puede distribuirse y copiarse libremente siempre que se mantenga intacto el aviso de copyright.

LISTA DE MATERIALES MACH I

Bomba de aguas sucias:	PP + GF20	Manguera de drenaje:	PP, EVA
Válvula de retención:	PP	Boquilla para suelos:	PP
Conexiones de tornillo:	PP	Tubo de aspiración:	PP
Acoplamientos en C:	PA6 + GF30	Cabezal de aspiración:	ABS
Manguera de aspiración:	PP, EVA		

Versión 3.11 (11.01.2021); Sujeto a cambios técnicos, © Bürkle GmbH 2021.

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Exhaust gases, alkaline	—	—		?		1/1	0/0	(2)	0/0	0/0	0/0	(1)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/4	1/0	1/0	1/0	0/0	(2)	(1)	(1)		
Exhaust gases, containing hydrogen fluoride	—	—	low	?		1/1	0/0	(3)	(3)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	(2)	(2)	1/1	
Exhaust gases, carbon dioxide-containing	—	—	low	?		1/1	0/0	(1)	(1)	(1)	(1)	(1)	1/1	(1)	(1)	1/1	(1)	(1)	1/1	1/1	1/1	1/1	1/0	1/0	(1)	(1)	(1)	(1)	(1)	0/0	
Exhaust gases, nitrous	—	—	low	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	(3)	0/0	(2)	(1)	(1)		
Exhaust gases containing hydrochloric acid	—	—	any	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	2/2L	2/2L	3/3	
Exhaust gases containing sulphur dioxide	—	—	low	?		1/1	0/0	(2)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	1/1	1/1	0/0	
Exhaust gases containing sulphuric acid	—	—	any	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0	
Exhaust gases, containing sulphur trioxide	—	—	low	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	4/4	0/0	0/0	1/1	0/0	0/0	(2)	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0	
Acetaldehyde	C_2H_4O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	3/4	
Acetaldehyde	C_2H_4O	000075-07-0	tech. pure	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Acetamide	C_2H_5NO	000060-35-5	saturated	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)	1/1	
Acetamino-4-ethoxybenzene, 1-	-> see: Phenacetin																														
Acetic anhydride	-> see: Acetic anhydride																														
Acetone	C_3H_6O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	1/1	
Acetonitrile	C_2H_3N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Acetophenone	C_8H_8O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Acetoxybenzoic acid, 2-	-> see: Acetylsalicylic acid																														
Acetyl-5-methyl-2,3-dihydropyran-2,4-dione, -2	-> see: PDehydroacetic acid																														
Acetyl chloride	C_2H_3ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	0/0	
Acetylene	C_2H_2	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	1/1	0/0	1/0	1/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	
Acetylene tetrabromide	-> see: Tetrabromomethane, 1,1,2,2-																														
Acetylene tetrachloride	-> see: Tetrachloroethane-1,1,2,2																														
Acetylsalicylic acid	$C_9H_8O_4$	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	1/0	
Acrylonitrile	C_3H_3N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	1/1	
Acrylic acid butyl ester	-> see: Butyl acrylate																														
Acrylic acid ethyl ester	-> see: Ethyl acrylate																														
Acrylic acid methyl ester	-> see: Methyl acrylate																														
Acrylic acid nitrile	-> see: Acrylonitrile																														
Adipic acid	$C_6H_{10}O_4$	000124-04-9	saturated	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	1/0	(2)	(2)	1/1	
Adipic acid dioctyl ester	-> see: Dioctyladipate																														
Acrylic acid	H_2SO_4	007664-93-9	38 %	C		1/1	1/1	4/4	1/1	(4)	1/1	4/4	1/1	1/1	1/1	1/3	3/4	0/0	(1)	1/1	1/1	1/1	1/0	1/1	4/4	0/0	3/4	2/3	2/3	1/1	"Battery acid"
Alanine	$C_3H_7NO_2$	000056-41-7		—		1/1	1/1	1/1	4/4	(2)	1/1	(1)	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(2)	(2)	(2)		
Alum	-> see: Potassium aluminium sulphate																														
Alcohol	-> see: Ethanol																														
Allyl acetate	$C_5H_8O_2$	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		
Allyl alcohol	C_3H_6O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	1/1	(2)	1/0	4/4	3/0	0/0	1/1	1/1	1/1	1/1	
Allyl chloride	C_3H_5Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)	0/0	
Allyl isothiocyanate	-> see: Allyl mustard oil																														
Allyl mustard oil	C_4H_5NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		Oleum Sinapis
Aluminium (hydroxide) acetate	$C_4H_7AlO_5$	000139-12-8	aqueous	Xn		1/1	1/1	1/1	(1)	1/0	1/1	1/0	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	(1)	1/0	(3)	3/0	0/0	1/1	1/1	1/1	0/0	"Acetic acid alumina"
Aluminium ammonium sulphate	$(NH_4)Al(SO_4)_2$	007784-26-1	saturated	Xi		1/1	1/1	3/4	(2)	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3	0/0	
Aluminium chloride	$AlCl_3$	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	1/1	0/0	1/1	0/0	1/1	2/2	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	4/4	3/4	1/1	
Aluminium chloride	$AlCl_3$	007784-13-6	solid	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	(3)	0/0	4/4	4/4	3/4	1/1	Hydrochloric acid aluminium salt, anhydrous
Aluminium chloride	$AlCl_3$	007784-13-6	saturated	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	(1)	1/1	(2)	1/0	1/1	0/0	4/4	4/4	3/4	1/1	Hydrochloric acid aluminium salt, anhydrous
Aluminium fluoride	AlF_3	007789-18-1	aqueous	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	0/0	
Aluminium hydroxide	$Al(HO)_3$	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1/1	1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	0/0	No chemical effect expected due to low solubility
Aluminium hydroxide diacetate	-> see: Acetic clay																														
Aluminium nitrate	$Al(NO_3)_3$	013473-90-0	aqueous	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Aluminium oxide	Al_2O_3	001344-28-1	solid	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	No chemical effect expected due to low solubility
Aluminium sulphate	$Al_2(SO_4)_3$	010043-01-3	10 %	?		1/1	1/1	1/0	1/0	(2)	1/1	3/4	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/2	1/1	1/1	
Aluminium sulphate	$Al_2(SO_4)_3$	010043-01-3	saturated	Xn		1/1	1/1	3/4	1/0	0/0	1/1	3/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	2/2	1/2	1/1	
Aluminium trifluoride	-> see: Aluminium fluoride																														
Formic acid	CH_2O_2	000064-18-6	50 %	C, F	X	1/1	1/2	4/4	3/3	0/0	1/2	4/4	1/2	3/3	2/2	2/3	0/0	1/3	1/1	1/1	1/1	1/1	3/4	4/4	4/4	0/0	(3)	1/3	1/2	1/1	
Formic acid	CH_2O_2	000064-18-6	98-100 %	C, F+, T	X	1/1	1/2	4/4	3/4	0/0	1/3	4/4	1/3	3/4	3/3	3/4	1/3	3/4	1/1	(1)	1/1	1/1	3/4	4/4	4/4	0/0	1/0	1/3	1/2	1/0	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Formic acid	CH_2O_2	000064-18-6	3 %	Xi		1/1	1/2	3/4	1/2	1/0	1/2	2/4	1/2	1/2	2/2	2/3	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(3)	4/4	0/0	(3)	1/2	1/1	1/1	
Formic acid amide	-> see: Formamide																													
Formic acid ethyl ester	-> see: Ethyl formate																													
Formic acid methyl ester	-> see: Methylformia																													
Aminobenzene	-> see: Aniline																													
Aminobutane	-> see: Buylamine																													
Aminoacetic acid	$C_2H_5NO_2$	000056-40-6	10 %	—		1/1	1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	(2)	(2)	(2)	0/0	
Aminoethanol, 2-	-> see: Ethanolamine																													
Aminoethanoic acid	-> see: Aminoacetic acid																													
Amonimethane	-> see: Methylamine, (mono-)																													
Aminopropane	-> see: Propylamine, n-																													
Aminopropionic acid, L-2-	-> see: Alanine, (L-)																													
Ammonia	-> see: Ammonium hydroxide																													
Ammonia, sulphuric acid	-> see: Ammonium sulphate																													
Ammonia water	-> see: Ammonium hydroxide																													
Ammonium 2-hydroxyacetate	-> see: Ammonium glycolate																													
Ammonium acetate	$C_2H_7NO_2$	000631-61-8	saturated	Xi		1/1	1/1	1/0	1/1	(2)	1/1	(1)	1/1	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(3)	2/2	0/0	1/1	(2)	(2)	1/1	
Ammonium alum	-> see: Aluminium ammonium sulphate																													
Ammonium aluminium sulphate	-> see: Aluminium ammonium sulphate																													
Ammonium bicarbonate	-> see: Ammonium hydrogen carbonate																													
Ammonium bifluoride	-> see: Ammoinium hydrogen difluoride																													
Ammonium carbonate	$(NH_4)_2CO_3$	010361-29-2	50 %	Xn		1/1	1/1	1/0	3/0	0/0	1/0	(2)	1/1	1/1	1/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Hartshorn salt
Ammonium carbonate	$(NH_4)_2CO_3$	010361-29-2	aqueous	Xn		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Hartshorn salt
Ammonium chloride	$(NH_4)Cl$	012125-02-9	solid	Xn		1/1	1/1	1/0	1/0	(2)	0/0	2/3	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	3/4	1/3L	1/2L	1/1	Ammonia
Ammonium chloride	$(NH_4)Cl$	012125-02-9	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	Ammonia
Ammonium dihydrogen phosphate	$(NH_4)H_2PO_4$	007722-76-1	any	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	3/0	1/1	0/0	4/4	(1)	(1)	1/1	
Ammonium iron(II) sulfate	$(NH_4)_2Fe(SO_4)_2$	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	(1)	(1)		
Ammonium iron(III) sulfate	$(NH_4)Fe(SO_4)_2$	007783-83-7	saturated	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0		
Ammonium fluoride	$(NH_4)F$	012125-01-8	saturated	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)	?	
Ammonium fluoride	$(NH_4)F$	012125-01-8	aqueous	T. C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3	1/1	
Ammonium glycolate	$C_2H_7NO_3$	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)		
Ammonium heptamolybdate	$(NH_4)_6Mo_7O_{24}$	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/0	(3)	(1)	0/0		(1)	(1)	0/0	
Ammonium hydrogen carbonate	CH_5NO_3	001066-33-7	saturated	Xi		1/1	1/1	1/0	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	(3)	0/0	1/1	1/1	1/1	1/1	
Ammonium hydrogen difluoride	F_2H_5N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0		
Ammonium hydrogen sulphide	-> see: Ammonium hydrosulphide																													
Ammonium hydrosulphide	$(NH_4)HS$	012124-99-1	any	T, C		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	(2)	0/0	(2)	(1)	(1)	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	1/2	2/3	2/3	1/2	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1	1/1	
Ammonium metaphosphate	$(NH_4PO_3)_n$	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)		
Ammonium molybdate	-> see: Ammonium heptamolybdate																													
Ammonium monophosphate, monobasic	-> see: Ammonium dihydrogen phosphate																													
Ammonium nitrate	$(NH_4)NO_3$	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	1/1	
Ammonium nitrate	$(NH_4)NO_3$	006484-52-2	saturated	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1	1/1	
Ammonium nitrite	$(NH_4)NO_2$	013446-48-5	aqueous	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/0	0/0	(2)	(1)	(1)		
Ammonium oxalate	$C_2H_8N_2O_4$	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1	0/0	
Ammoniumperoxodisulfat	$(NH_4)_2S_2O_8$	007727-54-0	saturated	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0	
Ammoniumperoxodisulfat	$(NH_4)_2S_2O_8$	007727-54-0	aqueous	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0	
Ammonium persulphate	-> see: Ammonium peroxodisulphate																													
Ammonium phosphate, primary	-> see: Ammonium dihydrogen phosphate																													
Ammoniumpolyphosphat	-> see: Ammonium metaphosphate																													
Ammonium rhodanide	-> see: Ammonium thiocyanate																													
Ammonium sulphate	$(NH_4)_2SO_4$	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	1/1	sulphuric acid ammonia
Ammonium sulphate	$(NH_4)_2SO_4$	007783-20-2	saturated	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2	1/1	sulphuric acid ammonia
Ammonium sulphide	$(NH_4)_2S$	012135-76-1	any	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	?	
Ammonium sulphide	$(NH_4)_2S$	012135-76-1	aqueous	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ammonium sulphocyanide	-> see: Ammonium thiocyanate																													
Ammonium thiocyanate	CH_4N_2S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)		
Ammonium nitrate	-> see: Ammonium nitrate																													
Amylacetate, n-	$C_7H_{11}O_2$	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Amyl alcohol, n-	$C_5H_{12}O$	000071-41-0		Xn	X	1/1	1/2	1/0	1/0	1/0	2/3	1/0	1/1	1/3	3/0	2/3	3/0	0/4	1/1	1/1	1/1	1/1	3/0	2/4	3/0	0/0	1/2	1/1	1/1	0/0	
Anym chloride	$C_5H_{11}Cl$	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L	0/0	
Amyl hydrosulphide	-> see: Pentanthiol, 1-																													
Amyl mercaptan	-> see: Pentanthiol, 1-																													
α-pentylcinnamaldehyde	$C_{14}H_{18}O$	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)	(1)		Fragrance
Pineapple juice	—	—		—		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	(1)	(1)		
Aniline	C_6H_7N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0	1/1	
Aniline chlorohydrate	$C_6H_3ClN_6$	000142-04-1	saturated	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4		
Aniline hydrochloride	-> see: Aniline chlorohydrate																													
Anilinium chloride	-> see: Aniline chlorohydrate																													
Anise	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Anise oil	C_7H_8O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Anise oil	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Anon	-> see: Cyclohexanone																													
Antimony (III) chloride	-> see: Antimony trichloride																													
Antimony (V) chloride	-> see: Antimony pentachloride																													
Antimony pentachloride	$SbCl_5$	007647-18-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	(4)	0/0	
Antimony trichloride	$SbCl_3$	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4	0/0	
Antimony trichloride	$SbCl_3$	010025-91-9	anhydrous	C		0/0	0/0	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	1/0	1/0	1/0	0/0	1/1	4/4	4/4		
Antimony trichloride	$SbCl_3$	010025-91-9	aqueous	C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4		
Apple juice	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	(2)	(1)	(1)		
Orange juice	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(2)	1/1	1/1		
Orange peel oil	—	008028-48-6		Xn		(3)	(3)	1/0	(3)	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	4/4	(2)	(3)	0/0	(1)	(1)	(1)		mainly +-Limes
Arcton 12	-> see: Dichlorodifluoromethane																													
Arcton 21	-> see: Dichlorofluoromethane																													
Arcton 22	-> see: Chlorodifluoromethane																													
Arsenic anhydride	-> see: Arsenic pentoxide																													
Arsenic pentoxide	As_2O_5	001303-28-2		T, N		1/1	1/1	(3)	(2)	0/0	0/0	(4)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	(2)	(3)	(3)	0/0	(3)	(1)	(1)		
Arsenic acid	H_3AsO_4	022538-92-7	aqueous	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	1/1	
Arsenic acid	H_3AsO_4	022538-92-7	80 %	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	0/0	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	1/1	
Arsenic anhydride	-> see: Arsenic pentoxide																													
Ascorbic acid	$C_6H_8O_6$	000050-81-7	aqueous	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	1/1	(1)	(1)	0/0	
Ether	-> siehe: Ethylether																													
Atropine sulphate	$C_{34}H_{48}N_2SO_{10}\cdot H_2O$	000055-48-1		T+		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)		
Caustic baryte	-> see: Barium hydroxide																													
Caustic potash	-> see: Potassium hydroxide																													
Caustic lime	-> see: Calcium oxide																													
Caustic soda	-> see: Sodium hydroxide																													
Azafluorene, 9-	-> siehe: Carbazole																													
Valerian drops	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	1/1	1/1	(1)	(3)	(3)	(2)	0/0	(2)	(1)	(1)		
Barium bromide	$BaBr_2$	010553-31-8		Xn		1/1	1/1	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	1/1	0/0	(2)	(2L)	(2L)		
Barium carbonate	$BaCO_3$	000513-77-9	saturated	Xn		1/1	1/1	1/1	(1)	1/1	1/1	(1)	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	No chemical effect expected due to low solubility
Barium chloride	$BaCl_2$	010361-37-2	saturated	T		1/1	1/1	1/0	1/0	1/0	1/1	(2)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1	
Barium chloride	$BaCl_2$	010361-37-2	aqueous	T		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1	
Barium hydroxide	$Ba(HO)_2$	012230-71-6	saturated	Xn		1/1	1/1	1/0	(3)	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/3	
Barium hydroxide	$Ba(HO)_2$	012230-71-6	aqueous	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	?	
Barium sulphide	BaS	021109-95-5	saturated	(T)		1/1	1/1	1/0	(2)	(2)	1/1	(2)	1/1	0/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	(2)	1/0	1/0	1/1	0/0	(3)	(1)	(1)	1/1	
Cottonseed oil	—	008001-29-4	tech. pure	?		0/0	0/0	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	3/0	1/0	1/0	0/0	(1)	1/1	1/1		
Benzaldehyde	C_7H_6O	000100-52-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	artificial almond oil
Benzene	-> see: Benzene (page 5)																													
Petrol	C_5H_{12} - $C_{12}H_{26}$	086290-81-5		F, Xn, N	X	2/3	3/4	1/0	3/3	(2)	2/3	1/2	3/4	4/4	3/3	2/4	0/0	0/4	1/1	1/1	1/1	1/1	4/4	(1-3)	3/0	0/0	1/1	1/1	1/1	1/1	Fuel, unleaded

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Benzoic acid	$C_7H_6O_2$	000065-85-0	saturated	Xn, Xi		1/1	1/1	3/4	4/4	1/0	1/2	2/4	1/3	2/2	3/3	1/2	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1	
Benzoic acid	$C_7H_6O_2$	000065-85-0	aqueous	Xn, Xi		1/1	1/1	3/4	4/4	1/0	0/0	2/4	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1	
Benzoic acid sodium salt	-> see: Sodium benzoate																														
Benzoic acid aldehyde	-> see: Benzaldehyde																														
Benzoic acid benzyl ester	-> see: Benzyl benzoate																														
Benzoic acid chloride	-> see: Benzoyl chloride																														
Benzoic acid ethyl ester	$C_9H_{10}O_2$	000093-89-0		Xn		2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Benzene	C_6H_6	000071-43-2		F, T	X	3/4	3/4	2/0	4/4	4/4	2/3	1/2	3/4	4/4	4/4	4/4	0/0	0/4	1/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	1/1	1/1	1/1	0/0	
Benzene-1,2-dicarboxylic acid	-> see: Phthalic acid																														
Benzene carboxylic acid	-> see: Benzoic acid																														
Benzene hexachloride (BHC)	-> see: Hexachlorocyclohexane																														
Benzenesulfonic acid	$C_6H_6SO_3$	000098-11-3	saturated	C		1/1	1/1	(4)	(3)	(4)	0/0	(4)	2/4	0/0	1/0	2/0	0/0	0/0	0/0	1/1	1/1	1/4	4/4	1/0	4/4	0/0	3/4	0/0	1/0	0/0	
Benzoyl chloride	C_7H_5ClO	000098-88-4	100 %	C		0/0	3/3	4/4	(4)	0/0	(4)	(3)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	(3)	4/4	0/0	1/0	(2L)	(2L)	0/0	
Benzyl acetate	$C_9H_{10}O_2$	000140-11-4		Xn/Xi		1/1	1/2	(2)	3/4	0/0	1/2	(2)	1/2	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	1/0	4/4	0/0	1/1	1/1	1/1		
Benzyl alcohol	C_7H_8O	000100-51-6		Xn		3/4	4/4	4/4	4/4	0/0	4/4	1/0	4/4	4/4	4/4	2/3	0/0	4/4	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	1/1	1/1	1/1	3/3	
Benzyl benzoate	$C_{14}H_{12}O_2$	000120-51-4		Xn		0/0	0/0	(2)	(3)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Benzylcarbinol	-> see: Phenylethanol																														
Benzyl chloride	C_7H_7Cl	000100-44-7	100 %	T/Xi		0/0	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	(3)	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0	
Benzylether	-> see: Dibenzyl ether																														
Succinic acid	$C_4H_6O_4$	000110-15-6	50 %	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	2/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/0	1/0	1/1	
Succinic acid	$C_4H_6O_4$	000110-15-6	saturated	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	?	
Succinic acid diethyl ester	$C_8H_{14}O_4$	000123-25-1		—		0/0	0/0	(2)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	4/4	4/4	0/0	(1)	(1)	(1)		
Bichromate sulphuric acid	-> see: Chromosulphuric acid																														
Beeswax	—	008012-89-3		—		1/1	1/1	1/1	(1)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	1/1	(1)	(1)		
Beer	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	
Bis(2-chloro-1-methylethyl)-ether	-> ssee: Dichloroisopropyl ether																														
Bis(2-ethylhexyl)-dipate	-> see: Dioctyladipate																														
Bis(2-ethylhexyl)-phthalate	-> see: Diisooctyl phthalate																														
Bis(2-ethylhexyl)-sebacate, sebacic acid bis(2-ethylhexyl)-ester	-> see: Dioctylsebacate																														
Bismuth chloride	$BiCl_3$	007787-60-2		Xi		1/1	1/1	(3)	(2)	(2)	0/0	(4)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(4)	0/0	0/0		
Bismuth subnitrate	$Bi_5O(HO)_9(NO_3)_4$	001304-85-4		O, Xi		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		
Bisulphite	-> see: Sodium bisulphite																														
Bisulphite lye	$NaHSO_3$	??		Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	3/0	0/0	(3)	1/1	1/1	1/1	
Bisulphite lye, containing $S0_2$	$NaHSO_3$	??	saturated	Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/1	4/4	0/0	(3)	1/1	1/1		
Bitter almond oil	C_7H_6O	090320-35-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1		Main ingredient: Benzaldehyde
Epsom salt	-> see: Magnesium sulphate																														
Bitumen	—	008052-42-4		—		0/0	0/0	1/0	(2)	(2)	0/0	2/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	(3)	0/0	1/1	(1)	(1)		
Hydrogen cyanide	HCN	000074-90-8	tech. pure	F+, T+	X	1/1	1/1	(3)	4/4	0/0	0/0	4/4	1/1	1/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	1/1	1/0	1/0	1/0	
Hydrogen cyanide	HCN	000074-90-8	aqueous	F+, T+	X	1/1	1/1	(3)	4/4	0/0	(4)	4/4	1/1	1/0	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(1)	1/0	1/0	?	
Lead (II) acetate	$C_4H_6PbO_4$	000301-04-2	aqueous	T, N		1/1	1/1	3/0	1/0	(2)	1/0	1/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	3/0	0/0	4/4	1/1	1/1	1/1	
Lead (II) acetate	$C_4H_6PbO_4$	000301-04-2		T, N		1/1	1/1	3/0	1/0	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	2/2	0/0	4/4	1/1	1/1	1/1	
Lead(II) nitrate	$Pb(NO_3)_2$	010099-74-8	aqueous	O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Lead(II) nitrate	$Pb(NO_3)_2$	010099-74-8		O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Lead nitrate	-> see: Lead (II) nitrate																														
Lead stearate	$C_{36}H_{70}PbO_4$	001072-35-1		?		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		No chemical effect expected due to low solubility
Lead sulphate	$PbSO_4$	007446-14-2		(T, N)		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	0/0	(1)	(1)	(1)	0/0	No chemical effect expected due to low solubility
Tetraethyllead	-> see: Tetraethyl lead																														
Lead sugar	-> see: Lead (II) acetate																														
Yellow prussiate of Potash	-> see: Potassium hexacyanoferrate(II)																														
Red prussiate of Potash	-> see: Potassium hexacyanoferrate(III)																														
Borax	-> see: Sodium borate																														
Boric acid	H_3BO_3	010043-35-3	10 %	Xi		1/1	1/1	1/0	1/1	1/0	1/1	2/3	1/1	1/2	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Boric acid	H_3BO_3	010043-35-3	aqueous	Xi		1/1	1/1	3/3	1/1	1/0	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Spirits	-> see: Spirits																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Brake fluid	—	—		?		1/0	1/0	1/0	4/4	0/0	1/1	(3)	1/1	3/0	0/0	1/0	3/0	4/4	0/0	(1)	1/0	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Bromine	Br_2	007726-95-6		T+, C		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	2/4	4/4	4/4	1/2	1/1	1/3	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	4/4	
Bromine benzene	-> see: Bromobenzene																													
Bromobenzene	C_6H_5Br	000108-86-1		Xn	X	3/4	4/4	1/0	4/4	(2)	4/4	1/0	4/4	4/4	4/4	4/4	0/0	0/0	2/4	1/1	1/0	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)		
Bromochloromethane	CH_2BrCl	000074-97-5	100 %	Xn		(4)	(4)	4/4	4/4	1/0	(4)	(3)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/0	(3)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	
Bromine vapours	Br_2	007726-95-6		T		(4)	(4)	4/4	(3)	4/4	(4)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(2-3)	4/4	0/0	(3)	(4)	(4)	4/4	
Bromine potassium	-> see: Potassium bromide																													
Bromomethane	CH_3Br	000074-83-9	tech. pure	T		3/0	4/4	1/0	(3)	0/0	0/0	1/0	4/4	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0	
Bromoform	$CHBr_3$	000075-25-2		T		4/4	4/4	4/4	4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	0/0	0/0	2/3	1/1	(1)	(2)	4/4	(4)	4/4	0/0	(3)	0/0	0/0	0/0	
Bromopental fluoride	BrF_5	007789-30-2		F, T, C		0/0	0/0	4/4	(4)	(4)	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromic acid	$HBrO_3$	007789-31-3	concentrated.	C		0/0	0/0	(4)	(4)	(4)	0/0	4/4	3/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(4)	(2)	4/4	0/0	(4)	(4)	(4)	0/0	
Bromine trifluoride	BrF_3	007787-71-5		T, C		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromotrifluoromethane	$CBrF_3$	000075-63-8		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Bromine water	Br_2+H_2O	007726-95-6	saturated	T		4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	4/4	0/0	3/4	0/0	0/0	0/0	0/0	1/1	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	0/0	
Hydrobromic acid	HBr	010035-10-6	40 %	C		1/0	1/1	4/4	4/4	(4)	4/4	4/4	1/1	4/4	0/0	1/1	3/3	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Hydrobromic acid	HBr	010035-10-6	50 %	C		1/1	1/2	4/4	4/4	(4)	4/4	4/4	1/2	4/4	0/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Hydrobromic acid	HBr	010035-10-6	diluted	C		1/1	1/1	4/4	4/4	3/0	4/4	4/4	1/1	4/4	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Butadiene, 1,3-	C_4H_6	000106-99-0		F+, T	X	3/4	4/4	1/0	4/4	1/0	4/4	(2)	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)	4/4	
Butane	C_4H_{10}	000106-97-8	tech. pure	F+	X	1/0	1/1	1/0	1/0	1/0	1/0	2/0	1/1	4/4	1/0	1/0	3/0	1/0	0/0	1/1	1/1	1/0	4/4	1/0	1/0	0/0	1/1	(1)	(1)	1/1	
Butanal	-> see: Butyraldehyde																													
Butanediol	-> see: Butylene glycol																													
Butanedioic acid	-> see: Succinic acid																													
Butanol	$C_4H_{10}O$	000071-36-3	techn. pure	Xn	X	1/1	1/3	1/0	2/3	1/0	1/2	1/2	1/2	1/2	2/3	2/3	4/4	1/3	1/1	1/1	1/1	1/1	2/0	3/4	1/0	0/0	1/1	(1)	(1)	0/0	
Butanol, secondary	-> see: Butyl alcohol, secondary																													
Butanol, tertiary	-> see: Butyl alcohol, tertiary																													
Butanol-2	-> see: Butyl alcohol, secondary																													
Butanone	-> see: Methyl ethyl ketone																													
Butanoic acid	-> see: Butyric acid																													
Butanetriol	$C_4H_{10}O_3$	—	100 %	—		(4)	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	3/3	4/4	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)		Isomer not specified in the source
Butene	C_4H_8	—	tech. pure	F+	X	4/4	0/0	1/0	(1)	1/0	0/0	1/0	4/4	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/0	1/0	3/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0	Isomer not specified in the source
Butenal, trans-2-	-> see: Crotonaldehyde																													
Butenedioic acid, cis-	-> see: Maleic acid																													
Butoxyethanol, 2-	-> see: Butyl glycol																													
Butter	—	—		—		1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	3/0	1/0	1/1	0/0	(1)	(1)	(1)		
Buttersäure	$C_4H_8O_2$	000107-92-6		C		3/4	4/4	3/3	4/4	0/0	4/4	4/4	4/4	4/4	2/2	2/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/2	1/2	1/1	1/1	
Butyric acid ethyl ester	-> see: Ethyl butyrate																													
Butyl acetate	-> see: Acetic acid butyl ester																													
Butyl acrylate	$C_7H_{12}O_2$	000141-32-2	100 %	Xi	X	1/2	2/3	2/0	4/4	1/3	2/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/0	
Butyl alcohol	-> see: Butanol																													
Butyl alcohol, secondary	$C_4H_{10}O$	000078-92-2		Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	2/2	2/3	2/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		
Butyl alcohol, tertiary	$C_4H_{10}O$	000075-65-0		F, Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		
Butylamine	$C_4H_{11}N$	000109-73-9		F, C	X	0/0	0/0	0/0	(3)	0/0	0/0	3/4	2/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Butyl carbinol	-> see: Amyl alcohol, n-																													
Butyl cellosolve	-> see: Butyl glycol																													
Butylene	-> see: Butene																													
Butylen glycol	$C_4H_{10}O_2$	—	tech. pure	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	4/4	(1)	0/0	1/1	(1)	(1)	0/0	Isomer not specified in the source
Butyl ether	-> see: Dibutyl ether																													
Butyl ethylene	-> see: Hexene, 1-																													
Butyl glycol	$C_4H_{14}O_2$	000111-76-2	100 %	Xn	X	0/0	1/0	1/0	(2)	1/0	0/0	1/0	1/0	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	1/1	3/0	3/4	3/4	0/0	1/1	(1)	(1)	0/0	
Butylphenol	$C_{10}H_{14}O$	—	100 %	Xi		0/0	1/1	(3)	(3)	0/0	(3)	(4)	1/1	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Isomer not specified in the source
Para tertiary butylphenol	$C_{11}H_{15}NO$	000098-54-4	tech. pure	C, Xn		3/0	0/0	(3)	(3)	0/0	(3)	(4)	1/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1		
Butyl stearate	-> see: Stearic acid butyl ester																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Butyraldehyde	C_4H_8O	000123-72-8		F, Xn	X	0/0	0/0	(3)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Cadmium bromide	CdBr	007789-42-6		T		1/1	1/1	(3)	(2)	(2)	0/0	(3)	(1)	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	4/4	0/0	0/0		
Calcium acetate	$C_4H_6CaO_4$	000062-54-4	aqueous	—		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(2)	(1)	(1)	0/0	
Calcium bicarbonate	$Ca(HCO_3)_2$	—	saturated	—		1/1	1/1	1/1	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	(2)	(1)	(1)	0/0	
Calcium bisulphite	$Ca(HSO_3)_2$	013780-03-5	saturated	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1	
Calcium bisulphite	$Ca(HSO_3)_2$	013780-03-5	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1	
Calcium bromide	$CaBr_2$	007789-41-5		?		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(3)	0/0	0/0	0/0	
Calcium carbide	CaC_2	000075-20-7		F	X	1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0	Carbide, reacts with water to form acetylene - highly flammable!
Calcium carbonate	$CaCO_3$	000471-34-1	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium chlorate	$Ca(ClO_3)_2$	010137-74-3	saturated	O, (T)		0/0	0/0	(3)	(2)	0/0	1/1	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(2)	(1)	(3)	0/0	1/1	(1)	1/0	1/1	
Calcium chloride	$CaCl_2$	010043-52-4	alcoholic	F, Xi		1/0	0/0	4/4	(2)	0/0	1/0	(3)	1/1	0/0	0/0	0/0	4/4	0/0	0/0	1/1	1/0	(1)	(2)	(2)	(2)	0/0	(3)	1/2L	1/2L	1/1	
Calcium chloride	$CaCl_2$	010043-52-4	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/1	(3)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/2L	1/2L	1/1	
Calcium hydrate	-> see: Calcium hydroxide																														
Calcium hydrogen carbonate	-> see: Calcium bicarbonate																														
Calcium hydrogen sulphite	-> see: Calcium bisulphite																														
Calcium hydroxide	CaH_2O_2	001305-62-0	aqueous	(Xi)		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calcium hydroxide	CaH_2O_2	001305-62-0	concentrated.	C		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	2/2	2/2	1/1	1/0	0/0	1/1	1/1	1/1	1/3	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calcium hypochlorite	$Ca(OCl)_2$	007778-54-3	saturated	O, C		1/1	1/1	1/4	3/4	3/0	1/2	1/0	1/1	2/3	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/3	(2)	2/3	4/4	0/0	4/4	3/0	2/0	1/1	Bleaching powder
Calcium hypochlorite	$Ca(OCl)_2$	007778-54-3	aqueous	O, C/Xi		0/0	0/0	4/4	1/0	3/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	4/4	3/0	2/0	1/1	Bleaching powder
Calcium nitrate	$Ca(NO_3)_2$	010124-37-5	50 %	O		1/1	1/1	(2)	1/0	(2)	1/1	(3)	1/1	1/1	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	1/0	1/1	1/1	1/1	
Calcium nitrate	$Ca(NO_3)_2$	010124-37-5	aqueous	O		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/1	1/1	1/1	
Calcium oxide	CaO	001305-78-8	Powder	C		1/0	1/1	(2)	(2)	(2)	0/0	0/0	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	1/1	1/1		
Calcium phosphate	$Ca_3(PO_4)_2$	007758-87-4	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium phosphate	$Ca_3(PO_4)_2$	007758-87-4		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium sulphate	$CaSO_4$	007778-18-9	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	Plaster
Calcium sulphide	CaS	020548-54-3	aqueous	C		0/0	0/0	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	(1)	(1)	0/0	
Calcium sulphide	CaS	020548-54-3		C		0/0	3/3	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Camphor	$C_{10}H_{16}O$	000464-48-2 / -49-2		F, Xn	X	3/4	3/4	(2)	(3)	0/0	0/0	(2)	1/0	1/3	0/0	4/4	4/4	1/1	0/0	(1)	1/0	(3)	4/4	3/4	1/0	0/0	(1)	1/0	1/0	1/0		
Camphor oil	—	008008-51-3		Xn		4/4	4/4	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	(3)	4/4	3/0	1/0	0/0	(1)	(1)	(1)	1/0	made from Cinnamomum Camphora
Paracymene	-> see: Cymene, p-																														
Capronaldehyde	-> see: Hexanal																														
Carbazole	$C_{12}H_9N$	000086-74-8		Xn		1/1	1/1	(2)	4/4	0/0	1/1	(1)	1/1	1/1	4/4	4/4	0/0	4/4	1/1	1/1	(2)	(2)	(2)	(3)	(2)	0/0	(1)	(1)	(1)	0/0	
Carbinol	-> see: Methanol																														
Carbolineum	—	008001-58-9	aqueous	(Xn)		1/0	1/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	(2)	3/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Carbolic acid	-> see: Phenol																														
Carbon disulfide	-> see: Carbon disulphide																														
Carbonyl chloride	-> see: Phosgene																														
Carnauba wax	—	008015-86-9		—		1/1	1/1	1/1	(1)	1/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(3)	(1)	(1)	0/0	1/1	(1)	(1)		
Caesium bromide	CsBr	007787-69-1		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	0/0	0/0		
Cellosolve	-> see: Ethyl glycol																														
Cellosolve acetate	-> see: Ethylene glycol monoethyl ether acetate																														
Cetyl alcohol	$C_{16}H_{34}O$	036653-82-4	100 %	Xi		1/1	1/1	4/4	(2)	1/0	0/0	(1)	1/1	0/0	1/0	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(1)	1/1	1/1		
Cetylic acid	-> see: Palmitic acid																														
Quinine	$C_{20}H_{24}N_2O_2$	000130-95-0		Xn		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)	0/0	
Chlorine	Cl_2	007782-50-5	10 % wet	T		3/4	3/4	4/4	2/3	4/4	2/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	(2)	2/0	3/0	4/4	0/0	4/4	4/4	4/4	0/0	
Chlorine	Cl_2	007782-50-5	97 %	T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0	1/1	
Chlorosulfonic acid	-> see: Chlorosulfunic acid																														
Chlorine-1-propene, 3-	-> see: Allyl chloride																														
Chlor-2-propanone, 1-	-> see: Chloroacetone																														
Chloroacetone	C_3H_5ClO	000078-95-5		(F, Xi)	X	0/0	0/0	(3)	(4)	(4)	(4)	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	0/0	
Chloroacetophenone, p-	C_8H_7ClO	000099-91-2		(Xn)		1/1	1/1	(2)	4/4	0/0	1/1	(2)	1/1	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(2)	(2)	(3)	4/4	4/4	0/0	(1)	0/0	0/0		
Chloral	-> see: Trichloroacetaldehyde																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Chloral hydrate	$C_2H_3Cl_3O_2$	000302-17-0	tech. pure	T/Xi		3/3	3/3	4/4	(3)	(4)	0/0	(3)	3/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	4/4	3/0	3/4	4/4	0/0	4/4	0/0	0/0	0/0	
Chloramine T	$C_7H_7ClNaNSO_2$	000127-65-1	diluted	Xi		1/0	1/0	4/4	1/0	0/0	0/0	(3)	(3)	0/0	0/0	0/0	1/0	0/0	0/0	(1)	1/0	3/4	1/0	4/4	1/0	0/0	3/4	2/2	1/1	0/0	Swimming pool disinfection
Phenyl chloride	-> see: Chlorobenzene																													
Chlorobenzene	C_6H_5Cl	000108-90-7		Xn	X	3/4	3/4	4/4	4/4	1/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/1	(1/1)[1]	(1/1)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chlorine bleach	-> see: Sodium hypochlorite																													
Bromochloromethane	-> see: Bromochloromethane																													
Chlorobutadiene	C_4H_5Cl	000126-99-8		F, Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/4	4/4	0/0	(3)	0/0	0/0		
Chlorobutadiene	-> see: Calcium chloride																													
Chlorodifluoromethane	$CHClF_2$	000075-45-6		N, Xn		0/0	3/0	1/0	3/0	1/0	0/0	1/0	4/4	4/4	4/4	2/0	4/4	0/0	0/0	3/3	1/0	(3)	1/0	4/4	4/4	0/0	(3)	0/0	0/0		
Chlorine dioxide	ClO_2	010049-04-4		E, T		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/0	(2)	4/4	1/0	4/4	0/0	3/4	3/4	3/4		
Chlordodecane	-> see: Lauryl chloride																													
Chloroacetic acid	$C_2H_3ClO_2$	000079-11-8	50 %	T, C		1/3	1/3	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/0	0/0	3/4	0/0	(1)	1/1	1/4	2/0	3/0	4/4	0/0	4/4	2/4	2/4	1/4	
Chloroacetic acid	$C_2H_3ClO_2$	000079-11-8		T, C		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/2	2/4	4/4	3/4	4/4	3/4	1/1	1/1	1/1	4/4	3/0	3/0	4/4	0/0	4/4	4/4	4/4	4/4	
Ethyl monochloroacetate	-> see: Ethyl chloroacetate																													
Chloroethanoic acid methyl ester	-> see: Methyl chloroacetate																													
Chlorethane	C_2H_5Cl	000075-00-3		F+, Xn	X	3/3	3/4	1/0	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/0	4/4	0/0	(3)	(1/1L)[1]	(1/1L)[1]	0/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloroethanol	C_2H_5ClO	000107-07-3	tech. pure	T+		1/1	0/0	4/4	4/4	0/0	0/0	3/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	1/1	1/0	1/3	3/0	4/4	4/4	0/0	(3)	1/0L	1/0L	1/0	
Chloroethyl alcohol, 2-	-> see: Chloroethanol																													
Chloroethylene	C_2H_3Cl	000075-01-4	tech. pure	F+, T	X	0/0	0/0	1/1	(4)	1/1	0/0		(3)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	1/1	3/0	3/0	4/4	0/0	(1)	0/0	0/0	0/0	
Chlorofluoromethane	CH_2ClF	000593-70-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	4/4	0/0	(3)	0/0	0/0		
Chlorine gas	Cl_2	007782-50-5		T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0		
Chlorinated potassium	-> see: Potassium chloride																													
Chlorinated lime	[3 x CaCl(OCl) + Ca(—		aqueous	?		0/0	0/0	4/4	(2)	3/0	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach
Chlorinated lime	[3 x CaCl(OCl) + Ca —			O, C		0/0	0/0	4/4	(2)	3/0	0/0	4/4	1/1	1/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach
Chloromethane	CH_3Cl	000074-87-3	tech. pure	F+, T	X	3/0	2/0	4/4	(3)	0/0	0/0	1/0	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/0	1/0	1/1	4/4	4/4	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]		[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloromethyl	-> see: Chloromethane																													
Chloromethylbenzene	-> see: Benzyl chloride																													
Chloromethyloxirane	-> see: Epichlorohydrin																													
Chloronaphthalene, 1-	$C_{10}H_7Cl$	000090-13-1		Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	4/4	0/0	(2)	1/0	1/0		
Nickel chloride	-> see: Nickel (II) chloride																													
Chloroform	$CHCl_3$	000067-66-3	100 %	Xn		3/4	4/4	3/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	1/1	4/4	3/4	4/4	0/0	(3)	(1/1)[1]	(1/1)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloroprene	-> see: Chlorobutadiene																													
Chloropentafluoroethane	C_2ClF_5	000076-15-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Chloropentane, 1-	-> see: Amyl chloride																													
Chlorophenyl methyl ketone, 4-	-> see: Chloroacetophenone, -p																													
Chloropropane, 2-	-> see: Isopropyl chloride																													
Chloropropylene, 3-	-> see: Allyl chloride																													
Chloric acid	$HClO_3$	007790-93-4	1 %	(C)		0/0	1/1	4/4	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/3	1/0	0/0	0/0	0/0	1/1	1/1	3/0	1/1	(3)	0/0	(3)	4/4	4/4	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Chloric acid	$HClO_3$	007790-93-4	10 %	(O), C		1/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	3/0	3/0	4/4	0/0	4/4	4/4	4/4	1/1	
Chloric acid	$HClO_3$	007790-93-4	20 %	(O), C		3/0	1/4	4/4	(3)	(4)	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/0	3/0	3/0	4/4	0/0	4/4	4/4	4/4	?	
Chlorosulfonic acid	$ClHSO_3$	007790-94-5	tech. pure	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	3/0	4/4	4/4	0/0	0/0	1/0	3/4	4/4	4/4	4/4	0/0	3/3	3/4	3/4	1/0	
Chlorotoluene	C_7H_7Cl	—		Xn		0/0	0/0	(2)	4/4	0/0	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(3)	1/0	1/0	1/1	Isomer not specified in the source
Chlorotoluene, alpha-	-> see: Benzyl chloride																													
Chlorine trifluoride	ClF_3	007790-91-2		(O, T)		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(4)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(4)	4/4	(4)	4/4	0/0	(4)	(4)	(4)		
Chlorotrifluoromethane	$CClF_3$	000075-72-9		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	0/0	
Chlorinated water	$Cl_2 \times H_2O$	007782-50-5		(T)		3/0	0/4	4/4	4/4	4/4	4/4	4/4	3/4	4/4	0/0	3/3	3/0	3/3	1/1	(1)	1/1	1/1	3/0	1/0	4/4	0/0	4/4	2/0L	2/0L	0/0	
Hydrochloric acid gas	HCl	007647-01-0	anhydrous	T, C		1/1	0/0	4/4	(3)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	2/2L	2/2L	0/0	
Hydrochloric gas	-> see: Hydrogen acid																													
Hydronium chloride	-> see: Hydrochloric acid																													
Chlorozinc	-> see: Zinc chloride																													
Chromium (III) potassium sulphate dodecahydrate	-> see: Chrome alum																													
Chromium (VI) oxide	-> see: Chromic acid																													
Chrome alum	$KCr(SO_4)_2 \times 12H_2O$	007788-99-0	saturated	Xn		1/1	0/0	(2)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(3)	1/3	1/3	1/1	
Chromium salts	—	—	any	T/Xn		0/0	0/0	0/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	0/0	K	K	K		
Chromic acid	CrO_3	001333-82-0	10 %	O, T, C, N		1/1	1/1	4/4	2/3	3/0	1/1	4/4	1/1	1/1	4/4	1/2	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	1/2	1/2	1/1	
Chromic acid	CrO_3	001333-82-0	20 %	O, T, C, N		0/0	1/3	4/4	3/4	(4)	0/0	4/4	3/3	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	(2)	(2)	1/1	
Chromic acid	CrO_3	001333-82-0	50 %	O, T, C, N		3/4	3/4	4/4	3/4	(4)	2/3	4/4	3/3	3/3	4/4	1/3	1/0	3/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	(3)	2/3	2/3	1/1	
Chromic acid potassium salt	-> see: Potassium chromate																													
Chromosulphuric acid	$CrO_3 + H_2SO_4$	065272-71-1	concentrated	O, T, C, N		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	4/4	4/4	1/1	0/0	1/1	4/4	4/4	1/0	4/4	4/4	4/4	2/3	2/3	0/0	
Chromium trioxide	-> see: Chromic acid																													
2-Hydroxypropane-1,2,3-tricarboxylic acid	-> see: Citric acid																													
Citric acid tributyl ester	-> see: Tributyl citrate																													
Clophen A60	—	011096-82-5		Xn, N		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	0/0	0/0	0/0	0/0	(1)	(2)	4/4	2/3	4/4	0/0	1/0	1/0	1/0	0/0	ppolychlorinated biphenyls, PCBs; Bayer
Cobalt (II) chloride	$CoCl_2$	007646-79-9	aqueous	Xn		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Cobalt dichloride	-> see: Cobalt (II) chloride																													
Colamine	-> see: Ethanolamine																													
Crotonaldehyde	C_4H_6O	004170-30-3	tech. pure	F, T	X	1/0	0/0	(2)	(4)	0/0	(4)	(2)	1/0	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	1/3	1/0	3/0	4/4	0/0	1/0	1/1	1/1	0/0	
Cumol	-> see: Cumene																													
Cumene	C_9H_{12}	000098-82-8		Xi	X	2/3	3/4	(2)	4/4	0/0	4/4	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Curry	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	3/3	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		could lead to discolouration
Ethyl cyanoacetate	-> see: Ethyl cyanoacetate																													
Cyanide	-> see: Potassium cyanide																													
Cyan potassium	-> see: Potassium cyanide																													
Cyannosodium	-> see: Sodium cyanide																													
Prussic acid	-> see: Hydrogen cyanide																													
Cyclanon	—	—		(Xn, Xi)		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/1	0/0	3/4	(1)	(1)	0/0	Polyquaternary compounds, dyeing auxiliaries; BASF
Cyclohexane	C_6H_{12}	000110-82-7		F	X	3/4	3/4	1/0	3/3	1/0	4/4	1/1	3/4	4/4	4/4	2/3	1/0	1/3	1/2	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Cyclohexanol	$C_6H_{12}O$	000108-93-0	tech. pure	Xn		1/1	1/1	1/1	3/0	0/0	1/2	1/0	1/3	3/3	1/0	1/1	4/4	1/3	0/0	(1)	1/1	1/3	4/4	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Cyclohexanone	$C_6H_{10}O$	000108-94-1	tech. pure	Xn	X	1/3	3/4	1/0	4/4	(4)	3/4	1/0	2/4	4/4	4/4	4/4	4/4	4/4	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Cyclohexylmethane	-> see: Methylcyclohexane																													
Cymene, p-	$C_{10}H_{14}$	000099-87-6		F, Xn/Xi	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Steam	H_2O	—	up to 150°C	?		4	4	4/4	0/0	0	0	(3)	(3)	0	0	0	0	0	0	0/0	1	0	1	3	4/4	0	(1)	1/1	1/1		
DDT (emulsion)	$C_{14}H_9Cl_5$	000050-29-3		T		0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(3)	(3)	0/0	(2)	(2)	(2)	0/0	
Decahydronaphthalene	$C_{10}H_{18}$	000091-17-8		Xn		1/3	3/4	1/0	4/4	3/0	4/4	1/0	3/4	4/4	4/4	1/2	3/0	3/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	(1)	(1)	0/0	
Decalin	-> see: Decahydronaphthalene																													
Decane	$C_{10}H_{22}$	000124-18-5		Xn	X	0/0	0/0	(1)	(2)	(1)	(3)	1/1	(3)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	(1)	(1)		
Decanedioic acid dibenzyl ester	-> see: Dibenzyl sebacate																													
Decanedioic acid dibutyl ester	-> see: Dibutyl sebacate																													
Decanedioic acid diethyl ester	-> see: Diethyl sebacate																													
Dehydroacetic acid	$C_8H_8O_4$	000520-45-6		Xn		0/0	0/0	(3)	(2)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(4)	(1)	(1)		
Densodrin W	—	—	aqueous	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/0	0/0	0/0	1/0	0/0	0/0	0/0	0/0		Hydrophobing agent for leather, silicone derivative; BASF

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Desmodur 44	$C_{15}H_{10}N_2O_2$	000101-68-8		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	0/0	4/4	0/0	(1)	(1)	(1)		
Dextrin	$(C_6H_{10}O_5)_n$ x H_2O	009004-53-9	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Dextrose	-> see: Glucose																														
Diacetone alcohol	$C_6H_{12}O_2$	000123-42-2		Xi	X	0/0	0/0	(3)	(3)	0/0	0/0	1/0	2/2	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(2)	(1)	(1)		
Diamide	-> see: Hydrazine																														
Diaminoethane	-> see: Ethylenediamine																														
Diazane	-> see: Hydrazine																														
Dibenzyl ether	$C_{14}H_{14}O$	000103-50-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Dibenzyl sebacate	$C_{24}H_{26}O_4$	??		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	(4)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dibromoethane-1,2	$C_2H_4Br_2$	000106-93-4		T		(4)	(4)	(2)	(4)	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/2	4/4	(3)	4/4	0/0	(3)	1/0L	1/0L	0/0	
Dibromotetrafluoromethane	$C_2Br_2F_4$	000124-73-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0		
Dibutylamine	$C_8H_{19}N$	000111-92-2		Xn	X	0/0	0/0	(2)	(3)	0/0	(3)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Dibutyl ether	$C_8H_{18}O$	000142-96-1	tech. pure	Xi	X	3/4	1/4	(2)	(3)	1/0	(4)	(1)	3/4	0/0	3/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Dibutyl phthalate	$C_{16}H_{22}O_4$	000084-74-2	FR, 80°C	T		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	(1)	0	0	0	4/4	0	0	0	0	0/0	Plasticiser
Dibutyl phthalate	$C_{16}H_{22}O_4$	000084-74-2		T		1/3	3/3	1/0	4/4	1/0	0/2	1/0	2/2	4/4	1/0	4/4	4/4	0/4	1/1	(1)	1/1	1/3	3/0	2/3	4/4	0/0	(1)	1/1	1/1	0/0	Plasticiser
Dibutyl sebacate	$C_{18}H_{34}O_4$	000109-43-3	tech. pure	—		1/0	1/3	1/0	(3)	0/0	0/0	(2)	1/0	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dichlorocide, 1,2-	-> see: Dichlorobenzene, 1,2-																														
Dichlorocide, 1,4-	-> see: Dichlorobenzene, 1,4-																														
Dichlorobenzene, 1,2-	$C_6H_4Cl_2$	000095-50-1		Xn		3/3	3/4	(1)	4/4	0/0	3/4	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/3	(1)	1/1	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Dichlorobenzene, 1,4-	$C_6H_4Cl_2$	000106-46-7		Xn		2/3	3/4	1/0	4/4	0/0	2/3	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/3	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
DCB, o-	-> see: Dichlorobenzene, 1,2-																														
DCB, p-	-> see: Dichlorobenzene, 1,4-																														
Dichlorodifluoromethane	CCl_2F_2	000075-71-8	tech. pure	N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0	
Dichlorodifluoromethane	CCl_2F_2	000075-71-8		N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0	
Dichlorodiphenyltrichloroethane	-> see: DDT (emulsion)																														
Dichloroacetic acid	$C_2H_2Cl_2O_2$	000079-43-6	50 %	C		1/1	1/1	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1	
Dichloroacetic acid	$C_2H_2Cl_2O_2$	000079-43-6	tech. pure	C		1/3	3/3	4/4	(4)	4/4	0/0	4/4	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1	
Dichloroacetic acid methyl ester	-> see: Methyl dichloroacetate																														
Dichlorethane, 1,2-	-> see: Ethylene chloride																														
Dichlorethene, 1,1-	-> see: Vinylidene chloride																														
Dichloroethylene	$C_2H_2Cl_2$	—	tech. pure	F+, Xn	X	4/4	4/4	3/0	(4)	4/4	(4)	4/4	3/0	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/0	1/1	4/4	3/4	4/4	0/0	(3)	1/1L	1/1L	0/0	Isomer not specified in the source
Dichloroethylene, 1,1-	-> see: Vinylidene chloride																														
Dichlorofluoromethane	$CHCl_2F$	000075-43-4	100 %	N		0/0	3/0	1/0	3/0	0/0	0/0	1/0	4/4	4/4	3/0	4/4	4/4	3/3	0/0	(3)	1/0	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Dichlorohexafluorocyclobutane	$C_4Cl_2F_6$	000356-18-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	(3)	1/0	0/0	(3)	0/0	0/0		
Dichloroisopropyl ether	$C_6H_{12}Cl_2O$	—		(Xn)		(4)	(4)	(2)	(3)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		Isomer not specified in the source
Dichlormethane	CH_2Cl_2	000075-09-2		Xn		4/4	4/4	3/4	4/4	4/4	3/4	3/0	3/4	4/4	4/4	4/4	4/4	4/4	2/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	4/4	(1/1L)[1)]	(1/1L)[1)]	1/1	[1)] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Dichlorpropane	$C_3H_6Cl_2$	—	100 %	F, T/Xn	X	0/0	0/0	(3)	-4	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Dichlorotetrafluoroethane	$C_2Cl_2F_4$	000076-14-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Dicyclohexylamine (DCHA)	$C_{12}H_{23}N$	000101-83-7		C, Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Dicyclohexyl phthalate	$C_{20}H_{26}O_4$	000084-61-7	tech. pure	(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	(3)	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diesel fuel	—	—		Xn, N		1/3	0/0	1/1	3/3	1/1	0/0	1/1	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	(1)	(1)	0/0	
Diesel oil	—	068334-30-5	100 %	(Xn)		1/3	1/4	1/1	3/3	1/1	0/0	1/1	1/3	3/4	0/0	1/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	(1)	(1)	0/0	
Diethanolamine (DEA)	$C_4H_{11}NO_2$	000111-42-2	100 %	Xi		0/0	1/0	(2)	(3)	0/0	0/0	(2)	1/2	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/3	3/0	(3)	4/4	0/0	1/1	(1)	(1)	0/0	
Diethylamine	$C_4H_{11}N$	000109-89-7	tech. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/2	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Diethylbenzene	$C_{10}H_{14}$	000135-01-3		Xi		3/4	4/4	(1)	3/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Diethylene glycol	$C_4H_{10}O_3$	000111-46-6		T		1/1	1/1	3/0	2/3	0/0	1/1	(2)	1/1	2/2	2/2	3/4	0/0	1/1	1/1	1/1	1/1	(2)	1/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0	
Diethylene glycol ether	—	—		(Xn)		1/1	1/1	3/0	3/4	0/0	1/1	(2)	1/1	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	3/0	(3)	3/3	0/0	(1)	(1)	(1)		
Diethyl ether	-> see: Ethyl ether																														
Diethyl ketone	$C_5H_{10}O$	000096-22-0		F		2/2	2/3	(3)	4/4	(4)	2/3	1/0	2/2	4/4	4/4	4/4	0/0	4/4	2/3	1/1	1/1	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	0/0	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Diethylmalonate	$C_7H_{12}O_4$	000105-53-3		Xi		1/1	1/1	(2)	3/4	0/0	1/2	(2)	1/1	4/4	3/3	2/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(4)	(3)	0/0	(1)	(1)	(1)		
Diethylmethane	-> see: Pentane																													
Diethyl sebacate	$C_{14}H_{26}O_4$	000110-40-7		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diethyl succinate	-> see: Succinic acid diethyl ester																													
Difluorochloroethane	$C_2H_3ClF_2$	000075-68-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluoroethane	$C_2H_2F_2$	000075-37-6		(E), F+		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluoromethane	CH_2F_2	000075-10-5		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluorotetrachloroethane	$C_2Cl_4F_2$	000076-12-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0		
Diglycol	-> see: Diethylene glycol																													
Diglycolic acid	$C_4H_6O_5$	000110-99-6	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/1	4/4	0/0	3/4	1/4	1/4	1/1	
Diglycolic acid	$C_4H_6O_5$	000110-99-6	30 %	Xn, Xi		1/1	1/1	(3)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/0	1/0	1/1	4/4	0/0	3/4	1/4	1/4	1/1	
Dihexyl phthalate	-> see: Dicyclohexyl phthalate																													
Dihydroxybenzene, 1,3-	-> see: Resorcinol																													
Dihydroxybenzene, 1,4-	-> see: Hydroquinone																													
Dihydroxysuccinic acid	-> see: Tartaric acid																													
Dihydroxydiethylamine	-> see: Diethanolamine																													
Diisobutylene (DIB)	C_8H_{16}	025167-70-8		F	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	1/2	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Diisobutylketone	$C_9H_{18}O$	000108-83-8	tech. pure	Xi	X	1/4	1/3	(3)	(3)	(4)	(4)	1/0	1/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/3	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Diisooctyl phthalate (DOP)	$C_{24}H_{38}O_4$	000117-81-7	tech. pure	Xn		4/4	4/4	1/0	4/4	1/0	1/0	(2)	4/4	4/4	1/0	4/4	4/4	0/0	0/0	1/1	1/0	(2)	3/0	2/3	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diisopropyl ether	-> see: Isopropyl ether																													
Diisopropyl ketone	$C_7H_{14}O$	000565-80-0		F	X	0/0	0/0	(3)	(3)	(4)	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Dimethylamine	C_2H_7N	000124-40-3	tech. pure	F+, Xn	X	1/3	1/3	1/0	4/4	0/0	0/0	(2)	1/3	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	3/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Dimethylaniline	$C_8H_{11}N$	—		T		0/0	0/0	(3)	4/4	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Dimethylbenzene	-> see: Xylene																													
Dimethylcarbinol	-> see: Isopropyl																													
Dimethyl ether	C_2H_6O	000115-10-6	Gas	F+	X	0/0	3/0	1/0	(3)	1/0	0/0	(2)	4/4	4/4	0/0	3/0	4/4	0/0	0/0	0/0	1/0	(3)	3/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Dimethylformamide (DMF)	C_3H_7NO	000068-12-2		T, F	X	1/1	1/3	1	4/4	1/0	1/1	1/2	1/1	4/4	4/4	3/4	0/0	4/4	2/2	1/1	1/1	4/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Dimethyl ketone	-> see: Acetone																													
Dimethylpentanone-3, 2,4-	-> see: Diisopropyl ketone																													
Dimethyl phthalate (DMP)	$C_{10}H_{10}O_4$	000131-11-3	100 %	(Xn)		4/4	1/3	(2)	4/4	0/0	0/0	(2)	2/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(2)	3/0	2/0	4/4	0/0	(1)	(1)	(1)	0/0	Plasticiser
Dimethylpropane	-> see: Pentane																													
Dimethyl sulphoxide (DMSO)	C_2H_6SO	000067-68-5		Xi		1/1	1/1	(2)	4/4	0/0	1/1	1/0	1/1	1/2	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(3)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		
Disodium hydrogen phosphate	-> see: Disodium phosphate																													
Disodium phosphate	Na_2HPO_4	007558-79-4		(Xi)		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	(1)	1/1	1/1	0/0	
Disodium sulphate	-> see: Sodium sulphate																													
Dinonyl phthalate (DNP)	$C_{26}H_{42}O_4$	000084-76-4	tech. pure	Xn		3/0	0/0	(2)	3/0	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioctyladipate	$C_{22}H_{42}O_4$	000103-23-1		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioctyl phthalate	-> see: Diisooctyl phthalate																													
Dioctyl sebacate	$C_{26}H_{50}O_4$	002432-87-3		—		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioxane	$C_4H_8O_2$	000123-91-1		F, Xn	X	2/2	2/3	1/0	4/4	1/0	2/3	1/2	3/3	4/4	2/3	3/4	4/4	4/4	1/3	1/1	1/1	3/3	2/0	4/4	4/4	0/0	1/1	1/0	1/0	0/0	
Dioxane, 1,4-	-> see: Dioxane																													
Dipentene	-> see: Limonene, DL-																													
Dipentyl phthalate	-> see: Phthalic acid amyl ester																													
Diphenylamine	$C_{12}H_{11}N$	000122-39-4		T		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	0/0	
Diphenyleneimine	-> see: Carbazole																													
Diphenyl ether	$C_{12}H_{10}O$	000101-84-8		Xn/Xi		0/0	1/0	3/0	(3)	(4)	0/0	1/1	4/4	4/4	0/0	0/0	4/4	4/4	0/0	(1)	1/0	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Diphenylmethane diisocyanate (MDI)	-> see: Desmodur 44																													
Diphenyl oxide	-> see: Diphenyl ether																													
Diphosphorus pentoxide	-> see: Phosphorus pentoxide																													
Diphyl	—	008004-13-5		?		0/0	0/0	1/1	(3)	4/4	0/0	1/1	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)		Mixture of diphenyl and diphenyl ether; Bayer
Dipropylene glycol	$C_6H_{14}O_3$	025265-71-8		Xi		1/1	1/1	(2)	2/3	0/0	1/1	1/0	1/1	1/1	2/2	2/3	0/0	0/0	1/1	1/1	(1)	(2)	4/4	3/0	3/3	0/0	(1)	(1)	(1)		
Dipropyl ketone	$C_7H_{14}O$	000123-19-3		—	X	0/0	0/0	(3)	(4)	(4)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Dipropylmethane, n-	-> see: Heptane, n-																													
Di-sulphur dichloride	-> see: Sulphur chloride																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals		
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Dinitrogen tetroxide	-> see: Nitrogen tetroxide																													
Disulphite	-> see: Sodium disulphite																													
Divinylensulphide	-> see: Thiophene																													
Dodecanol	-> see: Lauryl alcohol																													
Dodecyl alcohol	-> see: Lauryl alcohol																													
Dodecyl chloride	-> see: Lauryl chloride																													
Dolcymene	-> see: Cymene, p-																													
Eau de Labarraque	-> see: Sodium hypochlorite																													
Edetic acid	-> see: Ethylenediaminetetraacetic acid																													
Iron (II) ammonium sulphate	-> see: Ammonium iron (II) sulphate																													
Iron (II) chloride	$FeCl_2$	007758-94-3	saturated	Xn		1/1	1/1	3/0	1/0	(2)	1/0	(3)	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	(1)	0/0	4/4	(2)	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7	saturated	(Xn)		1/1	1/1	(2)	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7	aqueous	(Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7		Xn		1/1	1/1	(2)	1/0	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/0	(1)	0/0	4/4	1/1	1/1	1/1	
Iron (III) chloride	$FeCl_3$	007705-08-0	saturated	Xn		1/1	1/1	3/0	1/0	0/0	1/0	4/4	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	4/4	4/4	4/4	1/1	
Iron (III) nitrate	-> see: Ferric nitrate																													
Iron (III) sulphate	$Fe_2(SO_4)_3$	010028-22-5	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1	
Iron alum	-> see: Ammonium iron (III) sulphate																													
Iron ammonium alum	-> see: Ammonium iron (III) sulphate																													
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	aqueous	(O, Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	saturated	O, Xn		1/1	1/1	1/0	1/0	0/0	1/0	(3)	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Iron vitriol	-> see: Iron (II) sulphate																													
Glacial acetic acid	-> see: Acetic acid																													
Elaol	-> see: Dibutyl phthalate																													
Emulsifiers	—	—		?		0/0	0/0	(2)	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(3)	0/0	0/0	K	K		
Developer fluids	—	—		?		1/1	1/1	4/4	1/0	1/0	0/0	1/0	1/1	0/0	1/0	1/1	1/0	0/0	0/0	0/0	1/1	(1)	2/0	1/0	3/3	0/0	1/1	1/0	1/0	0/0	
Limescale	—	—	10% in Water	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Epichlorohydrin	C_3H_5ClO	000106-89-8	100 %	F, T	X	1/0	1/0	4/4	(4)	0/0	(4)	1/0	2/2	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(3)	3/0	4/4	4/4	0/0	(3)	0/0	0/0	0/0	
Epoxypropane	-> see: Propylene oxide																													
Epsom salt	-> see: Magnesium sulphate																													
Natural gas	—	—		F+	X	0/0	0/0	01/0	1/0	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	0/0	mainly methane
Peanut oil	—	008002-03-7		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Crude oil / petroleum	—	008002-05-9		(Xn)		0/0	0/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/3	0/0	(1)	(1)	(1)	0/0	Kerosene, lamp oil
Vinegar	$C_2H_4O_2$	000064-19-7		(Xi)		1/1	1/3	4/4	1/2	1/1	1/0	1/3	1/1	1/0	1/0	1/0	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/2	1/1	Wine vinegar, acetic acid
Acetic ester	-> see: Ethyl acetate																													
Acetic acid	$C_2H_4O_2$	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	90%	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1	1/1	
Acetic acid Silver salt	-> see: Silver acetate																													
Acetic alumina	$C_4H_7AlO_5 \times H_2O$	000142-03-0	saturated	Xi		1/1	1/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1		
Acetic acid allyl ester	-> see: Allyl acetate																													
Acetic acid amide	-> see: Acetamide																													
Acetic anhydride	$C_4H_6O_3$	000108-24-7	tech.pure	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1	1/1	
Acetic acid benzyl ester	-> see: Benzyl acetate																													
Acetic acid butyl ester	$C_6H_{12}O_2$	000123-86-4	100 %	—	X	2/2	2/3	1/0	4/4	3/0	3/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	3/0	4/4	4/4	0/0	1/1	(1)	(1)	4/4	
Acetic acid chloride	-> see: Acetyl chloride																													
Acetic acid ethyl ester	-> see: Ethyl acetate																													
Acetic acid isobutyl ester	-> see: Isobutyl acetate																													
Acetic acid isopropyl ester	-> see: Isopropyl acetate																													
Acetic acid methyl ester	$C_3H_6O_2$	000079-20-9	tech. pure	F	X	1/0	1/1	1/0	4/4	3/0	(4)	2/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Acetic acid-n-amyl ester	-> see: Amyl acetate, n-																													
Acetic acid pentyl ester	-> see: Amyl acetate, n-																													
Acetic acid propyl ester	-> see: Propyl acetate																													
Acetic acid vinyl ester	-> see: Vinyl acetate																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ethanal	-> see: Acetaldehyde																													
Ethane carboxylic acid	-> see: Propionic acid																													
Ethanediamine	-> see: Ethylenediamine																													
Ethanedicarboxylic acid	-> see: Succinic acid																													
Ethanediol	-> see: Ethylene glycol																													
Ethanedioic acid	-> see: Oxalic acid																													
Ethanol	C_2H_6O	000064-17-5	40 %	—	X	1/1	1/2	1/0	1/2	1/1	1/2	1/2	1/1	2/3	1/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Ethanol	C_2H_6O	000064-17-5	50 %	—	X	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	
Ethanol	C_2H_6O	000064-17-5	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	
Ethanolamine	C_2H_7NO	000141-43-5		Xn/Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/2	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Ethanoic acid	-> see: Acetic acid																													
Ethanethiol	C_2H_6S	000075-08-1		F, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ethene	-> see: Ethylene																													
Ether	-> see: Ethyl ether																													
Ethyne	-> see: Acetylene																													
Ethinylcarbiol	-> see: Propargyl alcohol																													
Ethoxyacetanilide, 4-	-> see: Phenacetin																													
Ethoxyethanol	-> see: Ethyl glycol																													
Ethoxyethyl acetate, 2-	-> see: Ethylene glycol monoethyl ether acetate																													
Ethyl(hydroxymethyl)-propanediol	-> see: Trimethylolpropane																													
Ethyl acetate	$C_4H_8O_2$	000141-78-6	100 %	F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/1	1/3	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	3/3	3/0	4/4	4/4	0/0	1/1	(1)	(1)	1/0	
Ethyl acrylate	$C_5H_8O_2$	000140-88-5	100 %	F, Xn	X	4/4	4/4	1/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	3/0	4/4	4/4	4/4	0/0	(1)	(1)	(1)	1/0	
Ethyl alcohol	-> see: Ethanol																													
Ethylbenzol	-> see: Ethylbenzene																													
Ethyl benzoate	-> see: Benzoic acid ethyl ester																													
Ethylbenzene	C_8H_{10}	000100-41-4		F, Xn	X	2/3	3/4	(2)	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	1/1	4/4	(2)	4/4	0/0	(1)	(1)	(1)	0/0	
Ethyl butyrate	$C_6H_{12}O_2$	000105-54-4		F	X	2/3	2/4	(2)	4/4	0/0	3/4	(2)	2/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethylcarbinol	-> see: Propanol																													
Ethyl cellosolve	-> see: Ethyl glycol																													
Ethyl chloroacetate	$C_4H_7ClO_2$	000105-39-5	tech. pure	T/Xi		1/1	1/1	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/4	3/4	0/0	0/0	(1)	1/1	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Ethyl chloride	-> see: Chlorethane																													
Ethyl cyanoacetate	$C_5H_7NO_2$	000105-56-6		Xn/Xi		1/1	1/1	0/0	3/4	0/0	1/1	(2)	1/1	2/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Ethylene	C_2H_4	000074-85-1		F+	X	0/0	0/0	1/0	(2)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	(3)	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Ethylene(di)bromide	-> see: Dibromoethane-1,2																													
Ethylene(di)chloride	-> see: Dichloroethane-1,2																													
Ethylene chlorohydrin	-> see: Chloroethanol																													
Ethylene chloride	$C_2H_4Cl_2$	—		F, T	X	3/3	2/4	3/0	4/4	4/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/3	1/1L	1/1L	0/0	Isomer not specified in the source
Ethylenediamine	$C_2H_8N_2$	000107-15-3	tech. pure	C, Xn	X	1/1	1/3	1/0	(3)	0/0	1/0	1/0	1/1	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/4	1/0	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Ethylenediaminetetraacetic acid (EDTA)	$C_{10}H_{16}N_2O_8$	000060-00-4		Xi		1/1	1/1	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(3)	0/0	0/0	0/0	
Ethylene dichloride	-> see: Ethylene chloride																													
Ethylenedinitrilotetraacetic acid	-> see: Ethylenediaminetetraacetic acid																													
Ethylene glycol	$C_2H_6O_2$	000107-21-1		Xn		1/1	1/1	3/3	2/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	1/1	
Ethylene glycol ethyl ether	-> see: Ethyl glycol																													
Ethylene glycol monobutyl ether	-> see: Butyl glycol																													
Ethylene glycol monobutyl ether	-> see: Ethyl glycol																													
Ethylene glycol monoethyl ether acetate	$C_6H_{12}O_3$	000115-15-9		Xn	X	1/1	1/2	0/0	3/4	0/0	1/2	(2)	1/2	4/4	4/4	3/4	0/0	0/0	1/2	1/1	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Ethylene glycol monomethyl ether	-> see: Methyl glycol																													
Ethylene oxide	C_2H_4O	000075-21-8		F+, T	X	2/3	3/3	3/0	3/4	1/0	3/4	1/0	3/3	4/4	1/1	3/4	0/0	0/0	1/1	1/1	(1)	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Ethylene tetrachloride	-> see: Perchloroethylene																													
Ethylene trichloride	-> see: Trichloroethylene																													
Ethylethanamine, N-	-> see: Diethylamine																													
Ethyl ether	$C_4H_{10}O$	000060-29-7	tech. pure	F+, Xn	X	3/4	4/4	1/1	4/4	1/0	4/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Ethyl formate	$C_3H_6O_2$	000109-94-4		F	X	0/0	0/0	0/0	(4)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethyl glycol	$C_4H_{10}O_2$	000110-80-5	100 %	T	X	0/0	4/4	(3)	(2)	0/0	0/0	1/0	2/4	4/4	1/0	4/4	4/4	4/4	0/0	1/1	1/0	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Ethyl glycol acetate	-> see: Ethylene glycol monoethyl ether acetate																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ethylhexanol-1	$C_8H_{18}O$	000104-76-7		Xn/Xi		0/0	1/3	(2)	(2)	(1)	1/0	1/0	1/0	3/0	0/0	1/0	4/4	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	
Ethyl lactate	$C_5H_{10}O_3$	000097-64-3		—	X	1/1	1/1	(2)	3/4	0/0	1/1	(2)	1/1	3/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	3/0	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Ethyl malonate	-> see: Diethylmalonate																													
Ethyl mercaptan	-> see: Ethanethiol																													
Ethyl methyl ketone	-> see: Methyl ethyl ketone																													
Ethyl silicate	-> see: Tetraethylorthosilicate																													
Eucalyptus oil	—	008000-48-8		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Desiccator grease	—	—		—		0/0	1/3	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(2)	(2)	0/0	(1)	(1)	(1)	0/0	
Ferrichloride	-> see: Iron (III) chloride																													
Potassium hexacyanoferrate(III)	$C_6FeK_3N_6$	013746-66-2	any	Xn		1/1	1/1	1/0	(1)	(1)	0/0	2/0	1/1	1/1	0/0	1/3	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1	1/1	
Ferrous chloride	-> see: Iron (II) chloride																													
Potassium hexacyanoferrate(II)	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	saturated	—		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(1)	1/1	1/1		
Potassium hexacyanoferrate(II)	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	diluted	—		1/0	1/1	1/0	(1)	(1)	0/0	2/0	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1		
Fat/Grease, mineral	—	—		(—)		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	(1)	1/0	0/0	(1)	1/1	1/1		
Fat/Grease, vegetable	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fat/Grease, animal	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fatty/Greasy alcohol sulphonates	—	—	aqueous	(Xn, Xi)		1/1	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	1/1	0/0	3/4	1/0	1/0	0/0	Fatty alcohol sulphates, wetting agents/surfactants
Fat/Grease, edible oil	—	—		—		0/0	1/0	1/0	1/0	1/0	1/0	1/1	3/0	0/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Fatty acid C16	-> see: Palmitic acid																													
Spruce needle oil	—	008008-80-8		?		1/2	2/4	(2)	2/3	0/0	2/3	(2)	1/2	4/4	3/3	3/4	0/0	3/4	1/2	1/1	(1)	(2)	4/4	1/0	3/3	0/0	(1)	(1)	(1)		Pinus sylvestris
Fish oil	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/4	1/0	1/0	0/0	(1)	(1)	(1)		
Fixing salt	-> see: Sodium thiosulphate																													
Aircraft engine fuels (JP)	—	—		(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	1/0	1/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	1/0	1/0	0/0	(1)	(1)	(1)		
Fluid 101, 100°C	—	—		?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	3	0	0	0	0		Brake fluid, polyglycol base
Fluorine	F_2	007782-41-4		O, T+, C+		4/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	4/4	4/4	3/0	4/4	0/0	4/4	(4)	(4)	0/0	
Fluorammonium	-> see: Ammonium fluoride																													
Fluorobenzene	C_6H_5F	000462-06-6		F, (Xn)	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0		
Fluorochloroalkanes (FCKW)	—	—		N		0/0	0/0	(2)	(3)	0/0	0/0	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(3)	(3)	0/0	(3)	0/0	(3)	0/0	0/0		Resistance varies depending on type
Fluorides	—	—		T		1/1	1/1	(2)	1/1	(2)	1/1	(1)	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	(1)	0/0	0/0	K	K		
Fluoropotassium	-> see: Potassium fluoride																													
Fluorosilicic acid	-> see: Silicofluoric acid																													
Fluorocarbons (FKW)	—	—		?		0/0	0/4	(2)	(3)	(2)	0/0	(2)	(3)	4/4	0/0	0/0	0/0	0/4	1/1	0/0	1/1	(3)	(3)	(3)	(3)	0/0	(1)	0/0	0/0		Resistance varies depending on type
Fluorosilicic acid	-> see: Silicofluoric acid																													
Fluorotrichloromethane	-> see: Trichlorofluoromethane																													
Hydrogen fluoride	HF	007664-39-3	anhydrous	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)		Hydrofluoric acid, anhydrous
Hydrogen fluoride solution	-> see: Hydrofluoric acid																													
Hydrofluoric acid	-> see: Hydrofluoric acid																													
Liquid soaps	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(2)	(2)	0/0	(3)	0/0	0/0		
Hydrofluoric acid	HF	007664-39-3	4 %	T, C		1/1	1/2	4/4	2/3	4/4	1/2	4/4	1/2	2/3	2/3	2/3	0/0	0/0	1/1	1/1	1/1	1/1	(3)	1/3	(2)	0/0	4/4	0/0	0/0	?	
Hydrofluoric acid	HF	007664-39-3	50 %	T+, C		1/1	1/1	4/4	4/4	4/4	1/1	4/4	1/1	4/4	3/4	2/3	2/0	3/3	1/1	1/1	1/1	1/1	3/4	1/3	3/4	0/0	4/4	4/4	4/4	?	
Hydrofluoric acid	HF	007664-39-3	70 %	T+, C		0/0	1/3	4/4	4/4	4/4	0/0	4/4	1/3	4/4	4/4	1/4	3/0	0/0	0/0	(1)	1/1	1/1	3/4	(3)	4/4	0/0	4/4	4/4	4/4	?	
Hydrofluoric acid	HF	007664-39-3	100 %	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)	?	
Hydrofluoric acid, anhydrous	-> see: Hydrogen fluoride																													
Formaldehyde solution	CH_2O	000050-00-0	10 %	Xn		1/1	1/1	3/3	1/2	1/0	1/2	1/2	1/1	3/4	2/3	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/0	3/0	(2)	0/0	1/1	1/1	1/1	1/1	
Formaldehyde solution	CH_2O	000050-00-0	30 %	T		1/1	1/1	3/3	1/2	1/0	0/0	1/2	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	1/1	1/1	
Formaldehyde solution	CH_2O	000050-00-0	40 %	T		1/2	2/3	1/3	1/2	1/0	1/2	1/2	1/2	4/4	2/3	2/3	3/3	0/4	1/1	1/1	1/1	1/1	1/0	3/0	(3)	0/0	1/1	1/1	1/1	1/1	
Formalin	-> see: Formaldehyde solution																													
Formamide	CH_3NO	000075-12-7	tech. pure	T/Xi		1/1	1/1	1/0	(3)	0/0	0/0	1/0	1/1	1/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	3/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	
Formin	-> see: Hexamethylenetetramine																													
Formylic acid	-> see: Formic acid																													
Photo emulsions	—	—		?		1/0	0/0	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(1)	0/0	(2)	0/0	0/0		
Photo developers	—	—		?		1/3	1/1	4/4	(2)	1/0	0/0	1/3	1/2	0/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Photo fixing baths	—	—		?		1/0	1/1	1/0	(2)	0/0	0/0	1/0	1/1	0/0	0/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/0	1/0		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Freon 11	-> see: Trichlorofluoromethane																													
Freon 112	-> see: Difluorotetrachloroethane																													
Freon 113	-> see: Trichlorotrifluoroethane																													
Freon 114	-> see: Dichlorotetrafluoroethane																													
Freon 114 B2	-> see: Dibromotetrafluoromethane																													
Freon 115	-> see: Chloropentafluoroethane																													
Freon 12	-> see: Dichlorodifluoromethane																													
Freon 13	-> see: Chlorotrifluoromethane																													
Freon 13 B1	-> see: Bromotrifluoromethane																													
Freon 14	-> see: Tetrafluoromethane																													
Freon 142b	-> see: Difluorochloroethane																													
Freon 152a	-> see: Difluoroethane																													
Freon 21	-> see: Dichlorofluoromethane																													
Freon 218	-> see: Perfluoropropane																													
Freon 22	-> see: Chlorodifluoromethane																													
Freon 31	-> see: Chlorofluoromethane																													
Freon 32	-> see: Difluoromethane																													
Freon C 318	-> see: Octafluorocyclobutane																													
Freon C316	-> see: Dichlorohexafluorocyclobutane																													
Frigen 12	-> see: Dichlorodifluoromethane																													
Frigen 21	-> see: Dichlorofluoromethane																													
Frigen 22	-> see: Chlorodifluoromethane																													
Antifreeze (KFZ)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1	1/1	Glycol-water mixtures
Fruit juices	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(2)	1/1	1/1	1/1	
Fruit sugar	-> see: Fructose																													
Fructose	$C_6H_{12}O_6$	000057-48-7	any	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Furan	C_4H_4O	000110-00-9		F+, T+	X	0/0	0/0	(3)	4/4	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Furanal	-> see: Furfural																													
Furancarbinol, 2-	-> see: Furfuryl alcohol																													
Furanmethanol, 2-	-> see: Furfuryl alcohol																													
Furfurol	-> see: Furfural																													
Furfural alcohol	-> see: Furfuryl alcohol																													
Furfuran	-> see: Furan																													
Furfural	$C_5H_4O_2$	000098-01-1		T		1/3	3/4	3/3	(3)	1/0	0/0	2/0	4/4	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	1/2	3/0	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Furfuryl alcohol	$C_5H_6O_2$	000098-00-0	tech. pure	Xn		1/1	1/3	1/0	(3)	1/0	0/0	1/0	1/3	0/0	4/4	4/4	4/4	3/4	0/0	(1)	1/1	1/3	3/0	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Furylaldehyde, 2-	-> see: Furfural																													
Furylmethanal, 2-	-> see: Furfural																													
Gallotannin	-> see: Tannin																													
Gallic acid	$C_7H_6O_5 \times H_2O$	000149-91-7		Xi		1/1	1/1	1/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/4	3/0	1/0	3/0	0/0	1/0	1/1	1/1	1/1	
Fermentation amyl alcohol	-> see: Isoamyl alcohol																													
Fermentation mash	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(1)	1/0	4/4	0/0	(2)	(1)	(1)	0/0	
Gas oil (straight-run)	—	—		(Xn)		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Gasoline	—	008006-61-9		(F, Xn)	X	0/0	0/0	(1)	3/4	(2)	0/0	1/2	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/0	0/0	1/1	(1)	(1)		
Gas water	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(2)	0/0	(2)	0/0	0/0		
Gelatine	—	009000-70-8	any	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Genantin	—	—		Xn		0/0	0/0	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		Antifreeze, basis glycol; Clariant
Tanning extracts, vegetable	—	—	tech. common	?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Tanning extracts	—	—		?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Tannic acid	-> see: Tannin																													
Gear oil, EP (hypoid), 110°C	—	—		?		0	0	1	1	1	0	4	(3)	0	0	0	0	0	0	0	(2)	0	4/4	0	4/4	0	(1)	1	1		
Plaster	-> see: Calcium sulphate																													
Glauber's salt	-> see: Sodium sulphate																													
Glucaric acid	-> see: Sugar acid																													
Glucose	$C_6H_{12}O_6$	000050-99-7	any	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Glucose syrup	-> see: Starch syrup																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Glycerine	$C_3H_8O_3$	000056-81-5	any	Xi		1/1	1/1	1/0	3/3	1/0	1/1	1/0	1/1	1/1	1/1	1/1	2/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Glycerol trinitrate	-> see: Nitroglycerin																													
Glycine	-> see: Aminoacetic acid																													
Glycol	-> see: Ethylene glycol																													
Glycol dinitrate	-> see: Nitroglycol																													
Glycolic acid	$C_2H_4O_3$	000079-14-1	37 %	Xn		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	2/0	1/0	0/0	1/0	1/3	1/3	1/1	
Glycolic acid	$C_2H_4O_3$	000079-14-1	70 %	C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(2)	1/0	3/0	(2)	0/0	(2)	1/3	1/3	1/1	
Glycocoll	-> see: Aminoacetic acid																													
Glycol chlorohydrin	-> see: Chloroethanol																													
Glysantin	—	—		Xn		1/1	1/1	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		Antifreeze, basis glycol; BASF
Glycerol triacetate	-> see: Triacetin																													
Firedamp	—	—		F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		mainly methane
Uric acid	$C_5H_4N_4O_3$	000069-93-2		Xi		1/1	1/1	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	4/4	1/1	1/1	0/0	
Urea	CH_4N_2O	000057-13-6	aqueous	Xi		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, carbamide, etc.
Urea	CH_4N_2O	000057-13-6		Xi		1/1	1/1	1/0	1/1	1/0	1/2	1/1	1/1	1/2	3/3	2/4	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, carbamide, etc.
HD oil engine oil, aromatics-free	—	—		?		1/0	1/3	1/0	1/1	1/1	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	(1)	3/3	0/0	1/1	1/1	1/1		
Yeast	—	—	any	—		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	(1)	(1)		
Heating oil	—	—		Xn		3/3	3/4	1/0	3/3	1/0	2/3	1/1	1/3	3/4	1/2	1/1	3/3	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Helium	He	007440-59-7		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	1/0	1/0	1/0	0/0	1/1	1/1	1/1		
Hendecanol	-> see: Undecyl alcohol																													
Henkel-P3-solution	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/0	0/0	0/0	1/1	1/1		Cleaning agents
Heptan, n-	C_7H_{16}	000142-82-5		F, Xn	X	2/3	3/4	1/0	1/2	1/0	3/3	1/2	2/4	4/4	1/2	2/3	4/4	1/0	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Heptanol, 1-	$C_7H_{16}O$	000111-70-6		Xn		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	(1)	(1)	(1)		
Heptanon	$C_7H_{14}O$	—		(Xn)	X	0/0	0/0	(3)	(4)	(4)	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(4)	(4)	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Heptanon-4	-> see: Dipropylketone																													
Heptyl alcohol	-> see: Heptanol, 1-																													
Hexachlorobenzene (HCB)	C_6Cl_6	000118-74-1		T		0/0	0/0	(3)	(4)	0/0	(4)	1/0	(3)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(2)	0/0	4/4	(3)	4/4	0/0	(1)	0/0	0/0		
Hexachlorobutadiene (HCBD)	C_4Cl_6	000087-68-3		T		0/0	0/0	(3)	4/4	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexachlorocyclohexane (HCH)	$C_6H_6Cl_6$	000319-84-6		T		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexadecanol	-> see: Cetyl alcohol																													
Hexadecanoic acid	-> see: Palmitic acid																													
Hexadecyl alcohol	-> see: Cetyl alcohol																													
Hexahydrobenzene	-> see: Cyclohexan																													
Hexahydrophenol	-> see: Cyclohexanol																													
Hexahydropyridine	-> see: Piperidine																													
Hexahydrotoluene	-> see: Methylcyclohexane																													
Hexaldehyde	-> see: Hexanal																													
Hexamethylenetetramine	$C_6H_{12}N_4$	000100-97-0		F, Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	1/1	1/1	0/0	
Hexamine	-> see: Hexamethylenetetramine																													
Hexane, n-	C_6H_{14}	000110-54-3		F, Xn	X	2/3	4/4	1/0	(2)	1/0	3/4	1/1	2/3	4/4	1/2	2/4	4/4	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Hexanal	$C_6H_{12}O$	000066-25-1		F, Xi	X	0/0	0/0	0/0	(4)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Hexanedioic acid	-> see: Adipic acid																													
Hexanol, (1-)	$C_6H_{14}O$	000111-27-3		Xn		1/0	1/0	(2)	(2)	(1)	0/0	(1)	1/2	0/0	3/0	1/0	3/0	1/3	0/0	(1)	1/0	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Hexanone-2	-> see: Methyl butyl ketone																													
Hexanetriol	$C_6H_{14}O_3$	—	100 %	?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	1/1	3/3	1/1	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Hexen, 1-	C_6H_{12}	000592-41-6		F, Xn	X	0/0	0/0	1/0	(2)	(1)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Hexylaldehyde	-> see: Hexanal																													
Hexyl alcohol	-> see: Hexanol, (1-)																													
Hexylene	-> see: Hexen, 1-																													
Staghorn salt	-> see: Ammonium carbonate																													
Wood alcohol	-> see: Methanol																													
Wood oil	—	008001-20-5		—		0/0	0/0	(1)	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	1/1	(1)	(1)		
Wood tar oil	-> see: Creosote																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Honey	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	0/0	(1)	(1)	(1)	0/0	
Gibbsite	-> see: Aluminium hydroxide																													
Hydraulic fluids, HFA	—	—	50°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFB	—	—	50°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFC	—	—	60°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	0	0	1	0	(2)	0	0		
Hydraulic fluids, HFD-R	—	—	100°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic fluids, HFD-S	—	—	100°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic oils (mineral oil based)	—	—		?		0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	(1)	1/0	0/0	1/1	1/1	1/1		
Hydrazine	N_2H_4	000302-01-2	10 %	T	X	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	1/1	
Hydrazine hydrate	N_2H_6O	010217-52-4	aqueous	(T, C)	(X)	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	0/0	
Hydrazinium hydroxide	-> see: Hydrazine hydrate																													
Hydrazinobenzene	-> see: Phenylhydrazine																													
Hydroquinone	$C_6H_6O_2$	000123-31-9	saturated	Xn		0/0	1/3	4/4	(3)	1/0	0/0	(3)	1/0	4/4	0/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	4/4	4/4	0/0	(1)	1/0	1/0	0/0	
Hydrosulphite	-> see: Sodium dithionite																													
Hydroxy-4-methyl-2-pentanone, 4-	-> see: Diacetone alcohol																													
Hydroxybenzaldehyde, 2-	-> see: Salicylaldehyde																													
Hydroxybenzoic acid, 2-	-> see: Salicylic acid																													
Hydroxybenzene	-> see: Phenol																													
Hydroxybenzenecarboxylic acid, 2-	-> see: Salicylic acid																													
Hydroxyacetic acid	-> see: Glycolic acid																													
Hydroxylamine sulphate	-> see: Hydroxylammonium sulphate																													
Hydroxylammonium sulphate	$H_8N_2SO_6$	010039-54-0	12 %	Xn		1/1	1/1	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	1/1	
Hydroxylammonium sulphate	$H_8N_2SO_6$	010039-54-0	any	Xn		1/1	0/0	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	1/1	
Hydroxymethoxybutane	-> see: Methoxybutanol																													
Hydroxymethylfuran, 2-	-> see: Furfuryl alcohol																													
Hydroxymethylfurfural, 5-	-> see: Oxymethylfurfurol, 5-																													
Hydroxymethyl tetrahydrofuran, 2-	-> see: Tetrahydrofurfuryl alcohol																													
Hydroxypropane	-> see: Propanol																													
Hydroxypropane, 2-	-> see: Isopropyl																													
Hydroxypropionic acid, 2-	-> see: Lactic acid																													
Hydroxypropionic acid ethyl ester, 2-	-> see: Ethyl lactate																													
Hydroxytoluene	-> see: Cresol (-mixtures)																													
Iminodiethanol	-> see: Diethanolamine																													
Ginger	—	—	grinded	?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Isoamyl alcohol	$C_5H_{12}O$	000123-51-3		Xn	X	0/0	0/0	(2)	3/0	1/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	1/3	0/0	(1)	!/1	1/1	3/0	2/4	3/3	0/0	(1)	(1)	(1)		
Isobutanol	$C_4H_{10}O$	000078-83-1		Xn	X	1/1	1/1	(2)	1/2	(2)	1/2	1/0	1/1	2/2	1/2	1/2	0/0	3/4	1/1	1/1	(1)	1/1	1/0	1/0	3/4	0/0	1/0	(1)	(1)	0/0	
Isobutyl acetate	$C_6H_{12}O_2$	000110-19-0		F	X	0/0	0/0	(2)	(4)	0/0	(4)	1/0	(3)	4/4	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Isobutyl alcohol	-> see: Isobutanol																													
Isobutyl ketone	-> see: Diisobutyl ketone																													
Isobutyl methyl ketone	$C_6H_{12}O$	000108-10-1		F	X	1/2	2/3	1/0	4/4	(4)	3/3	(2)	2/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Isobutyltrimethylmethane	-> see: Iso-octane																													
Iso-octane	C_8H_{18}	000540-84-1	tech. pure	F, Xn	X	1/3	1/3	1/0	(2)	1/0	(4)	1/0	1/3	3/4	1/0	1/0	4/4	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Isooctanol	-> see: Ethylhexanol-1																													
Isooctyl alcohol	-> see: Ethylhexanol-1																													
Isopropyl	C_3H_8O	000067-63-0	tech. pure	F	X	1/1	1/1	1/0	1/2	1/0	1/2	1/0	1/1	2/2	1/2	1/2	4/4	1/4	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	(2)	(1)	(1)	0/0	
Isopropyl-4-methylbenzene, 1-	-> see: Cymene, p-																													
Isopropyl-5-methylcyclohexanol, 2-	-> see: Menthol																													
Isopropyl-5-methylphenol, 2-	-> see: Thymol																													
Isopropyl acetate	$C_5H_{10}O_2$	000108-21-4		F, Xi	X	1/2	2/3	1/0	4/4	(3)	2/3	1/0	2/3	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/1	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Isopropyl acetone	-> see: Isobutyl methyl ketone																													
Isopropyl alcohol	-> see: Isopropyl																													
Isopropylbenzene	-> see: Cumene																													
Isopropylbenzol	-> see: Cumene																													
Isopropyl chloride	C_3H_7Cl	000075-29-6		F, Xn	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Isopropyl ether	$C_6H_{14}O$	000108-20-3	tech. pure	F	X	3/4	3/4	4/4	(4)	1/0	(4)	(1)	3/4	4/4	1/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Isopropylidene acetone	-> see: Mesityl oxide																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Isopropyl methyl ketone	$C_5H_{10}O$	000563-80-4		F	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Jasminaldehyde	-> see: α-pentylcinnamaldehyde																													
Iodine potassium	-> see: Potassium iodide																													
Iodoform	CHJ_3	000075-47-8	100 %	Xn		3/0	3/0	(3)	3/0	0/0	0/0	(2)	3/0	3/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(2)	1/0	1/0	(3)	0/0	(3)	(1)[1)]	(1)[1)]	1/1	[1)] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Iodine pentafluoride	JF_5	007783-66-6		(T, C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Tincture of iodine	I_2	007553-56-2		Xn	(X)	1/3	1/3	4/4	3/4	0/0	1/1	1/1	1/2	3/3	0/0	4/4	4/4	3/3	1/1	0/0	1/1	1/1	2/0	1/1	3/3	0/0	1/0	2/0L	1/0L	1/1		
Cocoa	—	—		(—)		1/1	1/1	(2)	(1)	(2)	0/0	1/1	(2)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Cocoa butter	—	008002-31-1		—		0/0	0/0	1/0	(1)	1/0	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1		
Potash alum	-> see: Potassium aluminium sulphate																													
Potash lye	-> see: Potassium hydroxide																													
Potassium peroxodisulphate	-> see: Potassium persulphate																													
Potassium nitrate	-> see: Potassium nitrate																													
Potassium (hexa)cyanoferrate-(II)	-> see: Potassium hexacyanoferrate (II)																													
Potassium (hexa)cyanoferrate-(III)	-> see: Potassium hexacyanoferrate (III)																													
Potassium acetate	$C_2H_3KO_2$	000127-08-2	aqueous	Xi		1/1	1/1	1/0	(1)	(2)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/0	1/1	1/1	3/0	3/3	0/0	1/3	1/1	1/1	0/0	
Potassium aluminium sulphate	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	diluted	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Potassium aluminium sulphate	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	saturated	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Potassium bicarbonate	-> see: Potassium hydrogen carbonate																													
Potassium bichromate	-> see: Potassium dichromate																													
Potassium bisulphate	-> see: Potassium hydrogen sulphate																													
Potassium bitartrate	-> see: Potassium hydrogentartate																													
Potassium borate	KBO_2	012228-88-5	10 %	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0	
Potassium borate	KBO_2	012228-88-5	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0	
Potassium bromate	$KBrO_3$	007758-01-2	saturated	O, T		1/3	1/3	(2)	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Potassium bromate	$KBrO_3$	007758-01-2	aqueous	O, T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Potassium bromide	KBr	007758-02-3	any	Xn		1/1	1/1	3/0	1/0	(1)	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/0L	1/0L	1/1	
Potassium carbonate	K_2CO_3	000584-08-7	saturated	Xn		1/1	1/1	1/1	3/3	(2)	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1	
Potassium carbonate	K_2CO_3	000584-08-7	aqueous	Xn		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1	
Potassium chlorate	$KClO_3$	003811-04-9	saturated	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium chlorate	$KClO_3$	003811-04-9	aqueous	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium chloride	KCl	007447-40-7	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/3	1/1L	1/1L	1/1	
Potassium chromate	K_2CrO_4	007789-00-6	saturated	T		1/0	1/1	2/0	(2)	0/0	1/0	(2)	1/1	1/1	0/0	1/1	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Potassium chromate	K_2CrO_4	007789-00-6	aqueous	T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Potassium cyanide	KCN	000151-50-8	saturated	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	4/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Potassium cyanide	KCN	000151-50-8	aqueous	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	1/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Potassium dichromate	$K_2Cr_2O_7$	007778-50-9	saturated	T		1/1	1/0	4/4	3/0	3/0	1/0	3/0	1/1	1/3	0/0	1/3	1/0	1/3	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Potassium dichromate	$K_2Cr_2O_7$	007778-50-9	aqueous	T		0/0	0/0	3/0	1/0	3/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Potassium iron (II) cyanide	-> see: Potassium hexacyanoferrate (III)																													
Potassium iron (III) cyanide	-> see: Potassium hexacyanoferrate (II)																													
Potassium fluoride	KF	007789-23-3		T		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	(1)	0/0	1/1	1/1	1/1	0/0	
Potassium hydrogen carbonate	$CHKO_3$	000298-14-6	saturated	—		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	4/4	(1)	(1)	1/1	
Potassium hydrogen sulphate	$KHSO_4$	007646-93-7	aqueous	(C)		1/1	1/1	4/4	1/0	(2)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	1/1	
Potassium hydrogen sulphate	$KHSO_4$	007646-93-7		C		1/1	1/1	4/4	1/0	0/0	0/0	2/0	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	?	
Potassium hydrogentartate	$C_4H_5KO_6$	000868-14-4	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(4)	1/3	1/2	0/0	
Potassium hydroxide	KHO	001310-58-3	10 %	C+		1/1	1/1	1/0	4/4	4/4	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	30 %	C+		1/1	1/1	1/3	4/4	4/4	1/0	(3)	1/1	1/0	1/0	1/3	1/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	50 %	C+		1/1	1/1	1/3	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/3	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	concentrated	C+		1/1	1/1	1/0	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/2	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	1 %	Xi		1/1	1/1	1/0	3/4	(4)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/3	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hypochlorite	KClO	007778-66-7	diluted	(O, C)		1/0	1/3	3/0	(3)	(3)	1/0	4/4	1/3	3/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	4/4	3/3L	2/2L	1/1	Javelle water, originally
Potassium iodate	KJO_3	007758-05-6		O		0/0	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/1	(1)	(1)	(2)	0/0	1/1	1/1	1/1	0/0	
Potassium iodide	KJ	007681-11-0	saturated	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Potassium iodide	KJ	007681-11-0	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	1/1	
Potassium nitrate	KNO_3	007757-79-1	50 %	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium nitrate	KNO_3	007757-79-1	aqueous	O, Xn		1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium perchlorate	$KClO_4$	007778-74-7	saturated	O, Xn		1/1	1/1	(1)	1/0	(1)	1/0	1/1	1/1	0/0	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	
Potassium perchlorate	$KClO_4$	007778-74-7	aqueous	O, Xn		1/1	1/1	(1)	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium permanganate	$KMnO_4$	007722-64-7	aqueous	O, Xn		0/0	0/0	4/4	1/0	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	hypermanganic potash
Potassium permanganate	$KMnO_4$	007722-64-7		O, Xn		1/3	1/1	4/4	1/0	(2)	1/1	1/1	1/1	1/3	0/0	1/3	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	hypermanganic potash
Potassium persulphate	$K_2(SO_4)_2$	007727-21-1	any	O, Xn		1/1	1/1	4/4	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/0	1/0	1/1	
Potassium sulphate	K_2SO_4	007778-80-5	aqueous	Xn		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium sulphide	K_2S	001312-73-8	diluted	(C)		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	(1)	(1)	2/0	0/0	3/4	1/1	1/1	0/0	
Potassium sulphite	K_2SO_3	010117-38-1	saturated	(Xi)		1/1	1/1	(1)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/0	1/0	0/0	
Potassium thiosulphate	$K_2S_2O_3$	010233-00-8	saturated	Xi		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	3/3	0/0	(1)	(1)	(1)		
Lime, burnt	-> see: Calcium oxide																													
Hydrated lime	-> see: Calcium hydroxide																													
Lime nitrate	-> see: Calcium nitrate																													
Lime water	-> see: Calcium hydroxide																													
Cardamom	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Rubber (caoutchouc) dispersion	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(1)	(2)	0/0	(3)	(1)	(1)		Latex
Kerosene	—	008008-20-6		(Xn)		2/2	3/4	(1)	4/4	1/1	2/3	1/1	3/3	4/4	2/3	1/1	0/0	0/0	2/3	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	Lamp oil, light petroleum
Pine needle oil	—	008023-99-2		?		0/0	0/0	1/0	(3)	0/0	(4)	(2)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	0/0	Pinus sylvestris
Silicofluoric acid	H_2SiF_6	016961-83-4	32 %	C		1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	3/0	2/2	3/4	0/0	4/4	(2)	1/1	1/1	
Silicic acid	SiO_2	001343-98-2	any	—		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Silicic acid tetraethylester	-> see: Tetraethylorthosilicate																													
Bone oil	—	008001-85-2		—		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Common salt	-> see: Sodium chloride																													
Carbon (substance) disulphide	-> see: Carbon disulphide																													
Carbon dioxide	CO_2	000124-38-9	saturated	?		1/3	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbon dioxide, moist	CO_2	000124-38-9	tech. pure	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbon dioxide, dry	CO_2	000124-38-9	tech. pure	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbonic acid	-> see: Carbon dioxide																													
Carbonic acid dichloride	-> see: Phosgene																													
Carbon tetrabromide	-> see: Carbon tetrabromide																													
Carbon tetrachloride	-> see: Carbon tetrachloride																													
Coconut fat	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1		
Coconut oil alcohol	—	068425-37-6	tech. pure	(Xi)		1/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1		
Coconut oil	—	008001-31-8	tech. pure	—		1/3	1/3	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Aqua regia	HNO_3 + HCl	008007-56-5		C		4/4	4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	4/4	0/0	4/4	4/4	4/4	4/4	Aqua regia = Nitric acid + hydrochloric acid
Fuel + 20% ethanol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	1/1	1/1		
Fuel + 20% methanol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	1/1	1/1		
Fuel, Normal	—	—		F, T	X	0/0	0/0	1/0	3/0	1/1	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Fuel, Super	—	—		F, T	X	0/0	0/0	1/0	4/4	(2)	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Chalk	$CaCO_3$	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	Calcium carbonate
Creosote	—	—		(T)		1/1	1/1	3/0	(3)	0/0	0/0	(3)	3/4	0/0	1/0	3/0	4/4	0/0	0/0	(1)	1/1	(3)	4/4	(3)	1/0	0/0	(2)	1/1	1/1	0/0	
Cresol (-mixtures)	C_7H_8O	001319-77-3		T, C		3/4	4/4	4/4	4/4	4/4	4/4	4/4	2/3	4/4	4/4	4/4	4/4	3/4	1/2	1/1	1/1	1/1	4/4	1/0	4/4	0/0	1/1	1/0	1/0	1/1	
Carum	—	—	grinded	?		0/0	0/0	(2)	(2)	(1)	0/0	1/1	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	4/4	(1)	(1)		
Kupfer-(I)-chlorid	CuCl	007758-89-6	aqueous	Xn		0/0	0/0	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1	
Kupfer-(I)-cyanid	-> see: Copper cyanide																													
Kupfer-(II)-chlorid	$CuCl_2$	007447-39-4	saturated	Xn		1/3	1/1	(3)	1/0	(2)	1/0	(2)	1/3	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1	
Kupfer-(II)-nitrat	$Cu(NO_3)_2$	003251-23-8	saturated	O, Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/0	1/1	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/1	1/1	1/1	
Kupfer-(II)-nitrat	$Cu(NO_3)_2$	003251-23-8	aqueous	O, Xn		0/0	0/0	(3)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	1/1	1/1	1/1	
Kupfer-(II)-sulfat	-> see: Copper sulphate																													
Copper acetate	$C_4H_6CuO_4$	004180-12-5	aqueous	Xn		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	(3)	3/3	0/0	4/4	1/1	1/1	1/1	Cupriacetate, verdigris
Copper cyanide	CCuN	000544-92-3	saturated	T		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/3	0/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	(3)	1/1	1/1		
Copper cyanuric	-> see: Copper cyanide																													
Copper sulphate, aqueous	-> see: Copper vitriol																													
Copper vitriol	$CuSO_4 \times 5H_2O$	007758-99-8	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/0	1/0	1/1	1/1	1/0	1/3	1/0	1/1	1/1	(1)	1/1	1/1	1/0	1/1	2/0	0/0	4/4	1/1	1/1	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Nitrous oxide	N_2O	010024-97-2		(O)		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	2/0	1/0	1/0	0/0	1/1	(1)	(1)		Nitrous oxide, "nitrogen oxydul"
Lactam	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	4/4	4/4	0/0	(2)	(1)	(1)		cyclic carboxylic acid amides
Lactobiosis	-> see: Lactose																													
Lactose	$C_{12}H_{22}O_{11}$	000063-42-3	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	
Lanolin	—	008006-54-0	tech. pure	—		3/3	3/3	1/0	1/0	1/0	0/0	(2)	3/3	1/1	0/0	3/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Latex	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(1)	(2)	0/0	(2)	(1)	(1)	1/1	Rubber dispersion
Lauryl alcohol	$C_{12}H_{26}O$	000112-53-8	100 %	Xi		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	(1)	(1)	0/0	
Lauryl chloride	$C_{12}H_{25}Cl$	000112-52-7	100 %	(Xi)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(1)	(3)	0/0	(3)	0/0	0/0		
Lavender oil	—	008000-28-0		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	(1)	(1)	(1)		
Cod liver oil	—	008001-69-2		—		1/3	1/3	(2)	1/0	(2)	0/0	(2)	1/3	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/0	(1)	(1)	1/1	
Glue (bone glue)	—	—	any	—		1/0	1/1	(1)	(1)	1/1	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(1)	(1)	1/0	1/0	0/0	(3)	1/1	1/1	0/0	
Linseed oil	—	008001-26-1	tech. pure	—		1/1	1/3	1/0	1/0	1/0	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Lemongrass oil	—	008007-02-1		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Luminous gas, benzene-free	—	—		F+, T	X	1/0	1/0	1/0	1/0	(2)	1/0	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/0	1/0	4/4	1/0	3/0	0/0	1/1	1/1	1/1	0/0	
Ligroin	—	008032-32-4		F, Xn	X	0/0	0/0	(2)	1/0	(2)	(4)	(2)	(3)	3/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		Light petrol
Liqueurs	—	—		—		1/0	0/0	(2)	1/0	1/0	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Limonene, DL-	$C_{10}H_{16}$	000138-86-3		Xn	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Lindane	-> see: Hexachlorocyclohexane																													
Lithium bromide	LiBr	007550-35-8		Xn		1/1	1/1	(3)	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Laurel	—	—	grinded	?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Lysol	—	—		T		0/0	0/0	(4)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(3)	1/1	1/1		Disinfectant, cresol + soap
Magnesite	-> see: Magnesium carbonate																													
Magnesium bromide	$MgBr_2$	007789-48-2		Xi		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	(3)	0/0	0/0		
Magnesium carbonate	$MgCO_3$	000546-93-0	saturated	—		1/1	1/1	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Magnesium chloride	$MgCl_2$	007786-30-3	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/2	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0L	1/0L	1/1	
Magnesium chlorite	$Mg(ClO_2)_2$	??		O		0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0		
Magnesium hydroxide	$Mg(HO)_2$	001309-42-8	saturated	—		1/1	1/1	1/0	(2)	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	1/1	1/1	1/1	1/1	0/0	
Magnesium iodide	MgJ_2	010377-58-9		(Xn)		1/1	1/1	(2)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/1	(1)	(2)	0/0	(2)	0/0	0/0		
Magnesium nitrate	$Mg(NO_3)_2$	010377-60-3	saturated	O, Xi		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	1/0	1/0	1/0	1/1	
Magnesium sulphate	$MgSO_4$	007487-88-9	any	—		1/1	1/1	1/0	1/0	1/0	1/0	1/0	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	0/0	1/1	1/1	1/1	1/1	
Magnesium sulphate heptahydrate	-> see: Epsom salt																													
Maize germ oil	—	008001-30-7	tech. pure	—		1/3	0/0	(2)	(1)	1/0	0/0	(2)	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	1/1	Maize oil
Maleic acid	$C_4H_4O_4$	000110-16-7	saturated	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Maleic acid	$C_4H_4O_4$	000110-16-7	aqueous	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Malonic ester	-> see: Diethylmalonate																													
Malonic acid diethyl ester	-> see: Diethylmalonate																													
Almond oil	—	008007-69-0		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	3/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(1)	(2)	0/0	(1)	1/1	1/1		
Margarine	—	—		—		0/0	0/0	(2)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Marmalade	—	—		—		1/1	1/1	(1)	1/1	1/1	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(2)	1/1	1/1	1/1	
Machine oil	—	—	100 %	?		0/0	1/4	(1)	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Matrium metabisulphite	-> see: Sodium disulphite																													
Matrium pyrochromate	-> see: Sodium dichromate																													
Marine water	-> see: Salt water, seawater																													
Molasses	—	—		—		1/1	1/1	1/0	(1)	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/0	1/0	3/4	
Molasses seasoning	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Menthadiene-1,8, p-	-> see: Limonene, DL-																													
Menthol	$C_{10}H_{20}O$	000089-78-1	solid	Xi		1/3	3/4	3/0	3/4	0/0	0/0	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	1/0	1/0		
Mercaptoacetic acid	-> see: Thioglycolic acid																													
Mercaptoethanoic acid, 2-	-> see: Thioglycolic acid																													
Mesityl oxide	$C_6H_{10}O$	000141-79-7		Xn	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	0/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methacrylic acid	$C_4H_6O_2$	000079-41-4		C		1/0	1/1	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	3/0	4/4	4/4	0/0	(4)	0/0	0/0		
Methacrylic acid methyl ester	-> see: Methyl methacrylate																													
Methane	CH_4	000074-82-8	tech. pure	F+	X	1/0	0/0	1/0	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Methanol solution	-> see: Formaldehyde solution																													
Methanamine	-> see: Methylamine, (mono)																													
Methane carboxylic acid	-> see: Acetic acid																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Methanol	CH_4O	000067-56-1		F, T	X	1/1	1/1	2/0	4/4	1/0	1/1	1/1	1/1	3/4	3/3	1/3	3/3	3/4	1/1	1/1	1/1	1/1	1/0	3/4	3/3	0/0	1/0	1/1	1/1	0/0	
Methanoic acid	-> see: Formic acid																													
Methenamine	-> see: Hexamethylenetetramine																													
Methoxybenzene	-> see: Anisole																													
Methoxybutanol	$C_5H_{12}O_2$	—	100 %	?	X	0/0	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	3/0	1/0	!/0	0/0	(1)	(1)	(1)		Isomer not specified in the source
Methoxyethanol	-> see: Methyl glycol																													
Methoxyethyl acetate	-> see: Methyl glycol acetate																													
Methoxyethyl oleate	$C_{21}H_{40}O_3$	000111-10-4		?		1/1	1/2	(2)	3/4	(2)	1/2	(2)	1/2	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(1)	(1)	4/4	(2)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Methoxypropanol	-> see: Propylene glycol methyl ether																													
Methyl ethyl ether	C_3H_8O	000540-67-0	100 %	(F+)	X	0/0	3/0	(1)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(2)	4/4	4/4	4/4	0/0	1/1	(1)	(1)		
Methyl 2-hydroxybenzoate	-> see: Methyl salicylate																													
Methyl 2-methyl propionate	-> see: Methyl methacrylate																													
Methyl acetate	-> see: Acetic acid methyl ester																													
Methacrolein	-> see: Crotonaldehyde																													
Methyl acrylate	$C_4H_6O_2$	000096-33-3		F, Xn	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Methylacrylic acid	-> see: Methacrylic acid																													
Methyl alcohol	-> see: Methanol																													
Methylamine, (Mono-)	CH_5N	000074-89-5	32 %	F+, C	X	1/0	1/0	4/4	4/4	0/0	0/0	1/0	1/0	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	3/0	1/0	4/4	4/4	0/0	1/0	1/0	1/0	0/0	
Methylbenzene	C_7H_8	000108-88-3		F, Xn	X	3/4	3/4	1/0	4/4	1/0	3/3	1/3	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/3	4/4	0/0	1/1	1/1	1/1	1/1	
Methyl bromide	-> see: Bromomethane																													
Methylbutanol	$C_5H_{12}O$	—		Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	1/3	0/0	(1)	1/1	1/1	3/0	2/2	3/3	0/0	(1)	(1)	(1)		Isomer not specified in the source
Methylbutanol, 3-	-> see: Isoamyl alcohol																													
Methylbutanone-2, 3-	-> see: Isopropyl methyl ketone																													
Methyl butyl alcohol	-> see: Methylbutanol																													
Methyl butyl ketone	$C_6H_{12}O$	000591-78-6		F, T	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl cellosolve	-> see: Methyl glycol																													
Methyl chloroacetate	$C_3H_5ClO_2$	000096-34-4	tech. pure	T/Xi	X	1/1	0/0	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/0	0/0	0/0	0/0	(1)	(1)	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Methyl chloride	-> see: Chloromethane																													
Methyl chloroform	-> see: Trichloroethane-1,1,1																													
Methyl cyanide	-> see: Acetonitrile																													
Methylcyclohexane	C_7H_{14}	000108-87-2		F, Xn	X	3/0	3/0	(2)	(2)	1/0	(4)	(2)	3/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	(1)	4/4	(1)	4/4	0/0	1/1	1/1	1/1	0/0	
Methylcyclopentane	C_6H_{12}	000096-37-7		F	X	0/0	0/0	(2)	(2)	1/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Methyl dichloroacetate	$C_3H_4Cl_2O_2$	000116-54-1		(Xn)		1/1	0/0	(3)	(4)		(4)	(3)	1/1	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	3/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Methylene(di)chloride	-> see: Dichloromethane																													
Methylene chlorobromide	-> see: Bromochloromethane																													
Methyl ether	-> see: Dimethyl ether																													
Methyl ethyl ketone (MEK)	C_4H_8O	000078-93-3		F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/2	1/3	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	3/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl formate	$C_2H_4O_2$	000107-31-3		F+	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl glycol	$C_3H_8O_2$	000109-86-4	100 %	T	X	1/0	1/1	1/0	3/4	0/0	1/1	1/0	1/1	4/4	3/3	3/4	4/4	0/0	1/1	1/1	1/1	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl glycol acetate	$C_5H_{10}O_3$	000110-49-6		T		0/0	0/0	1/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl isobutenyl ketone	-> see: Mesityl oxide																													
Methyl isobutyl ketone(MIBK)	-> see: Isobutyl methyl ketone																													
Methyl isopropyl ketone	-> see: Isopropyl methyl ketone																													
Methyl methacrylate	$C_5H_8O_2$	000080-62-6	100 %	F, Xi	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Methyl methanoate	-> see: Methyl formate																													
Methyl oleate	$C_{19}H_{36}O_2$	000112-62-9		—		0/0	0/0	(2)	(3)	(2)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	4/4	0/0	(1)	(1)	(1)		
Methyl oxirane	-> see: Propylene oxide																													
Methylpent-4-en-2-one, 5-	-> see: Mesityl oxide																													
Methylpentan-2-one, 4-	-> see: Isobutyl methyl ketone																													
Methylphenol	-> see: Cresol (-mixtures)																													
Methylphenyl ether	-> see: Anisole																													
Methylphenyl ketone	-> see: Acetophenone																													
Methylpropanol-1, 2-	-> see: Isobutanol																													
Methylpropanol-2, 2-	-> see: Butyl alcohol, tertiary																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Methyl propenoate	-> see: Methyl acrylate																													
Methylpropenoic acid, 2-	-> see: Methacrylic acid																													
Methyl propyl ketone	$C_5H_{10}O$	000107-87-9		(F)	X	1/2	2/3	(2)	4/4	(4)	3/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	(1)	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl salicylate	$C_8H_8O_3$	000119-36-8		Xn, Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/0	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	2/0	(3)	4/4	0/0	(2)	(1)	(1)	0/0	Synthetic Wintergreen Oil/Gaultheria Oil
Methyl sulphuric acid	CH_4SO_4	000077-78-1	50 %	(C)		0/0	1/1	4/4	(4)	(4)	0/0	4/4	2/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4	
Methyl sulphuric acid	CH_4SO_4	000077-78-1	aqueous	(C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4	
Milk	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Lactic acid	$C_3H_6O_3$	000050-21-5	3 %	?		1/1	1/2	(3)	1/2	1/0	1/2	2/4	1/2	2/2	1/1	2/3	0/0	1/1	1/1	1/1	1/1	1/1	3/4	1/1	(2)	0/0	(1)	1/1	1/1	1/1	Lactol
Lactic acid	$C_3H_6O_3$	000050-21-5	80 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/1	1/1	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1	Lactol
Lactic acid	$C_3H_6O_3$	000050-21-5	85 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/2	2/2	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1	Lactol
Lactic acid ethyl ester	-> see: Ethyl lactate																													
Milk sugar	-> see: Lactose																													
Mineral oil	—	008012-95-1		(Xn)		1/1	2/4	(1)	1/2	1/1	1/2	1/1	1/3	1/1	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	2/2	0/0	1/1	1/1	1/1	0/0	
Mineral water	—	—		—		1/1	1/1	(1)	1/0	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	(1)	(1)	1/1	
Mohr's salt	-> see: Ammonium iron (II) sulphate																													
Whey	—	—		—		1/1	0/0	(2)	(1)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(2)	1/1	1/1		
Monobromobenzene	-> see: Bromobenzene																													
Monochlorobenzene	-> see: Chlorobenzene																													
Monochloroacetic acid	-> see: Chloroacetic acid																													
Monochloroacetic acid ethyl ester	-> see: Ethyl chloroacetate																													
Monochloroacetic acid methyl ester	-> see: Methyl chloroacetate																													
Monoethanolamine	-> see: Ethanolamine																													
Monofluorodichloromethane	-> see: Dichlorofluoromethane																													
Monopotassium tartrate	-> see: Potassium hydrogentartate																													
Monopentyl phthalate	-> see: Phthalic acid monoamyl ester																													
Morpholine	C_4H_9NO	000110-91-8	tech. pure	C, Xn	X	1/1	1/1	(3)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	3/0	2/3	4/4	0/0	1/0	(1)	(1)	0/0	
Engine oil	—	—		?		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Mowilith D	—	—		?		1/0	0/0	(2)	0/0	(2)	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(2)	(2)	(2)	0/0	(2)	(1)	(1)	0/0	Polyvinylacetatdispersion; Clariant
Nutmeg	—	—	grinded	?		0/0	0/0	(2)	4/4	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Nutmeg oil	—	008008-45-5		(Xn)		0/0	0/0	(2)	4/4	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/4	0/0	(1)	(1)	(2)	(4)	(3)	(3)	0/0	(1)	(1)	(1)		
Nail varnish remover	—	—		?	(X)	0/0	0/0	(2)	4/4	0/0	(4)	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Naphtha	—	008032-32-4		(Xn)		1/3	3/4	1/0	(2)	(1)	1/0	1/0	1/3	3/0	1/0	1/0	4/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	Petroleum gasoline
Naphthalene	$C_{10}H_8$	000091-20-3	100 %	F, Xn	X	0/0	1/3	1/0	(3)	0/0	0/0	1/2	1/3	3/4	1/0	4/4	4/4	1/4	0/0	(1)	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	
Naphthalene (in alcohol)	—	—		F, Xn	X	1/4	1/4	(2)	(3)	0/0	0/0	1/2	1/3	3/4	0/0	0/0	0/0	3/4	0/0	(1)	1/1	(2)	4/4	(3)	(3)	0/0	(1)	(1)	(1)	0/0	
Naphthene	-> see: Cyclohexane																													
Sodium acetate	$C_2H_3NaO_2$	000127-09-3	any	—		1/1	1/1	1/0	1/2	(1)	1/1	1/1	1/1	2/2	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	1/1	1/1	1/1	
Sodium aluminium sulphate	$NaAl(SO_4)_2$	010102-71-3		?		1/1	1/1	(3)	(2)	(1)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)		
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1	36 %	Xn		1/1	1/1	1/0	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	1/1	0/0	(1)	(1)	(1)	1/1	
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1	aqueous	Xn		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1	
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1		Xn		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1	
Sodium bicarbonate	$NaHCO_3$	000144-55-8	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium bichromate	-> see: Sodium dichromate																													
Sodium bisulphate	$NaHSO_4$	007681-38-1	10 %	(C)		1/1	1/1	4/4	1/0	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	1/2	1/1	1/1	
Sodium bisulphate	$NaHSO_4$	007681-38-1	any	(C)		1/1	1/1	1/0	1/0	0/0	0/0	(3)	1/1	1/3	0/0	1/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	(2)	1/1	1/1	
Sodium bisulphite	$NaHSO_3$	007631-90-5	aqueous	Xn		1/1	1/1	1/0	(2)	1/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1	1/1	
Sodium borate	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	saturated	Xi		1/1	1/1	1/0	1/0	(2)	1/0	1/1	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/3	1/1	1/1	1/1	
Sodium borate	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/3	1/1	1/1	1/1	
Sodium bromate	$NaBrO_3$	007789-38-0	any	O, T		1/0	1/3	(3)	(2)	0/0	0/0	1/1	1/1	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	(2)	(1)	1/3	0/0	1/1	1/1L	1/1L	0/0	
Sodium bromide	NaBr	007647-15-6	any	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/3	0/0	4/4	0/0	0/0	0/0	
Sodium carbonate	Na_2CO_3	000497-19-8	saturated	Xi		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium carbonate	Na_2CO_3	000497-19-8	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium carbonate	Na_2CO_3	000497-19-8		Xi		1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	2/0	0/0	1/1	0/0	1/2	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium chlorate	$NaClO_3$	007775-09-9	any	O, Xn		1/1	1/0	1/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1L	1/1L	1/1	
Sodium chlorate	$NaClO_3$	007775-09-9	aqueous	O, Xn		0/0	0/0	3/0	1/0	1/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/0	1/1L	1/1L	1/1	
Sodium chloride	NaCl	007647-14-5	any	—		1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/2	1/2	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sodium chloride	NaCl	007647-14-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/4	1/2	1/2	1/1	
Sodium chlorite	$NaClO_2$	007758-19-2	diluted	(O, Xn)		1/0	1/3	1/4	(2)	0/0	0/0	(2)	1/3	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	3/4	3/4	3/3	0/0	
Sodium chromate	$NaCrO_4$	007775-11-3	diluted	T		1/0	1/0	1/1	(2)	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	1/1	1/1	1/1	0/0	
Sodium cyanide	CNNa	000143-33-9	saturated	T		1/1	1/1	1/0	(3)	0/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	4/4	(2)	(2)	0/0	
Sodium cyanide	CNNa	000143-33-9	aqueous	T		1/1	1/1	1/0	(3)	1/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	(2)	(2)	0/0	
Sodium dichromate	$Na_2Cr_2O_7$	010588-01-9		T		0/0	1/1	1/0	1/0	3/0	1/1	(3)	1/1	1/1	0/0	1/0	0/0	0/0	1/1	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Sodium disulphite	$Na_2S_2O_5$	007681-57-4	any	Xn		1/1	1/1	1/0	(2)	(2)	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1		
Sodium dithionite	$Na_2S_2O_4$	007775-14-6	10 %	Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		
Sodium dithionite	$Na_2S_2O_4$	007775-14-6		Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		
Sodium dodecylbenzene sulphonate	$C_{18}H_{29}NaSO_3$	025155-30-0		Xn		1/1	1/1	(2)	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(1)	(2)	0/0	(2)	(1)	(1)		
Sodium iron cyanide	-> see: Sodium hexacyanoferrate(II)																													
Sodium ferrocyanide	-> see: Sodium hexacyanoferrate(II)																													
Sodium fluoride	NaF	007681-49-4	saturated	T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/0	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	1/1	
Sodium hexacyanoferrate-(II)	$C_6FeNa_4N_6$	013601-19-9		Xn		1/1	1/1	(1)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(1)	(1)	(1)		
Sodium hexametaphosphate	$(NaPO_3)_6$	068915-31-1	saturated	—		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Sodium hydrogen carbonate	-> see: Sodium bicarbonate																													
Sodium hydrogen sulphate	-> see: Sodium bisulphate																													
Sodium hydrogen sulphite	-> see: Sodium bisulphite																													
Sodium hydrosulphite	-> see: Sodium dithionite																													
Sodium hydroxide	NaOH	001310-73-2	concentrated	C		1/1	1/1	1/3	4/4	4/4	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/4	0/0	4/4	(2)	(2)	?	
Sodium hydroxide	NaOH	001310-73-2	30 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/0	1/0	1/3	1/3	0/0	0/0	1/1	1/1	(2)	1/0	(3)	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	45 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/1	1/0	1/3	1/3	1/1	0/0	0/0	1/1	(2)	1/0	2/4	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	50 %	C+		1/1	1/1	1/0	4/4	4/4	1/1	1/3	1/1	2/2	1/1	1/2	0/0	0/3	1/1	1/1	1/1	3/3	1/0	3/4	3/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	60 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	(3)	1/1	1/0	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	3/4	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	1 %	Xi		1/1	1/1	1/0	3/4	(3)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	(4)	1/1	1/1	1/1	
Sodium hypochlorite	NaClO	007681-52-9	diluted	(O, C)		2/3	2/3	4/4	(3)	3/0	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	15 %	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/1	0/0	1/1	1/1	1/1	1/1	3/4	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	saturated	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	0/0	1/1	0/0	(1)	1/1	(3)	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	12,5 % Cl	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypodisulphite	-> see: Sodium dithionite																													
Sodium iodide	NaJ	007681-82-5	any	Xi		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/0	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	(1)	1/1	0/0	1/1	3/4	3/4	0/0	
Sodium metaborate peroxide	-> see: Sodium perborate																													
Sodium nitrate	$NaNO_3$	007631-99-4	saturated	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	
Sodium nitrate	$NaNO_3$	007631-99-4	aqueous	O, Xn		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Sodium nitrite	$NaNO_2$	007632-00-0	saturated	O, T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1	1/1	1/1	
Sodium nitrite	$NaNO_2$	007632-00-0	aqueous	O, T		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	1/0	1/1	1/1	1/1	
Sodium oxalate	$C_2Na_2O_4$	000062-76-0	saturated	Xn		1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	1/0	1/0	0/0	1/1	(2)	(2)		
Sodium perborate	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	saturated	(O, Xn)		1/1	1/1	4/4	(2)	0/0	0/0	2/0	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Sodium perborate	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	aqueous	(O, Xn)		1/1	1/1	4/4	(2)	3/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Sodium perchlorate	$NaClO_4$	007601-89-0	saturated	O, Xn		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	1/1	1/1	
Sodium peroxide	Na_2O_2	001313-60-6	10 %	O, C+		0/0	1/3	4/4	(3)	(4)	0/0	4/4	272	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	3/0	0/0	4/4	1/1	1/1	0/0	
Sodium peroxide	Na_2O_2	001313-60-6	saturated	O, C+		0/0	3/3	4/4	(3)	(4)	0/0	4/4	2/2	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	(4)	0/0	4/4	(2)	(2)	0/0	
Sodium peroxodisulphate	-> see: Sodium persulphate																													
Sodium persulphate	$Na_2S_2O_8$	007775-27-1	saturated	O, Xi		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(3)	0/0	4/4	0/0	1/0	0/0	
Sodium phosphate	$Na_3PO_4 \times 12H_2O$	010101-89-0	saturated	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium phosphate	$Na_3PO_4 \times 12H_2O$	010101-89-0	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium phosphate, secondary	-> see: Disodium phosphate																													
Sodium phosphate, tertiary	-> see: Trisodium phosphate																													
Sodium phosphate dodecahydrate	-> see: Sodium phosphate																													
Sodium pyrosulphite	-> see: Sodium disulphite																													
Sodium silicate	$Na_2Si_2O_7$	001344-09-8	any	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium stearate	$C_{18}H_{35}NaO_2$	000822-16-2	aqueous	(Xi)		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(1)	1/0	0/0	(1)	1/1	1/1		
Sodium sulphate	Na_2SO_4	007757-82-6	saturated	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/3	0/0	1/1	1/1	1/1	1/1	
Sodium sulphate	Na_2SO_4	007757-82-6	aqueous	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	0/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium sulphate	Na_2SO_4	007757-82-6		—		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	1/1	1/1	1/1	1/1	
Sodium sulphide	Na_2S	001313-82-2	saturated	C		1/1	1/1	1/0	3/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	0/0	1/1	1/1	3/3	1/0	1/1	2/3	0/0	3/4	(1)	(1)	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics					Elastomers		Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sodium sulphide	Na_2S	001313-82-2	aqueous	C		1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/2	1/2	1/1	
Sodium sulphite	Na_2SO_3	007757-83-7	saturated	Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/3	1/1	1/1	1/1	
Sodium tetraborate	-> see: Sodium borate																														
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	any	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	saturated	Xi		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	aqueous	Xi		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate-5-hydrate	-> see: Sodium thiosulphate																														
Sodium hypochlorite	-> see: Sodium hypochlorite																														
Caustic soda	-> see: Sodium hydroxide																														
Sodium nitrate	-> see: Sodium nitrate																														
Sodium liquid glass	-> see: Sodium silicate																														
Cloves	—	—	grinded	?		0/0	0/0	(2)	4/4	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	0/0	
Neon	Ne	007440-01-9		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(1)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1		
Wetting agent	—	—	5 %	?		1/0	0/0	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(2)	0/0	0/0	K	K		Surfactants
Niacin	-> see: Nicotinic acid																														
Nickel (II) chloride	$NiCl_2$	007718-54-9	saturated	T		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1	
Nickel (II) chloride	$NiCl_2$	007718-54-9	aqueous	T		1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1	
Nickel acetate	$C_4H_6NiO_4$	000373-02-4	aqueous	(T, N)		1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/0	0/0	4/4	0/0	0/0		
Nickel nitrate	$Ni(NO_3)_2$	013138-45-9	saturated	(O, Xn)		1/1	1/1	(3)	(2)	(1)	1/0	(2)	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Nickel sulphate	$NiSO_4$	007786-81-4	saturated	Xn		1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nickel sulphate	$NiSO_4$	007786-81-4	aqueous	Xn		1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nicotine	$C_{10}H_{14}N_2$	000054-11-5		T+		1/0	1/0	(3)	(3)	0/0	0/0	(2)	1/0	1/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/1	0/0	(1)	(1)	(1)	0/0	
Nicotinic acid	$C_6H_5NO_2$	000059-67-6	diluted	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/0	0/0	0/0	1/1	0/0	0/0	0/0	1/1	(1)	(2)	(2)	(3)	(2)	0/0	(3)	0/0	0/0	0/0	
Nitrobenzoic acid	$C_7H_5NO_4$	—		(Xn)		1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	(3)	(2)	0/0	(3)	0/0	0/0		Isomer not specified in the source
Nitrobenzene	$C_6H_5NO_2$	000098-95-3		T		3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitroethane	$C_2H_5NO_2$	000079-24-3		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Nitroglycerin	$C_3H_5(NO_3)_3$	000055-63-0	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(3)	1/0	1/0	4/4	0/0	0/0	0/0	0/0	0/0	
Nitro glycol	$C_2H_4(NO_3)_2$	000628-96-6	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(3)	1/0	1/0	4/4	0/0	0/0	(1)	(1)	0/0	
Nitropropane	$C_3H_7NO_2$	—		(T)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Nitrous gases	—	—	diluted	T		1/1	0/0	3/0	4/4	0/0	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	3/0	4/4	0/0	(2)	(1)	(1)	0/0	Nitrogen monoxide + nitrogen dioxide
Nitrotoluene	$C_7H_7NO_2$	001321-12-6	tech. pure	T		1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitro thinner	—	—		?	X	0/0	0/0	3/0	(4)	0/0	(4)	(3)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		Solvent mixture
Nonanol	$C_9H_{20}O$	000143-08-8	100 %	Xn, Xi		0/0	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Nonyl alcohol	-> see: Nonanol																														
Fruit pulp	—	—		—		1/1	1/1	(2)	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	
Fruit wine	—	—		—		1/1	1/1	(2)	(1)	1/1	0/0	1/1	1/0	0/0	0/0	1/0	0/0	0/0	1/1	1/1	(1)	1/1	1/0	(1)	1/0	0/0	(2)	1/1	1/1	0/0	
Octadec-9-enoic acid, cis-	-> see: Oleic acid																														
Octadecanoic acid	-> see: Stearic acid																														
Octafluorocyclobutane	C_4F_8	000115-25-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Octal	-> see: Diisooctyl phthalate																														
Octane, n-	C_8H_{18}	000111-65-9		F, Xn	X	1/1	1/1	1/0	2/3	(1)	1/1	1/0	1/1	4/4	2/3	3/4	3/3	1/1	1/1	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	0/0	
Octanol, 1-	-> see: Octyl alcohol, -n																														
Octyl alcohol, -n	$C_8H_{18}O$	000111-87-5		Xi		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Octylcresol	$C_{15}H_{24}O$	—	100 %	?		3/0	3/0	(3)	(4)	0/0	0/0	(3)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Oils and fats, vegetable	—	—		—		1/3	1/3	(2)	(2)	1/0	0/0	(2)	1/3	3/0	0/0	1/1	3/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	(2)	0/0	(1)	1/1	1/1	0/0	
Öle, Oils, ethereal	—	—		?		4/4	3/4	(2)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	(1-3)	(3)	0/0	1/1	(1)	(1)	0/0	
Olein	-> see: Oleic acid																														
Oleum	$H_2SO_4 \times SO_3$	008014-95-7	10 % SO_3	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/0	4/4	4/4	1/0	4/4	0/0	1/3	1/2	1/1	0/0	Fuming sulphuric acid
Oleum vapours	—	—	low	?		4/4	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	1/0	(3)	1/0	(3)	0/0	(3)	(1)	(1)	0/0	Sulphur trioxide
Olive oil	—	008001-25-0		—		1/3	0/0	(2)	(2)	1/0	0/0	1/1	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Oleic acid	$C_{18}H_{34}O_2$	000112-80-1	tech. pure	Xi		1/3	1/3	1/0	1/0	1/0	0/0	2/0	1/3	1/3	0/0	1/1	0/0	1/3	0/0	(1)	1/1	1/1	4/4	2/2	3/0	0/0	1/1	1/1	1/1	0/0	
Oleic acid methoxyethyl ester	-> see: Methoxyethyl oleate																														
Oleic acid methyl ester	-> see: Methyl oleate																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sweet orange juice	-> see: Orange juice																													
Sweet orange peel oil	-> see: Orange peel oil																													
Ortho-silicic acid tetraethyl ester	-> see: Tetraethylorthosilicate																													
Orthophosphoric acid	-> see: Phosphoric acid																													
Oxabutyl acetate	-> see: Methyl glycol acetate																													
Oxalic acid	$C_2H_2O_4 \times 2H_2O$	000144-62-7	aqueous	Xn		1/1	1/1	4/4	(2)	(2)	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/2	
Oxalic acid	$C_2H_2O_4 \times 2H_2O$	000144-62-7		Xn		1/1	1/1	3/4	1/0	0/0	1/1	4/4	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/3	
Oxalic acid sodium salt	-> see: Sodium oxalate																													
Oxalic acid ammonium salt	-> see: Ammonium oxalate																													
Oxirane	-> see: Ethylene oxide																													
Oxolane	-> see: Tetrahydrofuran																													
Oxydiacetic acid	-> see: Diglycolic acid																													
Oxymethylfurfurol, 5-	$C_6H_6O_3$	000067-47-0		Xi		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ozone	O_3	010028-15-6		(O, T)		3/4	3/4	4/4	1/2	0/0	1/1	4/4	3/4	2/2	1/1	1/2	0/0	1/1	1/1	1/1	(1)	1/3	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Ozone-air mixture-Luft-Gemisch	—	—		(O, T)		0/0	0/0	4/4	(2)	0/0	0/0	4/4	3/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Palmitic acid	$C_{16}H_{32}O_2$	000057-10-3	tech. pure	Xi		3/3	2/2	1/1	(2)	1/0	0/0	1/0	3/4	1/1	0/0	1/1	3/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
Palmityl alcohol	-> see: Cetyl alcohol																													
Palm seed oil	—	008023-79-8		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/3	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Palm oil	—	008002-75-3		—		1/3	0/0	1/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1		
Paraffins	C_nH_{2n+2}	—	100 %	?		1/0	1/1	1/0	1/0	1/0	1/1	1/1	1/0	1/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	
Paraffin emulsion	—	—		?		1/3	0/0	1/0	(2)	(2)	0/0	(2)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/0	1/1	0/0	(2)	(1)	(1)	0/0	
Paraffin wax	—	008002-74-2	melted	(—)		0	0	0	(2)	0	0	(2)	(2)	0	0	0	0	0	0	(1)	1	0	4	(2)	1	0	1	1	1		
Paraform	-> see: Paraformaldehyde																													
Paraformaldehyde	$(CH_2O)_nH_2O$	030525-89-4		F, T	X	0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	1/0	3/3	0/0	(1)	(1)	(1)		
Perfumes	—	—		?		3/0	3/0	1/0	(3)	1/0	0/0	(2)	1/0	4/4	0/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Pectin	—	009000-69-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Pectin
Pectin	—	009000-69-5		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Pectin
Penicillin	—	—		Xn		(1)	(1)	(2)	(1)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		Antibiotic
Pentaclorodiphenyl	$C_{12}H_5Cl_5$	—		Xn		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0		a PCB
Pentamethyleneimine	-> see: Piperidine																													
Pentane	C_5H_{12}	000109-66-0		F	X	1/3	1/3	1/0	1/0	1/1	(3)	1/0	(3)	3/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(1)	4/4	1/0	1/2	0/0	1/1	1/1	1/1		
Pentanone, 2-	-> see: Methyl propyl ketone																													
Pentanone, 3-	-> see: Diethyl ketone																													
Pentanethiol, 1-	$C_5H_{12}S$	000110-66-7		Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(2)	(1)	(1)		
Pentylacetate, n-	-> see: Amylacetate, n-																													
Pentyl alcohol	-> see: Amyl alcohol, n-																													
Pentyl chloride	-> see: Amyl chloride																													
Pentylcinnamaldehyde, a-	-> see: α-pentylcinnamaldehyde																													
Perchlorobutadiene	-> see: Hexachlorobutadiene																													
Perchlorethene	-> see: Perchloroethylene																													
Perchloroethylene (PER)	C_2Cl_4	000127-18-4		Xn		4/4	4/4	4/4	4/4	3/4	4/4	1/3	4/4	4/4	4/4	4/4	4/4	3/3	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	(3)	0/0	0/0	0/0	
Perchloric acid	$HClO_4$	007601-90-3	70 %	E, O, C+		2/4	3/4	4/4	4/4	(4)	2/4	4/4	4/4	2/3	4/4	3/4	4/4	0/0	1/2	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	0/0	0/0	?	
Perchloric acid	$HClO_4$	007601-90-3	20 %	Xi		0/0	1/3	4/4	3/0	0/0	0/0	4/4	1/3	0/0	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	2/0	1/1	4/4	0/0	4/4	0/0	0/0	1/1	
Perfluoropropane	C_3F_8	000076-19-7		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Perhydroxic acid	-> see: Hydrogen peroxide 30 %																													
Petrolatum, petroleum jelly	-> see: Vaseline																													
Petroleum ether	—	008032-32-4	tech. pure	(F, Xn)	X	1/3	1/3	1/0	3/0	1/0	1/0	1/1	1/3	4/4	1/0	1/1	3/3	3/3	0/0	(1)	1/1	1/1	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	
Petroleum	—	—	tech. pure	Xn, N	X	1/3	3/4	1/0	3/0	(1)	0/0	1/1	1/3	4/4	1/0	1/0	3/0	3/4	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Pepper	—	—	grinded	?		0/0	0/0	(2)	1/0	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Vegetable oils	—	—		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Phenacetin	$C_{10}H_{13}NO_2$	000062-44-2		Xn		0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)		
Phenetole	-> see: Phenylethylether																													
Phenol	C_6H_6O	000108-95-2	10 %	T		1/1	1/1	4/4	4/4	4/4	1/0	4/4	1/1	4/4	4/4	1/3	3/3	3/3	0/0	1/0	1/1	1/1	4/4	2/3	4/4	0/0	1/1	1/2	1/1	0/0	
Phenol	C_6H_6O	000108-95-2	100 %	T, C		2/3	3/3	4/4	4/4	4/4	1/1	4/4	1/2	4/4	3/3	4/4	3/0	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	0/0	
Phenolic resin moulding compound	—	—		?		1/1	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(4)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Phenyethylene	-> see: Styrene																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Phenyl-2-propenal, trans-3-	-> see: Cinnamaldehyde																													
Phenylamine	-> see: Aniline																													
Phenylaniline, N-	-> see: Diphenylamine																													
Phenyl bromide	-> see: Bromobenzene																													
Phenylcarbinol	-> see: Benzyl alcohol																													
Phenyl chloride	-> see: Chlorobenzene																													
Phenylethanol	$C_8H_{10}O$	000060-12-8		Xn		0/0	0/0	3/0	4/4	0/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(1)	(1)	(1)		
Phenyl ether	-> see: Diphenyl ether																													
Phenylethyl alcohol	-> see: Phenylethanol																													
Phenyl ethyl ether	$C_8H_{10}O$	000103-73-1		?		0/0	0/0	(2)	(4)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Phenylhydrazine	$C_6H_8N_2$	000100-63-0	tech. pure	T		3/0	0/0	(3)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/3	4/4	0/0	(2)	0/0	0/0	0/0	
Phenylhydrazine chlorohydrate	-> see: Phenylhydrazine-HCl																													
Phenylhydrazine-HCl	$C_6H_8N_2$-HCl	000059-88-1		T		0/0	0/0	(3)	(2)	0/0	0/0	(3)	1/3	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/3	1/3	0/0	(4)	(4L)	(4L)		
Phenylpropane	-> see: Cumene																													
Phenyl sulphonate	—	70528-83-5		?		0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Phenylsulfonic acid	-> see: Benzenesulfonic acid																													
Phosgene	$COCl_2$	000075-44-5	liquid	T+, C		0/0	0/0	1/0	(3)	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	1/0	3/0	0/0	(3)	3/4	3/4	0/0	
Phosgene	$COCl_2$	000075-44-5	gaseous	T+, C		0/0	3/0	1/0	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	3/0	0/0	(3)	3/4	3/4	0/0	
Phosphates	—	—	aqueous	?		1/1	1/1	0/0	0/0	(1)	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	0/0	(1)	(1)		Salts of phosphoric acid
Phosphine	PH_3	007803-51-2	concentrated	F+, T+	X	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Phosphorus (III) chloride	-> see: Phosphorus trichloride																													
Phosphorus oxychloride	PCl_3O	010025-87-3	100 %	T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	
Phosphorus oxychloride	PCl_3O	010025-87-3		T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	
Phosphorus pentachloride	PCl_5	010026-13-8		T+, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	1/1	(3)	(3)	4/4	0/0	1/1	1/3L	1/3L		
Phosphorus pentoxide	P_4O_{10}	001314-56-3	tech. rein	C		1/0	0/0	(4)	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	(3)	(2)	3/4	0/0	1/1	1/0	1/0	0/0	
Phosphorus perchloride	-> see: Phosphorus pentachloride																													
Phosphoric acid	H_3PO_4	007664-38-2	30 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	85 %	C		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	1/1	1/2	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	2/4	1/3	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	1-5 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	3/4	1/1	2/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	(4)	1/1	1/1	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	20%	Xi		1/1	1/1	4/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphoric anhydride	-> see: Phosphorus pentoxide																													
Phosphoric acid chloride	-> see: Phosphorus pentachloride																													
Phosphoric acid tritolyester	-> see: Tricresyl phosphate																													
Phosphorus trichloride	PCl_3	007719-12-2		T, C		3/3	3/3	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/1	1/0	3/4	4/4	0/0	1/1	0/0	0/0	1/1	
Hydrogen phosphide	-> see: Phosphine																													
Phosphoryl chloride	-> see: Phosphorus oxychloride																													
Phthalic acid	$C_8H_6O_4$	000088-99-3	saturated	Xi		1/1	1/1	3/3	(3)	1/0	0/0	1/0	1/1	1/0	0/0	1/4	0/0	1/1	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	
Phthalic acid amyl ester	$C_{18}H_{26}O_4$	000131-18-0	100 %	(T)		0/0	1/3	(1)	(4)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Phthalic acid dibutyl ester	-> see: Dibutyl phthalate																													
Phthalic acid dicyclohexyl ester	-> see: Dicyclohexyl phthalate																													
Phthalic acid dimethyl ester	-> see: Dimethyl phthalate																													
Phthalic acid dinonyl ester	-> see: Dinonyl phthalate																													
Phthalic acid monoamyl ester	$C_{13}H_{16}O_4$	??		(Xn)		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	(1)	(1)		
Picric acid	$C_6H_3N_3O_7$	000088-89-1	1 % aqueous	T		1/0	1/0	3/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	4/4	0/0	0/0	1/0	1/0	1/1	3/0	1/0	3/4	0/0	1/0	1/0	1/0	1/0	
Pimenta, allspice	—	—	grinded	?		0/0	0/0	(2)	4/4		0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Piperidine	$C_5H_{11}N$	000110-89-4		F, T, C		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Polyester resins	—	—		(Xn)	(X)	3/4	3/4	1/0	4/4	1/0	0/0	(2)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Polyethylene glycol	HO-$(C_2H_4O)_n$-H	025322-68-3	100 %	(—)		1/1	1/1	(3)	0/0	0/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2-3)	(2)	(3)	0/0	(1)	(1)	(1)	0/0	
Polyglycol	-> see: Polyethylene glycol																													
Polyoxyethylene	-> see: Polyethylene glycol																													
Polyoxymethylene	-> see: Paraformaldehyde																													
Polyran M25 N	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	3	0	0	(1)	(1)		Lubricating oil
Polyran M400	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	(3)	0	0	(1)	(1)		Lubricating oil
Polysiloxane	-> see: Silicone oil																													
Polysolvan O	$C_6H_{12}O_3$	007397-62-8	100 %	Xi		0/0	1/1	(2)	(3)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	(3)	0/0	(1)	(1)	(1)		Solvent, glycolic acid butyl ester; Celanese AG

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							---------- Thermoplastics ----------		---- Fluoroplastics ----		--- Elastomers ---		-------- Metals ---------			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Bitter orange oil	—	068916-04-1		?		2/3	3/4	(2)	3/3	1/0	3/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	4/4	(2)	(4)	0/0	(1)	(1)	(1)		
Potash	-> see: Potassium carbonate																													
Compressed air	—	—	oily	—		1/0	0/0	(2)	(2)	(1)	0/0	(1)	3/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	1/1	1/1	1/1		
Prontosil	—	—		(Xn)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	0/0	0/0		Chemotherapeutic agent; Bayer - no longer on the market
Prop-2-enyl acetate	-> see: Allyl acetate																													
Propane	C_3H_8	000074-98-6	liquid	F+	X	1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/0	0/0	1/0	1/0	3/0	1/0	0/0	(1)	1/1	1/1	4/4	1/0	(2)	0/0	1/1	1/1	1/1	0/0	
Propane	C_3H_8	000074-98-6	gaseous	F+	X	3/4	4/4	1/0	3/4	1/0	4/4	1/1	2/4	4/4	3/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Propandiol, 1,2-	-> see: Propylene glycol																													
Propanol	C_3H_8O	000071-23-8		F	X	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	3/0	0/0	2/2	3/3	1/4	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/1	(1)	(1)	0/0	
Propanol, 2-	-> see: Isopropyl																													
Propanone, 2-	-> see: Acetone																													
Propanoic acid	-> see: Propionic acid																													
Propanetriol	-> see: Glycerine																													
Propargyl alcohol	C_3H_4O	000107-19-7	7 %	Xn		1/1	1/1	(3)	1/0	0/0	0/0	(2)	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/3	1/0	1/1	1/1	0/0	1/0	(1)	(1)	0/0	
Propene	C_3H_6	000115-07-1		F+	X	1/1	1/1	1/0	(3)	1/0	0/0	1/0	1/1	4/4	0/0	3/4	4/4	0/0	0/0	(1)	1/1	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Propene-1-ol, 2-	-> see: Allyl alcohol																													
Propene acid ethyl ester	-> see: Ethyl acrylate																													
Propyn-1-ol, 2-	-> see: Propargyl alcohol																													
Propionic acid	$C_3H_6O_2$	000079-09-4	50 %	C, F	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/1	4/4	4/4	1/3	3/3	0/0	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	1/1	(1)	(1)	1/1	
Propionic acid	$C_3H_6O_2$	000079-09-4		C, F+	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	1/1	
Propyl acetate	$C_5H_{10}O_2$	000109-60-4		F	X	0/0	0/0	(1)	4/4	0/0	(4)	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Propyl alcohol	-> see: Propanol																													
Propylamine, n-	C_3H_9N	000107-10-8		F, C, Xn	X	0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Propylene	-> see: Propene																													
Propylene(di)chloride	-> see: Dichloropropane																													
Propylene glycol	$C_3H_8O_2$	000057-55-6		—		1/1	1/1	4/4	2/3	(2)	1/1	1/0	1/1	1/1	2/2	3/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	(1)	(1)	1/1	
Propylene glycol methyl ether	$C_4H_{10}O_2$	—		—	X	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Propylene oxide	C_3H_6O	000075-56-9		F+, T	X	1/1	1/2	(3)	2/3	0/0	1/2	(2)	1/2	4/4	2/2	3/4	0/0	4/4	3/4	1/1	1/0	1/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Propylidintris(methanol)	-> see: Trimethylol propane																													
Propyl nitrate	$C_3H_7NO_3$	000627-13-4		(E, Xn)	(X)	0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(2)	(1)	(1)		
Pseudocumene	C_9H_{12}	000095-63-6		Xn	X	0/0	0/0	(1)	(4)	0/0	0/0	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(2)	4/4	0/0	1/1	1/1	1/1		
Pydraul C (312, 540)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	1/0	4/4	0/0	0/0	(1)	(1)		Base phosphoric acid ester; Monsanto
Pydraul E (29, 30, 50, 65, 90, 11)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	4/4	0/0	0/0	(1)	(1)		Base phosphoric acid ester; Monsanto
Pyridine	C_5H_5N	000110-86-1		F, Xn	X	1/3	0/2	1/0	4/4	0/0	0/2	1/1	3/3	4/4	4/4	4/4	4/4	4/4	1/1	(2)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Pyridine-3-carboxylic acid	-> see: Nicotinic acid																													
Pyrogallol	$C_6H_6O_3$	000087-66-1		Xn		0/0	0/0	1/0	(3)	0/0	0/0	3/4	1/0	3/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	1/1	(3)	(3)	(3)	0/0	1/1	1/1	1/1	1/1	
Pyrosulphite	-> see: Sodium disulphite																													
Pyrrole	C_4H_5N	000109-97-7		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Mercury	Hg	007439-97-6	pure	T		1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(3)	1/1	1/1		
Mercury (II) chloride	$HgCl_2$	007487-94-7	aqueous	T+, C		1/1	1/1	4/4	1/0	(2)	1/1	3/0	1/1	1/3	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	(4)	(4)	1/1	Sublimate
Mercury (II) cyanide	C_2HgN_2	000592-04-1	saturated	T+		1/1	1/1	(3)	(2)	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	1/1	(1)	1/1	(2)	0/0	4/4	1/0	1/0	1/1	
Mercury (II) nitrate	-> see: Mercury nitrate																													
Mercury nitrate	$Hg(NO_3)_2$	010045-94-0	saturated	(T+)		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	1/0	0/0	1/3	1/0	0/0	(1)	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	1/1	1/1	1/1	
Mercuric nitrate	-> see: Mercury nitrate																													
Ramasit	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	Hydrophobing agent for textiles; BASF
Resorcinol	$C_6H_6O_2$	000108-46-3	5 %	—		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	2/4	0/0	3/3	1/3	1/1	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Resorcinol	$C_6H_6O_2$	000108-46-3	saturated	Xn		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	3/4	0/0	0/0	1/1	(1)	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Beef tallow	—	061789-97-7		—		0/0	0/0	1/0	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Beef tallow emulsion	—	—	sulphurised	(—)		1/0	0/0	(2)	(2)	0/0	0/0	0/0	1/0	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(2)	(2)	0/0	(2)	(1)	(1)	0/0	
Castor oil	—	008001-79-4	100 %	Xi		1/1	1/1	1/0	1/0	(1)	1/0	(2)	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Crude oil	—	—	100 %	(N)		0/0	1/3	1/0	(3)	1/0	0/0	1/0	1/3	3/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/3	0/0	(2)	(1)	(1)		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Rose oil	—	008007-01-0		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Roasting gases	—	—	any	(T)		0/0	0/0	(2)	0/0	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(4)	(2)	(2)	0/0	
Colza oil	—	008002-13-9		—		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	(1)	1/1	1/1		
Rum flavouring	—	008030-89-5		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(3)	(3)	(4)	(3)	0/0	(1)	(1)	(1)		
Sagrotan	—	—	liquid	?		1/2	1/3	0/0	3/0	0/0	0/0	(3)	1/3	3/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	3/0	0/0	(2)	(1)	(1)		Disinfectants; Schülke & Mayr
Salicylaldehyde	$C_7H_6O_2$	000090-02-8		Xn, Xi		1/1	1/2	(3)	2/3	0/0	1/2	(3)	1/2	4/4	3/3	3/4	0/0	0/0	1/4	1/1	(1)	(3)	(3)	(3)	4/4	0/0	(2)	(1)	(1)		
Salicylic acid	$C_7H_6O_3$	000069-72-7	saturated	(Xn, Xi)		1/1	1/1	1/0	1/2	1/0	1/1	4/4	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1	
Salicylic acid	$C_7H_6O_3$	000069-72-7	Powder	Xn, Xi		1/1	1/1	1/0	1/2	(1)	1/2	(3)	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1	
Salicylic acid methyl ester	-> see: Methyl salicylate																													
Salammoniac	-> see: Ammonium chloride																													
Ammonia solution	-> see: Ammonium hydroxide																													
Nitric acid	HNO_3	007697-37-2	1-10 %	C		1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1	1/1	
Nitric acid	HNO_3	007697-37-2	50 %	C+		2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO_3	007697-37-2	66 %	C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO_3	007697-37-2	100 %	O, C+		4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	0/0	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	?	
Nitric acid	HNO_3	007697-37-2	70 %	O, C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2	1/2	
Hydrochloric acid	HCl	007647-01-0	1-5 %	—		1/1	1/1	4/4	1/1	(2)	1/2	4/4	1/1	1/1	1/1	1/1	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	3/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	35 %	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	konz.	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	20 %	Xi		1/1	1/1	4/4	2/3	3/0	1/2	4/4	1/1	1/1	1/1	1/3	0/0	0/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	4/4	4/4	4/4	1/1	Hydrochloric acid
Hydrochloric acid aluminium salt, anhydrous	-> see: Aluminium chloride																													
Salt brine	NaCl	007647-14-5	saturated	—		1/1	1/1	1/0	(1)	(1)	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3	1/2	0/0	
Salt water, seawater	—	—		—		1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	
Saturated steam condensate	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(2)	1/1	1/1		
Oxygen	O_2	007782-44-7	tech. pure	O		1/3	1/3	2/0	1/0	(1)	0/0	1/0	1/3	1/0	0/0	1/1	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Lubricating oils	—	—		?		1/3	2/3	(2-3)	(1)	(2)	0/0	(2)	3/0	0/0	0/0	1/1	1/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0	
Lubricating soap	—	—	diluted	?		1/3	1/1	(2-3)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(1)	1/1	0/0	(2)	(1)	(1)	0/0	
Sulphur	S_8	007704-34-9	tech. pure	Xi		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	3/0	3/4	1/1	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	(1)	1/1	1/1	1/1	Sulphur, net sulphur, sulphur bloom
Sulphur, melted, 121 °C	S_8	007704-34-9		?		0	0	(4)	(3)	0	4	4	4	4	0	0	0	4	0	0	(1)	0	4	1	4	0	(3)	1	1	0/0	
Sulphur chloride	S_2Cl_2	010025-67-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	4/4	1/0	4/4	0/0	3/4	(1/1L)[1]	(1/1L)[1]	0/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Sulphur dioxide	SO_2	007446-09-5	moist	T, C		1/1	1/1	(3)	(3)	0/0	1/1	4/4	1/3	3/4	2/2	1/2	0/0	0/0	1/1	1/1	1/1	1/4	1/0	4/4	4/4	0/0	3/4	1/1	1/1	1/0	with H2O -> Sulphurous acid
Sulphur dioxide	SO_2	007446-09-5	liquid	T, C		3/4	4/4	(3)	3/4	0/0	4/4	4/4	4/4	4/4	2/2	3/4	0/0	0/0	1/2	1/1	1/1	4/4	1/0	4/4	4/4	0/0	(3)	(1)	(1)	1/0	with H2O -> Sulphurous acid
Sulphur dioxide, aqueous solution	-> see: Sulphurous acid																													
Sulphur ether	-> see: Ethyl ether																													
Sulphur hexaflurod	SF_6	002551-62-4		—		0/0	0/0	1/0	(2)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	1/0	0/0	0/0	(1)	(2)	1/0	3/0	1/0	0/0	(1)	(1)	(1)		
Carbon disulfide	CS_2	000075-15-0		F+, T	X	4/4	4/4	3/0	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/3	1/1	1/0	1/1	4/4	1/0	4/4	0/0	1/1	1/1	1/1	1/0	
Sulphur monochloride	-> see: Sulphur chloride																													
Sulphur sodium	-> see: Sodium sulphide																													
Sulphuric acid	H_2SO_4	007664-93-9	40 %	C+		1/1	1/1	4/4	2/0	(4)	1/2	4/4	1/1	2/0	3/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	(3)	1/1	4/4	0/0	3/4	2/3	2/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	60 %	C+		1/3	1/3	4/4	3/3	(4)	1/2	4/4	1/3	2/4	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	4/4	3/4	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	80 %	C+		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/1	3/4	3/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	2/4	2/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	95 %	C+		3/4	3/4	4/4	4/4	4/4	2/2	4/4	3/4	4/4	4/4	2/4	0/0	4/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	1/3	1/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	fuming	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	4/4	4/4	1/0	4/4	0/0	(3)	1/2	1/1	0/0	Oleum
Sulphuric acid	H_2SO_4	007664-93-9	1-6 %	Xi		1/1	1/1	4/4	1/1	0/0	1/1	4/4	1/1	1/2	1/1	1/2	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/0	0/0	(3)	2/2	1/2	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	20 %	Xi		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	(3)	2/3	2/3		
Sulphuric acid copper (II) salt	-> see: Copper sulphate																													
Sulphuric acid monomethyl ester	-> see: Methyl sulphuric acid																													
Sulphur trioxide	SO_3	007446-11-9		C+		4/4	4/4	4/4	(4)	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	(2)	(2)	3/4	3/0	1/0	4/4	0/0	(3)	(1)	(1)	0/0	
Hydrogen sulphide	H_2S	007783-06-4	saturated	F+, T+	X	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	3/0	1/0	1/3	3/3	1/0	0/0	1/0	1/1	1/1	1/0	(3)	4/4	0/0	1/1	1/1	1/1	0/0	
Sulphurous acid	H_2SO_3	007782-99-2	saturated	(C)		1/1	1/1	4/4	4/4	1/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	3/0	(3)	3/4	0/0	3/4	1/1	1/1	1/1	
Sulphuric acid dichloride	-> see: Thionyl chloride																													
Pork fat	—	—		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	2/0	1/0	1/0	0/0	(1)	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sebacic acid dibenzyl ester	-> see: Dibenzyl sebacate																													
Sebacic acid dibutyl ester	-> see: Dibutylsebacat																													
Sebacic acid diethyl ester	-> see: Diethylsebacate																													
Ocean water, seawater	-> see: Salt water, seawater																													
Soap solution	—	—	any	(—)		1/1	0/0	4/4	(2)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/1	
Mustard	—	—		—		0/0	0/0	(2)	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	1/0	1/0	0/0	(2)	1/0L	1/0L		
Mustard oil	-> see: Allyl mustard oil																													
Silver acetate	$C_2H_3AgO_2$	000563-63-3		Xi		1/1	1/1	(2)	1/2	(2)	1/1	(2)	1/1	2/2	1/1	2/2	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	(3)	0/0	(4)	0/0	0/0	0/0	
Silver cyanide	CAgN	000506-64-9		T		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	(1)	(1)	(3)	0/0	(4)	0/0	0/0	0/0	
Silver nitrate	$AgNO_3$	007761-88-8	aqueous	C		1/1	0/0	1/0	1/1	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	1/1	
Silver nitrate	$AgNO_3$	007761-88-8		C		1/1	1/2	1/0	1/1	(2)	1/1	1/0	1/2	2/3	1/1	1/2	1/3	1/2	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	1/1	
Silicon dioxide	-> see: Silicic acid																													
Silicone fats	—	—		(—)		0/0	0/0	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	1/0	1/0	1/1	0/0	1/1	1/1	1/1		
Silicone oil	—	—		?		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	3/3	1/0	1/4	0/0	1/1	0/0	1/1	1/1	(1)	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	Polysiloxan
Skydrol 500 (B4)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	0/0	1/0	4/4	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Solutia
Skydrol 7000	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	1/0	2/0	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Solutia
Soda	-> see: Sodium carbonate																													
Soya oil	—	008001-22-7		—		0/0	0/0	(2)	(1)	1/0	0/0	2/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	1/1	
Spindle oil	—	—		?		3/3	2/3	(2)	(2)	1/0	0/0	(2)	1/4	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Spinning bath acids	—	—	100mg CS_2/l	?		1/0	0/0	4/4	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(3)	(2)	4/4	0/0	(4)	3/4	2/4	0/0	
Spinning solution, viscous -	—	—		(Xn, Xi)		1/1	1/1	4/4	(3)	0/0	0/0		1/1	0/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	(3)	(2)	4/4	0/0	(3)	3/4	2/4	0/0	
Spirits	C_2H_6O	—		—		1/1	1/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	1/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	0/0	Ethanol 40 %
Spirit	C_2H_6O	—		F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1		Ethanol
Rinsing agent	—	—	aqueous	?		1/1	1/1	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0	
Starch gum	-> see: Dextrin																													
Starch solution	$(C_6H_{10}O_5)_n$	—	any	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Starch syrup	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Stauffer's grease	—	—		(—)		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	1/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	(1)	(2)	0/0	(1)	1/1	1/1	0/0	
Stearic acid	$C_{18}H_{36}O_2$	000057-11-4	fuming	Xi		1/3	1/3	1/0	1/2	1/0	1/1	1/0	1/3	1/2	2/2	1/2	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
Stearic acid zinc salt	-> see: Zinc stearate		crystals																											
Stearic acid butyl ester	$C_{22}H_{44}O_2$	000123-95-5	100 %	Xi		0/0	0/0	(1)	(3)	1/0	0/0	(2)	(2)	0/0	0/0	1/0	1/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1	0/0	
Coal tar oil	—	092045-38-0	100 %	T		1/0	1/3	1/0	(3)	0/0	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	1/1	1/1		
Nitrogen	N_2	007727-37-9		—		0/0	0/0	1/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1		
Nitrogen tetroxide	N_2O_4	010544-72-6		(O), T+, C		0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(2)	(1)	(1)		
Strontium bromide	$SrBr_2$	010476-81-0		Xi		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(3)	0/0	0/0		
Strychnine	$C_{21}H_{22}N_2O_2$	000057-24-9		T+		1/1	1/1	(1)	(1)	(2)	0/0	(2)	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)		
Styrene	C_8H_8	000100-42-5	100 %	Xn, Xi	X	4/4	3/4	1/1	4/4	1/1	(4)	1/1	3/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(2)	4/4	3/0	4/4	0/0	1/1	1/1	1/1	0/0	
Sulphite lye	-> see: Calcium bisulphite																													
Sulphuryl chloride	Cl_2SO_2	007791-25-5	tech. pure	C		4/4	4/4	4/4	1/0	0/0	0/0	4/4	4/4	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/0	3/0	3/0	1/0	4/4	0/0	3/4	0/0	0/0		
Tallow	—	—	tech. pure	—		1/1	1/1	1/0	(1)	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1	0/0	
Tannin	$C_{76}H_{52}O_{46}$	001401-55-4	10 %	Xi		1/1	1/1	1/0	3/3	0/0	1/1	4/4	1/1	3/3	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	1/1	
Tannin	$C_{76}H_{52}O_{46}$	001401-55-4		Xi		1/1	1/1	1/0	4/4	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	1/1	
Tar	—	—		T		0/0	1/0	1/0	(3)	1/0	0/0	1/0	(2)	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(1)	(1)	(1)		
Surfactants	-> see: Wetting agent																													
Turpentine substitute	—	—		Xn, N	X	0/0	0/0	1/0	(3)	1/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	(3)	0/0	1/1	1/1	1/1	1/1	
Turpentine oil	—	008006-64-2		Xn	X	2/2	3/4	1/0	4/4	1/0	3/3	1/1	4/4	4/4	4/4	2/3	4/4	3/3	1/1	1/1	1/0	1/3	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
White spirit	—	—	liquid	Xn, N	X	0/0	2/3	(1)	(3)	1/0	(4)	1/0	3/4	4/4	0/0	1/3	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0	
Test fuel A (ISO-Fluid A)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	1/0	0/0	(1)	(1)	(1)		
Test fuel B (ISO-Fluid B)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)		
Test fuel C (ISO-Fluid C)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)		
Test fuel D (ISO-Fluid D)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	4/4	0/0	(1)	(1)	(1)		
Tetrabromomethane (TBE)	$C_2H_2Br_4$	—	100 %	T+		4/4	3/4	(3)	4/4	(4)	(4)	(3)	3/4	4/4	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Carbon tetrabromide	CBr_4	000558-13-4		Xn, Xi		0/0	0/0	(3)	4/4	0/0	0/0	(3)	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Tetrabromomethane	-> see: Carbon tetrabromide																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Tetrachloroethane	$C_2H_2Cl_4$	—	tech. pure	T+		3/0	3/4	3/0	4/4	(4)	(4)	1/1	3/4	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Tetrachloroethene	-> see: Perchloroethylene																													
Tetrachloroethylene	-> see: Perchloroethylene																													
Carbon tetrachloride (TETRA)	CCl_4	000056-23-5		T		4/4	4/4	4/4	4/4	1/4	4/4	2/3	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	1/1	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Methane tetrachloride	-> see: Carbon tetrachloride																													
Tetrachlorotitanium	-> see: Titanium tetrachloride																													
Tetraethyl lead (TEL)	$C_8H_{20}Pb$	000078-00-2	techn. rein	T+	X	1/0	1/0	1/4	3/0	(2)	(4)	(2)	2/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/0	0/0	(2)	(1)	(1)	1/1	
Tetraethylorthosilicate	$C_8H_{20}SiO_4$	000078-10-4		Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	1/0	0/0	(1)	(1)	(1)		
Tetrafluoromethane	CF_4	000075-73-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Tetrahydro-1,4-oxazine	-> see: Morpholine																													
Tetrahydrofuran (THF)	C_4H_8O	000109-99-9		F, Xi	X	3/4	4/4	1/0	4/4	1/0	3/4	1/3	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	1/1	
Tetrahydrofurfuryl alcohol	$C_5H_{10}O_2$	000097-99-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(2)	(1)	(1)		
Tetrahydronaphthalene	$C_{10}H_{12}$	000119-64-2	tech. pure	Xi		3/4	4/4	1/0	4/4	1/0	(4)	1/0	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	1/0	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Tetralin	-> see: Tetrahydronaphthalene																													
Tetramethylene oxide	-> see: Tetrahydrofuran																													
Tetraphosphorus decaoxide	-> see: Phosphorus pentoxide																													
Thiacyclopentadiene	-> see: Thiophene																													
Thiofuran	-> see: Thiophene																													
Thioglycolic acid	$C_2H_4SO_2$	000068-11-1		T, C		0/0	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	(4)	0/0	3/4	0/0	1/1	0/0	
Thionyl chloride	Cl_2SO	007719-09-7	tech. pure	C		4/4	4/4	4/4	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	(3)	3/0	1/0	4/4	0/0	3/4	0/0	0/0	0/0	
Thiophene	C_2H_4S	000110-02-1		F, Xn	X	3/3	3/3	(2)	4/4	0/0	(4)	(2)	3/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	4/4	3/0	0/0	(1)	(1)	(1)	0/0	
Thymol	$C_{10}H_{14}O$	000089-83-8		C, Xn		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(3)	3/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	1/0	4/4	0/0	(1)	(1)	(1)		
Titanium chloride	-> see: Titanium tetrachloride																													
Titanium tetrachloride	$TiCl_4$	007550-45-0		C		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(4)	0/0	0/0		
Toluene	-> see: Methylbenzene																													
Toluol	-> see: Methylbenzene																													
Toluenesulphone chloramide sodium, p-	-> see: Chloramine T																													
Tragacanth	—	009000-65-1		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1		
Transformer oil	—	—		?		1/3	3/3	1/0	(3)	1/1	1/0	3/3	1/3	1/3	1/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	2/3	3/3	0/0	1/1	(1)	(1)	0/0	
Grape sugar	-> see: Glucose																													
Triacetin	$C_9H_{14}O_6$	000102-76-1		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	3/3	0/0	(1)	(1)	(1)		
Tribromomethane	-> see: Bromoform																													
Tributyl citrate	$C_{18}H_{32}O_7$	000077-94-1		—		1/2	2/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Tributyl phosphate (TBP)	$C_{12}H_{27}PO_4$	000126-73-8	tech. pure	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Trichloroacetaldehyde	C_2HCl_3O	000075-87-6	100 %	T/Xi		1/1	1/1	4/4	(3)	(4)	0/0	(3)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	0/0	(4)	3/0	(4)	4/4	0/0	4/4	0/0	0/0	0/0	
Trichloroacetaldehyde hydrate	-> see: Chloral hydrate																													
Trichloraldehyde hydrate	-> see: Chloral hydrate																													
Trichlorobenzene	$C_6H_3Cl_3$	—	100 %	(Xn)		4/4	4/4	(3)	(3)	0/0	(4)	(2)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	(2)	(3)	(4)	(3)	4/4	0/0	(2)	0/0	0/0	0/0	Isomer not specified in the source
Trichloroacetic acid (TCA)	$C_2HCl_3O_2$	000076-03-9		C+		1/4	3/4	4/4	4/4	4/4	0/0	4/4	1/1	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	1/3	3/0L	2/0L	1/1	
Trichloroethane	$C_2H_3Cl_3$	—		Xn		3/4	4/4	3/0	4/4	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	(1)	1/3	4/4	1/0	4/4	0/0	4/4	0/0	0/0	0/0	Isomer not specified in the source
Trichloroethene	-> see: Trichloroethylene																													
Trichloroethylene (TRI)	C_2HCl_3	000079-01-6	100 %	Xn		3/4	4/4	3/0	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/4	1/2	1/1	1/0	1/1	4/4	1/3	4/4	0/0	1/3	(1/1L)[1]	(1/1L)[1]	1/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Trichlorofluoromethane	CCl_3F	000075-69-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(3)	(1)	0/0	4/4	2/0	1/0	0/0	(3)	0/0	0/0	0/0	
Trichloromethane	-> siehe: Chloroform																													
Trichloromonofluoromethane	-> siehe: Trichlorfluormethan																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Trichlorophenol	$C_6H_3Cl_3O$	—		(Xn, Xi)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(4)	(3)	(4)	0/0	(3)	0/0	0/0		Isomer not specified in the source
Trichlorophosphine	-> see: Phosphorus trichloride																													
Trichlorophosphine oxide	-> see: Phosphorus oxychloride																													
Trichlorophosphorus oxide	-> see: Phosphorus oxychloride																													
Trichlorotrifluoroethane	$C_2Cl_3F_3$	000076-13-1		?		0/0	0/0	1/0	(3)	1/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		
Triethanolamine (TEA)	$C_6H_{15}NO_3$	000102-71-6	tech. pure	Xi		1/1	1/2	(2)	(2)	1/0	0/0	2/2	1/1	1/1	0/0	3/0	4/4	1/1	0/0	1/1	1/0	1/0	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Triethylamine (TEA)	$C_6H_{15}N$	000121-44-8	tech. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	1/1	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	3/4	4/4	3/0	3/4	0/0	(1)	(1)	(1)	0/0	
Triethylene glycol	-> see: Triglycol																													
Triethylene glycol diacetate	-> see: Triglycol acetate																													
Trifluorotrichloroethane	$C_2Cl_3F_3$	—	100 %	?		4/4	3/4	1/0	3/0	0/0	0/0	1/0	4/4	4/4	1/0	3/4	4/4	3/3	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		Isomer not specified in the source
Triglycol	$C_6H_{14}O_4$	000112-27-6		Xi		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	(3)	0/0	(1)	(1)	(1)	0/0	
Triglycol acetate	$C_{10}H_{18}O_6$	000111-21-7		?		0/0	0/0	(3)	(3)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)		
Trihydroxybenzoic acid, 3,4,5-	-> see: Gallic acid																													
Trihydroxybenzene, 1,2,3-	-> see: Pyrogallol																													
Trihydroxybutane	-> see: Butanetriol																													
Trihydroxypurine, 2,6,8-	-> see: Uric acid																													
Trihydroxytriethylamine	-> see: Triethanolamine																													
Triiodomethane	-> see: Iodoform																													
Triisopropylbenzene	$C_{15}H_{24}$	000717-74-8		—		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Tricresyl phosphate (TCF)	$C_{21}H_{21}PO_4$	—	tech. pure	T/Xn, N		1/1	1/1	1/0	4/4	1/0	0/0	1/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	1/1	1/1	1/1	1/1	Isomer not specified in the source
Trimethylbenzene, 1,3,4-	-> see: Pseudocumene																													
Trimethylolpropane	$C_6H_{14}O_3$	000077-99-6	aqueous	—		0/0	0/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	0/0	(1)	(1)	(1)		
Trimethylpentane, 2,2,4-	-> see: Iso-octan																													
Trisodium phosphate	Na_3PO_4	007601-54-9		Xi		1/1	1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(4)	1/1	1/1		
Trisodium phosphate, tribasic	-> see: Sodium phosphate																													
Trinitrophenol, 2,4,6-	-> see: Picric acid																													
Trioctyl phosphate	$C_{24}H_{54}PO_4$	000078-42-2	tech. pure	(Xn)		3/0	1/0	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	(1)	(1)	(1)	0/0	
Tripen	-> see: Hexachlorobutadiene																													
Tripropylene glycol (TPG)	$C_9H_{20}O_4$	024800-44-0		(—)		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/1	(2)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Tris(2-ethylhexyl) phosphate	-> see: Trioctyl phosphate																													
Tris(hydroxyethyl)-amine	-> see: Triethanolamine																													
Tris(hydroxymethyl)propane	-> see: Trimethylolpropane																													
Tropic acid tropylester sulphate	-> see: Atropine sulphate																													
Tung oil	-> see: Wood oil																													
Turbine oil (mineral oil base)	—	—		?		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	(2)	1/0	0/0	1/1	1/1	1/1		
Superchloric acid	-> see: Perchloric acid																													
Undecanol	-> see: Undecyl alcohol																													
Undecyl alcohol	$C_{11}H_{24}O$	000112-42-5		Xi		1/2	1/3	(1)	2/3	(1)	1/2	1/0	1/2	2/2	3/3	1/3	0/0	1/1	1/2	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(1)	(1)	(1)		
Urine	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	3/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	
Urotropine	-> see: Hexamethylenetetramine																													
Vaseline	—	008009-03-8	tech. pure	(—)		3/4	2/3	1/0	1/0	1/0	0/0		1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Vaseline oil	—	008012-95-1	100 %	?		0/0	1/3	1/0	(2)	1/0	1/0		1/3	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	Paraffin oil
Vaseline oil	—	008012-95-1		?		1/1	1/3	1/0	1/0	1/0	0/0	1/1	1/3	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/3	0/0	1/1	1/1	1/1	1/1	Paraffin oil
Vinyl acetate	$C_4H_6O_2$	000108-05-4	tech. pure	F	X	0/0	1/1	1/0	4/4	(3)	(4)		1/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	1/0	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Vinylbenzene	-> see: Styrene																													
Vinylcarbinol	-> see: Allyl alcohol																													
Vinyl chloride	-> see: Chlorethylene																													
Vinyl cyanide	-> see: Acrylonitrile																													
Vinyl ethylene	-> see: Butadiene, 1,3-																													
Vinylidene chloride	$C_2H_2Cl_2$	000075-35-4		F+, Xn	X	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	2/3	1/1	(1)	(2)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	
Vitamin C	$C_6H_8O_6$	000050-81-7	liquid	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	(1)	(1)		
Wax alcohol	—	—	tech. pure	(—)		3/4	3/4	(2)	(2)	1/0	0/0		3/4	0/0	0/0	1/1	3/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	(1)	(1)	0/0	
Waxes	—	—		—		0/0	1/3	1/1	1/1	1/1	0/0		1/3	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	(4)	1/0	(1)	0/0	1/1	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Walnut oil	—	008024-09-7		—		0/0	0/0	(2)	(2)	1/0	0/0		1/3	3/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	(1)	1/1	1/1		
Spermaceti	—	008002-23-1		—		0/0	1/3	(1)	1/1	1/0	0/0		1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Detergent	—	—		?		1/1	1/1	1/0	1/1	1/1	0/0		1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	(2)	0/0	1/1	1/1	1/1	1/1	
Water	H_2O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Water, distilled ~	H_2O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Water glass	$Na_2Si_3O_7$	001344-09-8	saturated	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	0/0	1/1	1/1	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	Aqueous solution of alkali silicates
Hydrogen	H_2	001333-74-0	tech. pure	F+	X	1/1	1/1	1/0	1/0	0/0	0/0		1/1	1/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Hydrogen peroxide	H_2O_2	007722-84-1	30 %	C		1/1	1/2	4/4	1/1	1/0	1/2	4/4	1/3	1/2	1/1	1/1	0/0	1/0	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	(3)	1/1	1/1	1/1	
Hydrogen peroxide	H_2O_2	007722-84-1	100 %	O, C		1/4	1/4	4/4	0/0	0/0	0/0	4/4	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(3)	(1)	(1)	?	
Hydrogen peroxide	H_2O_2	007722-84-1	90 %	O, C		1/1	1/2	4/4	1/1	0/0	1/2	4/4	1/3	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/3	4/4	0/0	(3)	1/1	1/1	?	
Hydrogen peroxide	H_2O_2	007722-84-1	3 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	1/0	1/1	1/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	3/4	0/0	(3)	1/1	1/1	1/1	
Oxygenated water	-> see: Hydrogen peroxide																														
Plasticiser	—	—		?		1/3	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	3/3	0/0	(1)	(1)	0/0	(2-3)	0/0	4/4	0/0	(1)	(1)	(1)		
Wines	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	(2)	1/1	1/1	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	1/1	1/1	1/1	
Spirit of wine	C_2H_6O	—	50 %	(F)	X	1/0	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	Ethanol
Spirit of wine	C_2H_6O	—	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	Ethanol
Tartaric acid	$C_4H_6O_6$	000087-69-4	aqueous	Xi		1/1	1/1	3/3	1/2	0/0	0/0	(3)	1/1	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2	1/1	
Tartaric acid	$C_4H_6O_6$	000087-69-4		Xi		1/1	1/1	4/4	1/2	0/0	1/1	(3)	1/1	2/2	1/1	1/2	1/3	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2	1/1	
Cream of tartar	-> see: Potassium hydrogentartate																														
Whiskey	—	—		—		0/0	0/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1		Whisky, Scotch, Bourbon
White spirit	—	008042-47-5		Xn		1/0	1/0	(1)	(3)	1/0	(4)	1/0	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	1/0	(2)	0/0	1/1	1/1	1/1		
Wool grease	-> see: Lanolin																														
Xenon	Xe	007440-63-3		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1		
Xylol	-> see: Xylene																														
Xylene	C_8H_{10}	001330-20-7		(F), Xn	X	3/4	3/4	1/0	4/4	0/0	3/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/0	1/3	4/4	1/3	4/4	0/0	1/1	1/1	1/1	1/1	
Cedar oil	—	008000-27-9		?		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(4)	(2)	(3)	0/0	(1)	(1)	(1)		
Cinnamon	—	—	grinded	?		0/0	0/0	(2)	1/0	(2)	0/0	(2)	(2)	3/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Cinnamaldehyde	C_9H_8O	000104-55-2		Xn, Xi		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(1)	(1)	(1)		
Cinnamon oil	—	008007-80-5		Xn, Xi		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Zinc acetate	$C_4H_6ZnO_4$	000557-34-6	aqueous	Xn, Xi		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/3	0/0	(3)	(1)	(1)		
Zinc bromide	$ZnBr_2$	007699-45-8		C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(3)	0/0	0/0		
Zinc carbonate	$ZnCO_3$	003486-35-9	saturated	?		1/1	1/1	(1)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	No chemical effect expected due to low solubility
Zinc chloride	$ZnCl_2$	007646-85-7	aqueous	(C, Xn)		1/1	1/1	3/4	(2)	0/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1	
Zinc chloride	$ZnCl_2$	007646-85-7	10 %	C, Xn		1/1	1/1	3/4	1/0	0/0	1/1	2/0	1/1	1/3	0/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1	
Zinc nitrate	$Zn(NO_3)_2$	007779-88-6		O, C, Xn		1/1	1/1	1/4	(2)	0/0	0/0	(2)	1/1	1/0	1/0	1/0	1/0	1/1	0/0	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(3)	(1)	(1)	0/0	
Zinc oxide	ZnO	001314-13-2	solid	Xn, Xi		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		No chemical effect expected due to low solubility
Zinc phosphate	$Zn_3(PO_4)_2$	007779-90-0	saturated	?		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	
Zinc ointment	—	—		?		0/0	0/0	(1)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	(4)	(2)	(2)	0/0	(2)	(1)	(1)		
Zinc sludge	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	(3)	0/0	0/0		
Zinc stearate	$C_{36}H_{70}ZnO_4$	000557-05-1		Xi		1/1	1/1	(1)	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	(2)	0/0	(2)	(1)	(1)		
Zinc sulphate	$ZnSO_4$	007733-02-0	10 %	—		1/1	1/1	(3)	1/0	(2)	1/0	2/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	1/1	
Zinc vitriol	-> see: Zinc sulphate																														
Tin (II) chloride	$SnCl_2$	007772-99-8	aqueous	(C, Xn)		1/1	1/1	(4)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	1/1	
Tin (II) chloride	$SnCl_2$	007772-99-8	saturated	C, Xn		1/1	1/1	4/4	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	1/1	
Tin (IV) chloride	$SnCl_4$	007646-78-8	aqueous	C		1/1	1/1	4/4	(3)	0/0	0/0	(4)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	4/4	3/4		
Tin dichloride	-> see: Tin (II) chloride																														
Tin protochloride	-> see: Tin (II) chloride																														
Tin tetrachloride	-> see: Tin (IV) chloride																														
Lemon juice	—	—		—		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	1/0	1/1	0/0	(1)	1/1	1/1		
Citric acid	$C_6H_8O_7$	000077-92-9	10 %	Xi		1/1	1/1	1/1	1/2	1/3	1/1	2/4	1/1	1/2	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/1	1/1	1/1	
Citric acid	$C_6H_8O_7$	000077-92-9	50 %	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1	
Citric acid	$C_6H_8O_7$	000077-92-9	saturated	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1	
Lemon peel oil	—	084929-31-7		Xi	(X)	0/0	0/0	(2)	(3)	1/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	3/3	0/0	1/0	(1)	(2)	4/4	(2)	3/3	0/0	1/1	(1)	(1)		mainly limes
Citrus juices	—	—	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	1/1	0/0	(2)	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers				Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sugar beet juice	—	—		—		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Sugar acid	—	—	saturated	(Xi)		1/1	1/1	(3)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		
Sugar syrup	—	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Two-stroke oil	—	—	100 %	—		0/0	1/3	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

Resistance

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

0	no information available/no statement possible
1	very good resistance/suitable
2	good resistance/suitable
3	limited resistance
4	not resistant
K	no general information possible
L	Risk of pitting or stress corrosion cracking
( )	Estimated value

Hazard preventions

E	explosive
O	oxidising
F	inflammatory
F+	extremely inflammable
T	toxic
T+	very toxic
C	caustic
Xn	harmful to health
Xi	irritant
N	environmentally hazardous

Name of materials

Thermoplastics

HDPE	High density polyethylene
LDPE	Low density polyethylene
PA	Polyamide (nylon)
PC	Polycarbonate
PETG	Polyethylene terephthalate glycol (co-
PMP	polyester) Polymethylpentene (TPX)
POM	Polyoxymethylene
PP	Polypropylene
PS	Polystyrene
PSU	Polysulfone
PVC	Polyvinyl chloride
SAN	Styrene acrylonitrile

Fluoroplastics

E-CTFE	Ethylene-chlorotrifluoroethylene (Halar)
ETFE	Ethylene tetrafluoroethylene
FEP	Tetrafluoroethylene-perfluoropropylene (Teflon,
PTFE	FEP) Polytetrafluoroethylene (Teflon)
PVDF	Polyvinylidene fluoride

Elastomers

EPDM	Ethylene propylene terpolymer rubber
FPM/FKM	Fluoropolymer (Viton)
NBR	Nitrile rubber
SI	Silicone rubber

Metals

Al	Aluminium
V2A	Stainless steel 1.4301 (AISI 304)
V4A	Stainless steel 1.4401 (AISI 316)
Hastelloy C	Nickel-chromium-molybdenum alloy

LISTE DES PRODUITS CHIMIQUES MACH I

AVIS IMPORTANT

Le tableau „Résistance chimique des matières plastiques“ a été établi sur la base d'informations fournies par différents fabricants de matières premières. Les valeurs se réfèrent exclusivement à des essais en laboratoire sur des matières premières. Les pièces en plastique fabriquées à partir de ces matières sont souvent soumises à des influences qui ne peuvent pas être détectées lors des essais en laboratoire (température, pression, contraintes du matériau, exposition à des substances chimiques, caractéristiques de conception, etc.) Pour ces raisons, les valeurs indiquées ne peuvent servir que de guide. En cas de doute, nous recommandons vivement d'effectuer un test. Aucune revendication légale ne peut être dérivée de ces informations, nous excluons toute garantie et responsabilité. La résistance chimique et mécanique ne suffit pas à elle seule à évaluer l'aptitude au service d'un produit. Il convient notamment de tenir compte des réglementations relatives aux liquides inflammables (protection contre les explosions).

COPYRIGHT

Nous tenons à remercier Bürkle GmbH de nous avoir accordé le droit d'utiliser ce tableau.
Ce tableau est publié et maintenu par Bürkle GmbH, D-79415 Bad Bellingen, Allemagne, en tant que guide de référence. Cet avis de droit d'auteur ne peut être supprimé. Le tableau peut être distribué et copié librement tant que l'avis de copyright reste intact.

Langue de la liste des produits chimiques: anglais

LISTE DES MATÉRIAUX MACH I

Réservoir:	PP	Tuyau d'aspiration:	PP, EVA
Pompe à eaux usées:	PP + GF20	Tuyau de vidange:	PP, EVA
Clapet anti-retour:	PP	Buse de sol:	PP
Raccords à vis:	PP	Tube d'aspiration:	PP
Accouplements en C:	PA6 + GF30	Tête d'aspiration:	ABS

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Exhaust gases, alkaline	—	—		?		1/1	0/0	(2)	0/0	0/0	0/0	(1)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/4	1/0	1/0	1/0	0/0	(2)	(1)	(1)		
Exhaust gases, containing hydrogen fluoride	—	—	low	?		1/1	0/0	(3)	(3)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	(2)	(2)	1/1	
Exhaust gases, carbon dioxide-containing	—	—	low	?		1/1	0/0	(1)	(1)	(1)	(1)	(1)	1/1	(1)	(1)	1/1	(1)	(1)	1/1	1/1	1/1	1/1	1/0	1/0	(1)	(1)	(1)	(1)	(1)	0/0	
Exhaust gases, nitrous	—	—	low	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	(3)	0/0	(2)	(1)	(1)		
Exhaust gases containing hydrochloric acid	—	—	any	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	2/2L	2/2L	3/3	
Exhaust gases containing sulphur dioxide	—	—	low	?		1/1	0/0	(2)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	1/1	1/1	0/0	
Exhaust gases containing sulphuric acid	—	—	any	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0	
Exhaust gases, containing sulphur trioxide	—	—	low	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	4/4	0/0	0/0	1/1	0/0	0/0	(2)	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0	
Acetaldehyde	C_2H_4O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	3/4	
Acetaldehyde	C_2H_4O	000075-07-0	tech. pure	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Acetamide	C_2H_5NO	000060-35-5	saturated	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)	1/1	
Acetamino-4-ethoxybenzene, 1-	-> see: Phenacetin																														
Acetic anhydride	-> see: Acetic anhydride																														
Acetone	C_3H_6O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	1/1	
Acetonitrile	C_2H_3N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Acetophenone	C_8H_8O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Acetoxybenzoic acid, 2-	-> see: Acetylsalicylic acid																														
Acetyl-5-methyl-2,3-dihydropyran-2,4-dione, -2	-> see: PDehydroacetic acid																														
Acetyl chloride	C_2H_3ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	0/0	
Acetylene	C_2H_2	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	1/1	0/0	1/0	1/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	
Acetylene tetrabromide	-> see: Tetrabromomethane, 1,1,2,2-																														
Acetylene tetrachloride	-> see: Tetrachloroethane-1,1,2,2																														
Acetylsalicylic acid	$C_9H_8O_4$	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	1/0	
Acrylonitrile	C_3H_3N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	1/1	
Acrylic acid butyl ester	-> see: Butyl acrylate																														
Acrylic acid ethyl ester	-> see: Ethyl acrylate																														
Acrylic acid methyl ester	-> see: Methyl acrylate																														
Acrylic acid nitrile	-> see: Acrylonitrile																														
Adipic acid	$C_6H_{10}O_4$	000124-04-9	saturated	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	1/0	(2)	(2)	1/1	
Adipic acid dioctyl ester	-> see: Dioctyladipate																														
Acrylic acid	H_2SO_4	007664-93-9	38 %	C		1/1	1/1	4/4	1/1	(4)	1/1	4/4	1/1	1/1	1/1	1/3	3/4	0/0	(1)	1/1	1/1	1/1	1/0	1/1	4/4	0/0	3/4	2/3	2/3	1/1	"Battery acid"
Alanine	$C_3H_7NO_2$	000056-41-7		—		1/1	1/1	1/1	4/4	(2)	1/1	(1)	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(2)	(2)	(2)		
Alum	-> see: Potassium aluminium sulphate																														
Alcohol	-> see: Ethanol																														
Allyl acetate	$C_5H_8O_2$	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		
Allyl alcohol	C_3H_6O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	1/1	(2)	1/0	4/4	3/0	0/0	1/1	1/1	1/1	1/1	
Allyl chloride	C_3H_5Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)	0/0	
Allyl isothiocyanate	-> see: Allyl mustard oil																														
Allyl mustard oil	C_4H_5NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		Oleum Sinapis
Aluminium (hydroxide) acetate	$C_4H_7AlO_5$	000139-12-8	aqueous	Xn		1/1	1/1	1/1	(1)	1/0	1/1	1/0	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	(1)	1/0	(3)	3/0	0/0	1/1	1/1	1/1	0/0	"Acetic acid alumina"
Aluminium ammonium sulphate	$(NH_4)Al(SO_4)_2$	007784-26-1	saturated	Xi		1/1	1/1	3/4	(2)	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3	0/0	
Aluminium chloride	$AlCl_3$	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	1/1	0/0	1/1	0/0	1/1	2/2	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	4/4	3/4	1/1	
Aluminium chloride	$AlCl_3$	007784-13-6	solid	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	(3)	0/0	4/4	4/4	3/4	1/1	Hydrochloric acid aluminium salt, anhydrous
Aluminium chloride	$AlCl_3$	007784-13-6	saturated	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	(1)	1/1	(2)	1/0	1/1	0/0	4/4	4/4	3/4	1/1	Hydrochloric acid aluminium salt, anhydrous
Aluminium fluoride	AlF_3	007789-18-1	aqueous	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	0/0	
Aluminium hydroxide	$Al(HO)_3$	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1/1	1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	0/0	No chemical effect expected due to low solubility
Aluminium hydroxide diacetate	-> see: Acetic clay																														
Aluminium nitrate	$Al(NO_3)_3$	013473-90-0	aqueous	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Aluminium oxide	Al_2O_3	001344-28-1	solid	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	No chemical effect expected due to low solubility
Aluminium sulphate	$Al_2(SO_4)_3$	010043-01-3	10 %	?		1/1	1/1	1/0	1/0	(2)	1/1	3/4	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/2	1/1	1/1	
Aluminium sulphate	$Al_2(SO_4)_3$	010043-01-3	saturated	Xn		1/1	1/1	3/4	1/0	0/0	1/1	3/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	2/2	1/2	1/1	
Aluminium trifluoride	-> see: Aluminium fluoride																														
Formic acid	CH_2O_2	000064-18-6	50 %	C, F	X	1/1	1/2	4/4	3/3	0/0	1/2	4/4	1/2	3/3	2/2	2/3	0/0	1/3	1/1	1/1	1/1	1/1	3/4	4/4	4/4	0/0	(3)	1/3	1/2	1/1	
Formic acid	CH_2O_2	000064-18-6	98-100 %	C, F+, T	X	1/1	1/2	4/4	3/4	0/0	1/3	4/4	1/3	3/4	3/3	3/4	1/3	3/4	1/1	(1)	1/1	1/1	3/4	4/4	4/4	0/0	1/0	1/3	1/2	1/0	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Formic acid	CH_2O_2	000064-18-6	3 %	Xi		1/1	1/2	3/4	1/2	1/0	1/2	2/4	1/2	1/2	2/2	2/3	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(3)	4/4	0/0	(3)	1/2	1/1	1/1	
Formic acid amide	-> see: Formamide																													
Formic acid ethyl ester	-> see: Ethyl formate																													
Formic acid methyl ester	-> see: Methylformia																													
Aminobenzene	-> see: Aniline																													
Aminobutane	-> see: Buylamine																													
Aminoacetic acid	$C_2H_5NO_2$	000056-40-6	10 %	—		1/1	1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	(2)	(2)	(2)	0/0	
Aminoethanol, 2-	-> see: Ethanolamine																													
Aminoethanoic acid	-> see: Aminoacetic acid																													
Amonimethane	-> see: Methylamine, (mono-)																													
Aminopropane	-> see: Propylamine, n-																													
Aminopropionic acid, L-2-	-> see: Alanine, (L-)																													
Ammonia	-> see: Ammonium hydroxide																													
Ammonia, sulphuric acid	-> see: Ammonium sulphate																													
Ammonia water	-> see: Ammonium hydroxide																													
Ammonium 2-hydroxyacetate	-> see: Ammonium glycolate																													
Ammonium acetate	$C_2H_7NO_2$	000631-61-8	saturated	Xi		1/1	1/1	1/0	1/1	(2)	1/1	(1)	1/1	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(3)	2/2	0/0	1/1	(2)	(2)	1/1	
Ammonium alum	-> see: Aluminium ammonium sulphate																													
Ammonium aluminium sulphate	-> see: Aluminium ammonium sulphate																													
Ammonium bicarbonate	-> see: Ammonium hydrogen carbonate																													
Ammonium bifluoride	-> see: Ammoinium hydrogen difluoride																													
Ammonium carbonate	$(NH_4)_2CO_3$	010361-29-2	50 %	Xn		1/1	1/1	1/0	3/0	0/0	1/0	(2)	1/1	1/1	1/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Hartshorn salt
Ammonium carbonate	$(NH_4)_2CO_3$	010361-29-2	aqueous	Xn		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Hartshorn salt
Ammonium chloride	$(NH_4)Cl$	012125-02-9	solid	Xn		1/1	1/1	1/0	1/0	(2)	0/0	2/3	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	3/4	1/3L	1/2L	1/1	Ammonia
Ammonium chloride	$(NH_4)Cl$	012125-02-9	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	Ammonia
Ammonium dihydrogen phosphate	$(NH_4)H_2PO_4$	007722-76-1	any	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	3/0	1/1	0/0	4/4	(1)	(1)	1/1	
Ammonium iron(II) sulfate	$(NH_4)_2Fe(SO_4)_2$	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	(1)	(1)		
Ammonium iron(III) sulfate	$(NH_4)Fe(SO_4)_2$	007783-83-7	saturated	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0		
Ammonium fluoride	$(NH_4)F$	012125-01-8	saturated	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)	?	
Ammonium fluoride	$(NH_4)F$	012125-01-8	aqueous	T. C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3	1/1	
Ammonium glycolate	$C_2H_7NO_3$	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)		
Ammonium heptamolybdate	$(NH_4)_6Mo_7O_{24}$	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/0	(3)	(1)	0/0		(1)	(1)	0/0	
Ammonium hydrogen carbonate	CH_5NO_3	001066-33-7	saturated	Xi		1/1	1/1	1/0	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	(3)	0/0	1/1	1/1	1/1	1/1	
Ammonium hydrogen difluoride	F_2H_5N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0		
Ammonium hydrogen sulphide	-> see: Ammonium hydrosulphide																													
Ammonium hydrosulphide	$(NH_4)HS$	012124-99-1	any	T, C		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	(2)	0/0	(2)	(1)	(1)	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	1/2	2/3	2/3	1/2	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1	1/1	
Ammonium metaphosphate	$(NH_4PO_3)_n$	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)		
Ammonium molybdate	-> see: Ammonium heptamolybdate																													
Ammonium monophosphate, monobasic	-> see: Ammonium dihydrogen phosphate																													
Ammonium nitrate	$(NH_4)NO_3$	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	1/1	
Ammonium nitrate	$(NH_4)NO_3$	006484-52-2	saturated	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1	1/1	
Ammonium nitrite	$(NH_4)NO_2$	013446-48-5	aqueous	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/0	0/0	(2)	(1)	(1)		
Ammonium oxalate	$C_2H_8N_2O_4$	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1	0/0	
Ammoniumperoxodisulfat	$(NH_4)_2S_2O_8$	007727-54-0	saturated	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0	
Ammoniumperoxodisulfat	$(NH_4)_2S_2O_8$	007727-54-0	aqueous	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0	
Ammonium persulphate	-> see: Ammonium peroxodisulphate																													
Ammonium phosphate, primary	-> see: Ammonium dihydrogen phosphate																													
Ammoniumpolyphosphat	-> see: Ammonium metaphosphate																													
Ammonium rhodanide	-> see: Ammonium thiocyanate																													
Ammonium sulphate	$(NH_4)_2SO_4$	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	1/1	sulphuric acid ammonia
Ammonium sulphate	$(NH_4)_2SO_4$	007783-20-2	saturated	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2	1/1	sulphuric acid ammonia
Ammonium sulphide	$(NH_4)_2S$	012135-76-1	any	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	?	
Ammonium sulphide	$(NH_4)_2S$	012135-76-1	aqueous	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ammonium sulphocyanide	-> see: Ammonium thiocyanate																													
Ammonium thiocyanate	CH_4N_2S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)		
Ammonium nitrate	-> see: Ammonium nitrate																													
Amylacetate, n-	$C_7H_{11}O_2$	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Amyl alcohol, n-	$C_5H_{12}O$	000071-41-0		Xn	X	1/1	1/2	1/0	1/0	1/0	2/3	1/0	1/1	1/3	3/0	2/3	3/0	0/4	1/1	1/1	1/1	1/1	3/0	2/4	3/0	0/0	1/2	1/1	1/1	0/0	
Anym chloride	$C_5H_{11}Cl$	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L	0/0	
Amyl hydrosulphide	-> see: Pentanthiol, 1-																													
Amyl mercaptan	-> see: Pentanthiol, 1-																													
α-pentylcinnamaldehyde	$C_{14}H_{18}O$	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)	(1)		Fragrance
Pineapple juice	—	—		—		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	(1)	(1)		
Aniline	C_6H_7N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0	1/1	
Aniline chlorohydrate	$C_6H_3ClN_6$	000142-04-1	saturated	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4		
Aniline hydrochloride	-> see: Aniline chlorohydrate																													
Anilinium chloride	-> see: Aniline chlorohydrate																													
Anise	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Anise oil	C_7H_8O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Anise oil	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Anon	-> see: Cyclohexanone																													
Antimony (III) chloride	-> see: Antimony trichloride																													
Antimony (V) chloride	-> see: Antimony pentachloride																													
Antimony pentachloride	$SbCl_5$	007647-18-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	(4)	0/0	
Antimony trichloride	$SbCl_3$	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4	0/0	
Antimony trichloride	$SbCl_3$	010025-91-9	anhydrous	C		0/0	0/0	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	1/0	1/0	1/0	0/0	1/1	4/4	4/4		
Antimony trichloride	$SbCl_3$	010025-91-9	aqueous	C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4		
Apple juice	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	(2)	(1)	(1)		
Orange juice	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(2)	1/1	1/1		
Orange peel oil	—	008028-48-6		Xn		(3)	(3)	1/0	(3)	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	4/4	(2)	(3)	0/0	(1)	(1)	(1)		mainly +-Limes
Arcton 12	-> see: Dichlorodifluoromethane																													
Arcton 21	-> see: Dichlorofluoromethane																													
Arcton 22	-> see: Chlorodifluoromethane																													
Arsenic anhydride	-> see: Arsenic pentoxide																													
Arsenic pentoxide	As_2O_5	001303-28-2		T, N		1/1	1/1	(3)	(2)	0/0	0/0	(4)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	(2)	(3)	(3)	0/0	(3)	(1)	(1)		
Arsenic acid	H_3AsO_4	022538-92-7	aqueous	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	1/1	
Arsenic acid	H_3AsO_4	022538-92-7	80 %	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	0/0	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	1/1	
Arsenic anhydride	-> see: Arsenic pentoxide																													
Ascorbic acid	$C_6H_8O_6$	000050-81-7	aqueous	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	1/1	(1)	(1)	0/0	
Ether	-> siehe: Ethylether																													
Atropine sulphate	$C_{34}H_{48}N_2SO_{10}\cdot H_2O$	000055-48-1		T+		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)		
Caustic baryte	-> see: Barium hydroxide																													
Caustic potash	-> see: Potassium hydroxide																													
Caustic lime	-> see: Calcium oxide																													
Caustic soda	-> see: Sodium hydroxide																													
Azafluorene, 9-	-> siehe: Carbazole																													
Valerian drops	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	1/1	1/1	(1)	(3)	(3)	(2)	0/0	(2)	(1)	(1)		
Barium bromide	$BaBr_2$	010553-31-8		Xn		1/1	1/1	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	1/1	0/0	(2)	(2L)	(2L)		
Barium carbonate	$BaCO_3$	000513-77-9	saturated	Xn		1/1	1/1	1/1	(1)	1/1	1/1	(1)	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	No chemical effect expected due to low solubility
Barium chloride	$BaCl_2$	010361-37-2	saturated	T		1/1	1/1	1/0	1/0	1/0	1/1	(2)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1	
Barium chloride	$BaCl_2$	010361-37-2	aqueous	T		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1	
Barium hydroxide	$Ba(HO)_2$	012230-71-6	saturated	Xn		1/1	1/1	1/0	(3)	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/3	
Barium hydroxide	$Ba(HO)_2$	012230-71-6	aqueous	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	?	
Barium sulphide	BaS	021109-95-5	saturated	(T)		1/1	1/1	1/0	(2)	(2)	1/1	(2)	1/1	0/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	(2)	1/0	1/0	1/1	0/0	(3)	(1)	(1)	1/1	
Cottonseed oil	—	008001-29-4	tech. pure	?		0/0	0/0	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	3/0	1/0	1/0	0/0	(1)	1/1	1/1		
Benzaldehyde	C_7H_6O	000100-52-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	artificial almond oil
Benzene	-> see: Benzene (page 5)																													
Petrol	C_5H_{12} - $C_{12}H_{26}$	086290-81-5		F, Xn, N	X	2/3	3/4	1/0	3/3	(2)	2/3	1/2	3/4	4/4	3/3	2/4	0/0	0/4	1/1	1/1	1/1	1/1	4/4	(1-3)	3/0	0/0	1/1	1/1	1/1	1/1	Fuel, unleaded

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Benzoic acid	$C_7H_6O_2$	000065-85-0	saturated	Xn, Xi		1/1	1/1	3/4	4/4	1/0	1/2	2/4	1/3	2/2	3/3	1/2	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1	
Benzoic acid	$C_7H_6O_2$	000065-85-0	aqueous	Xn, Xi		1/1	1/1	3/4	4/4	1/0	0/0	2/4	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1	
Benzoic acid sodium salt	-> see: Sodium benzoate																														
Benzoic acid aldehyde	-> see: Benzaldehyde																														
Benzoic acid benzyl ester	-> see: Benzyl benzoate																														
Benzoic acid chloride	-> see: Benzoyl chloride																														
Benzoic acid ethyl ester	$C_9H_{10}O_2$	000093-89-0		Xn		2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Benzene	C_6H_6	000071-43-2		F, T	X	3/4	3/4	2/0	4/4	4/4	2/3	1/2	3/4	4/4	4/4	4/4	0/0	0/4	1/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	1/1	1/1	1/1	0/0	
Benzene-1,2-dicarboxylic acid	-> see: Phthalic acid																														
Benzene carboxylic acid	-> see: Benzoic acid																														
Benzene hexachloride (BHC)	-> see: Hexachlorocyclohexane																														
Benzenesulfonic acid	$C_6H_6SO_3$	000098-11-3	saturated	C		1/1	1/1	(4)	(3)	(4)	0/0	(4)	2/4	0/0	1/0	2/0	0/0	0/0	0/0	1/1	1/1	1/4	4/4	1/0	4/4	0/0	3/4	0/0	1/0	0/0	
Benzoyl chloride	C_7H_5ClO	000098-88-4	100 %	C		0/0	3/3	4/4	(4)	0/0	(4)	(3)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	(3)	4/4	0/0	1/0	(2L)	(2L)	0/0	
Benzyl acetate	$C_9H_{10}O_2$	000140-11-4		Xn/Xi		1/1	1/2	(2)	3/4	0/0	1/2	(2)	1/2	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	1/0	4/4	0/0	1/1	1/1	1/1		
Benzyl alcohol	C_7H_8O	000100-51-6		Xn		3/4	4/4	4/4	4/4	0/0	4/4	1/0	4/4	4/4	4/4	2/3	0/0	4/4	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	1/1	1/1	1/1	3/3	
Benzyl benzoate	$C_{14}H_{12}O_2$	000120-51-4		Xn		0/0	0/0	(2)	(3)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Benzylcarbinol	-> see: Phenylethanol																														
Benzyl chloride	C_7H_7Cl	000100-44-7	100 %	T/Xi		0/0	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	(3)	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0	
Benzylether	-> see: Dibenzyl ether																														
Succinic acid	$C_4H_6O_4$	000110-15-6	50 %	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	2/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/0	1/0	1/1	
Succinic acid	$C_4H_6O_4$	000110-15-6	saturated	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	?	
Succinic acid diethyl ester	$C_8H_{14}O_4$	000123-25-1		—		0/0	0/0	(2)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	4/4	4/4	0/0	(1)	(1)	(1)		
Bichromate sulphuric acid	-> see: Chromosulphuric acid																														
Beeswax	—	008012-89-3		—		1/1	1/1	1/1	(1)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	1/1	(1)	(1)		
Beer	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	
Bis(2-chloro-1-methylethyl)-ether	-> ssee: Dichloroisopropyl ether																														
Bis(2-ethylhexyl)-dipate	-> see: Dioctyladipate																														
Bis(2-ethylhexyl)-phthalate	-> see: Diisooctyl phthalate																														
Bis(2-ethylhexyl)-sebacate, sebacic acid bis(2-ethylhexyl)-ester	-> see: Dioctylsebacate																														
Bismuth chloride	$BiCl_3$	007787-60-2		Xi		1/1	1/1	(3)	(2)	(2)	0/0	(4)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(4)	0/0	0/0		
Bismuth subnitrate	$Bi_5O(HO)_9(NO_3)_4$	001304-85-4		O, Xi		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		
Bisulphite	-> see: Sodium bisulphite																														
Bisulphite lye	$NaHSO_3$	??		Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	3/0	0/0	(3)	1/1	1/1	1/1	
Bisulphite lye, containing $S0_2$	$NaHSO_3$	??	saturated	Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/1	4/4	0/0	(3)	1/1	1/1		
Bitter almond oil	C_7H_6O	090320-35-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1		Main ingredient: Benzaldehyde
Epsom salt	-> see: Magnesium sulphate																														
Bitumen	—	008052-42-4		—		0/0	0/0	1/0	(2)	(2)	0/0	2/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	(3)	0/0	1/1	(1)	(1)		
Hydrogen cyanide	HCN	000074-90-8	tech. pure	F+, T+	X	1/1	1/1	(3)	4/4	0/0	0/0	4/4	1/1	1/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	1/1	1/0	1/0	1/0	
Hydrogen cyanide	HCN	000074-90-8	aqueous	F+, T+	X	1/1	1/1	(3)	4/4	0/0	(4)	4/4	1/1	1/0	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(1)	1/0	1/0	?	
Lead (II) acetate	$C_4H_6PbO_4$	000301-04-2	aqueous	T, N		1/1	1/1	3/0	1/0	(2)	1/0	1/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	3/0	0/0	4/4	1/1	1/1	1/1	
Lead (II) acetate	$C_4H_6PbO_4$	000301-04-2		T, N		1/1	1/1	3/0	1/0	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	2/2	0/0	4/4	1/1	1/1	1/1	
Lead(II) nitrate	$Pb(NO_3)_2$	010099-74-8	aqueous	O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Lead(II) nitrate	$Pb(NO_3)_2$	010099-74-8		O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Lead nitrate	-> see: Lead (II) nitrate																														
Lead stearate	$C_{36}H_{70}PbO_4$	001072-35-1		?		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		No chemical effect expected due to low solubility
Lead sulphate	$PbSO_4$	007446-14-2		(T, N)		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	0/0	(1)	(1)	(1)	0/0	No chemical effect expected due to low solubility
Tetraethyllead	-> see: Tetraethyl lead																														
Lead sugar	-> see: Lead (II) acetate																														
Yellow prussiate of Potash	-> see: Potassium hexacyanoferrate(II)																														
Red prussiate of Potash	-> see: Potassium hexacyanoferrate(III)																														
Borax	-> see: Sodium borate																														
Boric acid	H_3BO_3	010043-35-3	10 %	Xi		1/1	1/1	1/0	1/1	1/0	1/1	2/3	1/1	1/2	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Boric acid	H_3BO_3	010043-35-3	aqueous	Xi		1/1	1/1	3/3	1/1	1/0	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Spirits	-> see: Spirits																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Brake fluid	—	—		?		1/0	1/0	1/0	4/4	0/0	1/1	(3)	1/1	3/0	0/0	1/0	3/0	4/4	0/0	(1)	1/0	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Bromine	Br_2	007726-95-6		T+, C		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	2/4	4/4	4/4	1/2	1/1	1/3	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	4/4	
Bromine benzene	-> see: Bromobenzene																													
Bromobenzene	C_6H_5Br	000108-86-1		Xn	X	3/4	4/4	1/0	4/4	(2)	4/4	1/0	4/4	4/4	4/4	4/4	0/0	0/0	2/4	1/1	1/0	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)		
Bromochloromethane	CH_2BrCl	000074-97-5	100 %	Xn		(4)	(4)	4/4	4/4	1/0	(4)	(3)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/0	(3)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	
Bromine vapours	Br_2	007726-95-6		T		(4)	(4)	4/4	(3)	4/4	(4)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(2-3)	4/4	0/0	(3)	(4)	(4)	4/4	
Bromine potassium	-> see: Potassium bromide																													
Bromomethane	CH_3Br	000074-83-9	tech. pure	T		3/0	4/4	1/0	(3)	0/0	0/0	1/0	4/4	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0	
Bromoform	$CHBr_3$	000075-25-2		T		4/4	4/4	4/4	4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	0/0	0/0	2/3	1/1	(1)	(2)	4/4	(4)	4/4	0/0	(3)	0/0	0/0	0/0	
Bromopental fluoride	BrF_5	007789-30-2		F, T, C		0/0	0/0	4/4	(4)	(4)	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromic acid	$HBrO_3$	007789-31-3	concentrated.	C		0/0	0/0	(4)	(4)	(4)	0/0	4/4	3/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(4)	(2)	4/4	0/0	(4)	(4)	(4)	0/0	
Bromine trifluoride	BrF_3	007787-71-5		T, C		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromotrifluoromethane	$CBrF_3$	000075-63-8		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Bromine water	Br_2+H_2O	007726-95-6	saturated	T		4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	4/4	0/0	3/4	0/0	0/0	0/0	0/0	1/1	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	0/0	
Hydrobromic acid	HBr	010035-10-6	40 %	C		1/0	1/1	4/4	4/4	(4)	4/4	4/4	1/1	4/4	0/0	1/1	3/3	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Hydrobromic acid	HBr	010035-10-6	50 %	C		1/1	1/2	4/4	4/4	(4)	4/4	4/4	1/2	4/4	0/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Hydrobromic acid	HBr	010035-10-6	diluted	C		1/1	1/1	4/4	4/4	3/0	4/4	4/4	1/1	4/4	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Butadiene, 1,3-	C_4H_6	000106-99-0		F+, T	X	3/4	4/4	1/0	4/4	1/0	4/4	(2)	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)	4/4	
Butane	C_4H_{10}	000106-97-8	tech. pure	F+	X	1/0	1/1	1/0	1/0	1/0	1/0	2/0	1/1	4/4	1/0	1/0	3/0	1/0	0/0	1/1	1/1	1/0	4/4	1/0	1/0	0/0	1/1	(1)	(1)	1/1	
Butanal	-> see: Butyraldehyde																													
Butanediol	-> see: Butylene glycol																													
Butanedioic acid	-> see: Succinic acid																													
Butanol	$C_4H_{10}O$	000071-36-3	techn. pure	Xn	X	1/1	1/3	1/0	2/3	1/0	1/2	1/2	1/2	1/2	2/3	2/3	4/4	1/3	1/1	1/1	1/1	1/1	2/0	3/4	1/0	0/0	1/1	(1)	(1)	0/0	
Butanol, secondary	-> see: Butyl alcohol, secondary																													
Butanol, tertiary	-> see: Butyl alcohol, tertiary																													
Butanol-2	-> see: Butyl alcohol, secondary																													
Butanone	-> see: Methyl ethyl ketone																													
Butanoic acid	-> see: Butyric acid																													
Butanetriol	$C_4H_{10}O_3$	—	100 %	—		(4)	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	3/3	4/4	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)		Isomer not specified in the source
Butene	C_4H_8	—	tech. pure	F+	X	4/4	0/0	1/0	(1)	1/0	0/0	1/0	4/4	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/0	1/0	3/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0	Isomer not specified in the source
Butenal, trans-2-	-> see: Crotonaldehyde																													
Butenedioic acid, cis-	-> see: Maleic acid																													
Butoxyethanol, 2-	-> see: Butyl glycol																													
Butter	—	—		—		1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	3/0	1/0	1/1	0/0	(1)	(1)	(1)		
Buttersäure	$C_4H_8O_2$	000107-92-6		C		3/4	4/4	3/3	4/4	0/0	4/4	4/4	4/4	4/4	2/2	2/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/2	1/2	1/1	1/1	
Butyric acid ethyl ester	-> see: Ethyl butyrate																													
Butyl acetate	-> see: Acetic acid butyl ester																													
Butyl acrylate	$C_7H_{12}O_2$	000141-32-2	100 %	Xi	X	1/2	2/3	2/0	4/4	1/3	2/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/0	
Butyl alcohol	-> see: Butanol																													
Butyl alcohol, secondary	$C_4H_{10}O$	000078-92-2		Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	2/2	2/3	2/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		
Butyl alcohol, tertiary	$C_4H_{10}O$	000075-65-0		F, Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		
Butylamine	$C_4H_{11}N$	000109-73-9		F, C	X	0/0	0/0	0/0	(3)	0/0	0/0	3/4	2/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Butyl carbinol	-> see: Amyl alcohol, n-																													
Butyl cellosolve	-> see: Butyl glycol																													
Butylene	-> see: Butene																													
Butylen glycol	$C_4H_{10}O_2$	—	tech. pure	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	4/4	(1)	0/0	1/1	(1)	(1)	0/0	Isomer not specified in the source
Butyl ether	-> see: Dibutyl ether																													
Butyl ethylene	-> see: Hexene, 1-																													
Butyl glycol	$C_4H_{14}O_2$	000111-76-2	100 %	Xn	X	0/0	1/0	1/0	(2)	1/0	0/0	1/0	1/0	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	1/1	3/0	3/4	3/4	0/0	1/1	(1)	(1)	0/0	
Butylphenol	$C_{10}H_{14}O$	—	100 %	Xi		0/0	1/1	(3)	(3)	0/0	(3)	(4)	1/1	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Isomer not specified in the source
Para tertiary butylphenol	$C_{11}H_{15}NO$	000098-54-4	tech. pure	C, Xn		3/0	0/0	(3)	(3)	0/0	(3)	(4)	1/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1		
Butyl stearate	-> see: Stearic acid butyl ester																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Butyraldehyde	C_4H_8O	000123-72-8		F, Xn	X	0/0	0/0	(3)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Cadmium bromide	CdBr	007789-42-6		T		1/1	1/1	(3)	(2)	(2)	0/0	(3)	(1)	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	4/4	0/0	0/0		
Calcium acetate	$C_4H_6CaO_4$	000062-54-4	aqueous	—		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(2)	(1)	(1)	0/0	
Calcium bicarbonate	$Ca(HCO_3)_2$	—	saturated	—		1/1	1/1	1/1	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	(2)	(1)	(1)	0/0	
Calcium bisulphite	$Ca(HSO_3)_2$	013780-03-5	saturated	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1	
Calcium bisulphite	$Ca(HSO_3)_2$	013780-03-5	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1	
Calcium bromide	$CaBr_2$	007789-41-5		?		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(3)	0/0	0/0	0/0	
Calcium carbide	CaC_2	000075-20-7		F	X	1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0	Carbide, reacts with water to form acetylene - highly flammable!
Calcium carbonate	$CaCO_3$	000471-34-1	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium chlorate	$Ca(ClO_3)_2$	010137-74-3	saturated	O, (T)		0/0	0/0	(3)	(2)	0/0	1/1	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(2)	(1)	(3)	0/0	1/1	(1)	1/0	1/1	
Calcium chloride	$CaCl_2$	010043-52-4	alcoholic	F, Xi		1/0	0/0	4/4	(2)	0/0	1/0	(3)	1/1	0/0	0/0	0/0	4/4	0/0	0/0	1/1	1/0	(1)	(2)	(2)	(2)	0/0	(3)	1/2L	1/2L	1/1	
Calcium chloride	$CaCl_2$	010043-52-4	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/1	(3)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/2L	1/2L	1/1	
Calcium hydrate	-> see: Calcium hydroxide																														
Calcium hydrogen carbonate	-> see: Calcium bicarbonate																														
Calcium hydrogen sulphite	-> see: Calcium bisulphite																														
Calcium hydroxide	CaH_2O_2	001305-62-0	aqueous	(Xi)		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calcium hydroxide	CaH_2O_2	001305-62-0	concentrated.	C		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	2/2	2/2	1/1	1/0	0/0	1/1	1/1	1/1	1/3	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calcium hypochlorite	$Ca(OCl)_2$	007778-54-3	saturated	O, C		1/1	1/1	1/4	3/4	3/0	1/2	1/0	1/1	2/3	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/3	(2)	2/3	4/4	0/0	4/4	3/0	2/0	1/1	Bleaching powder
Calcium hypochlorite	$Ca(OCl)_2$	007778-54-3	aqueous	O, C/Xi		0/0	0/0	4/4	1/0	3/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	4/4	3/0	2/0	1/1	Bleaching powder
Calcium nitrate	$Ca(NO_3)_2$	010124-37-5	50 %	O		1/1	1/1	(2)	1/0	(2)	1/1	(3)	1/1	1/1	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	1/0	1/1	1/1	1/1	
Calcium nitrate	$Ca(NO_3)_2$	010124-37-5	aqueous	O		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/1	1/1	1/1	
Calcium oxide	CaO	001305-78-8	Powder	C		1/0	1/1	(2)	(2)	(2)	0/0	0/0	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	1/1	1/1		
Calcium phosphate	$Ca_3(PO_4)_2$	007758-87-4	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium phosphate	$Ca_3(PO_4)_2$	007758-87-4		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium sulphate	$CaSO_4$	007778-18-9	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	Plaster
Calcium sulphide	CaS	020548-54-3	aqueous	C		0/0	0/0	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	(1)	(1)	0/0	
Calcium sulphide	CaS	020548-54-3		C		0/0	3/3	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Camphor	$C_{10}H_{16}O$	000464-48-2 / -49-2		F, Xn	X	3/4	3/4	(2)	(3)	0/0	0/0	(2)	1/0	1/3	0/0	4/4	4/4	1/1	0/0	(1)	1/0	(3)	4/4	3/4	1/0	0/0	(1)	1/0	1/0	1/0		
Camphor oil	—	008008-51-3		Xn		4/4	4/4	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	(3)	4/4	3/0	1/0	0/0	(1)	(1)	(1)	1/0	made from Cinnamomum Camphora
Paracymene	-> see: Cymene, p-																														
Capronaldehyde	-> see: Hexanal																														
Carbazole	$C_{12}H_9N$	000086-74-8		Xn		1/1	1/1	(2)	4/4	0/0	1/1	(1)	1/1	1/1	4/4	4/4	0/0	4/4	1/1	1/1	(2)	(2)	(2)	(3)	(2)	0/0	(1)	(1)	(1)	0/0	
Carbinol	-> see: Methanol																														
Carbolineum	—	008001-58-9	aqueous	(Xn)		1/0	1/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	(2)	3/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Carbolic acid	-> see: Phenol																														
Carbon disulfide	-> see: Carbon disulphide																														
Carbonyl chloride	-> see: Phosgene																														
Carnauba wax	—	008015-86-9		—		1/1	1/1	1/1	(1)	1/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(3)	(1)	(1)	0/0	1/1	(1)	(1)		
Caesium bromide	CsBr	007787-69-1		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	0/0	0/0		
Cellosolve	-> see: Ethyl glycol																														
Cellosolve acetate	-> see: Ethylene glycol monoethyl ether acetate																														
Cetyl alcohol	$C_{16}H_{34}O$	036653-82-4	100 %	Xi		1/1	1/1	4/4	(2)	1/0	0/0	(1)	1/1	0/0	1/0	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(1)	1/1	1/1		
Cetylic acid	-> see: Palmitic acid																														
Quinine	$C_{20}H_{24}N_2O_2$	000130-95-0		Xn		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)	0/0	
Chlorine	Cl_2	007782-50-5	10 % wet	T		3/4	3/4	4/4	2/3	4/4	2/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	(2)	2/0	3/0	4/4	0/0	4/4	4/4	4/4	0/0	
Chlorine	Cl_2	007782-50-5	97 %	T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0	1/1	
Chlorosulfonic acid	-> see: Chlorosulfunic acid																														
Chlorine-1-propene, 3-	-> see: Allyl chloride																														
Chlor-2-propanone, 1-	-> see: Chloroacetone																														
Chloroacetone	C_3H_5ClO	000078-95-5		(F, Xi)	X	0/0	0/0	(3)	(4)	(4)	(4)	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	0/0	
Chloroacetophenone, p-	C_8H_7ClO	000099-91-2		(Xn)		1/1	1/1	(2)	4/4	0/0	1/1	(2)	1/1	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(2)	(2)	(3)	4/4	4/4	0/0	(1)	0/0	0/0		
Chloral	-> see: Trichloroacetaldehyde																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Chloral hydrate	$C_2H_3Cl_3O_2$	000302-17-0	tech. pure	T/Xi		3/3	3/3	4/4	(3)	(4)	0/0	(3)	3/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	4/4	3/0	3/4	4/4	0/0	4/4	0/0	0/0	0/0	
Chloramine T	$C_7H_7ClNaNSO_2$	000127-65-1	diluted	Xi		1/0	1/0	4/4	1/0	0/0	0/0	(3)	(3)	0/0	0/0	0/0	1/0	0/0	0/0	(1)	1/0	3/4	1/0	4/4	1/0	0/0	3/4	2/2	1/1	0/0	Swimming pool disinfection
Phenyl chloride	-> see: Chlorobenzene																													
Chlorobenzene	C_6H_5Cl	000108-90-7		Xn	X	3/4	3/4	4/4	4/4	1/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/1	(1/1)[1]	(1/1)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chlorine bleach	-> see: Sodium hypochlorite																													
Bromochloromethane	-> see: Bromochloromethane																													
Chlorobutadiene	C_4H_5Cl	000126-99-8		F, Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/4	4/4	0/0	(3)	0/0	0/0		
Chlorobutadiene	-> see: Calcium chloride																													
Chlorodifluoromethane	$CHClF_2$	000075-45-6		N, Xn		0/0	3/0	1/0	3/0	1/0	0/0	1/0	4/4	4/4	4/4	2/0	4/4	0/0	0/0	3/3	1/0	(3)	1/0	4/4	4/4	0/0	(3)	0/0	0/0		
Chlorine dioxide	ClO_2	010049-04-4		E, T		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/0	(2)	4/4	1/0	4/4	0/0	3/4	3/4	3/4		
Chlordodecane	-> see: Lauryl chloride																													
Chloroacetic acid	$C_2H_3ClO_2$	000079-11-8	50 %	T, C		1/3	1/3	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/0	0/0	3/4	0/0	(1)	1/1	1/4	2/0	3/0	4/4	0/0	4/4	2/4	2/4	1/4	
Chloroacetic acid	$C_2H_3ClO_2$	000079-11-8		T, C		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/2	2/4	4/4	3/4	4/4	3/4	1/1	1/1	1/1	4/4	3/0	3/0	4/4	0/0	4/4	4/4	4/4	4/4	
Ethyl monochloroacetate	-> see: Ethyl chloroacetate																													
Chloroethanoic acid methyl ester	-> see: Methyl chloroacetate																													
Chlorethane	C_2H_5Cl	000075-00-3		F+, Xn	X	3/3	3/4	1/0	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/0	4/4	0/0	(3)	(1/1L)[1]	(1/1L)[1]	0/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloroethanol	C_2H_5ClO	000107-07-3	tech. pure	T+		1/1	0/0	4/4	4/4	0/0	0/0	3/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	1/1	1/0	1/3	3/0	4/4	4/4	0/0	(3)	1/0L	1/0L	1/0	
Chloroethyl alcohol, 2-	-> see: Chloroethanol																													
Chloroethylene	C_2H_3Cl	000075-01-4	tech. pure	F+, T	X	0/0	0/0	1/1	(4)	1/1	0/0		(3)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	1/1	3/0	3/0	4/4	0/0	(1)	0/0	0/0	0/0	
Chlorofluoromethane	CH_2ClF	000593-70-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	4/4	0/0	(3)	0/0	0/0		
Chlorine gas	Cl_2	007782-50-5		T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0		
Chlorinated potassium	-> see: Potassium chloride																													
Chlorinated lime	[3 x CaCl(OCl) + Ca(—		aqueous	?		0/0	0/0	4/4	(2)	3/0	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach
Chlorinated lime	[3 x CaCl(OCl) + Ca —			O, C		0/0	0/0	4/4	(2)	3/0	0/0	4/4	1/1	1/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach
Chloromethane	CH_3Cl	000074-87-3	tech. pure	F+, T	X	3/0	2/0	4/4	(3)	0/0	0/0	1/0	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/0	1/0	1/1	4/4	4/4	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]		[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloromethyl	-> see: Chloromethane																													
Chloromethylbenzene	-> see: Benzyl chloride																													
Chloromethyloxirane	-> see: Epichlorohydrin																													
Chloronaphthalene, 1-	$C_{10}H_7Cl$	000090-13-1		Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	4/4	0/0	(2)	1/0	1/0		
Nickel chloride	-> see: Nickel (II) chloride																													
Chloroform	$CHCl_3$	000067-66-3	100 %	Xn		3/4	4/4	3/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	1/1	4/4	3/4	4/4	0/0	(3)	(1/1)[1]	(1/1)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloroprene	-> see: Chlorobutadiene																													
Chloropentafluoroethane	C_2ClF_5	000076-15-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Chloropentane, 1-	-> see: Amyl chloride																													
Chlorophenyl methyl ketone, 4-	-> see: Chloroacetophenone, -p																													
Chloropropane, 2-	-> see: Isopropyl chloride																													
Chloropropylene, 3-	-> see: Allyl chloride																													
Chloric acid	$HClO_3$	007790-93-4	1 %	(C)		0/0	1/1	4/4	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/3	1/0	0/0	0/0	0/0	1/1	1/1	3/0	1/1	(3)	0/0	(3)	4/4	4/4	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Chloric acid	$HClO_3$	007790-93-4	10 %	(O), C		1/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	3/0	3/0	4/4	0/0	4/4	4/4	4/4	1/1	
Chloric acid	$HClO_3$	007790-93-4	20 %	(O), C		3/0	1/4	4/4	(3)	(4)	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/0	3/0	3/0	4/4	0/0	4/4	4/4	4/4	?	
Chlorosulfonic acid	$ClHSO_3$	007790-94-5	tech. pure	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	3/0	4/4	4/4	0/0	0/0	1/0	3/4	4/4	4/4	4/4	0/0	3/3	3/4	3/4	1/0	
Chlorotoluene	C_7H_7Cl	—		Xn		0/0	0/0	(2)	4/4	0/0	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(3)	1/0	1/0	1/1	Isomer not specified in the source
Chlorotoluene, alpha-	-> see: Benzyl chloride																													
Chlorine trifluoride	ClF_3	007790-91-2		(O, T)		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(4)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(4)	4/4	(4)	4/4	0/0	(4)	(4)	(4)		
Chlorotrifluoromethane	$CClF_3$	000075-72-9		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	0/0	
Chlorinated water	$Cl_2 \times H_2O$	007782-50-5		(T)		3/0	0/4	4/4	4/4	4/4	4/4	4/4	3/4	4/4	0/0	3/3	3/0	3/3	1/1	(1)	1/1	1/1	3/0	1/0	4/4	0/0	4/4	2/0L	2/0L	0/0	
Hydrochloric acid gas	HCl	007647-01-0	anhydrous	T, C		1/1	0/0	4/4	(3)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	2/2L	2/2L	0/0	
Hydrochloric gas	-> see: Hydrogen acid																													
Hydronium chloride	-> see: Hydrochloric acid																													
Chlorozinc	-> see: Zinc chloride																													
Chromium (III) potassium sulphate dodecahydrate	-> see: Chrome alum																													
Chromium (VI) oxide	-> see: Chromic acid																													
Chrome alum	$KCr(SO_4)_2 \times 12H_2O$	007788-99-0	saturated	Xn		1/1	0/0	(2)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(3)	1/3	1/3	1/1	
Chromium salts	—	—	any	T/Xn		0/0	0/0	0/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	0/0	K	K	K		
Chromic acid	CrO_3	001333-82-0	10 %	O, T, C, N		1/1	1/1	4/4	2/3	3/0	1/1	4/4	1/1	1/1	4/4	1/2	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	1/2	1/2	1/1	
Chromic acid	CrO_3	001333-82-0	20 %	O, T, C, N		0/0	1/3	4/4	3/4	(4)	0/0	4/4	3/3	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	(2)	(2)	1/1	
Chromic acid	CrO_3	001333-82-0	50 %	O, T, C, N		3/4	3/4	4/4	3/4	(4)	2/3	4/4	3/3	3/3	4/4	1/3	1/0	3/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	(3)	2/3	2/3	1/1	
Chromic acid potassium salt	-> see: Potassium chromate																													
Chromosulphuric acid	$CrO_3 + H_2SO_4$	065272-71-1	concentrated	O, T, C, N		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	4/4	4/4	1/1	0/0	1/1	4/4	4/4	1/0	4/4	4/4	4/4	2/3	2/3	0/0	
Chromium trioxide	-> see: Chromic acid																													
2-Hydroxypropane-1,2,3-tricarboxylic acid	-> see: Citric acid																													
Citric acid tributyl ester	-> see: Tributyl citrate																													
Clophen A60	—	011096-82-5		Xn, N		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	0/0	0/0	0/0	0/0	(1)	(2)	4/4	2/3	4/4	0/0	1/0	1/0	1/0	0/0	ppolychlorinated biphenyls, PCBs; Bayer
Cobalt (II) chloride	$CoCl_2$	007646-79-9	aqueous	Xn		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Cobalt dichloride	-> see: Cobalt (II) chloride																													
Colamine	-> see: Ethanolamine																													
Crotonaldehyde	C_4H_6O	004170-30-3	tech. pure	F, T	X	1/0	0/0	(2)	(4)	0/0	(4)	(2)	1/0	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	1/3	1/0	3/0	4/4	0/0	1/0	1/1	1/1	0/0	
Cumol	-> see: Cumene																													
Cumene	C_9H_{12}	000098-82-8		Xi	X	2/3	3/4	(2)	4/4	0/0	4/4	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Curry	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	3/3	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		could lead to discolouration
Ethyl cyanoacetate	-> see: Ethyl cyanoacetate																													
Cyanide	-> see: Potassium cyanide																													
Cyan potassium	-> see: Potassium cyanide																													
Cyannosodium	-> see: Sodium cyanide																													
Prussic acid	-> see: Hydrogen cyanide																													
Cyclanon	—	—		(Xn, Xi)		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/1	0/0	3/4	(1)	(1)	0/0	Polyquaternary compounds, dyeing auxiliaries; BASF
Cyclohexane	C_6H_{12}	000110-82-7		F	X	3/4	3/4	1/0	3/3	1/0	4/4	1/1	3/4	4/4	4/4	2/3	1/0	1/3	1/2	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Cyclohexanol	$C_6H_{12}O$	000108-93-0	tech. pure	Xn		1/1	1/1	1/1	3/0	0/0	1/2	1/0	1/3	3/3	1/0	1/1	4/4	1/3	0/0	(1)	1/1	1/3	4/4	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Cyclohexanone	$C_6H_{10}O$	000108-94-1	tech. pure	Xn	X	1/3	3/4	1/0	4/4	(4)	3/4	1/0	2/4	4/4	4/4	4/4	4/4	4/4	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Cyclohexylmethane	-> see: Methylcyclohexane																													
Cymene, p-	$C_{10}H_{14}$	000099-87-6		F, Xn/Xi	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Steam	H_2O	—	up to 150°C	?		4	4	4/4	0/0	0	0	(3)	(3)	0	0	0	0	0	0	0/0	1	0	1	3	4/4	0	(1)	1/1	1/1		
DDT (emulsion)	$C_{14}H_9Cl_5$	000050-29-3		T		0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(3)	(3)	0/0	(2)	(2)	(2)	0/0	
Decahydronaphthalene	$C_{10}H_{18}$	000091-17-8		Xn		1/3	3/4	1/0	4/4	3/0	4/4	1/0	3/4	4/4	4/4	1/2	3/0	3/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	(1)	(1)	0/0	
Decalin	-> see: Decahydronaphthalene																													
Decane	$C_{10}H_{22}$	000124-18-5		Xn	X	0/0	0/0	(1)	(2)	(1)	(3)	1/1	(3)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	(1)	(1)		
Decanedioic acid dibenzyl ester	-> see: Dibenzyl sebacate																													
Decanedioic acid dibutyl ester	-> see: Dibutyl sebacate																													
Decanedioic acid diethyl ester	-> see: Diethyl sebacate																													
Dehydroacetic acid	$C_8H_8O_4$	000520-45-6		Xn		0/0	0/0	(3)	(2)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(4)	(1)	(1)		
Densodrin W	—	—	aqueous	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/0	0/0	0/0	1/0	0/0	0/0	0/0	0/0		Hydrophobing agent for leather, silicone derivative; BASF

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Desmodur 44	$C_{15}H_{10}N_2O_2$	000101-68-8		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	0/0	4/4	0/0	(1)	(1)	(1)		
Dextrin	$(C_6H_{10}O_5)_n$ x H_2O	009004-53-9	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Dextrose	-> see: Glucose																														
Diacetone alcohol	$C_6H_{12}O_2$	000123-42-2		Xi	X	0/0	0/0	(3)	(3)	0/0	0/0	1/0	2/2	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(2)	(1)	(1)		
Diamide	-> see: Hydrazine																														
Diaminoethane	-> see: Ethylenediamine																														
Diazane	-> see: Hydrazine																														
Dibenzyl ether	$C_{14}H_{14}O$	000103-50-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Dibenzyl sebacate	$C_{24}H_{26}O_4$	??		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	(4)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dibromoethane-1,2	$C_2H_4Br_2$	000106-93-4		T		(4)	(4)	(2)	(4)	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/2	4/4	(3)	4/4	0/0	(3)	1/0L	1/0L	0/0	
Dibromotetrafluoromethane	$C_2Br_2F_4$	000124-73-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0		
Dibutylamine	$C_8H_{19}N$	000111-92-2		Xn	X	0/0	0/0	(2)	(3)	0/0	(3)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Dibutyl ether	$C_8H_{18}O$	000142-96-1	tech. pure	Xi	X	3/4	1/4	(2)	(3)	1/0	(4)	(1)	3/4	0/0	3/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Dibutyl phthalate	$C_{16}H_{22}O_4$	000084-74-2	FR, 80°C	T		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	(1)	0	0	0	4/4	0	0	0	0	0/0	Plasticiser
Dibutyl phthalate	$C_{16}H_{22}O_4$	000084-74-2		T		1/3	3/3	1/0	4/4	1/0	0/2	1/0	2/2	4/4	1/0	4/4	4/4	0/4	1/1	(1)	1/1	1/3	3/0	2/3	4/4	0/0	(1)	1/1	1/1	0/0	Plasticiser
Dibutyl sebacate	$C_{18}H_{34}O_4$	000109-43-3	tech. pure	—		1/0	1/3	1/0	(3)	0/0	0/0	(2)	1/0	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dichlorocide, 1,2-	-> see: Dichlorobenzene, 1,2-																														
Dichlorocide, 1,4-	-> see: Dichlorobenzene, 1,4-																														
Dichlorobenzene, 1,2-	$C_6H_4Cl_2$	000095-50-1		Xn		3/3	3/4	(1)	4/4	0/0	3/4	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/3	(1)	1/1	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Dichlorobenzene, 1,4-	$C_6H_4Cl_2$	000106-46-7		Xn		2/3	3/4	1/0	4/4	0/0	2/3	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/3	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
DCB, o-	-> see: Dichlorobenzene, 1,2-																														
DCB, p-	-> see: Dichlorobenzene, 1,4-																														
Dichlorodifluoromethane	CCl_2F_2	000075-71-8	tech. pure	N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0	
Dichlorodifluoromethane	CCl_2F_2	000075-71-8		N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0	
Dichlorodiphenyltrichloroethane	-> see: DDT (emulsion)																														
Dichloroacetic acid	$C_2H_2Cl_2O_2$	000079-43-6	50 %	C		1/1	1/1	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1	
Dichloroacetic acid	$C_2H_2Cl_2O_2$	000079-43-6	tech. pure	C		1/3	3/3	4/4	(4)	4/4	0/0	4/4	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1	
Dichloroacetic acid methyl ester	-> see: Methyl dichloroacetate																														
Dichlorethane, 1,2-	-> see: Ethylene chloride																														
Dichlorethene, 1,1-	-> see: Vinylidene chloride																														
Dichloroethylene	$C_2H_2Cl_2$	—	tech. pure	F+, Xn	X	4/4	4/4	3/0	(4)	4/4	(4)	4/4	3/0	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/0	1/1	4/4	3/4	4/4	0/0	(3)	1/1L	1/1L	0/0	Isomer not specified in the source
Dichloroethylene, 1,1-	-> see: Vinylidene chloride																														
Dichlorofluoromethane	$CHCl_2F$	000075-43-4	100 %	N		0/0	3/0	1/0	3/0	0/0	0/0	1/0	4/4	4/4	3/0	4/4	4/4	3/3	0/0	(3)	1/0	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Dichlorohexafluorocyclobutane	$C_4Cl_2F_6$	000356-18-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	(3)	1/0	0/0	(3)	0/0	0/0		
Dichloroisopropyl ether	$C_6H_{12}Cl_2O$	—		(Xn)		(4)	(4)	(2)	(3)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		Isomer not specified in the source
Dichlormethane	CH_2Cl_2	000075-09-2		Xn		4/4	4/4	3/4	4/4	4/4	3/4	3/0	3/4	4/4	4/4	4/4	4/4	4/4	2/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	4/4	(1/1L)[1)]	(1/1L)[1)]	1/1	[1)] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Dichlorpropane	$C_3H_6Cl_2$	—	100 %	F, T/Xn	X	0/0	0/0	(3)	-4	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Dichlorotetrafluoroethane	$C_2Cl_2F_4$	000076-14-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Dicyclohexylamine (DCHA)	$C_{12}H_{23}N$	000101-83-7		C, Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Dicyclohexyl phthalate	$C_{20}H_{26}O_4$	000084-61-7	tech. pure	(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	(3)	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diesel fuel	—	—		Xn, N		1/3	0/0	1/1	3/3	1/1	0/0	1/1	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	(1)	(1)	0/0	
Diesel oil	—	068334-30-5	100 %	(Xn)		1/3	1/4	1/1	3/3	1/1	0/0	1/1	1/3	3/4	0/0	1/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	(1)	(1)	0/0	
Diethanolamine (DEA)	$C_4H_{11}NO_2$	000111-42-2	100 %	Xi		0/0	1/0	(2)	(3)	0/0	0/0	(2)	1/2	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/3	3/0	(3)	4/4	0/0	1/1	(1)	(1)	0/0	
Diethylamine	$C_4H_{11}N$	000109-89-7	tech. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/2	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Diethylbenzene	$C_{10}H_{14}$	000135-01-3		Xi		3/4	4/4	(1)	3/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Diethylene glycol	$C_4H_{10}O_3$	000111-46-6		T		1/1	1/1	3/0	2/3	0/0	1/1	(2)	1/1	2/2	2/2	3/4	0/0	1/1	1/1	1/1	1/1	(2)	1/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0	
Diethylene glycol ether	—	—		(Xn)		1/1	1/1	3/0	3/4	0/0	1/1	(2)	1/1	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	3/0	(3)	3/3	0/0	(1)	(1)	(1)		
Diethyl ether	-> see: Ethyl ether																														
Diethyl ketone	$C_5H_{10}O$	000096-22-0		F		2/2	2/3	(3)	4/4	(4)	2/3	1/0	2/2	4/4	4/4	4/4	0/0	4/4	2/3	1/1	1/1	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	0/0	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Diethylmalonate	$C_7H_{12}O_4$	000105-53-3		Xi		1/1	1/1	(2)	3/4	0/0	1/2	(2)	1/1	4/4	3/3	2/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(4)	(3)	0/0	(1)	(1)	(1)		
Diethylmethane	-> see: Pentane																													
Diethyl sebacate	$C_{14}H_{26}O_4$	000110-40-7		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diethyl succinate	-> see: Succinic acid diethyl ester																													
Difluorochloroethane	$C_2H_3ClF_2$	000075-68-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluoroethane	$C_2H_2F_2$	000075-37-6		(E), F+		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluoromethane	CH_2F_2	000075-10-5		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluorotetrachloroethane	$C_2Cl_4F_2$	000076-12-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0		
Diglycol	-> see: Diethylene glycol																													
Diglycolic acid	$C_4H_6O_5$	000110-99-6	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/1	4/4	0/0	3/4	1/4	1/4	1/1	
Diglycolic acid	$C_4H_6O_5$	000110-99-6	30 %	Xn, Xi		1/1	1/1	(3)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/0	1/0	1/1	4/4	0/0	3/4	1/4	1/4	1/1	
Dihexyl phthalate	-> see: Dicyclohexyl phthalate																													
Dihydroxybenzene, 1,3-	-> see: Resorcinol																													
Dihydroxybenzene, 1,4-	-> see: Hydroquinone																													
Dihydroxysuccinic acid	-> see: Tartaric acid																													
Dihydroxydiethylamine	-> see: Diethanolamine																													
Diisobutylene (DIB)	C_8H_{16}	025167-70-8		F	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	1/2	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Diisobutylketone	$C_9H_{18}O$	000108-83-8	tech. pure	Xi	X	1/4	1/3	(3)	(3)	(4)	(4)	1/0	1/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/3	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Diisooctyl phthalate (DOP)	$C_{24}H_{38}O_4$	000117-81-7	tech. pure	Xn		4/4	4/4	1/0	4/4	1/0	1/0	(2)	4/4	4/4	1/0	4/4	4/4	0/0	0/0	1/1	1/0	(2)	3/0	2/3	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diisopropyl ether	-> see: Isopropyl ether																													
Diisopropyl ketone	$C_7H_{14}O$	000565-80-0		F	X	0/0	0/0	(3)	(3)	(4)	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Dimethylamine	C_2H_7N	000124-40-3	tech. pure	F+, Xn	X	1/3	1/3	1/0	4/4	0/0	0/0	(2)	1/3	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	3/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Dimethylaniline	$C_8H_{11}N$	—		T		0/0	0/0	(3)	4/4	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Dimethylbenzene	-> see: Xylene																													
Dimethylcarbinol	-> see: Isopropyl																													
Dimethyl ether	C_2H_6O	000115-10-6	Gas	F+	X	0/0	3/0	1/0	(3)	1/0	0/0	(2)	4/4	4/4	0/0	3/0	4/4	0/0	0/0	0/0	1/0	(3)	3/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Dimethylformamide (DMF)	C_3H_7NO	000068-12-2		T, F	X	1/1	1/3	1	4/4	1/0	1/1	1/2	1/1	4/4	4/4	3/4	0/0	4/4	2/2	1/1	1/1	4/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Dimethyl ketone	-> see: Acetone																													
Dimethylpentanone-3, 2,4-	-> see: Diisopropyl ketone																													
Dimethyl phthalate (DMP)	$C_{10}H_{10}O_4$	000131-11-3	100 %	(Xn)		4/4	1/3	(2)	4/4	0/0	0/0	(2)	2/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(2)	3/0	2/0	4/4	0/0	(1)	(1)	(1)	0/0	Plasticiser
Dimethylpropane	-> see: Pentane																													
Dimethyl sulphoxide (DMSO)	C_2H_6SO	000067-68-5		Xi		1/1	1/1	(2)	4/4	0/0	1/1	1/0	1/1	1/2	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(3)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		
Disodium hydrogen phosphate	-> see: Disodium phosphate																													
Disodium phosphate	Na_2HPO_4	007558-79-4		(Xi)		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	(1)	1/1	1/1	0/0	
Disodium sulphate	-> see: Sodium sulphate																													
Dinonyl phthalate (DNP)	$C_{26}H_{42}O_4$	000084-76-4	tech. pure	Xn		3/0	0/0	(2)	3/0	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioctyladipate	$C_{22}H_{42}O_4$	000103-23-1		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioctyl phthalate	-> see: Diisooctyl phthalate																													
Dioctyl sebacate	$C_{26}H_{50}O_4$	002432-87-3		—		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioxane	$C_4H_8O_2$	000123-91-1		F, Xn	X	2/2	2/3	1/0	4/4	1/0	2/3	1/2	3/3	4/4	2/3	3/4	4/4	4/4	1/3	1/1	1/1	3/3	2/0	4/4	4/4	0/0	1/1	1/0	1/0	0/0	
Dioxane, 1,4-	-> see: Dioxane																													
Dipentene	-> see: Limonene, DL-																													
Dipentyl phthalate	-> see: Phthalic acid amyl ester																													
Diphenylamine	$C_{12}H_{11}N$	000122-39-4		T		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	0/0	
Diphenyleneimine	-> see: Carbazole																													
Diphenyl ether	$C_{12}H_{10}O$	000101-84-8		Xn/Xi		0/0	1/0	3/0	(3)	(4)	0/0	1/1	4/4	4/4	0/0	0/0	4/4	4/4	0/0	(1)	1/0	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Diphenylmethane diisocyanate (MDI)	-> see: Desmodur 44																													
Diphenyl oxide	-> see: Diphenyl ether																													
Diphosphorus pentoxide	-> see: Phosphorus pentoxide																													
Diphyl	—	008004-13-5		?		0/0	0/0	1/1	(3)	4/4	0/0	1/1	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)		Mixture of diphenyl and diphenyl ether; Bayer
Dipropylene glycol	$C_6H_{14}O_3$	025265-71-8		Xi		1/1	1/1	(2)	2/3	0/0	1/1	1/0	1/1	1/1	2/2	2/3	0/0	0/0	1/1	1/1	(1)	(2)	4/4	3/0	3/3	0/0	(1)	(1)	(1)		
Dipropyl ketone	$C_7H_{14}O$	000123-19-3		—	X	0/0	0/0	(3)	(4)	(4)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Dipropylmethane, n-	-> see: Heptane, n-																													
Di-sulphur dichloride	-> see: Sulphur chloride																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals		
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Dinitrogen tetroxide	-> see: Nitrogen tetroxide																													
Disulphite	-> see: Sodium disulphite																													
Divinylensulphide	-> see: Thiophene																													
Dodecanol	-> see: Lauryl alcohol																													
Dodecyl alcohol	-> see: Lauryl alcohol																													
Dodecyl chloride	-> see: Lauryl chloride																													
Dolcymene	-> see: Cymene, p-																													
Eau de Labarraque	-> see: Sodium hypochlorite																													
Edetic acid	-> see: Ethylenediaminetetraacetic acid																													
Iron (II) ammonium sulphate	-> see: Ammonium iron (II) sulphate																													
Iron (II) chloride	$FeCl_2$	007758-94-3	saturated	Xn		1/1	1/1	3/0	1/0	(2)	1/0	(3)	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	(1)	0/0	4/4	(2)	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7	saturated	(Xn)		1/1	1/1	(2)	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7	aqueous	(Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7		Xn		1/1	1/1	(2)	1/0	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/0	(1)	0/0	4/4	1/1	1/1	1/1	
Iron (III) chloride	$FeCl_3$	007705-08-0	saturated	Xn		1/1	1/1	3/0	1/0	0/0	1/0	4/4	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	4/4	4/4	4/4	1/1	
Iron (III) nitrate	-> see: Ferric nitrate																													
Iron (III) sulphate	$Fe_2(SO_4)_3$	010028-22-5	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1	
Iron alum	-> see: Ammonium iron (III) sulphate																													
Iron ammonium alum	-> see: Ammonium iron (III) sulphate																													
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	aqueous	(O, Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	saturated	O, Xn		1/1	1/1	1/0	1/0	0/0	1/0	(3)	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Iron vitriol	-> see: Iron (II) sulphate																													
Glacial acetic acid	-> see: Acetic acid																													
Elaol	-> see: Dibutyl phthalate																													
Emulsifiers	—	—		?		0/0	0/0	(2)	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(3)	0/0	0/0	K	K		
Developer fluids	—	—		?		1/1	1/1	4/4	1/0	1/0	0/0	1/0	1/1	0/0	1/0	1/1	1/0	0/0	0/0	0/0	1/1	(1)	2/0	1/0	3/3	0/0	1/1	1/0	1/0	0/0	
Limescale	—	—	10% in Water	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Epichlorohydrin	C_3H_5ClO	000106-89-8	100 %	F, T	X	1/0	1/0	4/4	(4)	0/0	(4)	1/0	2/2	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(3)	3/0	4/4	4/4	0/0	(3)	0/0	0/0	0/0	
Epoxypropane	-> see: Propylene oxide																													
Epsom salt	-> see: Magnesium sulphate																													
Natural gas	—	—		F+	X	0/0	0/0	01/0	1/0	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	0/0	mainly methane
Peanut oil	—	008002-03-7		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Crude oil / petroleum	—	008002-05-9		(Xn)		0/0	0/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/3	0/0	(1)	(1)	(1)	0/0	Kerosene, lamp oil
Vinegar	$C_2H_4O_2$	000064-19-7		(Xi)		1/1	1/3	4/4	1/2	1/1	1/0	1/3	1/1	1/0	1/0	1/0	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/2	1/1	Wine vinegar, acetic acid
Acetic ester	-> see: Ethyl acetate																													
Acetic acid	$C_2H_4O_2$	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	90%	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1	1/1	
Acetic acid Silver salt	-> see: Silver acetate																													
Acetic alumina	$C_4H_7AlO_5 \times H_2O$	000142-03-0	saturated	Xi		1/1	1/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1		
Acetic acid allyl ester	-> see: Allyl acetate																													
Acetic acid amide	-> see: Acetamide																													
Acetic anhydride	$C_4H_6O_3$	000108-24-7	tech.pure	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1	1/1	
Acetic acid benzyl ester	-> see: Benzyl acetate																													
Acetic acid butyl ester	$C_6H_{12}O_2$	000123-86-4	100 %	—	X	2/2	2/3	1/0	4/4	3/0	3/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	3/0	4/4	4/4	0/0	1/1	(1)	(1)	4/4	
Acetic acid chloride	-> see: Acetyl chloride																													
Acetic acid ethyl ester	-> see: Ethyl acetate																													
Acetic acid isobutyl ester	-> see: Isobutyl acetate																													
Acetic acid isopropyl ester	-> see: Isopropyl acetate																													
Acetic acid methyl ester	$C_3H_6O_2$	000079-20-9	tech. pure	F	X	1/0	1/1	1/0	4/4	3/0	(4)	2/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Acetic acid-n-amyl ester	-> see: Amyl acetate, n-																													
Acetic acid pentyl ester	-> see: Amyl acetate, n-																													
Acetic acid propyl ester	-> see: Propyl acetate																													
Acetic acid vinyl ester	-> see: Vinyl acetate																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ethanal	-> see: Acetaldehyde																													
Ethane carboxylic acid	-> see: Propionic acid																													
Ethanediamine	-> see: Ethylenediamine																													
Ethanedicarboxylic acid	-> see: Succinic acid																													
Ethanediol	-> see: Ethylene glycol																													
Ethanedioic acid	-> see: Oxalic acid																													
Ethanol	C_2H_6O	000064-17-5	40 %	—	X	1/1	1/2	1/0	1/2	1/1	1/2	1/2	1/1	2/3	1/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Ethanol	C_2H_6O	000064-17-5	50 %	—	X	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	
Ethanol	C_2H_6O	000064-17-5	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	
Ethanolamine	C_2H_7NO	000141-43-5		Xn/Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/2	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Ethanoic acid	-> see: Acetic acid																													
Ethanethiol	C_2H_6S	000075-08-1		F, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ethene	-> see: Ethylene																													
Ether	-> see: Ethyl ether																													
Ethyne	-> see: Acetylene																													
Ethinylcarbiol	-> see: Propargyl alcohol																													
Ethoxyacetanilide, 4-	-> see: Phenacetin																													
Ethoxyethanol	-> see: Ethyl glycol																													
Ethoxyethyl acetate, 2-	-> see: Ethylene glycol monoethyl ether acetate																													
Ethyl(hydroxymethyl)-propanediol	-> see: Trimethylolpropane																													
Ethyl acetate	$C_4H_8O_2$	000141-78-6	100 %	F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/1	1/3	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	3/3	3/0	4/4	4/4	0/0	1/1	(1)	(1)	1/0	
Ethyl acrylate	$C_5H_8O_2$	000140-88-5	100 %	F, Xn	X	4/4	4/4	1/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	3/0	4/4	4/4	4/4	0/0	(1)	(1)	(1)	1/0	
Ethyl alcohol	-> see: Ethanol																													
Ethylbenzol	-> see: Ethylbenzene																													
Ethyl benzoate	-> see: Benzoic acid ethyl ester																													
Ethylbenzene	C_8H_{10}	000100-41-4		F, Xn	X	2/3	3/4	(2)	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	1/1	4/4	(2)	4/4	0/0	(1)	(1)	(1)	0/0	
Ethyl butyrate	$C_6H_{12}O_2$	000105-54-4		F	X	2/3	2/4	(2)	4/4	0/0	3/4	(2)	2/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethylcarbinol	-> see: Propanol																													
Ethyl cellosolve	-> see: Ethyl glycol																													
Ethyl chloroacetate	$C_4H_7ClO_2$	000105-39-5	tech. pure	T/Xi		1/1	1/1	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/4	3/4	0/0	0/0	(1)	1/1	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Ethyl chloride	-> see: Chlorethane																													
Ethyl cyanoacetate	$C_5H_7NO_2$	000105-56-6		Xn/Xi		1/1	1/1	0/0	3/4	0/0	1/1	(2)	1/1	2/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Ethylene	C_2H_4	000074-85-1		F+	X	0/0	0/0	1/0	(2)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	(3)	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Ethylene(di)bromide	-> see: Dibromoethane-1,2																													
Ethylene(di)chloride	-> see: Dichloroethane-1,2																													
Ethylene chlorohydrin	-> see: Chloroethanol																													
Ethylene chloride	$C_2H_4Cl_2$	—		F, T	X	3/3	2/4	3/0	4/4	4/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/3	1/1L	1/1L	0/0	Isomer not specified in the source
Ethylenediamine	$C_2H_8N_2$	000107-15-3	tech. pure	C, Xn	X	1/1	1/3	1/0	(3)	0/0	1/0	1/0	1/1	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/4	1/0	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Ethylenediaminetetraacetic acid (EDTA)	$C_{10}H_{16}N_2O_8$	000060-00-4		Xi		1/1	1/1	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(3)	0/0	0/0	0/0	
Ethylene dichloride	-> see: Ethylene chloride																													
Ethylenedinitrilotetraacetic acid	-> see: Ethylenediaminetetraacetic acid																													
Ethylene glycol	$C_2H_6O_2$	000107-21-1		Xn		1/1	1/1	3/3	2/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	1/1	
Ethylene glycol ethyl ether	-> see: Ethyl glycol																													
Ethylene glycol monobutyl ether	-> see: Butyl glycol																													
Ethylene glycol monobutyl ether	-> see: Ethyl glycol																													
Ethylene glycol monoethyl ether acetate	$C_6H_{12}O_3$	000115-15-9		Xn	X	1/1	1/2	0/0	3/4	0/0	1/2	(2)	1/2	4/4	4/4	3/4	0/0	0/0	1/2	1/1	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Ethylene glycol monomethyl ether	-> see: Methyl glycol																													
Ethylene oxide	C_2H_4O	000075-21-8		F+, T	X	2/3	3/3	3/0	3/4	1/0	3/4	1/0	3/3	4/4	1/1	3/4	0/0	0/0	1/1	1/1	(1)	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Ethylene tetrachloride	-> see: Perchloroethylene																													
Ethylene trichloride	-> see: Trichloroethylene																													
Ethylethanamine, N-	-> see: Diethylamine																													
Ethyl ether	$C_4H_{10}O$	000060-29-7	tech. pure	F+, Xn	X	3/4	4/4	1/1	4/4	1/0	4/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Ethyl formate	$C_3H_6O_2$	000109-94-4		F	X	0/0	0/0	0/0	(4)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethyl glycol	$C_4H_{10}O_2$	000110-80-5	100 %	T	X	0/0	4/4	(3)	(2)	0/0	0/0	1/0	2/4	4/4	1/0	4/4	4/4	4/4	0/0	1/1	1/0	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Ethyl glycol acetate	-> see: Ethylene glycol monoethyl ether acetate																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ethylhexanol-1	$C_8H_{18}O$	000104-76-7		Xn/Xi		0/0	1/3	(2)	(2)	(1)	1/0	1/0	1/0	3/0	0/0	1/0	4/4	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	
Ethyl lactate	$C_5H_{10}O_3$	000097-64-3		—	X	1/1	1/1	(2)	3/4	0/0	1/1	(2)	1/1	3/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	3/0	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Ethyl malonate	-> see: Diethylmalonate																													
Ethyl mercaptan	-> see: Ethanethiol																													
Ethyl methyl ketone	-> see: Methyl ethyl ketone																													
Ethyl silicate	-> see: Tetraethylorthosilicate																													
Eucalyptus oil	—	008000-48-8		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Desiccator grease	—	—		—		0/0	1/3	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(2)	(2)	0/0	(1)	(1)	(1)	0/0	
Ferrichloride	-> see: Iron (III) chloride																													
Potassium hexacyanoferrate(III)	$C_6FeK_3N_6$	013746-66-2	any	Xn		1/1	1/1	1/0	(1)	(1)	0/0	2/0	1/1	1/1	0/0	1/3	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1	1/1	
Ferrous chloride	-> see: Iron (II) chloride																													
Potassium hexacyanoferrate(II)	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	saturated	—		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(1)	1/1	1/1		
Potassium hexacyanoferrate(II)	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	diluted	—		1/0	1/1	1/0	(1)	(1)	0/0	2/0	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1		
Fat/Grease, mineral	—	—		(—)		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	(1)	1/0	0/0	(1)	1/1	1/1		
Fat/Grease, vegetable	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fat/Grease, animal	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fatty/Greasy alcohol sulphonates	—	—	aqueous	(Xn, Xi)		1/1	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	1/1	0/0	3/4	1/0	1/0	0/0	Fatty alcohol sulphates, wetting agents/surfactants
Fat/Grease, edible oil	—	—		—		0/0	1/0	1/0	1/0	1/0	1/0	1/1	3/0	0/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Fatty acid C16	-> see: Palmitic acid																													
Spruce needle oil	—	008008-80-8		?		1/2	2/4	(2)	2/3	0/0	2/3	(2)	1/2	4/4	3/3	3/4	0/0	3/4	1/2	1/1	(1)	(2)	4/4	1/0	3/3	0/0	(1)	(1)	(1)		Pinus sylvestris
Fish oil	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/4	1/0	1/0	0/0	(1)	(1)	(1)		
Fixing salt	-> see: Sodium thiosulphate																													
Aircraft engine fuels (JP)	—	—		(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	1/0	1/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	1/0	1/0	0/0	(1)	(1)	(1)		
Fluid 101, 100°C	—	—		?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	3	0	0	0	0		Brake fluid, polyglycol base
Fluorine	F_2	007782-41-4		O, T+, C+		4/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	4/4	4/4	3/0	4/4	0/0	4/4	(4)	(4)	0/0	
Fluorammonium	-> see: Ammonium fluoride																													
Fluorobenzene	C_6H_5F	000462-06-6		F, (Xn)	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0		
Fluorochloroalkanes (FCKW)	—	—		N		0/0	0/0	(2)	(3)	0/0	0/0	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(3)	(3)	0/0	(3)	0/0	(3)	0/0	0/0		Resistance varies depending on type
Fluorides	—	—		T		1/1	1/1	(2)	1/1	(2)	1/1	(1)	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	(1)	0/0	0/0	K	K		
Fluoropotassium	-> see: Potassium fluoride																													
Fluorosilicic acid	-> see: Silicofluoric acid																													
Fluorocarbons (FKW)	—	—		?		0/0	0/4	(2)	(3)	(2)	0/0	(2)	(3)	4/4	0/0	0/0	0/0	0/4	1/1	0/0	1/1	(3)	(3)	(3)	(3)	0/0	(1)	0/0	0/0		Resistance varies depending on type
Fluorosilicic acid	-> see: Silicofluoric acid																													
Fluorotrichloromethane	-> see: Trichlorofluoromethane																													
Hydrogen fluoride	HF	007664-39-3	anhydrous	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)		Hydrofluoric acid, anhydrous
Hydrogen fluoride solution	-> see: Hydrofluoric acid																													
Hydrofluoric acid	-> see: Hydrofluoric acid																													
Liquid soaps	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(2)	(2)	0/0	(3)	0/0	0/0		
Hydrofluoric acid	HF	007664-39-3	4 %	T, C		1/1	1/2	4/4	2/3	4/4	1/2	4/4	1/2	2/3	2/3	2/3	0/0	0/0	1/1	1/1	1/1	1/1	(3)	1/3	(2)	0/0	4/4	0/0	0/0	?	
Hydrofluoric acid	HF	007664-39-3	50 %	T+, C		1/1	1/1	4/4	4/4	4/4	1/1	4/4	1/1	4/4	3/4	2/3	2/0	3/3	1/1	1/1	1/1	1/1	3/4	1/3	3/4	0/0	4/4	4/4	4/4	?	
Hydrofluoric acid	HF	007664-39-3	70 %	T+, C		0/0	1/3	4/4	4/4	4/4	0/0	4/4	1/3	4/4	4/4	1/4	3/0	0/0	0/0	(1)	1/1	1/1	3/4	(3)	4/4	0/0	4/4	4/4	4/4	?	
Hydrofluoric acid	HF	007664-39-3	100 %	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)	?	
Hydrofluoric acid, anhydrous	-> see: Hydrogen fluoride																													
Formaldehyde solution	CH_2O	000050-00-0	10 %	Xn		1/1	1/1	3/3	1/2	1/0	1/2	1/2	1/1	3/4	2/3	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/0	3/0	(2)	0/0	1/1	1/1	1/1	1/1	
Formaldehyde solution	CH_2O	000050-00-0	30 %	T		1/1	1/1	3/3	1/2	1/0	0/0	1/2	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	1/1	1/1	
Formaldehyde solution	CH_2O	000050-00-0	40 %	T		1/2	2/3	1/3	1/2	1/0	1/2	1/2	1/2	4/4	2/3	2/3	3/3	0/4	1/1	1/1	1/1	1/1	1/0	3/0	(3)	0/0	1/1	1/1	1/1	1/1	
Formalin	-> see: Formaldehyde solution																													
Formamide	CH_3NO	000075-12-7	tech. pure	T/Xi		1/1	1/1	1/0	(3)	0/0	0/0	1/0	1/1	1/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	3/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	
Formin	-> see: Hexamethylenetetramine																													
Formylic acid	-> see: Formic acid																													
Photo emulsions	—	—		?		1/0	0/0	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(1)	0/0	(2)	0/0	0/0		
Photo developers	—	—		?		1/3	1/1	4/4	(2)	1/0	0/0	1/3	1/2	0/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Photo fixing baths	—	—		?		1/0	1/1	1/0	(2)	0/0	0/0	1/0	1/1	0/0	0/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/0	1/0		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Freon 11	-> see: Trichlorofluoromethane																													
Freon 112	-> see: Difluorotetrachloroethane																													
Freon 113	-> see: Trichlorotrifluoroethane																													
Freon 114	-> see: Dichlorotetrafluoroethane																													
Freon 114 B2	-> see: Dibromotetrafluoromethane																													
Freon 115	-> see: Chloropentafluoroethane																													
Freon 12	-> see: Dichlorodifluoromethane																													
Freon 13	-> see: Chlorotrifluoromethane																													
Freon 13 B1	-> see: Bromotrifluoromethane																													
Freon 14	-> see: Tetrafluoromethane																													
Freon 142b	-> see: Difluorochloroethane																													
Freon 152a	-> see: Difluoroethane																													
Freon 21	-> see: Dichlorofluoromethane																													
Freon 218	-> see: Perfluoropropane																													
Freon 22	-> see: Chlorodifluoromethane																													
Freon 31	-> see: Chlorofluoromethane																													
Freon 32	-> see: Difluoromethane																													
Freon C 318	-> see: Octafluorocyclobutane																													
Freon C316	-> see: Dichlorohexafluorocyclobutane																													
Frigen 12	-> see: Dichlorodifluoromethane																													
Frigen 21	-> see: Dichlorofluoromethane																													
Frigen 22	-> see: Chlorodifluoromethane																													
Antifreeze (KFZ)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1	1/1	Glycol-water mixtures
Fruit juices	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(2)	1/1	1/1	1/1	
Fruit sugar	-> see: Fructose																													
Fructose	$C_6H_{12}O_6$	000057-48-7	any	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Furan	C_4H_4O	000110-00-9		F+, T+	X	0/0	0/0	(3)	4/4	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Furanal	-> see: Furfural																													
Furancarbinol, 2-	-> see: Furfuryl alcohol																													
Furanmethanol, 2-	-> see: Furfuryl alcohol																													
Furfurol	-> see: Furfural																													
Furfural alcohol	-> see: Furfuryl alcohol																													
Furfuran	-> see: Furan																													
Furfural	$C_5H_4O_2$	000098-01-1		T		1/3	3/4	3/3	(3)	1/0	0/0	2/0	4/4	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	1/2	3/0	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Furfuryl alcohol	$C_5H_6O_2$	000098-00-0	tech. pure	Xn		1/1	1/3	1/0	(3)	1/0	0/0	1/0	1/3	0/0	4/4	4/4	4/4	3/4	0/0	(1)	1/1	1/3	3/0	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Furylaldehyde, 2-	-> see: Furfural																													
Furylmethanal, 2-	-> see: Furfural																													
Gallotannin	-> see: Tannin																													
Gallic acid	$C_7H_6O_5 \times H_2O$	000149-91-7		Xi		1/1	1/1	1/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/4	3/0	1/0	3/0	0/0	1/0	1/1	1/1	1/1	
Fermentation amyl alcohol	-> see: Isoamyl alcohol																													
Fermentation mash	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(1)	1/0	4/4	0/0	(2)	(1)	(1)	0/0	
Gas oil (straight-run)	—	—		(Xn)		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Gasoline	—	008006-61-9		(F, Xn)	X	0/0	0/0	(1)	3/4	(2)	0/0	1/2	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/0	0/0	1/1	(1)	(1)		
Gas water	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(2)	0/0	(2)	0/0	0/0		
Gelatine	—	009000-70-8	any	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Genantin	—	—		Xn		0/0	0/0	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		Antifreeze, basis glycol; Clariant
Tanning extracts, vegetable	—	—	tech. common	?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Tanning extracts	—	—		?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Tannic acid	-> see: Tannin																													
Gear oil, EP (hypoid), 110°C	—	—		?		0	0	1	1	1	0	4	(3)	0	0	0	0	0	0	0	(2)	0	4/4	0	4/4	0	(1)	1	1		
Plaster	-> see: Calcium sulphate																													
Glauber's salt	-> see: Sodium sulphate																													
Glucaric acid	-> see: Sugar acid																													
Glucose	$C_6H_{12}O_6$	000050-99-7	any	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Glucose syrup	-> see: Starch syrup																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Glycerine	$C_3H_8O_3$	000056-81-5	any	Xi		1/1	1/1	1/0	3/3	1/0	1/1	1/0	1/1	1/1	1/1	1/1	2/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Glycerol trinitrate	-> see: Nitroglycerin																													
Glycine	-> see: Aminoacetic acid																													
Glycol	-> see: Ethylene glycol																													
Glycol dinitrate	-> see: Nitroglycol																													
Glycolic acid	$C_2H_4O_3$	000079-14-1	37 %	Xn		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	2/0	1/0	0/0	1/0	1/3	1/3	1/1	
Glycolic acid	$C_2H_4O_3$	000079-14-1	70 %	C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(2)	1/0	3/0	(2)	0/0	(2)	1/3	1/3	1/1	
Glycocoll	-> see: Aminoacetic acid																													
Glycol chlorohydrin	-> see: Chloroethanol																													
Glysantin	—	—		Xn		1/1	1/1	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		Antifreeze, basis glycol; BASF
Glycerol triacetate	-> see: Triacetin																													
Firedamp	—	—		F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		mainly methane
Uric acid	$C_5H_4N_4O_3$	000069-93-2		Xi		1/1	1/1	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	4/4	1/1	1/1	0/0	
Urea	CH_4N_2O	000057-13-6	aqueous	Xi		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, carbamide, etc.
Urea	CH_4N_2O	000057-13-6		Xi		1/1	1/1	1/0	1/1	1/0	1/2	1/1	1/1	1/2	3/3	2/4	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, carbamide, etc.
HD oil engine oil, aromatics-free	—	—		?		1/0	1/3	1/0	1/1	1/1	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	(1)	3/3	0/0	1/1	1/1	1/1		
Yeast	—	—	any	—		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	(1)	(1)		
Heating oil	—	—		Xn		3/3	3/4	1/0	3/3	1/0	2/3	1/1	1/3	3/4	1/2	1/1	3/3	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Helium	He	007440-59-7		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	1/0	1/0	1/0	0/0	1/1	1/1	1/1		
Hendecanol	-> see: Undecyl alcohol																													
Henkel-P3-solution	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/0	0/0	0/0	1/1	1/1		Cleaning agents
Heptan, n-	C_7H_{16}	000142-82-5		F, Xn	X	2/3	3/4	1/0	1/2	1/0	3/3	1/2	2/4	4/4	1/2	2/3	4/4	1/0	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Heptanol, 1-	$C_7H_{16}O$	000111-70-6		Xn		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	(1)	(1)	(1)		
Heptanon	$C_7H_{14}O$	—		(Xn)	X	0/0	0/0	(3)	(4)	(4)	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(4)	(4)	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Heptanon-4	-> see: Dipropylketone																													
Heptyl alcohol	-> see: Heptanol, 1-																													
Hexachlorobenzene (HCB)	C_6Cl_6	000118-74-1		T		0/0	0/0	(3)	(4)	0/0	(4)	1/0	(3)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(2)	0/0	4/4	(3)	4/4	0/0	(1)	0/0	0/0		
Hexachlorobutadiene (HCBD)	C_4Cl_6	000087-68-3		T		0/0	0/0	(3)	4/4	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexachlorocyclohexane (HCH)	$C_6H_6Cl_6$	000319-84-6		T		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexadecanol	-> see: Cetyl alcohol																													
Hexadecanoic acid	-> see: Palmitic acid																													
Hexadecyl alcohol	-> see: Cetyl alcohol																													
Hexahydrobenzene	-> see: Cyclohexan																													
Hexahydrophenol	-> see: Cyclohexanol																													
Hexahydropyridine	-> see: Piperidine																													
Hexahydrotoluene	-> see: Methylcyclohexane																													
Hexaldehyde	-> see: Hexanal																													
Hexamethylenetetramine	$C_6H_{12}N_4$	000100-97-0		F, Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	1/1	1/1	0/0	
Hexamine	-> see: Hexamethylenetetramine																													
Hexane, n-	C_6H_{14}	000110-54-3		F, Xn	X	2/3	4/4	1/0	(2)	1/0	3/4	1/1	2/3	4/4	1/2	2/4	4/4	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Hexanal	$C_6H_{12}O$	000066-25-1		F, Xi	X	0/0	0/0	0/0	(4)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Hexanedioic acid	-> see: Adipic acid																													
Hexanol, (1-)	$C_6H_{14}O$	000111-27-3		Xn		1/0	1/0	(2)	(2)	(1)	0/0	(1)	1/2	0/0	3/0	1/0	3/0	1/3	0/0	(1)	1/0	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Hexanone-2	-> see: Methyl butyl ketone																													
Hexanetriol	$C_6H_{14}O_3$	—	100 %	?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	1/1	3/3	1/1	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Hexen, 1-	C_6H_{12}	000592-41-6		F, Xn	X	0/0	0/0	1/0	(2)	(1)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Hexylaldehyde	-> see: Hexanal																													
Hexyl alcohol	-> see: Hexanol, (1-)																													
Hexylene	-> see: Hexen, 1-																													
Staghorn salt	-> see: Ammonium carbonate																													
Wood alcohol	-> see: Methanol																													
Wood oil	—	008001-20-5		—		0/0	0/0	(1)	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	1/1	(1)	(1)		
Wood tar oil	-> see: Creosote																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Honey	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	0/0	(1)	(1)	(1)	0/0	
Gibbsite	-> see: Aluminium hydroxide																													
Hydraulic fluids, HFA	—	—	50°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFB	—	—	50°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFC	—	—	60°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	0	0	1	0	(2)	0	0		
Hydraulic fluids, HFD-R	—	—	100°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic fluids, HFD-S	—	—	100°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic oils (mineral oil based)	—	—		?		0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	(1)	1/0	0/0	1/1	1/1	1/1		
Hydrazine	N_2H_4	000302-01-2	10 %	T	X	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	1/1	
Hydrazine hydrate	N_2H_6O	010217-52-4	aqueous	(T, C)	(X)	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	0/0	
Hydrazinium hydroxide	-> see: Hydrazine hydrate																													
Hydrazinobenzene	-> see: Phenylhydrazine																													
Hydroquinone	$C_6H_6O_2$	000123-31-9	saturated	Xn		0/0	1/3	4/4	(3)	1/0	0/0	(3)	1/0	4/4	0/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	4/4	4/4	0/0	(1)	1/0	1/0	0/0	
Hydrosulphite	-> see: Sodium dithionite																													
Hydroxy-4-methyl-2-pentanone, 4-	-> see: Diacetone alcohol																													
Hydroxybenzaldehyde, 2-	-> see: Salicylaldehyde																													
Hydroxybenzoic acid, 2-	-> see: Salicylic acid																													
Hydroxybenzene	-> see: Phenol																													
Hydroxybenzenecarboxylic acid, 2-	-> see: Salicylic acid																													
Hydroxyacetic acid	-> see: Glycolic acid																													
Hydroxylamine sulphate	-> see: Hydroxylammonium sulphate																													
Hydroxylammonium sulphate	$H_8N_2SO_6$	010039-54-0	12 %	Xn		1/1	1/1	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	1/1	
Hydroxylammonium sulphate	$H_8N_2SO_6$	010039-54-0	any	Xn		1/1	0/0	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	1/1	
Hydroxymethoxybutane	-> see: Methoxybutanol																													
Hydroxymethylfuran, 2-	-> see: Furfuryl alcohol																													
Hydroxymethylfurfural, 5-	-> see: Oxymethylfurfurol, 5-																													
Hydroxymethyl tetrahydrofuran, 2-	-> see: Tetrahydrofurfuryl alcohol																													
Hydroxypropane	-> see: Propanol																													
Hydroxypropane, 2-	-> see: Isopropyl																													
Hydroxypropionic acid, 2-	-> see: Lactic acid																													
Hydroxypropionic acid ethyl ester, 2-	-> see: Ethyl lactate																													
Hydroxytoluene	-> see: Cresol (-mixtures)																													
Iminodiethanol	-> see: Diethanolamine																													
Ginger	—	—	grinded	?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Isoamyl alcohol	$C_5H_{12}O$	000123-51-3		Xn	X	0/0	0/0	(2)	3/0	1/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	1/3	0/0	(1)	!/1	1/1	3/0	2/4	3/3	0/0	(1)	(1)	(1)		
Isobutanol	$C_4H_{10}O$	000078-83-1		Xn	X	1/1	1/1	(2)	1/2	(2)	1/2	1/0	1/1	2/2	1/2	1/2	0/0	3/4	1/1	1/1	(1)	1/1	1/0	1/0	3/4	0/0	1/0	(1)	(1)	0/0	
Isobutyl acetate	$C_6H_{12}O_2$	000110-19-0		F	X	0/0	0/0	(2)	(4)	0/0	(4)	1/0	(3)	4/4	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Isobutyl alcohol	-> see: Isobutanol																													
Isobutyl ketone	-> see: Diisobutyl ketone																													
Isobutyl methyl ketone	$C_6H_{12}O$	000108-10-1		F	X	1/2	2/3	1/0	4/4	(4)	3/3	(2)	2/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Isobutyltrimethylmethane	-> see: Iso-octane																													
Iso-octane	C_8H_{18}	000540-84-1	tech. pure	F, Xn	X	1/3	1/3	1/0	(2)	1/0	(4)	1/0	1/3	3/4	1/0	1/0	4/4	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Isooctanol	-> see: Ethylhexanol-1																													
Isooctyl alcohol	-> see: Ethylhexanol-1																													
Isopropyl	C_3H_8O	000067-63-0	tech. pure	F	X	1/1	1/1	1/0	1/2	1/0	1/2	1/0	1/1	2/2	1/2	1/2	4/4	1/4	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	(2)	(1)	(1)	0/0	
Isopropyl-4-methylbenzene, 1-	-> see: Cymene, p-																													
Isopropyl-5-methylcyclohexanol, 2-	-> see: Menthol																													
Isopropyl-5-methylphenol, 2-	-> see: Thymol																													
Isopropyl acetate	$C_5H_{10}O_2$	000108-21-4		F, Xi	X	1/2	2/3	1/0	4/4	(3)	2/3	1/0	2/3	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/1	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Isopropyl acetone	-> see: Isobutyl methyl ketone																													
Isopropyl alcohol	-> see: Isopropyl																													
Isopropylbenzene	-> see: Cumene																													
Isopropylbenzol	-> see: Cumene																													
Isopropyl chloride	C_3H_7Cl	000075-29-6		F, Xn	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Isopropyl ether	$C_6H_{14}O$	000108-20-3	tech. pure	F	X	3/4	3/4	4/4	(4)	1/0	(4)	(1)	3/4	4/4	1/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Isopropylidene acetone	-> see: Mesityl oxide																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Isopropyl methyl ketone	$C_5H_{10}O$	000563-80-4		F	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Jasminaldehyde	-> see: α-pentylcinnamaldehyde																													
Iodine potassium	-> see: Potassium iodide																													
Iodoform	CHJ_3	000075-47-8	100 %	Xn		3/0	3/0	(3)	3/0	0/0	0/0	(2)	3/0	3/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(2)	1/0	1/0	(3)	0/0	(3)	(1)[1)]	(1)[1)]	1/1	[1)] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Iodine pentafluoride	JF_5	007783-66-6		(T, C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Tincture of iodine	I_2	007553-56-2		Xn	(X)	1/3	1/3	4/4	3/4	0/0	1/1	1/1	1/2	3/3	0/0	4/4	4/4	3/3	1/1	0/0	1/1	1/1	2/0	1/1	3/3	0/0	1/0	2/0L	1/0L	1/1		
Cocoa	—	—		(—)		1/1	1/1	(2)	(1)	(2)	0/0	1/1	(2)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Cocoa butter	—	008002-31-1		—		0/0	0/0	1/0	(1)	1/0	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1		
Potash alum	-> see: Potassium aluminium sulphate																													
Potash lye	-> see: Potassium hydroxide																													
Potassium peroxodisulphate	-> see: Potassium persulphate																													
Potassium nitrate	-> see: Potassium nitrate																													
Potassium (hexa)cyanoferrate-(II)	-> see: Potassium hexacyanoferrate (II)																													
Potassium (hexa)cyanoferrate-(III)	-> see: Potassium hexacyanoferrate (III)																													
Potassium acetate	$C_2H_3KO_2$	000127-08-2	aqueous	Xi		1/1	1/1	1/0	(1)	(2)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/0	1/1	1/1	3/0	3/3	0/0	1/3	1/1	1/1	0/0	
Potassium aluminium sulphate	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	diluted	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Potassium aluminium sulphate	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	saturated	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Potassium bicarbonate	-> see: Potassium hydrogen carbonate																													
Potassium bichromate	-> see: Potassium dichromate																													
Potassium bisulphate	-> see: Potassium hydrogen sulphate																													
Potassium bitartrate	-> see: Potassium hydrogentartate																													
Potassium borate	KBO_2	012228-88-5	10 %	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0	
Potassium borate	KBO_2	012228-88-5	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0	
Potassium bromate	$KBrO_3$	007758-01-2	saturated	O, T		1/3	1/3	(2)	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Potassium bromate	$KBrO_3$	007758-01-2	aqueous	O, T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Potassium bromide	KBr	007758-02-3	any	Xn		1/1	1/1	3/0	1/0	(1)	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/0L	1/0L	1/1	
Potassium carbonate	K_2CO_3	000584-08-7	saturated	Xn		1/1	1/1	1/1	3/3	(2)	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1	
Potassium carbonate	K_2CO_3	000584-08-7	aqueous	Xn		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1	
Potassium chlorate	$KClO_3$	003811-04-9	saturated	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium chlorate	$KClO_3$	003811-04-9	aqueous	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium chloride	KCl	007447-40-7	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/3	1/1L	1/1L	1/1	
Potassium chromate	K_2CrO_4	007789-00-6	saturated	T		1/0	1/1	2/0	(2)	0/0	1/0	(2)	1/1	1/1	0/0	1/1	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Potassium chromate	K_2CrO_4	007789-00-6	aqueous	T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Potassium cyanide	KCN	000151-50-8	saturated	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	4/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Potassium cyanide	KCN	000151-50-8	aqueous	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	1/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Potassium dichromate	$K_2Cr_2O_7$	007778-50-9	saturated	T		1/1	1/0	4/4	3/0	3/0	1/0	3/0	1/1	1/3	0/0	1/3	1/0	1/3	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Potassium dichromate	$K_2Cr_2O_7$	007778-50-9	aqueous	T		0/0	0/0	3/0	1/0	3/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Potassium iron (II) cyanide	-> see: Potassium hexacyanoferrate (III)																													
Potassium iron (III) cyanide	-> see: Potassium hexacyanoferrate (II)																													
Potassium fluoride	KF	007789-23-3		T		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	(1)	0/0	1/1	1/1	1/1	0/0	
Potassium hydrogen carbonate	$CHKO_3$	000298-14-6	saturated	—		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	4/4	(1)	(1)	1/1	
Potassium hydrogen sulphate	$KHSO_4$	007646-93-7	aqueous	(C)		1/1	1/1	4/4	1/0	(2)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	1/1	
Potassium hydrogen sulphate	$KHSO_4$	007646-93-7		C		1/1	1/1	4/4	1/0	0/0	0/0	2/0	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	?	
Potassium hydrogentartate	$C_4H_5KO_6$	000868-14-4	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(4)	1/3	1/2	0/0	
Potassium hydroxide	KHO	001310-58-3	10 %	C+		1/1	1/1	1/0	4/4	4/4	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	30 %	C+		1/1	1/1	1/3	4/4	4/4	1/0	(3)	1/1	1/0	1/0	1/3	1/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	50 %	C+		1/1	1/1	1/3	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/3	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	concentrated	C+		1/1	1/1	1/0	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/2	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	1 %	Xi		1/1	1/1	1/0	3/4	(4)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/3	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hypochlorite	KClO	007778-66-7	diluted	(O, C)		1/0	1/3	3/0	(3)	(3)	1/0	4/4	1/3	3/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	4/4	3/3L	2/2L	1/1	Javelle water, originally
Potassium iodate	KJO_3	007758-05-6		O		0/0	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/1	(1)	(1)	(2)	0/0	1/1	1/1	1/1	0/0	
Potassium iodide	KJ	007681-11-0	saturated	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Potassium iodide	KJ	007681-11-0	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	1/1	
Potassium nitrate	KNO_3	007757-79-1	50 %	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium nitrate	KNO_3	007757-79-1	aqueous	O, Xn		1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium perchlorate	$KClO_4$	007778-74-7	saturated	O, Xn		1/1	1/1	(1)	1/0	(1)	1/0	1/1	1/1	0/0	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	
Potassium perchlorate	$KClO_4$	007778-74-7	aqueous	O, Xn		1/1	1/1	(1)	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium permanganate	$KMnO_4$	007722-64-7	aqueous	O, Xn		0/0	0/0	4/4	1/0	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	hypermanganic potash
Potassium permanganate	$KMnO_4$	007722-64-7		O, Xn		1/3	1/1	4/4	1/0	(2)	1/1	1/1	1/1	1/3	0/0	1/3	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	hypermanganic potash
Potassium persulphate	$K_2(SO_4)_2$	007727-21-1	any	O, Xn		1/1	1/1	4/4	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/0	1/0	1/1	
Potassium sulphate	K_2SO_4	007778-80-5	aqueous	Xn		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium sulphide	K_2S	001312-73-8	diluted	(C)		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	(1)	(1)	2/0	0/0	3/4	1/1	1/1	0/0	
Potassium sulphite	K_2SO_3	010117-38-1	saturated	(Xi)		1/1	1/1	(1)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/0	1/0	0/0	
Potassium thiosulphate	$K_2S_2O_3$	010233-00-8	saturated	Xi		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	3/3	0/0	(1)	(1)	(1)		
Lime, burnt	-> see: Calcium oxide																													
Hydrated lime	-> see: Calcium hydroxide																													
Lime nitrate	-> see: Calcium nitrate																													
Lime water	-> see: Calcium hydroxide																													
Cardamom	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Rubber (caoutchouc) dispersion	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(1)	(2)	0/0	(3)	(1)	(1)		Latex
Kerosene	—	008008-20-6		(Xn)		2/2	3/4	(1)	4/4	1/1	2/3	1/1	3/3	4/4	2/3	1/1	0/0	0/0	2/3	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	Lamp oil, light petroleum
Pine needle oil	—	008023-99-2		?		0/0	0/0	1/0	(3)	0/0	(4)	(2)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	0/0	Pinus sylvestris
Silicofluoric acid	H_2SiF_6	016961-83-4	32 %	C		1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	3/0	2/2	3/4	0/0	4/4	(2)	1/1	1/1	
Silicic acid	SiO_2	001343-98-2	any	—		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Silicic acid tetraethylester	-> see: Tetraethylorthosilicate																													
Bone oil	—	008001-85-2		—		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Common salt	-> see: Sodium chloride																													
Carbon (substance) disulphide	-> see: Carbon disulphide																													
Carbon dioxide	CO_2	000124-38-9	saturated	?		1/3	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbon dioxide, moist	CO_2	000124-38-9	tech. pure	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbon dioxide, dry	CO_2	000124-38-9	tech. pure	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbonic acid	-> see: Carbon dioxide																													
Carbonic acid dichloride	-> see: Phosgene																													
Carbon tetrabromide	-> see: Carbon tetrabromide																													
Carbon tetrachloride	-> see: Carbon tetrachloride																													
Coconut fat	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1		
Coconut oil alcohol	—	068425-37-6	tech. pure	(Xi)		1/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1		
Coconut oil	—	008001-31-8	tech. pure	—		1/3	1/3	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Aqua regia	HNO_3 + HCl	008007-56-5		C		4/4	4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	4/4	0/0	4/4	4/4	4/4	4/4	Aqua regia = Nitric acid + hydrochloric acid
Fuel + 20% ethanol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	1/1	1/1		
Fuel + 20% methanol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	1/1	1/1		
Fuel, Normal	—	—		F, T	X	0/0	0/0	1/0	3/0	1/1	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Fuel, Super	—	—		F, T	X	0/0	0/0	1/0	4/4	(2)	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Chalk	$CaCO_3$	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	Calcium carbonate
Creosote	—	—		(T)		1/1	1/1	3/0	(3)	0/0	0/0	(3)	3/4	0/0	1/0	3/0	4/4	0/0	0/0	(1)	1/1	(3)	4/4	(3)	1/0	0/0	(2)	1/1	1/1	0/0	
Cresol (-mixtures)	C_7H_8O	001319-77-3		T, C		3/4	4/4	4/4	4/4	4/4	4/4	4/4	2/3	4/4	4/4	4/4	4/4	3/4	1/2	1/1	1/1	1/1	4/4	1/0	4/4	0/0	1/1	1/0	1/0	1/1	
Carum	—	—	grinded	?		0/0	0/0	(2)	(2)	(1)	0/0	1/1	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	4/4	(1)	(1)		
Kupfer-(I)-chlorid	CuCl	007758-89-6	aqueous	Xn		0/0	0/0	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1	
Kupfer-(I)-cyanid	-> see: Copper cyanide																													
Kupfer-(II)-chlorid	$CuCl_2$	007447-39-4	saturated	Xn		1/3	1/1	(3)	1/0	(2)	1/0	(2)	1/3	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1	
Kupfer-(II)-nitrat	$Cu(NO_3)_2$	003251-23-8	saturated	O, Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/0	1/1	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/1	1/1	1/1	
Kupfer-(II)-nitrat	$Cu(NO_3)_2$	003251-23-8	aqueous	O, Xn		0/0	0/0	(3)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	1/1	1/1	1/1	
Kupfer-(II)-sulfat	-> see: Copper sulphate																													
Copper acetate	$C_4H_6CuO_4$	004180-12-5	aqueous	Xn		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	(3)	3/3	0/0	4/4	1/1	1/1	1/1	Cupriacetate, verdigris
Copper cyanide	CCuN	000544-92-3	saturated	T		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/3	0/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	(3)	1/1	1/1		
Copper cyanuric	-> see: Copper cyanide																													
Copper sulphate, aqueous	-> see: Copper vitriol																													
Copper vitriol	$CuSO_4 \times 5H_2O$	007758-99-8	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/0	1/0	1/1	1/1	1/0	1/3	1/0	1/1	1/1	(1)	1/1	1/1	1/0	1/1	2/0	0/0	4/4	1/1	1/1	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Nitrous oxide	N_2O	010024-97-2		(O)		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	2/0	1/0	1/0	0/0	1/1	(1)	(1)		Nitrous oxide, "nitrogen oxydul"
Lactam	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	4/4	4/4	0/0	(2)	(1)	(1)		cyclic carboxylic acid amides
Lactobiosis	-> see: Lactose																													
Lactose	$C_{12}H_{22}O_{11}$	000063-42-3	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	
Lanolin	—	008006-54-0	tech. pure	—		3/3	3/3	1/0	1/0	1/0	0/0	(2)	3/3	1/1	0/0	3/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Latex	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(1)	(2)	0/0	(2)	(1)	(1)	1/1	Rubber dispersion
Lauryl alcohol	$C_{12}H_{26}O$	000112-53-8	100 %	Xi		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	(1)	(1)	0/0	
Lauryl chloride	$C_{12}H_{25}Cl$	000112-52-7	100 %	(Xi)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(1)	(3)	0/0	(3)	0/0	0/0		
Lavender oil	—	008000-28-0		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	(1)	(1)	(1)		
Cod liver oil	—	008001-69-2		—		1/3	1/3	(2)	1/0	(2)	0/0	(2)	1/3	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/0	(1)	(1)	1/1	
Glue (bone glue)	—	—	any	—		1/0	1/1	(1)	(1)	1/1	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(1)	(1)	1/0	1/0	0/0	(3)	1/1	1/1	0/0	
Linseed oil	—	008001-26-1	tech. pure	—		1/1	1/3	1/0	1/0	1/0	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Lemongrass oil	—	008007-02-1		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Luminous gas, benzene-free	—	—		F+, T	X	1/0	1/0	1/0	1/0	(2)	1/0	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/0	1/0	4/4	1/0	3/0	0/0	1/1	1/1	1/1	0/0	
Ligroin	—	008032-32-4		F, Xn	X	0/0	0/0	(2)	1/0	(2)	(4)	(2)	(3)	3/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		Light petrol
Liqueurs	—	—		—		1/0	0/0	(2)	1/0	1/0	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Limonene, DL-	$C_{10}H_{16}$	000138-86-3		Xn	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Lindane	-> see: Hexachlorocyclohexane																													
Lithium bromide	LiBr	007550-35-8		Xn		1/1	1/1	(3)	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Laurel	—	—	grinded	?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Lysol	—	—		T		0/0	0/0	(4)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(3)	1/1	1/1		Disinfectant, cresol + soap
Magnesite	-> see: Magnesium carbonate																													
Magnesium bromide	$MgBr_2$	007789-48-2		Xi		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	(3)	0/0	0/0		
Magnesium carbonate	$MgCO_3$	000546-93-0	saturated	—		1/1	1/1	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Magnesium chloride	$MgCl_2$	007786-30-3	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/2	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0L	1/0L	1/1	
Magnesium chlorite	$Mg(ClO_2)_2$	??		O		0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0		
Magnesium hydroxide	$Mg(HO)_2$	001309-42-8	saturated	—		1/1	1/1	1/0	(2)	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	1/1	1/1	1/1	1/1	0/0	
Magnesium iodide	MgJ_2	010377-58-9		(Xn)		1/1	1/1	(2)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/1	(1)	(2)	0/0	(2)	0/0	0/0		
Magnesium nitrate	$Mg(NO_3)_2$	010377-60-3	saturated	O, Xi		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	1/0	1/0	1/0	1/1	
Magnesium sulphate	$MgSO_4$	007487-88-9	any	—		1/1	1/1	1/0	1/0	1/0	1/0	1/0	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	0/0	1/1	1/1	1/1	1/1	
Magnesium sulphate heptahydrate	-> see: Epsom salt																													
Maize germ oil	—	008001-30-7	tech. pure	—		1/3	0/0	(2)	(1)	1/0	0/0	(2)	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	1/1	Maize oil
Maleic acid	$C_4H_4O_4$	000110-16-7	saturated	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Maleic acid	$C_4H_4O_4$	000110-16-7	aqueous	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Malonic ester	-> see: Diethylmalonate																													
Malonic acid diethyl ester	-> see: Diethylmalonate																													
Almond oil	—	008007-69-0		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	3/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(1)	(2)	0/0	(1)	1/1	1/1		
Margarine	—	—		—		0/0	0/0	(2)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Marmalade	—	—		—		1/1	1/1	(1)	1/1	1/1	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(2)	1/1	1/1	1/1	
Machine oil	—	—	100 %	?		0/0	1/4	(1)	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Matrium metabisulphite	-> see: Sodium disulphite																													
Matrium pyrochromate	-> see: Sodium dichromate																													
Marine water	-> see: Salt water, seawater																													
Molasses	—	—		—		1/1	1/1	1/0	(1)	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/0	1/0	3/4	
Molasses seasoning	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Menthadiene-1,8, p-	-> see: Limonene, DL-																													
Menthol	$C_{10}H_{20}O$	000089-78-1	solid	Xi		1/3	3/4	3/0	3/4	0/0	0/0	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	1/0	1/0		
Mercaptoacetic acid	-> see: Thioglycolic acid																													
Mercaptoethanoic acid, 2-	-> see: Thioglycolic acid																													
Mesityl oxide	$C_6H_{10}O$	000141-79-7		Xn	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	0/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methacrylic acid	$C_4H_6O_2$	000079-41-4		C		1/0	1/1	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	3/0	4/4	4/4	0/0	(4)	0/0	0/0		
Methacrylic acid methyl ester	-> see: Methyl methacrylate																													
Methane	CH_4	000074-82-8	tech. pure	F+	X	1/0	0/0	1/0	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Methanol solution	-> see: Formaldehyde solution																													
Methanamine	-> see: Methylamine, (mono)																													
Methane carboxylic acid	-> see: Acetic acid																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Methanol	CH_4O	000067-56-1		F, T	X	1/1	1/1	2/0	4/4	1/0	1/1	1/1	1/1	3/4	3/3	1/3	3/3	3/4	1/1	1/1	1/1	1/1	1/0	3/4	3/3	0/0	1/0	1/1	1/1	0/0	
Methanoic acid	-> see: Formic acid																													
Methenamine	-> see: Hexamethylenetetramine																													
Methoxybenzene	-> see: Anisole																													
Methoxybutanol	$C_5H_{12}O_2$	—	100 %	?	X	0/0	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	3/0	1/0	!/0	0/0	(1)	(1)	(1)		Isomer not specified in the source
Methoxyethanol	-> see: Methyl glycol																													
Methoxyethyl acetate	-> see: Methyl glycol acetate																													
Methoxyethyl oleate	$C_{21}H_{40}O_3$	000111-10-4		?		1/1	1/2	(2)	3/4	(2)	1/2	(2)	1/2	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(1)	(1)	4/4	(2)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Methoxypropanol	-> see: Propylene glycol methyl ether																													
Methyl ethyl ether	C_3H_8O	000540-67-0	100 %	(F+)	X	0/0	3/0	(1)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(2)	4/4	4/4	4/4	0/0	1/1	(1)	(1)		
Methyl 2-hydroxybenzoate	-> see: Methyl salicylate																													
Methyl 2-methyl propionate	-> see: Methyl methacrylate																													
Methyl acetate	-> see: Acetic acid methyl ester																													
Methacrolein	-> see: Crotonaldehyde																													
Methyl acrylate	$C_4H_6O_2$	000096-33-3		F, Xn	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Methylacrylic acid	-> see: Methacrylic acid																													
Methyl alcohol	-> see: Methanol																													
Methylamine, (Mono-)	CH_5N	000074-89-5	32 %	F+, C	X	1/0	1/0	4/4	4/4	0/0	0/0	1/0	1/0	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	3/0	1/0	4/4	4/4	0/0	1/0	1/0	1/0	0/0	
Methylbenzene	C_7H_8	000108-88-3		F, Xn	X	3/4	3/4	1/0	4/4	1/0	3/3	1/3	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/3	4/4	0/0	1/1	1/1	1/1	1/1	
Methyl bromide	-> see: Bromomethane																													
Methylbutanol	$C_5H_{12}O$	—		Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	1/3	0/0	(1)	1/1	1/1	3/0	2/2	3/3	0/0	(1)	(1)	(1)		Isomer not specified in the source
Methylbutanol, 3-	-> see: Isoamyl alcohol																													
Methylbutanone-2, 3-	-> see: Isopropyl methyl ketone																													
Methyl butyl alcohol	-> see: Methylbutanol																													
Methyl butyl ketone	$C_6H_{12}O$	000591-78-6		F, T	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl cellosolve	-> see: Methyl glycol																													
Methyl chloroacetate	$C_3H_5ClO_2$	000096-34-4	tech. pure	T/Xi	X	1/1	0/0	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/0	0/0	0/0	0/0	(1)	(1)	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Methyl chloride	-> see: Chloromethane																													
Methyl chloroform	-> see: Trichloroethane-1,1,1																													
Methyl cyanide	-> see: Acetonitrile																													
Methylcyclohexane	C_7H_{14}	000108-87-2		F, Xn	X	3/0	3/0	(2)	(2)	1/0	(4)	(2)	3/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	(1)	4/4	(1)	4/4	0/0	1/1	1/1	1/1	0/0	
Methylcyclopentane	C_6H_{12}	000096-37-7		F	X	0/0	0/0	(2)	(2)	1/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Methyl dichloroacetate	$C_3H_4Cl_2O_2$	000116-54-1		(Xn)		1/1	0/0	(3)	(4)		(4)	(3)	1/1	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	3/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Methylene(di)chloride	-> see: Dichloromethane																													
Methylene chlorobromide	-> see: Bromochloromethane																													
Methyl ether	-> see: Dimethyl ether																													
Methyl ethyl ketone (MEK)	C_4H_8O	000078-93-3		F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/2	1/3	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	3/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl formate	$C_2H_4O_2$	000107-31-3		F+	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl glycol	$C_3H_8O_2$	000109-86-4	100 %	T	X	1/0	1/1	1/0	3/4	0/0	1/1	1/0	1/1	4/4	3/3	3/4	4/4	0/0	1/1	1/1	1/1	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl glycol acetate	$C_5H_{10}O_3$	000110-49-6		T		0/0	0/0	1/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl isobutenyl ketone	-> see: Mesityl oxide																													
Methyl isobutyl ketone(MIBK)	-> see: Isobutyl methyl ketone																													
Methyl isopropyl ketone	-> see: Isopropyl methyl ketone																													
Methyl methacrylate	$C_5H_8O_2$	000080-62-6	100 %	F, Xi	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Methyl methanoate	-> see: Methyl formate																													
Methyl oleate	$C_{19}H_{36}O_2$	000112-62-9		—		0/0	0/0	(2)	(3)	(2)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	4/4	0/0	(1)	(1)	(1)		
Methyl oxirane	-> see: Propylene oxide																													
Methylpent-4-en-2-one, 5-	-> see: Mesityl oxide																													
Methylpentan-2-one, 4-	-> see: Isobutyl methyl ketone																													
Methylphenol	-> see: Cresol (-mixtures)																													
Methylphenyl ether	-> see: Anisole																													
Methylphenyl ketone	-> see: Acetophenone																													
Methylpropanol-1, 2-	-> see: Isobutanol																													
Methylpropanol-2, 2-	-> see: Butyl alcohol, tertiary																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Methyl propenoate	-> see: Methyl acrylate																													
Methylpropenoic acid, 2-	-> see: Methacrylic acid																													
Methyl propyl ketone	$C_5H_{10}O$	000107-87-9		(F)	X	1/2	2/3	(2)	4/4	(4)	3/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	(1)	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl salicylate	$C_8H_8O_3$	000119-36-8		Xn, Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/0	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	2/0	(3)	4/4	0/0	(2)	(1)	(1)	0/0	Synthetic Wintergreen Oil/Gaultheria Oil
Methyl sulphuric acid	CH_4SO_4	000077-78-1	50 %	(C)		0/0	1/1	4/4	(4)	(4)	0/0	4/4	2/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4	
Methyl sulphuric acid	CH_4SO_4	000077-78-1	aqueous	(C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4	
Milk	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Lactic acid	$C_3H_6O_3$	000050-21-5	3 %	?		1/1	1/2	(3)	1/2	1/0	1/2	2/4	1/2	2/2	1/1	2/3	0/0	1/1	1/1	1/1	1/1	1/1	3/4	1/1	(2)	0/0	(1)	1/1	1/1	1/1	Lactol
Lactic acid	$C_3H_6O_3$	000050-21-5	80 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/1	1/1	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1	Lactol
Lactic acid	$C_3H_6O_3$	000050-21-5	85 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/2	2/2	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1	Lactol
Lactic acid ethyl ester	-> see: Ethyl lactate																													
Milk sugar	-> see: Lactose																													
Mineral oil	—	008012-95-1		(Xn)		1/1	2/4	(1)	1/2	1/1	1/2	1/1	1/3	1/1	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	2/2	0/0	1/1	1/1	1/1	0/0	
Mineral water	—	—		—		1/1	1/1	(1)	1/0	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	(1)	(1)	1/1	
Mohr's salt	-> see: Ammonium iron (II) sulphate																													
Whey	—	—		—		1/1	0/0	(2)	(1)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(2)	1/1	1/1		
Monobromobenzene	-> see: Bromobenzene																													
Monochlorobenzene	-> see: Chlorobenzene																													
Monochloroacetic acid	-> see: Chloroacetic acid																													
Monochloroacetic acid ethyl ester	-> see: Ethyl chloroacetate																													
Monochloroacetic acid methyl ester	-> see: Methyl chloroacetate																													
Monoethanolamine	-> see: Ethanolamine																													
Monofluorodichloromethane	-> see: Dichlorofluoromethane																													
Monopotassium tartrate	-> see: Potassium hydrogentartate																													
Monopentyl phthalate	-> see: Phthalic acid monoamyl ester																													
Morpholine	C_4H_9NO	000110-91-8	tech. pure	C, Xn	X	1/1	1/1	(3)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	3/0	2/3	4/4	0/0	1/0	(1)	(1)	0/0	
Engine oil	—	—		?		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Mowilith D	—	—		?		1/0	0/0	(2)	0/0	(2)	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(2)	(2)	(2)	0/0	(2)	(1)	(1)	0/0	Polyvinylacetatdispersion; Clariant
Nutmeg	—	—	grinded	?		0/0	0/0	(2)	4/4	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Nutmeg oil	—	008008-45-5		(Xn)		0/0	0/0	(2)	4/4	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/4	0/0	(1)	(1)	(2)	(4)	(3)	(3)	0/0	(1)	(1)	(1)		
Nail varnish remover	—	—		?	(X)	0/0	0/0	(2)	4/4	0/0	(4)	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Naphtha	—	008032-32-4		(Xn)		1/3	3/4	1/0	(2)	(1)	1/0	1/0	1/3	3/0	1/0	1/0	4/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	Petroleum gasoline
Naphthalene	$C_{10}H_8$	000091-20-3	100 %	F, Xn	X	0/0	1/3	1/0	(3)	0/0	0/0	1/2	1/3	3/4	1/0	4/4	4/4	1/4	0/0	(1)	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	
Naphthalene (in alcohol)	—	—		F, Xn	X	1/4	1/4	(2)	(3)	0/0	0/0	1/2	1/3	3/4	0/0	0/0	0/0	3/4	0/0	(1)	1/1	(2)	4/4	(3)	(3)	0/0	(1)	(1)	(1)	0/0	
Naphthene	-> see: Cyclohexane																													
Sodium acetate	$C_2H_3NaO_2$	000127-09-3	any	—		1/1	1/1	1/0	1/2	(1)	1/1	1/1	1/1	2/2	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	1/1	1/1	1/1	
Sodium aluminium sulphate	$NaAl(SO_4)_2$	010102-71-3		?		1/1	1/1	(3)	(2)	(1)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)		
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1	36 %	Xn		1/1	1/1	1/0	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	1/1	0/0	(1)	(1)	(1)	1/1	
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1	aqueous	Xn		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1	
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1		Xn		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1	
Sodium bicarbonate	$NaHCO_3$	000144-55-8	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium bichromate	-> see: Sodium dichromate																													
Sodium bisulphate	$NaHSO_4$	007681-38-1	10 %	(C)		1/1	1/1	4/4	1/0	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	1/2	1/1	1/1	
Sodium bisulphate	$NaHSO_4$	007681-38-1	any	(C)		1/1	1/1	1/0	1/0	0/0	0/0	(3)	1/1	1/3	0/0	1/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	(2)	1/1	1/1	
Sodium bisulphite	$NaHSO_3$	007631-90-5	aqueous	Xn		1/1	1/1	1/0	(2)	1/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1	1/1	
Sodium borate	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	saturated	Xi		1/1	1/1	1/0	1/0	(2)	1/0	1/1	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/3	1/1	1/1	1/1	
Sodium borate	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/3	1/1	1/1	1/1	
Sodium bromate	$NaBrO_3$	007789-38-0	any	O, T		1/0	1/3	(3)	(2)	0/0	0/0	1/1	1/1	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	(2)	(1)	1/3	0/0	1/1	1/1L	1/1L	0/0	
Sodium bromide	NaBr	007647-15-6	any	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/3	0/0	4/4	0/0	0/0	0/0	
Sodium carbonate	Na_2CO_3	000497-19-8	saturated	Xi		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium carbonate	Na_2CO_3	000497-19-8	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium carbonate	Na_2CO_3	000497-19-8		Xi		1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	2/0	0/0	1/1	0/0	1/2	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium chlorate	$NaClO_3$	007775-09-9	any	O, Xn		1/1	1/0	1/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1L	1/1L	1/1	
Sodium chlorate	$NaClO_3$	007775-09-9	aqueous	O, Xn		0/0	0/0	3/0	1/0	1/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/0	1/1L	1/1L	1/1	
Sodium chloride	NaCl	007647-14-5	any	—		1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/2	1/2	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sodium chloride	NaCl	007647-14-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/4	1/2	1/2	1/1	
Sodium chlorite	$NaClO_2$	007758-19-2	diluted	(O, Xn)		1/0	1/3	1/4	(2)	0/0	0/0	(2)	1/3	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	3/4	3/4	3/3	0/0	
Sodium chromate	$NaCrO_4$	007775-11-3	diluted	T		1/0	1/0	1/1	(2)	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	1/1	1/1	1/1	0/0	
Sodium cyanide	CNNa	000143-33-9	saturated	T		1/1	1/1	1/0	(3)	0/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	4/4	(2)	(2)	0/0	
Sodium cyanide	CNNa	000143-33-9	aqueous	T		1/1	1/1	1/0	(3)	1/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	(2)	(2)	0/0	
Sodium dichromate	$Na_2Cr_2O_7$	010588-01-9		T		0/0	1/1	1/0	1/0	3/0	1/1	(3)	1/1	1/1	0/0	1/0	0/0	0/0	1/1	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Sodium disulphite	$Na_2S_2O_5$	007681-57-4	any	Xn		1/1	1/1	1/0	(2)	(2)	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1		
Sodium dithionite	$Na_2S_2O_4$	007775-14-6	10 %	Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		
Sodium dithionite	$Na_2S_2O_4$	007775-14-6		Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		
Sodium dodecylbenzene sulphonate	$C_{18}H_{29}NaSO_3$	025155-30-0		Xn		1/1	1/1	(2)	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(1)	(2)	0/0	(2)	(1)	(1)		
Sodium iron cyanide	-> see: Sodium hexacyanoferrate(II)																													
Sodium ferrocyanide	-> see: Sodium hexacyanoferrate(II)																													
Sodium fluoride	NaF	007681-49-4	saturated	T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/0	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	1/1	
Sodium hexacyanoferrate-(II)	$C_6FeNa_4N_6$	013601-19-9		Xn		1/1	1/1	(1)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(1)	(1)	(1)		
Sodium hexametaphosphate	$(NaPO_3)_6$	068915-31-1	saturated	—		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Sodium hydrogen carbonate	-> see: Sodium bicarbonate																													
Sodium hydrogen sulphate	-> see: Sodium bisulphate																													
Sodium hydrogen sulphite	-> see: Sodium bisulphite																													
Sodium hydrosulphite	-> see: Sodium dithionite																													
Sodium hydroxide	NaOH	001310-73-2	concentrated	C		1/1	1/1	1/3	4/4	4/4	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/4	0/0	4/4	(2)	(2)	?	
Sodium hydroxide	NaOH	001310-73-2	30 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/0	1/0	1/3	1/3	0/0	0/0	1/1	1/1	(2)	1/0	(3)	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	45 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/1	1/0	1/3	1/3	1/1	0/0	0/0	1/1	(2)	1/0	2/4	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	50 %	C+		1/1	1/1	1/0	4/4	4/4	1/1	1/3	1/1	2/2	1/1	1/2	0/0	0/3	1/1	1/1	1/1	3/3	1/0	3/4	3/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	60 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	(3)	1/1	1/0	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	3/4	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	1 %	Xi		1/1	1/1	1/0	3/4	(3)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	(4)	1/1	1/1	1/1	
Sodium hypochlorite	NaClO	007681-52-9	diluted	(O, C)		2/3	2/3	4/4	(3)	3/0	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	15 %	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/1	0/0	1/1	1/1	1/1	1/1	3/4	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	saturated	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	0/0	1/1	0/0	(1)	1/1	(3)	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	12,5 % Cl	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypodisulphite	-> see: Sodium dithionite																													
Sodium iodide	NaJ	007681-82-5	any	Xi		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/0	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	(1)	1/1	0/0	1/1	3/4	3/4	0/0	
Sodium metaborate peroxide	-> see: Sodium perborate																													
Sodium nitrate	$NaNO_3$	007631-99-4	saturated	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	
Sodium nitrate	$NaNO_3$	007631-99-4	aqueous	O, Xn		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Sodium nitrite	$NaNO_2$	007632-00-0	saturated	O, T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1	1/1	1/1	
Sodium nitrite	$NaNO_2$	007632-00-0	aqueous	O, T		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	1/0	1/1	1/1	1/1	
Sodium oxalate	$C_2Na_2O_4$	000062-76-0	saturated	Xn		1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	1/0	1/0	0/0	1/1	(2)	(2)		
Sodium perborate	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	saturated	(O, Xn)		1/1	1/1	4/4	(2)	0/0	0/0	2/0	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Sodium perborate	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	aqueous	(O, Xn)		1/1	1/1	4/4	(2)	3/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Sodium perchlorate	$NaClO_4$	007601-89-0	saturated	O, Xn		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	1/1	1/1	
Sodium peroxide	Na_2O_2	001313-60-6	10 %	O, C+		0/0	1/3	4/4	(3)	(4)	0/0	4/4	272	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	3/0	0/0	4/4	1/1	1/1	0/0	
Sodium peroxide	Na_2O_2	001313-60-6	saturated	O, C+		0/0	3/3	4/4	(3)	(4)	0/0	4/4	2/2	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	(4)	0/0	4/4	(2)	(2)	0/0	
Sodium peroxodisulphate	-> see: Sodium persulphate																													
Sodium persulphate	$Na_2S_2O_8$	007775-27-1	saturated	O, Xi		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(3)	0/0	4/4	0/0	1/0	0/0	
Sodium phosphate	$Na_3PO_4 \times 12H_2O$	010101-89-0	saturated	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium phosphate	$Na_3PO_4 \times 12H_2O$	010101-89-0	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium phosphate, secondary	-> see: Disodium phosphate																													
Sodium phosphate, tertiary	-> see: Trisodium phosphate																													
Sodium phosphate dodecahydrate	-> see: Sodium phosphate																													
Sodium pyrosulphite	-> see: Sodium disulphite																													
Sodium silicate	$Na_2Si_2O_7$	001344-09-8	any	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium stearate	$C_{18}H_{35}NaO_2$	000822-16-2	aqueous	(Xi)		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(1)	1/0	0/0	(1)	1/1	1/1		
Sodium sulphate	Na_2SO_4	007757-82-6	saturated	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/3	0/0	1/1	1/1	1/1	1/1	
Sodium sulphate	Na_2SO_4	007757-82-6	aqueous	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	0/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium sulphate	Na_2SO_4	007757-82-6		—		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	1/1	1/1	1/1	1/1	
Sodium sulphide	Na_2S	001313-82-2	saturated	C		1/1	1/1	1/0	3/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	0/0	1/1	1/1	3/3	1/0	1/1	2/3	0/0	3/4	(1)	(1)	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics					Elastomers		Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sodium sulphide	Na_2S	001313-82-2	aqueous	C		1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/2	1/2	1/1	
Sodium sulphite	Na_2SO_3	007757-83-7	saturated	Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/3	1/1	1/1	1/1	
Sodium tetraborate	-> see: Sodium borate																														
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	any	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	saturated	Xi		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	aqueous	Xi		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate-5-hydrate	-> see: Sodium thiosulphate																														
Sodium hypochlorite	-> see: Sodium hypochlorite																														
Caustic soda	-> see: Sodium hydroxide																														
Sodium nitrate	-> see: Sodium nitrate																														
Sodium liquid glass	-> see: Sodium silicate																														
Cloves	—	—	grinded	?		0/0	0/0	(2)	4/4	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	0/0	
Neon	Ne	007440-01-9		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(1)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1		
Wetting agent	—	—	5 %	?		1/0	0/0	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(2)	0/0	0/0	K	K		Surfactants
Niacin	-> see: Nicotinic acid																														
Nickel (II) chloride	$NiCl_2$	007718-54-9	saturated	T		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1	
Nickel (II) chloride	$NiCl_2$	007718-54-9	aqueous	T		1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1	
Nickel acetate	$C_4H_6NiO_4$	000373-02-4	aqueous	(T, N)		1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/0	0/0	4/4	0/0	0/0		
Nickel nitrate	$Ni(NO_3)_2$	013138-45-9	saturated	(O, Xn)		1/1	1/1	(3)	(2)	(1)	1/0	(2)	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Nickel sulphate	$NiSO_4$	007786-81-4	saturated	Xn		1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nickel sulphate	$NiSO_4$	007786-81-4	aqueous	Xn		1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nicotine	$C_{10}H_{14}N_2$	000054-11-5		T+		1/0	1/0	(3)	(3)	0/0	0/0	(2)	1/0	1/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/1	0/0	(1)	(1)	(1)	0/0	
Nicotinic acid	$C_6H_5NO_2$	000059-67-6	diluted	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/0	0/0	0/0	1/1	0/0	0/0	0/0	1/1	(1)	(2)	(2)	(3)	(2)	0/0	(3)	0/0	0/0	0/0	
Nitrobenzoic acid	$C_7H_5NO_4$	—		(Xn)		1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	(3)	(2)	0/0	(3)	0/0	0/0		Isomer not specified in the source
Nitrobenzene	$C_6H_5NO_2$	000098-95-3		T		3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitroethane	$C_2H_5NO_2$	000079-24-3		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Nitroglycerin	$C_3H_5(NO_3)_3$	000055-63-0	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(3)	1/0	1/0	4/4	0/0	0/0	0/0	0/0	0/0	
Nitro glycol	$C_2H_4(NO_3)_2$	000628-96-6	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(3)	1/0	1/0	4/4	0/0	0/0	(1)	(1)	0/0	
Nitropropane	$C_3H_7NO_2$	—		(T)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Nitrous gases	—	—	diluted	T		1/1	0/0	3/0	4/4	0/0	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	3/0	4/4	0/0	(2)	(1)	(1)	0/0	Nitrogen monoxide + nitrogen dioxide
Nitrotoluene	$C_7H_7NO_2$	001321-12-6	tech. pure	T		1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitro thinner	—	—		?	X	0/0	0/0	3/0	(4)	0/0	(4)	(3)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		Solvent mixture
Nonanol	$C_9H_{20}O$	000143-08-8	100 %	Xn, Xi		0/0	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Nonyl alcohol	-> see: Nonanol																														
Fruit pulp	—	—		—		1/1	1/1	(2)	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	
Fruit wine	—	—		—		1/1	1/1	(2)	(1)	1/1	0/0	1/1	1/0	0/0	0/0	1/0	0/0	0/0	1/1	1/1	(1)	1/1	1/0	(1)	1/0	0/0	(2)	1/1	1/1	0/0	
Octadec-9-enoic acid, cis-	-> see: Oleic acid																														
Octadecanoic acid	-> see: Stearic acid																														
Octafluorocyclobutane	C_4F_8	000115-25-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Octal	-> see: Diisooctyl phthalate																														
Octane, n-	C_8H_{18}	000111-65-9		F, Xn	X	1/1	1/1	1/0	2/3	(1)	1/1	1/0	1/1	4/4	2/3	3/4	3/3	1/1	1/1	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	0/0	
Octanol, 1-	-> see: Octyl alcohol, -n																														
Octyl alcohol, -n	$C_8H_{18}O$	000111-87-5		Xi		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Octylcresol	$C_{15}H_{24}O$	—	100 %	?		3/0	3/0	(3)	(4)	0/0	0/0	(3)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Oils and fats, vegetable	—	—		—		1/3	1/3	(2)	(2)	1/0	0/0	(2)	1/3	3/0	0/0	1/1	3/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	(2)	0/0	(1)	1/1	1/1	0/0	
Öle, Oils, ethereal	—	—		?		4/4	3/4	(2)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	(1-3)	(3)	0/0	1/1	(1)	(1)	0/0	
Olein	-> see: Oleic acid																														
Oleum	$H_2SO_4 \times SO_3$	008014-95-7	10 % SO_3	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/0	4/4	4/4	1/0	4/4	0/0	1/3	1/2	1/1	0/0	Fuming sulphuric acid
Oleum vapours	—	—	low	?		4/4	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	1/0	(3)	1/0	(3)	0/0	(3)	(1)	(1)	0/0	Sulphur trioxide
Olive oil	—	008001-25-0		—		1/3	0/0	(2)	(2)	1/0	0/0	1/1	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Oleic acid	$C_{18}H_{34}O_2$	000112-80-1	tech. pure	Xi		1/3	1/3	1/0	1/0	1/0	0/0	2/0	1/3	1/3	0/0	1/1	0/0	1/3	0/0	(1)	1/1	1/1	4/4	2/2	3/0	0/0	1/1	1/1	1/1	0/0	
Oleic acid methoxyethyl ester	-> see: Methoxyethyl oleate																														
Oleic acid methyl ester	-> see: Methyl oleate																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sweet orange juice	-> see: Orange juice																													
Sweet orange peel oil	-> see: Orange peel oil																													
Ortho-silicic acid tetraethyl ester	-> see: Tetraethylorthosilicate																													
Orthophosphoric acid	-> see: Phosphoric acid																													
Oxabutyl acetate	-> see: Methyl glycol acetate																													
Oxalic acid	$C_2H_2O_4 \times 2H_2O$	000144-62-7	aqueous	Xn		1/1	1/1	4/4	(2)	(2)	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/2	
Oxalic acid	$C_2H_2O_4 \times 2H_2O$	000144-62-7		Xn		1/1	1/1	3/4	1/0	0/0	1/1	4/4	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/3	
Oxalic acid sodium salt	-> see: Sodium oxalate																													
Oxalic acid ammonium salt	-> see: Ammonium oxalate																													
Oxirane	-> see: Ethylene oxide																													
Oxolane	-> see: Tetrahydrofuran																													
Oxydiacetic acid	-> see: Diglycolic acid																													
Oxymethylfurfurol, 5-	$C_6H_6O_3$	000067-47-0		Xi		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ozone	O_3	010028-15-6		(O, T)		3/4	3/4	4/4	1/2	0/0	1/1	4/4	3/4	2/2	1/1	1/2	0/0	1/1	1/1	1/1	(1)	1/3	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Ozone-air mixture-Luft-Gemisch	—	—		(O, T)		0/0	0/0	4/4	(2)	0/0	0/0	4/4	3/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Palmitic acid	$C_{16}H_{32}O_2$	000057-10-3	tech. pure	Xi		3/3	2/2	1/1	(2)	1/0	0/0	1/0	3/4	1/1	0/0	1/1	3/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
Palmityl alcohol	-> see: Cetyl alcohol																													
Palm seed oil	—	008023-79-8		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/3	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Palm oil	—	008002-75-3		—		1/3	0/0	1/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1		
Paraffins	C_nH_{2n+2}	—	100 %	?		1/0	1/1	1/0	1/0	1/0	1/1	1/1	1/0	1/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	
Paraffin emulsion	—	—		?		1/3	0/0	1/0	(2)	(2)	0/0	(2)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/0	1/1	0/0	(2)	(1)	(1)	0/0	
Paraffin wax	—	008002-74-2	melted	(—)		0	0	0	(2)	0	0	(2)	(2)	0	0	0	0	0	0	(1)	1	0	4	(2)	1	0	1	1	1		
Paraform	-> see: Paraformaldehyde																													
Paraformaldehyde	$(CH_2O)_nH_2O$	030525-89-4		F, T	X	0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	1/0	3/3	0/0	(1)	(1)	(1)		
Perfumes	—	—		?		3/0	3/0	1/0	(3)	1/0	0/0	(2)	1/0	4/4	0/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Pectin	—	009000-69-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Pectin
Pectin	—	009000-69-5		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Pectin
Penicillin	—	—		Xn		(1)	(1)	(2)	(1)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		Antibiotic
Pentaclorodiphenyl	$C_{12}H_5Cl_5$	—		Xn		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0		a PCB
Pentamethyleneimine	-> see: Piperidine																													
Pentane	C_5H_{12}	000109-66-0		F	X	1/3	1/3	1/0	1/0	1/1	(3)	1/0	(3)	3/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(1)	4/4	1/0	1/2	0/0	1/1	1/1	1/1		
Pentanone, 2-	-> see: Methyl propyl ketone																													
Pentanone, 3-	-> see: Diethyl ketone																													
Pentanethiol, 1-	$C_5H_{12}S$	000110-66-7		Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(2)	(1)	(1)		
Pentylacetate, n-	-> see: Amylacetate, n-																													
Pentyl alcohol	-> see: Amyl alcohol, n-																													
Pentyl chloride	-> see: Amyl chloride																													
Pentylcinnamaldehyde, a-	-> see: α-pentylcinnamaldehyde																													
Perchlorobutadiene	-> see: Hexachlorobutadiene																													
Perchlorethene	-> see: Perchloroethylene																													
Perchloroethylene (PER)	C_2Cl_4	000127-18-4		Xn		4/4	4/4	4/4	4/4	3/4	4/4	1/3	4/4	4/4	4/4	4/4	4/4	3/3	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	(3)	0/0	0/0	0/0	
Perchloric acid	$HClO_4$	007601-90-3	70 %	E, O, C+		2/4	3/4	4/4	4/4	(4)	2/4	4/4	4/4	2/3	4/4	3/4	4/4	0/0	1/2	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	0/0	0/0	?	
Perchloric acid	$HClO_4$	007601-90-3	20 %	Xi		0/0	1/3	4/4	3/0	0/0	0/0	4/4	1/3	0/0	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	2/0	1/1	4/4	0/0	4/4	0/0	0/0	1/1	
Perfluoropropane	C_3F_8	000076-19-7		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Perhydroxic acid	-> see: Hydrogen peroxide 30 %																													
Petrolatum, petroleum jelly	-> see: Vaseline																													
Petroleum ether	—	008032-32-4	tech. pure	(F, Xn)	X	1/3	1/3	1/0	3/0	1/0	1/0	1/1	1/3	4/4	1/0	1/1	3/3	3/3	0/0	(1)	1/1	1/1	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	
Petroleum	—	—	tech. pure	Xn, N	X	1/3	3/4	1/0	3/0	(1)	0/0	1/1	1/3	4/4	1/0	1/0	3/0	3/4	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Pepper	—	—	grinded	?		0/0	0/0	(2)	1/0	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Vegetable oils	—	—		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Phenacetin	$C_{10}H_{13}NO_2$	000062-44-2		Xn		0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)		
Phenetole	-> see: Phenylethylether																													
Phenol	C_6H_6O	000108-95-2	10 %	T		1/1	1/1	4/4	4/4	4/4	1/0	4/4	1/1	4/4	4/4	1/3	3/3	3/3	0/0	1/0	1/1	1/1	4/4	2/3	4/4	0/0	1/1	1/2	1/1	0/0	
Phenol	C_6H_6O	000108-95-2	100 %	T, C		2/3	3/3	4/4	4/4	4/4	1/1	4/4	1/2	4/4	3/3	4/4	3/0	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	0/0	
Phenolic resin moulding compound	—	—		?		1/1	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(4)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Phenyethylene	-> see: Styrene																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Phenyl-2-propenal, trans-3-	-> see: Cinnamaldehyde																													
Phenylamine	-> see: Aniline																													
Phenylaniline, N-	-> see: Diphenylamine																													
Phenyl bromide	-> see: Bromobenzene																													
Phenylcarbinol	-> see: Benzyl alcohol																													
Phenyl chloride	-> see: Chlorobenzene																													
Phenylethanol	$C_8H_{10}O$	000060-12-8		Xn		0/0	0/0	3/0	4/4	0/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(1)	(1)	(1)		
Phenyl ether	-> see: Diphenyl ether																													
Phenylethyl alcohol	-> see: Phenylethanol																													
Phenyl ethyl ether	$C_8H_{10}O$	000103-73-1		?		0/0	0/0	(2)	(4)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Phenylhydrazine	$C_6H_8N_2$	000100-63-0	tech. pure	T		3/0	0/0	(3)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/3	4/4	0/0	(2)	0/0	0/0	0/0	
Phenylhydrazine chlorohydrate	-> see: Phenylhydrazine-HCl																													
Phenylhydrazine-HCl	$C_6H_8N_2$-HCl	000059-88-1		T		0/0	0/0	(3)	(2)	0/0	0/0	(3)	1/3	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/3	1/3	0/0	(4)	(4L)	(4L)		
Phenylpropane	-> see: Cumene																													
Phenyl sulphonate	—	70528-83-5		?		0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Phenylsulfonic acid	-> see: Benzenesulfonic acid																													
Phosgene	$COCl_2$	000075-44-5	liquid	T+, C		0/0	0/0	1/0	(3)	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	1/0	3/0	0/0	(3)	3/4	3/4	0/0	
Phosgene	$COCl_2$	000075-44-5	gaseous	T+, C		0/0	3/0	1/0	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	3/0	0/0	(3)	3/4	3/4	0/0	
Phosphates	—	—	aqueous	?		1/1	1/1	0/0	0/0	(1)	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	0/0	(1)	(1)		Salts of phosphoric acid
Phosphine	PH_3	007803-51-2	concentrated	F+, T+	X	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Phosphorus (III) chloride	-> see: Phosphorus trichloride																													
Phosphorus oxychloride	PCl_3O	010025-87-3	100 %	T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	
Phosphorus oxychloride	PCl_3O	010025-87-3		T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	
Phosphorus pentachloride	PCl_5	010026-13-8		T+, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	1/1	(3)	(3)	4/4	0/0	1/1	1/3L	1/3L		
Phosphorus pentoxide	P_4O_{10}	001314-56-3	tech. rein	C		1/0	0/0	(4)	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	(3)	(2)	3/4	0/0	1/1	1/0	1/0	0/0	
Phosphorus perchloride	-> see: Phosphorus pentachloride																													
Phosphoric acid	H_3PO_4	007664-38-2	30 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	85 %	C		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	1/1	1/2	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	2/4	1/3	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	1-5 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	3/4	1/1	2/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	(4)	1/1	1/1	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	20%	Xi		1/1	1/1	4/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphoric anhydride	-> see: Phosphorus pentoxide																													
Phosphoric acid chloride	-> see: Phosphorus pentachloride																													
Phosphoric acid tritolyester	-> see: Tricresyl phosphate																													
Phosphorus trichloride	PCl_3	007719-12-2		T, C		3/3	3/3	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/1	1/0	3/4	4/4	0/0	1/1	0/0	0/0	1/1	
Hydrogen phosphide	-> see: Phosphine																													
Phosphoryl chloride	-> see: Phosphorus oxychloride																													
Phthalic acid	$C_8H_6O_4$	000088-99-3	saturated	Xi		1/1	1/1	3/3	(3)	1/0	0/0	1/0	1/1	1/0	0/0	1/4	0/0	1/1	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	
Phthalic acid amyl ester	$C_{18}H_{26}O_4$	000131-18-0	100 %	(T)		0/0	1/3	(1)	(4)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Phthalic acid dibutyl ester	-> see: Dibutyl phthalate																													
Phthalic acid dicyclohexyl ester	-> see: Dicyclohexyl phthalate																													
Phthalic acid dimethyl ester	-> see: Dimethyl phthalate																													
Phthalic acid dinonyl ester	-> see: Dinonyl phthalate																													
Phthalic acid monoamyl ester	$C_{13}H_{16}O_4$	??		(Xn)		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	(1)	(1)		
Picric acid	$C_6H_3N_3O_7$	000088-89-1	1 % aqueous	T		1/0	1/0	3/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	4/4	0/0	0/0	1/0	1/0	1/1	3/0	1/0	3/4	0/0	1/0	1/0	1/0	1/0	
Pimenta, allspice	—	—	grinded	?		0/0	0/0	(2)	4/4		0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Piperidine	$C_5H_{11}N$	000110-89-4		F, T, C		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Polyester resins	—	—		(Xn)	(X)	3/4	3/4	1/0	4/4	1/0	0/0	(2)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Polyethylene glycol	HO-$(C_2H_4O)_n$-H	025322-68-3	100 %	(—)		1/1	1/1	(3)	0/0	0/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2-3)	(2)	(3)	0/0	(1)	(1)	(1)	0/0	
Polyglycol	-> see: Polyethylene glycol																													
Polyoxyethylene	-> see: Polyethylene glycol																													
Polyoxymethylene	-> see: Paraformaldehyde																													
Polyran M25 N	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	3	0	0	(1)	(1)		Lubricating oil
Polyran M400	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	(3)	0	0	(1)	(1)		Lubricating oil
Polysiloxane	-> see: Silicone oil																													
Polysolvan O	$C_6H_{12}O_3$	007397-62-8	100 %	Xi		0/0	1/1	(2)	(3)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	(3)	0/0	(1)	(1)	(1)		Solvent, glycolic acid butyl ester; Celanese AG

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							---------- Thermoplastics ----------		---- Fluoroplastics ----		--- Elastomers ---		-------- Metals ---------			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Bitter orange oil	—	068916-04-1		?		2/3	3/4	(2)	3/3	1/0	3/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	4/4	(2)	(4)	0/0	(1)	(1)	(1)		
Potash	-> see: Potassium carbonate																													
Compressed air	—	—	oily	—		1/0	0/0	(2)	(2)	(1)	0/0	(1)	3/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	1/1	1/1	1/1		
Prontosil	—	—		(Xn)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	0/0	0/0		Chemotherapeutic agent; Bayer - no longer on the market
Prop-2-enyl acetate	-> see: Allyl acetate																													
Propane	C_3H_8	000074-98-6	liquid	F+	X	1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/0	0/0	1/0	1/0	3/0	1/0	0/0	(1)	1/1	1/1	4/4	1/0	(2)	0/0	1/1	1/1	1/1	0/0	
Propane	C_3H_8	000074-98-6	gaseous	F+	X	3/4	4/4	1/0	3/4	1/0	4/4	1/1	2/4	4/4	3/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Propandiol, 1,2-	-> see: Propylene glycol																													
Propanol	C_3H_8O	000071-23-8		F	X	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	3/0	0/0	2/2	3/3	1/4	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/1	(1)	(1)	0/0	
Propanol, 2-	-> see: Isopropyl																													
Propanone, 2-	-> see: Acetone																													
Propanoic acid	-> see: Propionic acid																													
Propanetriol	-> see: Glycerine																													
Propargyl alcohol	C_3H_4O	000107-19-7	7 %	Xn		1/1	1/1	(3)	1/0	0/0	0/0	(2)	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/3	1/0	1/1	1/1	0/0	1/0	(1)	(1)	0/0	
Propene	C_3H_6	000115-07-1		F+	X	1/1	1/1	1/0	(3)	1/0	0/0	1/0	1/1	4/4	0/0	3/4	4/4	0/0	0/0	(1)	1/1	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Propene-1-ol, 2-	-> see: Allyl alcohol																													
Propene acid ethyl ester	-> see: Ethyl acrylate																													
Propyn-1-ol, 2-	-> see: Propargyl alcohol																													
Propionic acid	$C_3H_6O_2$	000079-09-4	50 %	C, F	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/1	4/4	4/4	1/3	3/3	0/0	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	1/1	(1)	(1)	1/1	
Propionic acid	$C_3H_6O_2$	000079-09-4		C, F+	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	1/1	
Propyl acetate	$C_5H_{10}O_2$	000109-60-4		F	X	0/0	0/0	(1)	4/4	0/0	(4)	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Propyl alcohol	-> see: Propanol																													
Propylamine, n-	C_3H_9N	000107-10-8		F, C, Xn	X	0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Propylene	-> see: Propene																													
Propylene(di)chloride	-> see: Dichloropropane																													
Propylene glycol	$C_3H_8O_2$	000057-55-6		—		1/1	1/1	4/4	2/3	(2)	1/1	1/0	1/1	1/1	2/2	3/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	(1)	(1)	1/1	
Propylene glycol methyl ether	$C_4H_{10}O_2$	—		—	X	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Propylene oxide	C_3H_6O	000075-56-9		F+, T	X	1/1	1/2	(3)	2/3	0/0	1/2	(2)	1/2	4/4	2/2	3/4	0/0	4/4	3/4	1/1	1/0	1/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Propylidintris(methanol)	-> see: Trimethylol propane																													
Propyl nitrate	$C_3H_7NO_3$	000627-13-4		(E, Xn)	(X)	0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(2)	(1)	(1)		
Pseudocumene	C_9H_{12}	000095-63-6		Xn	X	0/0	0/0	(1)	(4)	0/0	0/0	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(2)	4/4	0/0	1/1	1/1	1/1		
Pydraul C (312, 540)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	1/0	4/4	0/0	0/0	(1)	(1)		Base phosphoric acid ester; Monsanto
Pydraul E (29, 30, 50, 65, 90, 11)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	4/4	0/0	0/0	(1)	(1)		Base phosphoric acid ester; Monsanto
Pyridine	C_5H_5N	000110-86-1		F, Xn	X	1/3	0/2	1/0	4/4	0/0	0/2	1/1	3/3	4/4	4/4	4/4	4/4	4/4	1/1	(2)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Pyridine-3-carboxylic acid	-> see: Nicotinic acid																													
Pyrogallol	$C_6H_6O_3$	000087-66-1		Xn		0/0	0/0	1/0	(3)	0/0	0/0	3/4	1/0	3/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	1/1	(3)	(3)	(3)	0/0	1/1	1/1	1/1	1/1	
Pyrosulphite	-> see: Sodium disulphite																													
Pyrrole	C_4H_5N	000109-97-7		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Mercury	Hg	007439-97-6	pure	T		1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(3)	1/1	1/1		
Mercury (II) chloride	$HgCl_2$	007487-94-7	aqueous	T+, C		1/1	1/1	4/4	1/0	(2)	1/1	3/0	1/1	1/3	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	(4)	(4)	1/1	Sublimate
Mercury (II) cyanide	C_2HgN_2	000592-04-1	saturated	T+		1/1	1/1	(3)	(2)	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	1/1	(1)	1/1	(2)	0/0	4/4	1/0	1/0	1/1	
Mercury (II) nitrate	-> see: Mercury nitrate																													
Mercury nitrate	$Hg(NO_3)_2$	010045-94-0	saturated	(T+)		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	1/0	0/0	1/3	1/0	0/0	(1)	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	1/1	1/1	1/1	
Mercuric nitrate	-> see: Mercury nitrate																													
Ramasit	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	Hydrophobing agent for textiles; BASF
Resorcinol	$C_6H_6O_2$	000108-46-3	5 %	—		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	2/4	0/0	3/3	1/3	1/1	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Resorcinol	$C_6H_6O_2$	000108-46-3	saturated	Xn		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	3/4	0/0	0/0	1/1	(1)	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Beef tallow	—	061789-97-7		—		0/0	0/0	1/0	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Beef tallow emulsion	—	—	sulphurised	(—)		1/0	0/0	(2)	(2)	0/0	0/0	0/0	1/0	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(2)	(2)	0/0	(2)	(1)	(1)	0/0	
Castor oil	—	008001-79-4	100 %	Xi		1/1	1/1	1/0	1/0	(1)	1/0	(2)	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Crude oil	—	—	100 %	(N)		0/0	1/3	1/0	(3)	1/0	0/0	1/0	1/3	3/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/3	0/0	(2)	(1)	(1)		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Rose oil	—	008007-01-0		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Roasting gases	—	—	any	(T)		0/0	0/0	(2)	0/0	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(4)	(2)	(2)	0/0	
Colza oil	—	008002-13-9		—		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	(1)	1/1	1/1		
Rum flavouring	—	008030-89-5		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(3)	(3)	(4)	(3)	0/0	(1)	(1)	(1)		
Sagrotan	—	—	liquid	?		1/2	1/3	0/0	3/0	0/0	0/0	(3)	1/3	3/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	3/0	0/0	(2)	(1)	(1)		Disinfectants; Schülke & Mayr
Salicylaldehyde	$C_7H_6O_2$	000090-02-8		Xn, Xi		1/1	1/2	(3)	2/3	0/0	1/2	(3)	1/2	4/4	3/3	3/4	0/0	0/0	1/4	1/1	(1)	(3)	(3)	(3)	4/4	0/0	(2)	(1)	(1)		
Salicylic acid	$C_7H_6O_3$	000069-72-7	saturated	(Xn, Xi)		1/1	1/1	1/0	1/2	1/0	1/1	4/4	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1	
Salicylic acid	$C_7H_6O_3$	000069-72-7	Powder	Xn, Xi		1/1	1/1	1/0	1/2	(1)	1/2	(3)	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1	
Salicylic acid methyl ester	-> see: Methyl salicylate																													
Salammoniac	-> see: Ammonium chloride																													
Ammonia solution	-> see: Ammonium hydroxide																													
Nitric acid	HNO_3	007697-37-2	1-10 %	C		1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1	1/1	
Nitric acid	HNO_3	007697-37-2	50 %	C+		2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO_3	007697-37-2	66 %	C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO_3	007697-37-2	100 %	O, C+		4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	0/0	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	?	
Nitric acid	HNO_3	007697-37-2	70 %	O, C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2	1/2	
Hydrochloric acid	HCl	007647-01-0	1-5 %	—		1/1	1/1	4/4	1/1	(2)	1/2	4/4	1/1	1/1	1/1	1/1	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	3/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	35 %	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	konz.	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	20 %	Xi		1/1	1/1	4/4	2/3	3/0	1/2	4/4	1/1	1/1	1/1	1/3	0/0	0/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	4/4	4/4	4/4	1/1	Hydrochloric acid
Hydrochloric acid aluminium salt, anhydrous	-> see: Aluminium chloride																													
Salt brine	NaCl	007647-14-5	saturated	—		1/1	1/1	1/0	(1)	(1)	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3	1/2	0/0	
Salt water, seawater	—	—		—		1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	
Saturated steam condensate	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(2)	1/1	1/1		
Oxygen	O_2	007782-44-7	tech. pure	O		1/3	1/3	2/0	1/0	(1)	0/0	1/0	1/3	1/0	0/0	1/1	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Lubricating oils	—	—		?		1/3	2/3	(2-3)	(1)	(2)	0/0	(2)	3/0	0/0	0/0	1/1	1/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0	
Lubricating soap	—	—	diluted	?		1/3	1/1	(2-3)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(1)	1/1	0/0	(2)	(1)	(1)	0/0	
Sulphur	S_8	007704-34-9	tech. pure	Xi		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	3/0	3/4	1/1	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	(1)	1/1	1/1	1/1	Sulphur, net sulphur, sulphur bloom
Sulphur, melted, 121 °C	S_8	007704-34-9		?		0	0	(4)	(3)	0	4	4	4	4	0	0	0	4	0	0	(1)	0	4	1	4	0	(3)	1	1	0/0	
Sulphur chloride	S_2Cl_2	010025-67-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	4/4	1/0	4/4	0/0	3/4	(1/1L)[1]	(1/1L)[1]	0/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Sulphur dioxide	SO_2	007446-09-5	moist	T, C		1/1	1/1	(3)	(3)	0/0	1/1	4/4	1/3	3/4	2/2	1/2	0/0	0/0	1/1	1/1	1/1	1/4	1/0	4/4	4/4	0/0	3/4	1/1	1/1	1/0	with H2O -> Sulphurous acid
Sulphur dioxide	SO_2	007446-09-5	liquid	T, C		3/4	4/4	(3)	3/4	0/0	4/4	4/4	4/4	4/4	2/2	3/4	0/0	0/0	1/2	1/1	1/1	4/4	1/0	4/4	4/4	0/0	(3)	(1)	(1)	1/0	with H2O -> Sulphurous acid
Sulphur dioxide, aqueous solution	-> see: Sulphurous acid																													
Sulphur ether	-> see: Ethyl ether																													
Sulphur hexaflurod	SF_6	002551-62-4		—		0/0	0/0	1/0	(2)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	1/0	0/0	0/0	(1)	(2)	1/0	3/0	1/0	0/0	(1)	(1)	(1)		
Carbon disulfide	CS_2	000075-15-0		F+, T	X	4/4	4/4	3/0	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/3	1/1	1/0	1/1	4/4	1/0	4/4	0/0	1/1	1/1	1/1	1/0	
Sulphur monochloride	-> see: Sulphur chloride																													
Sulphur sodium	-> see: Sodium sulphide																													
Sulphuric acid	H_2SO_4	007664-93-9	40 %	C+		1/1	1/1	4/4	2/0	(4)	1/2	4/4	1/1	2/0	3/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	(3)	1/1	4/4	0/0	3/4	2/3	2/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	60 %	C+		1/3	1/3	4/4	3/3	(4)	1/2	4/4	1/3	2/4	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	4/4	3/4	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	80 %	C+		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/1	3/4	3/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	2/4	2/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	95 %	C+		3/4	3/4	4/4	4/4	4/4	2/2	4/4	3/4	4/4	4/4	2/4	0/0	4/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	1/3	1/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	fuming	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	4/4	4/4	1/0	4/4	0/0	(3)	1/2	1/1	0/0	Oleum
Sulphuric acid	H_2SO_4	007664-93-9	1-6 %	Xi		1/1	1/1	4/4	1/1	0/0	1/1	4/4	1/1	1/2	1/1	1/2	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/0	0/0	(3)	2/2	1/2	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	20 %	Xi		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	(3)	2/3	2/3		
Sulphuric acid copper (II) salt	-> see: Copper sulphate																													
Sulphuric acid monomethyl ester	-> see: Methyl sulphuric acid																													
Sulphur trioxide	SO_3	007446-11-9		C+		4/4	4/4	4/4	(4)	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	(2)	(2)	3/4	3/0	1/0	4/4	0/0	(3)	(1)	(1)	0/0	
Hydrogen sulphide	H_2S	007783-06-4	saturated	F+, T+	X	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	3/0	1/0	1/3	3/3	1/0	0/0	1/0	1/1	1/1	1/0	(3)	4/4	0/0	1/1	1/1	1/1	0/0	
Sulphurous acid	H_2SO_3	007782-99-2	saturated	(C)		1/1	1/1	4/4	4/4	1/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	3/0	(3)	3/4	0/0	3/4	1/1	1/1	1/1	
Sulphuric acid dichloride	-> see: Thionyl chloride																													
Pork fat	—	—		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	2/0	1/0	1/0	0/0	(1)	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sebacic acid dibenzyl ester	-> see: Dibenzyl sebacate																													
Sebacic acid dibutyl ester	-> see: Dibutylsebacat																													
Sebacic acid diethyl ester	-> see: Diethylsebacate																													
Ocean water, seawater	-> see: Salt water, seawater																													
Soap solution	—	—	any	(—)		1/1	0/0	4/4	(2)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/1	
Mustard	—	—		—		0/0	0/0	(2)	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	1/0	1/0	0/0	(2)	1/0L	1/0L		
Mustard oil	-> see: Allyl mustard oil																													
Silver acetate	$C_2H_3AgO_2$	000563-63-3		Xi		1/1	1/1	(2)	1/2	(2)	1/1	(2)	1/1	2/2	1/1	2/2	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	(3)	0/0	(4)	0/0	0/0	0/0	
Silver cyanide	CAgN	000506-64-9		T		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	(1)	(1)	(3)	0/0	(4)	0/0	0/0	0/0	
Silver nitrate	$AgNO_3$	007761-88-8	aqueous	C		1/1	0/0	1/0	1/1	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	1/1	
Silver nitrate	$AgNO_3$	007761-88-8		C		1/1	1/2	1/0	1/1	(2)	1/1	1/0	1/2	2/3	1/1	1/2	1/3	1/2	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	1/1	
Silicon dioxide	-> see: Silicic acid																													
Silicone fats	—	—		(—)		0/0	0/0	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	1/0	1/0	1/1	0/0	1/1	1/1	1/1		
Silicone oil	—	—		?		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	3/3	1/0	1/4	0/0	1/1	0/0	1/1	1/1	(1)	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	Polysiloxan
Skydrol 500 (B4)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	0/0	1/0	4/4	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Solutia
Skydrol 7000	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	1/0	2/0	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Solutia
Soda	-> see: Sodium carbonate																													
Soya oil	—	008001-22-7		—		0/0	0/0	(2)	(1)	1/0	0/0	2/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	1/1	
Spindle oil	—	—		?		3/3	2/3	(2)	(2)	1/0	0/0	(2)	1/4	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Spinning bath acids	—	—	100mg CS_2/l	?		1/0	0/0	4/4	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(3)	(2)	4/4	0/0	(4)	3/4	2/4	0/0	
Spinning solution, viscous -	—	—		(Xn, Xi)		1/1	1/1	4/4	(3)	0/0	0/0		1/1	0/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	(3)	(2)	4/4	0/0	(3)	3/4	2/4	0/0	
Spirits	C_2H_6O	—		—		1/1	1/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	1/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	0/0	Ethanol 40 %
Spirit	C_2H_6O	—		F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1		Ethanol
Rinsing agent	—	—	aqueous	?		1/1	1/1	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0	
Starch gum	-> see: Dextrin																													
Starch solution	$(C_6H_{10}O_5)_n$	—	any	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Starch syrup	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Stauffer's grease	—	—		(—)		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	1/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	(1)	(2)	0/0	(1)	1/1	1/1	0/0	
Stearic acid	$C_{18}H_{36}O_2$	000057-11-4	fuming	Xi		1/3	1/3	1/0	1/2	1/0	1/1	1/0	1/3	1/2	2/2	1/2	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
Stearic acid zinc salt	-> see: Zinc stearate		crystals																											
Stearic acid butyl ester	$C_{22}H_{44}O_2$	000123-95-5	100 %	Xi		0/0	0/0	(1)	(3)	1/0	0/0	(2)	(2)	0/0	0/0	1/0	1/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1	0/0	
Coal tar oil	—	092045-38-0	100 %	T		1/0	1/3	1/0	(3)	0/0	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	1/1	1/1		
Nitrogen	N_2	007727-37-9		—		0/0	0/0	1/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1		
Nitrogen tetroxide	N_2O_4	010544-72-6		(O), T+, C		0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(2)	(1)	(1)		
Strontium bromide	$SrBr_2$	010476-81-0		Xi		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(3)	0/0	0/0		
Strychnine	$C_{21}H_{22}N_2O_2$	000057-24-9		T+		1/1	1/1	(1)	(1)	(2)	0/0	(2)	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)		
Styrene	C_8H_8	000100-42-5	100 %	Xn, Xi	X	4/4	3/4	1/1	4/4	1/1	(4)	1/1	3/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(2)	4/4	3/0	4/4	0/0	1/1	1/1	1/1	0/0	
Sulphite lye	-> see: Calcium bisulphite																													
Sulphuryl chloride	Cl_2SO_2	007791-25-5	tech. pure	C		4/4	4/4	4/4	1/0	0/0	0/0	4/4	4/4	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/0	3/0	3/0	1/0	4/4	0/0	3/4	0/0	0/0		
Tallow	—	—	tech. pure	—		1/1	1/1	1/0	(1)	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1	0/0	
Tannin	$C_{76}H_{52}O_{46}$	001401-55-4	10 %	Xi		1/1	1/1	1/0	3/3	0/0	1/1	4/4	1/1	3/3	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	1/1	
Tannin	$C_{76}H_{52}O_{46}$	001401-55-4		Xi		1/1	1/1	1/0	4/4	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	1/1	
Tar	—	—		T		0/0	1/0	1/0	(3)	1/0	0/0	1/0	(2)	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(1)	(1)	(1)		
Surfactants	-> see: Wetting agent																													
Turpentine substitute	—	—		Xn, N	X	0/0	0/0	1/0	(3)	1/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	(3)	0/0	1/1	1/1	1/1	1/1	
Turpentine oil	—	008006-64-2		Xn	X	2/2	3/4	1/0	4/4	1/0	3/3	1/1	4/4	4/4	4/4	2/3	4/4	3/3	1/1	1/1	1/0	1/3	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
White spirit	—	—	liquid	Xn, N	X	0/0	2/3	(1)	(3)	1/0	(4)	1/0	3/4	4/4	0/0	1/3	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0	
Test fuel A (ISO-Fluid A)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	1/0	0/0	(1)	(1)	(1)		
Test fuel B (ISO-Fluid B)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)		
Test fuel C (ISO-Fluid C)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)		
Test fuel D (ISO-Fluid D)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	4/4	0/0	(1)	(1)	(1)		
Tetrabromomethane (TBE)	$C_2H_2Br_4$	—	100 %	T+		4/4	3/4	(3)	4/4	(4)	(4)	(3)	3/4	4/4	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Carbon tetrabromide	CBr_4	000558-13-4		Xn, Xi		0/0	0/0	(3)	4/4	0/0	0/0	(3)	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Tetrabromomethane	-> see: Carbon tetrabromide																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Tetrachloroethane	$C_2H_2Cl_4$	—	tech. pure	T+		3/0	3/4	3/0	4/4	(4)	(4)	1/1	3/4	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Tetrachloroethene	-> see: Perchloroethylene																													
Tetrachloroethylene	-> see: Perchloroethylene																													
Carbon tetrachloride (TETRA)	CCl_4	000056-23-5		T		4/4	4/4	4/4	4/4	1/4	4/4	2/3	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	1/1	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Methane tetrachloride	-> see: Carbon tetrachloride																													
Tetrachlorotitanium	-> see: Titanium tetrachloride																													
Tetraethyl lead (TEL)	$C_8H_{20}Pb$	000078-00-2	techn. rein	T+	X	1/0	1/0	1/4	3/0	(2)	(4)	(2)	2/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/0	0/0	(2)	(1)	(1)	1/1	
Tetraethylorthosilicate	$C_8H_{20}SiO_4$	000078-10-4		Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	1/0	0/0	(1)	(1)	(1)		
Tetrafluoromethane	CF_4	000075-73-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Tetrahydro-1,4-oxazine	-> see: Morpholine																													
Tetrahydrofuran (THF)	C_4H_8O	000109-99-9		F, Xi	X	3/4	4/4	1/0	4/4	1/0	3/4	1/3	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	1/1	
Tetrahydrofurfuryl alcohol	$C_5H_{10}O_2$	000097-99-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(2)	(1)	(1)		
Tetrahydronaphthalene	$C_{10}H_{12}$	000119-64-2	tech. pure	Xi		3/4	4/4	1/0	4/4	1/0	(4)	1/0	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	1/0	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Tetralin	-> see: Tetrahydronaphthalene																													
Tetramethylene oxide	-> see: Tetrahydrofuran																													
Tetraphosphorus decaoxide	-> see: Phosphorus pentoxide																													
Thiacyclopentadiene	-> see: Thiophene																													
Thiofuran	-> see: Thiophene																													
Thioglycolic acid	$C_2H_4SO_2$	000068-11-1		T, C		0/0	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	(4)	0/0	3/4	0/0	1/1	0/0	
Thionyl chloride	Cl_2SO	007719-09-7	tech. pure	C		4/4	4/4	4/4	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	(3)	3/0	1/0	4/4	0/0	3/4	0/0	0/0	0/0	
Thiophene	C_2H_4S	000110-02-1		F, Xn	X	3/3	3/3	(2)	4/4	0/0	(4)	(2)	3/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	4/4	3/0	0/0	(1)	(1)	(1)	0/0	
Thymol	$C_{10}H_{14}O$	000089-83-8		C, Xn		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(3)	3/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	1/0	4/4	0/0	(1)	(1)	(1)		
Titanium chloride	-> see: Titanium tetrachloride																													
Titanium tetrachloride	$TiCl_4$	007550-45-0		C		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(4)	0/0	0/0		
Toluene	-> see: Methylbenzene																													
Toluol	-> see: Methylbenzene																													
Toluenesulphone chloramide sodium, p-	-> see: Chloramine T																													
Tragacanth	—	009000-65-1		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1		
Transformer oil	—	—		?		1/3	3/3	1/0	(3)	1/1	1/0	3/3	1/3	1/3	1/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	2/3	3/3	0/0	1/1	(1)	(1)	0/0	
Grape sugar	-> see: Glucose																													
Triacetin	$C_9H_{14}O_6$	000102-76-1		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	3/3	0/0	(1)	(1)	(1)		
Tribromomethane	-> see: Bromoform																													
Tributyl citrate	$C_{18}H_{32}O_7$	000077-94-1		—		1/2	2/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Tributyl phosphate (TBP)	$C_{12}H_{27}PO_4$	000126-73-8	tech. pure	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Trichloroacetaldehyde	C_2HCl_3O	000075-87-6	100 %	T/Xi		1/1	1/1	4/4	(3)	(4)	0/0	(3)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	0/0	(4)	3/0	(4)	4/4	0/0	4/4	0/0	0/0	0/0	
Trichloroacetaldehyde hydrate	-> see: Chloral hydrate																													
Trichloraldehyde hydrate	-> see: Chloral hydrate																													
Trichlorobenzene	$C_6H_3Cl_3$	—	100 %	(Xn)		4/4	4/4	(3)	(3)	0/0	(4)	(2)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	(2)	(3)	(4)	(3)	4/4	0/0	(2)	0/0	0/0	0/0	Isomer not specified in the source
Trichloroacetic acid (TCA)	$C_2HCl_3O_2$	000076-03-9		C+		1/4	3/4	4/4	4/4	4/4	0/0	4/4	1/1	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	1/3	3/0L	2/0L	1/1	
Trichloroethane	$C_2H_3Cl_3$	—		Xn		3/4	4/4	3/0	4/4	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	(1)	1/3	4/4	1/0	4/4	0/0	4/4	0/0	0/0	0/0	Isomer not specified in the source
Trichloroethene	-> see: Trichloroethylene																													
Trichloroethylene (TRI)	C_2HCl_3	000079-01-6	100 %	Xn		3/4	4/4	3/0	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/4	1/2	1/1	1/0	1/1	4/4	1/3	4/4	0/0	1/3	(1/1L)[1]	(1/1L)[1]	1/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Trichlorofluoromethane	CCl_3F	000075-69-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(3)	(1)	0/0	4/4	2/0	1/0	0/0	(3)	0/0	0/0	0/0	
Trichloromethane	-> siehe: Chloroform																													
Trichloromonofluoromethane	-> siehe: Trichlorfluormethan																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Trichlorophenol	$C_6H_3Cl_3O$	—		(Xn, Xi)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(4)	(3)	(4)	0/0	(3)	0/0	0/0		Isomer not specified in the source
Trichlorophosphine	-> see: Phosphorus trichloride																													
Trichlorophosphine oxide	-> see: Phosphorus oxychloride																													
Trichlorophosphorus oxide	-> see: Phosphorus oxychloride																													
Trichlorotrifluoroethane	$C_2Cl_3F_3$	000076-13-1		?		0/0	0/0	1/0	(3)	1/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		
Triethanolamine (TEA)	$C_6H_{15}NO_3$	000102-71-6	tech. pure	Xi		1/1	1/2	(2)	(2)	1/0	0/0	2/2	1/1	1/1	0/0	3/0	4/4	1/1	0/0	1/1	1/0	1/0	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Triethylamine (TEA)	$C_6H_{15}N$	000121-44-8	tech. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	1/1	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	3/4	4/4	3/0	3/4	0/0	(1)	(1)	(1)	0/0	
Triethylene glycol	-> see: Triglycol																													
Triethylene glycol diacetate	-> see: Triglycol acetate																													
Trifluorotrichloroethane	$C_2Cl_3F_3$	—	100 %	?		4/4	3/4	1/0	3/0	0/0	0/0	1/0	4/4	4/4	1/0	3/4	4/4	3/3	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		Isomer not specified in the source
Triglycol	$C_6H_{14}O_4$	000112-27-6		Xi		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	(3)	0/0	(1)	(1)	(1)	0/0	
Triglycol acetate	$C_{10}H_{18}O_6$	000111-21-7		?		0/0	0/0	(3)	(3)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)		
Trihydroxybenzoic acid, 3,4,5-	-> see: Gallic acid																													
Trihydroxybenzene, 1,2,3-	-> see: Pyrogallol																													
Trihydroxybutane	-> see: Butanetriol																													
Trihydroxypurine, 2,6,8-	-> see: Uric acid																													
Trihydroxytriethylamine	-> see: Triethanolamine																													
Triiodomethane	-> see: Iodoform																													
Triisopropylbenzene	$C_{15}H_{24}$	000717-74-8		—		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Tricresyl phosphate (TCF)	$C_{21}H_{21}PO_4$	—	tech. pure	T/Xn, N		1/1	1/1	1/0	4/4	1/0	0/0	1/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	1/1	1/1	1/1	1/1	Isomer not specified in the source
Trimethylbenzene, 1,3,4-	-> see: Pseudocumene																													
Trimethylolpropane	$C_6H_{14}O_3$	000077-99-6	aqueous	—		0/0	0/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	0/0	(1)	(1)	(1)		
Trimethylpentane, 2,2,4-	-> see: Iso-octan																													
Trisodium phosphate	Na_3PO_4	007601-54-9		Xi		1/1	1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(4)	1/1	1/1		
Trisodium phosphate, tribasic	-> see: Sodium phosphate																													
Trinitrophenol, 2,4,6-	-> see: Picric acid																													
Trioctyl phosphate	$C_{24}H_{54}PO_4$	000078-42-2	tech. pure	(Xn)		3/0	1/0	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	(1)	(1)	(1)	0/0	
Tripen	-> see: Hexachlorobutadiene																													
Tripropylene glycol (TPG)	$C_9H_{20}O_4$	024800-44-0		(—)		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/1	(2)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Tris(2-ethylhexyl) phosphate	-> see: Trioctyl phosphate																													
Tris(hydroxyethyl)-amine	-> see: Triethanolamine																													
Tris(hydroxymethyl)propane	-> see: Trimethylolpropane																													
Tropic acid tropylester sulphate	-> see: Atropine sulphate																													
Tung oil	-> see: Wood oil																													
Turbine oil (mineral oil base)	—	—		?		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	(2)	1/0	0/0	1/1	1/1	1/1		
Superchloric acid	-> see: Perchloric acid																													
Undecanol	-> see: Undecyl alcohol																													
Undecyl alcohol	$C_{11}H_{24}O$	000112-42-5		Xi		1/2	1/3	(1)	2/3	(1)	1/2	1/0	1/2	2/2	3/3	1/3	0/0	1/1	1/2	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(1)	(1)	(1)		
Urine	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	3/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	
Urotropine	-> see: Hexamethylenetetramine																													
Vaseline	—	008009-03-8	tech. pure	(—)		3/4	2/3	1/0	1/0	1/0	0/0		1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Vaseline oil	—	008012-95-1	100 %	?		0/0	1/3	1/0	(2)	1/0	1/0		1/3	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	Paraffin oil
Vaseline oil	—	008012-95-1		?		1/1	1/3	1/0	1/0	1/0	0/0	1/1	1/3	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/3	0/0	1/1	1/1	1/1	1/1	Paraffin oil
Vinyl acetate	$C_4H_6O_2$	000108-05-4	tech. pure	F	X	0/0	1/1	1/0	4/4	(3)	(4)		1/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	1/0	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Vinylbenzene	-> see: Styrene																													
Vinylcarbinol	-> see: Allyl alcohol																													
Vinyl chloride	-> see: Chlorethylene																													
Vinyl cyanide	-> see: Acrylonitrile																													
Vinyl ethylene	-> see: Butadiene, 1,3-																													
Vinylidene chloride	$C_2H_2Cl_2$	000075-35-4		F+, Xn	X	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	2/3	1/1	(1)	(2)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	
Vitamin C	$C_6H_8O_6$	000050-81-7	liquid	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	(1)	(1)		
Wax alcohol	—	—	tech. pure	(—)		3/4	3/4	(2)	(2)	1/0	0/0		3/4	0/0	0/0	1/1	3/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	(1)	(1)	0/0	
Waxes	—	—		—		0/0	1/3	1/1	1/1	1/1	0/0		1/3	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	(4)	1/0	(1)	0/0	1/1	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Walnut oil	—	008024-09-7		—		0/0	0/0	(2)	(2)	1/0	0/0		1/3	3/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	(1)	1/1	1/1		
Spermaceti	—	008002-23-1		—		0/0	1/3	(1)	1/1	1/0	0/0		1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Detergent	—	—		?		1/1	1/1	1/0	1/1	1/1	0/0		1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	(2)	0/0	1/1	1/1	1/1	1/1	
Water	H_2O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Water, distilled ~	H_2O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Water glass	$Na_2Si_3O_7$	001344-09-8	saturated	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	0/0	1/1	1/1	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	Aqueous solution of alkali silicates
Hydrogen	H_2	001333-74-0	tech. pure	F+	X	1/1	1/1	1/0	1/0	0/0	0/0		1/1	1/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Hydrogen peroxide	H_2O_2	007722-84-1	30 %	C		1/1	1/2	4/4	1/1	1/0	1/2	4/4	1/3	1/2	1/1	1/1	0/0	1/0	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	(3)	1/1	1/1	1/1	
Hydrogen peroxide	H_2O_2	007722-84-1	100 %	O, C		1/4	1/4	4/4	0/0	0/0	0/0	4/4	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(3)	(1)	(1)	?	
Hydrogen peroxide	H_2O_2	007722-84-1	90 %	O, C		1/1	1/2	4/4	1/1	0/0	1/2	4/4	1/3	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/3	4/4	0/0	(3)	1/1	1/1	?	
Hydrogen peroxide	H_2O_2	007722-84-1	3 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	1/0	1/1	1/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	3/4	0/0	(3)	1/1	1/1	1/1	
Oxygenated water	-> see: Hydrogen peroxide																														
Plasticiser	—	—		?		1/3	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	3/3	0/0	(1)	(1)	0/0	(2-3)	0/0	4/4	0/0	(1)	(1)	(1)		
Wines	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	(2)	1/1	1/1	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	1/1	1/1	1/1	
Spirit of wine	C_2H_6O	—	50 %	(F)	X	1/0	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	Ethanol
Spirit of wine	C_2H_6O	—	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	Ethanol
Tartaric acid	$C_4H_6O_6$	000087-69-4	aqueous	Xi		1/1	1/1	3/3	1/2	0/0	0/0	(3)	1/1	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2	1/1	
Tartaric acid	$C_4H_6O_6$	000087-69-4		Xi		1/1	1/1	4/4	1/2	0/0	1/1	(3)	1/1	2/2	1/1	1/2	1/3	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2	1/1	
Cream of tartar	-> see: Potassium hydrogentartate																														
Whiskey	—	—		—		0/0	0/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1		Whisky, Scotch, Bourbon
White spirit	—	008042-47-5		Xn		1/0	1/0	(1)	(3)	1/0	(4)	1/0	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	1/0	(2)	0/0	1/1	1/1	1/1		
Wool grease	-> see: Lanolin																														
Xenon	Xe	007440-63-3		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1		
Xylol	-> see: Xylene																														
Xylene	C_8H_{10}	001330-20-7		(F), Xn	X	3/4	3/4	1/0	4/4	0/0	3/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/0	1/3	4/4	1/3	4/4	0/0	1/1	1/1	1/1	1/1	
Cedar oil	—	008000-27-9		?		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(4)	(2)	(3)	0/0	(1)	(1)	(1)		
Cinnamon	—	—	grinded	?		0/0	0/0	(2)	1/0	(2)	0/0	(2)	(2)	3/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Cinnamaldehyde	C_9H_8O	000104-55-2		Xn, Xi		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(1)	(1)	(1)		
Cinnamon oil	—	008007-80-5		Xn, Xi		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Zinc acetate	$C_4H_6ZnO_4$	000557-34-6	aqueous	Xn, Xi		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/3	0/0	(3)	(1)	(1)		
Zinc bromide	$ZnBr_2$	007699-45-8		C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(3)	0/0	0/0		
Zinc carbonate	$ZnCO_3$	003486-35-9	saturated	?		1/1	1/1	(1)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	No chemical effect expected due to low solubility
Zinc chloride	$ZnCl_2$	007646-85-7	aqueous	(C, Xn)		1/1	1/1	3/4	(2)	0/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1	
Zinc chloride	$ZnCl_2$	007646-85-7	10 %	C, Xn		1/1	1/1	3/4	1/0	0/0	1/1	2/0	1/1	1/3	0/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1	
Zinc nitrate	$Zn(NO_3)_2$	007779-88-6		O, C, Xn		1/1	1/1	1/4	(2)	0/0	0/0	(2)	1/1	1/0	1/0	1/0	1/0	1/1	0/0	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(3)	(1)	(1)	0/0	
Zinc oxide	ZnO	001314-13-2	solid	Xn, Xi		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		No chemical effect expected due to low solubility
Zinc phosphate	$Zn_3(PO_4)_2$	007779-90-0	saturated	?		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	
Zinc ointment	—	—		?		0/0	0/0	(1)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	(4)	(2)	(2)	0/0	(2)	(1)	(1)		
Zinc sludge	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	(3)	0/0	0/0		
Zinc stearate	$C_{36}H_{70}ZnO_4$	000557-05-1		Xi		1/1	1/1	(1)	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	(2)	0/0	(2)	(1)	(1)		
Zinc sulphate	$ZnSO_4$	007733-02-0	10 %	—		1/1	1/1	(3)	1/0	(2)	1/0	2/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	1/1	
Zinc vitriol	-> see: Zinc sulphate																														
Tin (II) chloride	$SnCl_2$	007772-99-8	aqueous	(C, Xn)		1/1	1/1	(4)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	1/1	
Tin (II) chloride	$SnCl_2$	007772-99-8	saturated	C, Xn		1/1	1/1	4/4	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	1/1	
Tin (IV) chloride	$SnCl_4$	007646-78-8	aqueous	C		1/1	1/1	4/4	(3)	0/0	0/0	(4)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	4/4	3/4		
Tin dichloride	-> see: Tin (II) chloride																														
Tin protochloride	-> see: Tin (II) chloride																														
Tin tetrachloride	-> see: Tin (IV) chloride																														
Lemon juice	—	—		—		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	1/0	1/1	0/0	(1)	1/1	1/1		
Citric acid	$C_6H_8O_7$	000077-92-9	10 %	Xi		1/1	1/1	1/1	1/2	1/3	1/1	2/4	1/1	1/2	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/1	1/1	1/1	
Citric acid	$C_6H_8O_7$	000077-92-9	50 %	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1	
Citric acid	$C_6H_8O_7$	000077-92-9	saturated	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1	
Lemon peel oil	—	084929-31-7		Xi	(X)	0/0	0/0	(2)	(3)	1/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	3/3	0/0	1/0	(1)	(2)	4/4	(2)	3/3	0/0	1/1	(1)	(1)		mainly limes
Citrus juices	—	—	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	1/1	0/0	(2)	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers				Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sugar beet juice	—	—		—		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Sugar acid	—	—	saturated	(Xi)		1/1	1/1	(3)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		
Sugar syrup	—	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Two-stroke oil	—	—	100 %	—		0/0	1/3	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

Résistance

Deux valeurs sont données pour chaque milieu:
numéro de gauche = valeur à +20°C / numéro de droite = valeur à +50°C

0	aucune information disponible/aucune déclaration possible
1	très bonne résistance/convenable
2	bonne résistance/convenable
3	résistance limitée
4	non résistant
K	aucune information générale possible
L	Risque de piqûres ou de fissures par corrosion sous contrainte
( )	Valeur estimée

Prévention des risques

E	explosif
O	oxydant
F	inflammatoire
F+	extrêmement inflammable
T	toxique
T+	très toxique
C	caustique
Xn	nocif pour la santé
Xi	irritant
N	dangereux pour l'environnement

Nom des matériaux

Thermoplastiques

HDPE	Polyéthylène haute densité
BDPE	Polyéthylène basse densité
PA	Polyamide (nylon)
PC	Polycarbonate
PETG	Polyéthylène téréphtalate glycol (co-
PMP	polyester) Polyméthylpentène (TPX)
POM	Polyoxyméthylène
PP	Polypropylène
PS	Polystyrène
PSU	Polysulfone
PVC	Chlorure de polyvinyle
SAN	Styrène acrylonitrile

Fluoroplastiques

E-CTFE	Éthylène-chlorotrifluoroéthylène (Halar)
ETFE	Éthylène tétrafluoroéthylène
FEP	Tétrafluoroéthylène-perfluoropropylène (Téflon,
PTFE	FEP) Polytétrafluoroéthylène (Téflon)
PVDF	Fluorure de polyvinylidène

Elastomères

EPDM	Caoutchouc terpolymère éthylène-propylène
FPM/FKM	Fluoropolymère (Viton)
NBR	Caoutchouc nitrile
SI	Caoutchouc de silicone

Métaux

Al	Aluminium
V2A	Acier inoxydable 1.4301 (AISI 304)
V4A	Acier inoxydable 1.4401 (AISI 316)
Hastelloy C	Alliage nickel-chrome-molybdène