LISTA DE PRODUCTOS QUÍMICOS MACH I

AVISO IMPORTANTE

La tabla „Resistencia química de los plásticos“ se ha elaborado a partir de la información facilitada por diversos fabricantes de materias primas. Los valores se refieren exclusivamente a ensayos de laboratorio con materias primas. A menudo, las piezas de plástico fabricadas con ellas están sometidas a influencias que no pueden detectarse en los ensayos de laboratorio (temperatura, presión, tensiones del material, exposición a sustancias químicas, características de diseño, etc.). Por estas razones, los valores indicados sólo pueden servir de orientación. En caso de duda, recomendamos encarecidamente realizar una prueba. No se puede derivar ninguna reclamación legal de esta información, excluimos cualquier garantía y responsabilidad. La resistencia química y mecánica por sí sola no es suficiente para evaluar la utilidad de un producto. En particular, debe tenerse en cuenta la normativa sobre líquidos inflamables (protección contra explosiones).

DERECHOS DE AUTOR

Agradecemos a Bürkle GmbH que nos haya concedido el derecho a utilizar esta tabla.
Esta tabla es publicada y mantenida por Bürkle GmbH, D-79415 Bad Bellingen, Alemania, como guía de referencia. Este aviso de copyright no puede ser eliminado. La tabla puede distribuirse y copiarse libremente siempre que se mantenga intacto el aviso de copyright.

LISTA DE MATERIALES MACH I

Bomba de aguas sucias:	PP + GF20	Manguera de drenaje:	PP, EVA
Válvula de retención:	PP	Boquilla para suelos:	PP
Conexiones de tornillo:	PP	Tubo de aspiración:	PP
Acoplamientos en C:	PA6 + GF30	Cabezal de aspiración:	ABS
Manguera de aspiración:	PP, EVA		

Versión 3.11 (11.01.2021); Sujeto a cambios técnicos, © Bürkle GmbH 2021.

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Exhaust gases, alkaline	—	—		?		1/1	0/0	(2)	0/0	0/0	0/0	(1)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/4	1/0	1/0	1/0	0/0	(2)	(1)	(1)		
Exhaust gases, containing hydrogen fluoride	—	—	low	?		1/1	0/0	(3)	(3)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	(2)	(2)	1/1	
Exhaust gases, carbon dioxide-containing	—	—	low	?		1/1	0/0	(1)	(1)	(1)	(1)	(1)	1/1	(1)	(1)	1/1	(1)	(1)	1/1	1/1	1/1	1/1	1/0	1/0	(1)	(1)	(1)	(1)	(1)	0/0	
Exhaust gases, nitrous	—	—	low	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	(3)	0/0	(2)	(1)	(1)		
Exhaust gases containing hydrochloric acid	—	—	any	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	2/2L	2/2L	3/3	
Exhaust gases containing sulphur dioxide	—	—	low	?		1/1	0/0	(2)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	1/1	1/1	0/0	
Exhaust gases containing sulphuric acid	—	—	any	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0	
Exhaust gases, containing sulphur trioxide	—	—	low	?		1/1	0/0	(4)	0/0	0/0	0/0	(4)	4/4	0/0	0/0	1/1	0/0	0/0	(2)	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)	0/0	
Acetaldehyde	C_2H_4O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	3/4	
Acetaldehyde	C_2H_4O	000075-07-0	tech. pure	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Acetamide	C_2H_5NO	000060-35-5	saturated	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)	1/1	
Acetamino-4-ethoxybenzene, 1-	-> see: Phenacetin																														
Acetic anhydride	-> see: Acetic anhydride																														
Acetone	C_3H_6O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	1/1	
Acetonitrile	C_2H_3N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Acetophenone	C_8H_8O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Acetoxybenzoic acid, 2-	-> see: Acetylsalicylic acid																														
Acetyl-5-methyl-2,3-dihydropyran-2,4-dione, -2	-> see: PDehydroacetic acid																														
Acetyl chloride	C_2H_3ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	0/0	
Acetylene	C_2H_2	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	1/1	0/0	1/0	1/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	
Acetylene tetrabromide	-> see: Tetrabromomethane, 1,1,2,2-																														
Acetylene tetrachloride	-> see: Tetrachloroethane-1,1,2,2																														
Acetylsalicylic acid	$C_9H_8O_4$	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	1/0	
Acrylonitrile	C_3H_3N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	1/1	
Acrylic acid butyl ester	-> see: Butyl acrylate																														
Acrylic acid ethyl ester	-> see: Ethyl acrylate																														
Acrylic acid methyl ester	-> see: Methyl acrylate																														
Acrylic acid nitrile	-> see: Acrylonitrile																														
Adipic acid	$C_6H_{10}O_4$	000124-04-9	saturated	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	1/0	(2)	(2)	1/1	
Adipic acid dioctyl ester	-> see: Dioctyladipate																														
Acrylic acid	H_2SO_4	007664-93-9	38 %	C		1/1	1/1	4/4	1/1	(4)	1/1	4/4	1/1	1/1	1/1	1/3	3/4	0/0	(1)	1/1	1/1	1/1	1/0	1/1	4/4	0/0	3/4	2/3	2/3	1/1	"Battery acid"
Alanine	$C_3H_7NO_2$	000056-41-7		—		1/1	1/1	1/1	4/4	(2)	1/1	(1)	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(2)	(2)	(2)		
Alum	-> see: Potassium aluminium sulphate																														
Alcohol	-> see: Ethanol																														
Allyl acetate	$C_5H_8O_2$	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		
Allyl alcohol	C_3H_6O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	1/1	(2)	1/0	4/4	3/0	0/0	1/1	1/1	1/1	1/1	
Allyl chloride	C_3H_5Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)	0/0	
Allyl isothiocyanate	-> see: Allyl mustard oil																														
Allyl mustard oil	C_4H_5NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		Oleum Sinapis
Aluminium (hydroxide) acetate	$C_4H_7AlO_5$	000139-12-8	aqueous	Xn		1/1	1/1	1/1	(1)	1/0	1/1	1/0	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	(1)	1/0	(3)	3/0	0/0	1/1	1/1	1/1	0/0	"Acetic acid alumina"
Aluminium ammonium sulphate	$(NH_4)Al(SO_4)_2$	007784-26-1	saturated	Xi		1/1	1/1	3/4	(2)	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3	0/0	
Aluminium chloride	$AlCl_3$	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	1/1	0/0	1/1	0/0	1/1	2/2	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	4/4	3/4	1/1	
Aluminium chloride	$AlCl_3$	007784-13-6	solid	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	(3)	0/0	4/4	4/4	3/4	1/1	Hydrochloric acid aluminium salt, anhydrous
Aluminium chloride	$AlCl_3$	007784-13-6	saturated	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	(1)	1/1	(2)	1/0	1/1	0/0	4/4	4/4	3/4	1/1	Hydrochloric acid aluminium salt, anhydrous
Aluminium fluoride	AlF_3	007789-18-1	aqueous	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	0/0	
Aluminium hydroxide	$Al(HO)_3$	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1/1	1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	0/0	No chemical effect expected due to low solubility
Aluminium hydroxide diacetate	-> see: Acetic clay																														
Aluminium nitrate	$Al(NO_3)_3$	013473-90-0	aqueous	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Aluminium oxide	Al_2O_3	001344-28-1	solid	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	No chemical effect expected due to low solubility
Aluminium sulphate	$Al_2(SO_4)_3$	010043-01-3	10 %	?		1/1	1/1	1/0	1/0	(2)	1/1	3/4	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/2	1/1	1/1	
Aluminium sulphate	$Al_2(SO_4)_3$	010043-01-3	saturated	Xn		1/1	1/1	3/4	1/0	0/0	1/1	3/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	2/2	1/2	1/1	
Aluminium trifluoride	-> see: Aluminium fluoride																														
Formic acid	CH_2O_2	000064-18-6	50 %	C, F	X	1/1	1/2	4/4	3/3	0/0	1/2	4/4	1/2	3/3	2/2	2/3	0/0	1/3	1/1	1/1	1/1	1/1	3/4	4/4	4/4	0/0	(3)	1/3	1/2	1/1	
Formic acid	CH_2O_2	000064-18-6	98-100 %	C, F+, T	X	1/1	1/2	4/4	3/4	0/0	1/3	4/4	1/3	3/4	3/3	3/4	1/3	3/4	1/1	(1)	1/1	1/1	3/4	4/4	4/4	0/0	1/0	1/3	1/2	1/0	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Formic acid	CH_2O_2	000064-18-6	3 %	Xi		1/1	1/2	3/4	1/2	1/0	1/2	2/4	1/2	1/2	2/2	2/3	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(3)	4/4	0/0	(3)	1/2	1/1	1/1	
Formic acid amide	-> see: Formamide																													
Formic acid ethyl ester	-> see: Ethyl formate																													
Formic acid methyl ester	-> see: Methylformia																													
Aminobenzene	-> see: Aniline																													
Aminobutane	-> see: Buylamine																													
Aminoacetic acid	$C_2H_5NO_2$	000056-40-6	10 %	—		1/1	1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	(2)	(2)	(2)	0/0	
Aminoethanol, 2-	-> see: Ethanolamine																													
Aminoethanoic acid	-> see: Aminoacetic acid																													
Amonimethane	-> see: Methylamine, (mono-)																													
Aminopropane	-> see: Propylamine, n-																													
Aminopropionic acid, L-2-	-> see: Alanine, (L-)																													
Ammonia	-> see: Ammonium hydroxide																													
Ammonia, sulphuric acid	-> see: Ammonium sulphate																													
Ammonia water	-> see: Ammonium hydroxide																													
Ammonium 2-hydroxyacetate	-> see: Ammonium glycolate																													
Ammonium acetate	$C_2H_7NO_2$	000631-61-8	saturated	Xi		1/1	1/1	1/0	1/1	(2)	1/1	(1)	1/1	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(3)	2/2	0/0	1/1	(2)	(2)	1/1	
Ammonium alum	-> see: Aluminium ammonium sulphate																													
Ammonium aluminium sulphate	-> see: Aluminium ammonium sulphate																													
Ammonium bicarbonate	-> see: Ammonium hydrogen carbonate																													
Ammonium bifluoride	-> see: Ammoinium hydrogen difluoride																													
Ammonium carbonate	$(NH_4)_2CO_3$	010361-29-2	50 %	Xn		1/1	1/1	1/0	3/0	0/0	1/0	(2)	1/1	1/1	1/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Hartshorn salt
Ammonium carbonate	$(NH_4)_2CO_3$	010361-29-2	aqueous	Xn		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Hartshorn salt
Ammonium chloride	$(NH_4)Cl$	012125-02-9	solid	Xn		1/1	1/1	1/0	1/0	(2)	0/0	2/3	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	3/4	1/3L	1/2L	1/1	Ammonia
Ammonium chloride	$(NH_4)Cl$	012125-02-9	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	Ammonia
Ammonium dihydrogen phosphate	$(NH_4)H_2PO_4$	007722-76-1	any	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	3/0	1/1	0/0	4/4	(1)	(1)	1/1	
Ammonium iron(II) sulfate	$(NH_4)_2Fe(SO_4)_2$	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	(1)	(1)		
Ammonium iron(III) sulfate	$(NH_4)Fe(SO_4)_2$	007783-83-7	saturated	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0		
Ammonium fluoride	$(NH_4)F$	012125-01-8	saturated	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)	?	
Ammonium fluoride	$(NH_4)F$	012125-01-8	aqueous	T. C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3	1/1	
Ammonium glycolate	$C_2H_7NO_3$	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)		
Ammonium heptamolybdate	$(NH_4)_6Mo_7O_{24}$	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/0	(3)	(1)	0/0		(1)	(1)	0/0	
Ammonium hydrogen carbonate	CH_5NO_3	001066-33-7	saturated	Xi		1/1	1/1	1/0	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	(3)	0/0	1/1	1/1	1/1	1/1	
Ammonium hydrogen difluoride	F_2H_5N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0		
Ammonium hydrogen sulphide	-> see: Ammonium hydrosulphide																													
Ammonium hydrosulphide	$(NH_4)HS$	012124-99-1	any	T, C		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	(2)	0/0	(2)	(1)	(1)	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	1/2	2/3	2/3	1/2	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1	1/1	
Ammonium hydroxide	$NH_3 + H_2O$	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1	1/1	
Ammonium metaphosphate	$(NH_4PO_3)_n$	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)		
Ammonium molybdate	-> see: Ammonium heptamolybdate																													
Ammonium monophosphate, monobasic	-> see: Ammonium dihydrogen phosphate																													
Ammonium nitrate	$(NH_4)NO_3$	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	1/1	
Ammonium nitrate	$(NH_4)NO_3$	006484-52-2	saturated	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1	1/1	
Ammonium nitrite	$(NH_4)NO_2$	013446-48-5	aqueous	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/0	0/0	(2)	(1)	(1)		
Ammonium oxalate	$C_2H_8N_2O_4$	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1	0/0	
Ammoniumperoxodisulfat	$(NH_4)_2S_2O_8$	007727-54-0	saturated	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0	
Ammoniumperoxodisulfat	$(NH_4)_2S_2O_8$	007727-54-0	aqueous	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0	
Ammonium persulphate	-> see: Ammonium peroxodisulphate																													
Ammonium phosphate, primary	-> see: Ammonium dihydrogen phosphate																													
Ammoniumpolyphosphat	-> see: Ammonium metaphosphate																													
Ammonium rhodanide	-> see: Ammonium thiocyanate																													
Ammonium sulphate	$(NH_4)_2SO_4$	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	1/1	sulphuric acid ammonia
Ammonium sulphate	$(NH_4)_2SO_4$	007783-20-2	saturated	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2	1/1	sulphuric acid ammonia
Ammonium sulphide	$(NH_4)_2S$	012135-76-1	any	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	?	
Ammonium sulphide	$(NH_4)_2S$	012135-76-1	aqueous	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ammonium sulphocyanide	-> see: Ammonium thiocyanate																													
Ammonium thiocyanate	CH_4N_2S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)		
Ammonium nitrate	-> see: Ammonium nitrate																													
Amylacetate, n-	$C_7H_{11}O_2$	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Amyl alcohol, n-	$C_5H_{12}O$	000071-41-0		Xn	X	1/1	1/2	1/0	1/0	1/0	2/3	1/0	1/1	1/3	3/0	2/3	3/0	0/4	1/1	1/1	1/1	1/1	3/0	2/4	3/0	0/0	1/2	1/1	1/1	0/0	
Anym chloride	$C_5H_{11}Cl$	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L	0/0	
Amyl hydrosulphide	-> see: Pentanthiol, 1-																													
Amyl mercaptan	-> see: Pentanthiol, 1-																													
α-pentylcinnamaldehyde	$C_{14}H_{18}O$	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)	(1)		Fragrance
Pineapple juice	—	—		—		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	(1)	(1)		
Aniline	C_6H_7N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0	1/1	
Aniline chlorohydrate	$C_6H_3ClN_6$	000142-04-1	saturated	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4		
Aniline hydrochloride	-> see: Aniline chlorohydrate																													
Anilinium chloride	-> see: Aniline chlorohydrate																													
Anise	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Anise oil	C_7H_8O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Anise oil	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Anon	-> see: Cyclohexanone																													
Antimony (III) chloride	-> see: Antimony trichloride																													
Antimony (V) chloride	-> see: Antimony pentachloride																													
Antimony pentachloride	$SbCl_5$	007647-18-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	(4)	0/0	
Antimony trichloride	$SbCl_3$	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4	0/0	
Antimony trichloride	$SbCl_3$	010025-91-9	anhydrous	C		0/0	0/0	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	1/0	1/0	1/0	0/0	1/1	4/4	4/4		
Antimony trichloride	$SbCl_3$	010025-91-9	aqueous	C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4		
Apple juice	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	(2)	(1)	(1)		
Orange juice	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(2)	1/1	1/1		
Orange peel oil	—	008028-48-6		Xn		(3)	(3)	1/0	(3)	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	4/4	(2)	(3)	0/0	(1)	(1)	(1)		mainly +-Limes
Arcton 12	-> see: Dichlorodifluoromethane																													
Arcton 21	-> see: Dichlorofluoromethane																													
Arcton 22	-> see: Chlorodifluoromethane																													
Arsenic anhydride	-> see: Arsenic pentoxide																													
Arsenic pentoxide	As_2O_5	001303-28-2		T, N		1/1	1/1	(3)	(2)	0/0	0/0	(4)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	(2)	(3)	(3)	0/0	(3)	(1)	(1)		
Arsenic acid	H_3AsO_4	022538-92-7	aqueous	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	1/1	
Arsenic acid	H_3AsO_4	022538-92-7	80 %	T, N		1/1	0/2	(3)	1/0	0/0	0/0	4/4	1/1	1/1	0/0	1/3	3/0	0/0	1/1	0/0	1/1	1/1	1/0	2/2	1/1	0/0	4/4	1/0	1/1	1/1	
Arsenic anhydride	-> see: Arsenic pentoxide																													
Ascorbic acid	$C_6H_8O_6$	000050-81-7	aqueous	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	1/1	(1)	(1)	0/0	
Ether	-> siehe: Ethylether																													
Atropine sulphate	$C_{34}H_{48}N_2SO_{10}\cdot H_2O$	000055-48-1		T+		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)		
Caustic baryte	-> see: Barium hydroxide																													
Caustic potash	-> see: Potassium hydroxide																													
Caustic lime	-> see: Calcium oxide																													
Caustic soda	-> see: Sodium hydroxide																													
Azafluorene, 9-	-> siehe: Carbazole																													
Valerian drops	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	1/1	1/1	(1)	(3)	(3)	(2)	0/0	(2)	(1)	(1)		
Barium bromide	$BaBr_2$	010553-31-8		Xn		1/1	1/1	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	1/1	0/0	(2)	(2L)	(2L)		
Barium carbonate	$BaCO_3$	000513-77-9	saturated	Xn		1/1	1/1	1/1	(1)	1/1	1/1	(1)	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	No chemical effect expected due to low solubility
Barium chloride	$BaCl_2$	010361-37-2	saturated	T		1/1	1/1	1/0	1/0	1/0	1/1	(2)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1	
Barium chloride	$BaCl_2$	010361-37-2	aqueous	T		1/1	1/1	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1	
Barium hydroxide	$Ba(HO)_2$	012230-71-6	saturated	Xn		1/1	1/1	1/0	(3)	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/3	
Barium hydroxide	$Ba(HO)_2$	012230-71-6	aqueous	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	?	
Barium sulphide	BaS	021109-95-5	saturated	(T)		1/1	1/1	1/0	(2)	(2)	1/1	(2)	1/1	0/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	(2)	1/0	1/0	1/1	0/0	(3)	(1)	(1)	1/1	
Cottonseed oil	—	008001-29-4	tech. pure	?		0/0	0/0	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	3/0	1/0	1/0	0/0	(1)	1/1	1/1		
Benzaldehyde	C_7H_6O	000100-52-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	artificial almond oil
Benzene	-> see: Benzene (page 5)																													
Petrol	C_5H_{12} - $C_{12}H_{26}$	086290-81-5		F, Xn, N	X	2/3	3/4	1/0	3/3	(2)	2/3	1/2	3/4	4/4	3/3	2/4	0/0	0/4	1/1	1/1	1/1	1/1	4/4	(1-3)	3/0	0/0	1/1	1/1	1/1	1/1	Fuel, unleaded

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Benzoic acid	$C_7H_6O_2$	000065-85-0	saturated	Xn, Xi		1/1	1/1	3/4	4/4	1/0	1/2	2/4	1/3	2/2	3/3	1/2	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1	
Benzoic acid	$C_7H_6O_2$	000065-85-0	aqueous	Xn, Xi		1/1	1/1	3/4	4/4	1/0	0/0	2/4	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1	
Benzoic acid sodium salt	-> see: Sodium benzoate																														
Benzoic acid aldehyde	-> see: Benzaldehyde																														
Benzoic acid benzyl ester	-> see: Benzyl benzoate																														
Benzoic acid chloride	-> see: Benzoyl chloride																														
Benzoic acid ethyl ester	$C_9H_{10}O_2$	000093-89-0		Xn		2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Benzene	C_6H_6	000071-43-2		F, T	X	3/4	3/4	2/0	4/4	4/4	2/3	1/2	3/4	4/4	4/4	4/4	0/0	0/4	1/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	1/1	1/1	1/1	0/0	
Benzene-1,2-dicarboxylic acid	-> see: Phthalic acid																														
Benzene carboxylic acid	-> see: Benzoic acid																														
Benzene hexachloride (BHC)	-> see: Hexachlorocyclohexane																														
Benzenesulfonic acid	$C_6H_6SO_3$	000098-11-3	saturated	C		1/1	1/1	(4)	(3)	(4)	0/0	(4)	2/4	0/0	1/0	2/0	0/0	0/0	0/0	1/1	1/1	1/4	4/4	1/0	4/4	0/0	3/4	0/0	1/0	0/0	
Benzoyl chloride	C_7H_5ClO	000098-88-4	100 %	C		0/0	3/3	4/4	(4)	0/0	(4)	(3)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	(3)	4/4	0/0	1/0	(2L)	(2L)	0/0	
Benzyl acetate	$C_9H_{10}O_2$	000140-11-4		Xn/Xi		1/1	1/2	(2)	3/4	0/0	1/2	(2)	1/2	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	1/0	4/4	0/0	1/1	1/1	1/1		
Benzyl alcohol	C_7H_8O	000100-51-6		Xn		3/4	4/4	4/4	4/4	0/0	4/4	1/0	4/4	4/4	4/4	2/3	0/0	4/4	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	1/1	1/1	1/1	3/3	
Benzyl benzoate	$C_{14}H_{12}O_2$	000120-51-4		Xn		0/0	0/0	(2)	(3)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Benzylcarbinol	-> see: Phenylethanol																														
Benzyl chloride	C_7H_7Cl	000100-44-7	100 %	T/Xi		0/0	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	(3)	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0	
Benzylether	-> see: Dibenzyl ether																														
Succinic acid	$C_4H_6O_4$	000110-15-6	50 %	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	2/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/0	1/0	1/1	
Succinic acid	$C_4H_6O_4$	000110-15-6	saturated	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	?	
Succinic acid diethyl ester	$C_8H_{14}O_4$	000123-25-1		—		0/0	0/0	(2)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	4/4	4/4	0/0	(1)	(1)	(1)		
Bichromate sulphuric acid	-> see: Chromosulphuric acid																														
Beeswax	—	008012-89-3		—		1/1	1/1	1/1	(1)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	1/1	(1)	(1)		
Beer	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	
Bis(2-chloro-1-methylethyl)-ether	-> ssee: Dichloroisopropyl ether																														
Bis(2-ethylhexyl)-dipate	-> see: Dioctyladipate																														
Bis(2-ethylhexyl)-phthalate	-> see: Diisooctyl phthalate																														
Bis(2-ethylhexyl)-sebacate, sebacic acid bis(2-ethylhexyl)-ester	-> see: Dioctylsebacate																														
Bismuth chloride	$BiCl_3$	007787-60-2		Xi		1/1	1/1	(3)	(2)	(2)	0/0	(4)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(4)	0/0	0/0		
Bismuth subnitrate	$Bi_5O(HO)_9(NO_3)_4$	001304-85-4		O, Xi		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		
Bisulphite	-> see: Sodium bisulphite																														
Bisulphite lye	$NaHSO_3$	??		Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	3/0	0/0	(3)	1/1	1/1	1/1	
Bisulphite lye, containing $S0_2$	$NaHSO_3$	??	saturated	Xn		1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/1	4/4	0/0	(3)	1/1	1/1		
Bitter almond oil	C_7H_6O	090320-35-7		Xn		1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1		Main ingredient: Benzaldehyde
Epsom salt	-> see: Magnesium sulphate																														
Bitumen	—	008052-42-4		—		0/0	0/0	1/0	(2)	(2)	0/0	2/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	(3)	0/0	1/1	(1)	(1)		
Hydrogen cyanide	HCN	000074-90-8	tech. pure	F+, T+	X	1/1	1/1	(3)	4/4	0/0	0/0	4/4	1/1	1/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	1/1	1/0	1/0	1/0	
Hydrogen cyanide	HCN	000074-90-8	aqueous	F+, T+	X	1/1	1/1	(3)	4/4	0/0	(4)	4/4	1/1	1/0	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(1)	1/0	1/0	?	
Lead (II) acetate	$C_4H_6PbO_4$	000301-04-2	aqueous	T, N		1/1	1/1	3/0	1/0	(2)	1/0	1/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	3/0	0/0	4/4	1/1	1/1	1/1	
Lead (II) acetate	$C_4H_6PbO_4$	000301-04-2		T, N		1/1	1/1	3/0	1/0	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	2/2	0/0	4/4	1/1	1/1	1/1	
Lead(II) nitrate	$Pb(NO_3)_2$	010099-74-8	aqueous	O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Lead(II) nitrate	$Pb(NO_3)_2$	010099-74-8		O, T, N		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Lead nitrate	-> see: Lead (II) nitrate																														
Lead stearate	$C_{36}H_{70}PbO_4$	001072-35-1		?		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		No chemical effect expected due to low solubility
Lead sulphate	$PbSO_4$	007446-14-2		(T, N)		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	0/0	(1)	(1)	(1)	0/0	No chemical effect expected due to low solubility
Tetraethyllead	-> see: Tetraethyl lead																														
Lead sugar	-> see: Lead (II) acetate																														
Yellow prussiate of Potash	-> see: Potassium hexacyanoferrate(II)																														
Red prussiate of Potash	-> see: Potassium hexacyanoferrate(III)																														
Borax	-> see: Sodium borate																														
Boric acid	H_3BO_3	010043-35-3	10 %	Xi		1/1	1/1	1/0	1/1	1/0	1/1	2/3	1/1	1/2	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Boric acid	H_3BO_3	010043-35-3	aqueous	Xi		1/1	1/1	3/3	1/1	1/0	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1	
Spirits	-> see: Spirits																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Brake fluid	—	—		?		1/0	1/0	1/0	4/4	0/0	1/1	(3)	1/1	3/0	0/0	1/0	3/0	4/4	0/0	(1)	1/0	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Bromine	Br_2	007726-95-6		T+, C		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	2/4	4/4	4/4	1/2	1/1	1/3	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	4/4	
Bromine benzene	-> see: Bromobenzene																													
Bromobenzene	C_6H_5Br	000108-86-1		Xn	X	3/4	4/4	1/0	4/4	(2)	4/4	1/0	4/4	4/4	4/4	4/4	0/0	0/0	2/4	1/1	1/0	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)		
Bromochloromethane	CH_2BrCl	000074-97-5	100 %	Xn		(4)	(4)	4/4	4/4	1/0	(4)	(3)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/0	(3)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	
Bromine vapours	Br_2	007726-95-6		T		(4)	(4)	4/4	(3)	4/4	(4)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(2-3)	4/4	0/0	(3)	(4)	(4)	4/4	
Bromine potassium	-> see: Potassium bromide																													
Bromomethane	CH_3Br	000074-83-9	tech. pure	T		3/0	4/4	1/0	(3)	0/0	0/0	1/0	4/4	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0	
Bromoform	$CHBr_3$	000075-25-2		T		4/4	4/4	4/4	4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	0/0	0/0	2/3	1/1	(1)	(2)	4/4	(4)	4/4	0/0	(3)	0/0	0/0	0/0	
Bromopental fluoride	BrF_5	007789-30-2		F, T, C		0/0	0/0	4/4	(4)	(4)	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromic acid	$HBrO_3$	007789-31-3	concentrated.	C		0/0	0/0	(4)	(4)	(4)	0/0	4/4	3/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(4)	(2)	4/4	0/0	(4)	(4)	(4)	0/0	
Bromine trifluoride	BrF_3	007787-71-5		T, C		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)		
Bromotrifluoromethane	$CBrF_3$	000075-63-8		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Bromine water	Br_2+H_2O	007726-95-6	saturated	T		4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	4/4	0/0	3/4	0/0	0/0	0/0	0/0	1/1	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	0/0	
Hydrobromic acid	HBr	010035-10-6	40 %	C		1/0	1/1	4/4	4/4	(4)	4/4	4/4	1/1	4/4	0/0	1/1	3/3	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Hydrobromic acid	HBr	010035-10-6	50 %	C		1/1	1/2	4/4	4/4	(4)	4/4	4/4	1/2	4/4	0/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Hydrobromic acid	HBr	010035-10-6	diluted	C		1/1	1/1	4/4	4/4	3/0	4/4	4/4	1/1	4/4	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	0/0	
Butadiene, 1,3-	C_4H_6	000106-99-0		F+, T	X	3/4	4/4	1/0	4/4	1/0	4/4	(2)	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	(1)	(1)	4/4	
Butane	C_4H_{10}	000106-97-8	tech. pure	F+	X	1/0	1/1	1/0	1/0	1/0	1/0	2/0	1/1	4/4	1/0	1/0	3/0	1/0	0/0	1/1	1/1	1/0	4/4	1/0	1/0	0/0	1/1	(1)	(1)	1/1	
Butanal	-> see: Butyraldehyde																													
Butanediol	-> see: Butylene glycol																													
Butanedioic acid	-> see: Succinic acid																													
Butanol	$C_4H_{10}O$	000071-36-3	techn. pure	Xn	X	1/1	1/3	1/0	2/3	1/0	1/2	1/2	1/2	1/2	2/3	2/3	4/4	1/3	1/1	1/1	1/1	1/1	2/0	3/4	1/0	0/0	1/1	(1)	(1)	0/0	
Butanol, secondary	-> see: Butyl alcohol, secondary																													
Butanol, tertiary	-> see: Butyl alcohol, tertiary																													
Butanol-2	-> see: Butyl alcohol, secondary																													
Butanone	-> see: Methyl ethyl ketone																													
Butanoic acid	-> see: Butyric acid																													
Butanetriol	$C_4H_{10}O_3$	—	100 %	—		(4)	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	3/3	4/4	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)		Isomer not specified in the source
Butene	C_4H_8	—	tech. pure	F+	X	4/4	0/0	1/0	(1)	1/0	0/0	1/0	4/4	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/0	1/0	3/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0	Isomer not specified in the source
Butenal, trans-2-	-> see: Crotonaldehyde																													
Butenedioic acid, cis-	-> see: Maleic acid																													
Butoxyethanol, 2-	-> see: Butyl glycol																													
Butter	—	—		—		1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	3/0	1/0	1/1	0/0	(1)	(1)	(1)		
Buttersäure	$C_4H_8O_2$	000107-92-6		C		3/4	4/4	3/3	4/4	0/0	4/4	4/4	4/4	4/4	2/2	2/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/2	1/2	1/1	1/1	
Butyric acid ethyl ester	-> see: Ethyl butyrate																													
Butyl acetate	-> see: Acetic acid butyl ester																													
Butyl acrylate	$C_7H_{12}O_2$	000141-32-2	100 %	Xi	X	1/2	2/3	2/0	4/4	1/3	2/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/0	
Butyl alcohol	-> see: Butanol																													
Butyl alcohol, secondary	$C_4H_{10}O$	000078-92-2		Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	2/2	2/3	2/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		
Butyl alcohol, tertiary	$C_4H_{10}O$	000075-65-0		F, Xn	X	1/1	1/2	(1)	2/3	1/0	1/2	(1)	1/2	1/1	2/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(1)	(2)	0/0	1/1	(1)	(1)		
Butylamine	$C_4H_{11}N$	000109-73-9		F, C	X	0/0	0/0	0/0	(3)	0/0	0/0	3/4	2/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Butyl carbinol	-> see: Amyl alcohol, n-																													
Butyl cellosolve	-> see: Butyl glycol																													
Butylene	-> see: Butene																													
Butylen glycol	$C_4H_{10}O_2$	—	tech. pure	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	4/4	(1)	0/0	1/1	(1)	(1)	0/0	Isomer not specified in the source
Butyl ether	-> see: Dibutyl ether																													
Butyl ethylene	-> see: Hexene, 1-																													
Butyl glycol	$C_4H_{14}O_2$	000111-76-2	100 %	Xn	X	0/0	1/0	1/0	(2)	1/0	0/0	1/0	1/0	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	1/1	3/0	3/4	3/4	0/0	1/1	(1)	(1)	0/0	
Butylphenol	$C_{10}H_{14}O$	—	100 %	Xi		0/0	1/1	(3)	(3)	0/0	(3)	(4)	1/1	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1	1/1	Isomer not specified in the source
Para tertiary butylphenol	$C_{11}H_{15}NO$	000098-54-4	tech. pure	C, Xn		3/0	0/0	(3)	(3)	0/0	(3)	(4)	1/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	3/0	4/4	0/0	1/1	1/1	1/1		
Butyl stearate	-> see: Stearic acid butyl ester																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Butyraldehyde	C_4H_8O	000123-72-8		F, Xn	X	0/0	0/0	(3)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Cadmium bromide	CdBr	007789-42-6		T		1/1	1/1	(3)	(2)	(2)	0/0	(3)	(1)	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	4/4	0/0	0/0		
Calcium acetate	$C_4H_6CaO_4$	000062-54-4	aqueous	—		1/1	1/1	(2)	(1)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(2)	(1)	(1)	0/0	
Calcium bicarbonate	$Ca(HCO_3)_2$	—	saturated	—		1/1	1/1	1/1	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	(2)	(1)	(1)	0/0	
Calcium bisulphite	$Ca(HSO_3)_2$	013780-03-5	saturated	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1	
Calcium bisulphite	$Ca(HSO_3)_2$	013780-03-5	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	3/3	0/0	(3)	1/1	1/3	1/1	
Calcium bromide	$CaBr_2$	007789-41-5		?		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(3)	0/0	0/0	0/0	
Calcium carbide	CaC_2	000075-20-7		F	X	1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0	Carbide, reacts with water to form acetylene - highly flammable!
Calcium carbonate	$CaCO_3$	000471-34-1	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium chlorate	$Ca(ClO_3)_2$	010137-74-3	saturated	O, (T)		0/0	0/0	(3)	(2)	0/0	1/1	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(2)	(1)	(3)	0/0	1/1	(1)	1/0	1/1	
Calcium chloride	$CaCl_2$	010043-52-4	alcoholic	F, Xi		1/0	0/0	4/4	(2)	0/0	1/0	(3)	1/1	0/0	0/0	0/0	4/4	0/0	0/0	1/1	1/0	(1)	(2)	(2)	(2)	0/0	(3)	1/2L	1/2L	1/1	
Calcium chloride	$CaCl_2$	010043-52-4	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/1	(3)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/2L	1/2L	1/1	
Calcium hydrate	-> see: Calcium hydroxide																														
Calcium hydrogen carbonate	-> see: Calcium bicarbonate																														
Calcium hydrogen sulphite	-> see: Calcium bisulphite																														
Calcium hydroxide	CaH_2O_2	001305-62-0	aqueous	(Xi)		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calcium hydroxide	CaH_2O_2	001305-62-0	concentrated.	C		1/1	1/1	1/0	4/4	1/0	1/1	1/1	1/1	2/2	2/2	1/1	1/0	0/0	1/1	1/1	1/1	1/3	1/0	1/1	1/0	0/0	3/4	1/1	1/1	0/0	
Calcium hypochlorite	$Ca(OCl)_2$	007778-54-3	saturated	O, C		1/1	1/1	1/4	3/4	3/0	1/2	1/0	1/1	2/3	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/3	(2)	2/3	4/4	0/0	4/4	3/0	2/0	1/1	Bleaching powder
Calcium hypochlorite	$Ca(OCl)_2$	007778-54-3	aqueous	O, C/Xi		0/0	0/0	4/4	1/0	3/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	4/4	3/0	2/0	1/1	Bleaching powder
Calcium nitrate	$Ca(NO_3)_2$	010124-37-5	50 %	O		1/1	1/1	(2)	1/0	(2)	1/1	(3)	1/1	1/1	0/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	1/0	1/1	1/1	1/1	
Calcium nitrate	$Ca(NO_3)_2$	010124-37-5	aqueous	O		1/1	1/1	(2)	(1)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/1	1/1	1/1	
Calcium oxide	CaO	001305-78-8	Powder	C		1/0	1/1	(2)	(2)	(2)	0/0	0/0	1/1	1/1	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	1/1	1/1		
Calcium phosphate	$Ca_3(PO_4)_2$	007758-87-4	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium phosphate	$Ca_3(PO_4)_2$	007758-87-4		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	No chemical effect expected due to low solubility
Calcium sulphate	$CaSO_4$	007778-18-9	saturated	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	Plaster
Calcium sulphide	CaS	020548-54-3	aqueous	C		0/0	0/0	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/0	(1)	(1)	0/0	
Calcium sulphide	CaS	020548-54-3		C		0/0	3/3	(2)	(2)	0/0	0/0	(1)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Camphor	$C_{10}H_{16}O$	000464-48-2 / -49-2		F, Xn	X	3/4	3/4	(2)	(3)	0/0	0/0	(2)	1/0	1/3	0/0	4/4	4/4	1/1	0/0	(1)	1/0	(3)	4/4	3/4	1/0	0/0	(1)	1/0	1/0	1/0		
Camphor oil	—	008008-51-3		Xn		4/4	4/4	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(2)	(3)	4/4	3/0	1/0	0/0	(1)	(1)	(1)	1/0	made from Cinnamomum Camphora
Paracymene	-> see: Cymene, p-																														
Capronaldehyde	-> see: Hexanal																														
Carbazole	$C_{12}H_9N$	000086-74-8		Xn		1/1	1/1	(2)	4/4	0/0	1/1	(1)	1/1	1/1	4/4	4/4	0/0	4/4	1/1	1/1	(2)	(2)	(2)	(3)	(2)	0/0	(1)	(1)	(1)	0/0	
Carbinol	-> see: Methanol																														
Carbolineum	—	008001-58-9	aqueous	(Xn)		1/0	1/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	(2)	3/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Carbolic acid	-> see: Phenol																														
Carbon disulfide	-> see: Carbon disulphide																														
Carbonyl chloride	-> see: Phosgene																														
Carnauba wax	—	008015-86-9		—		1/1	1/1	1/1	(1)	1/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(3)	(1)	(1)	0/0	1/1	(1)	(1)		
Caesium bromide	CsBr	007787-69-1		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	0/0	0/0		
Cellosolve	-> see: Ethyl glycol																														
Cellosolve acetate	-> see: Ethylene glycol monoethyl ether acetate																														
Cetyl alcohol	$C_{16}H_{34}O$	036653-82-4	100 %	Xi		1/1	1/1	4/4	(2)	1/0	0/0	(1)	1/1	0/0	1/0	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(1)	1/1	1/1		
Cetylic acid	-> see: Palmitic acid																														
Quinine	$C_{20}H_{24}N_2O_2$	000130-95-0		Xn		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)	0/0	
Chlorine	Cl_2	007782-50-5	10 % wet	T		3/4	3/4	4/4	2/3	4/4	2/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	(2)	2/0	3/0	4/4	0/0	4/4	4/4	4/4	0/0	
Chlorine	Cl_2	007782-50-5	97 %	T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0	1/1	
Chlorosulfonic acid	-> see: Chlorosulfunic acid																														
Chlorine-1-propene, 3-	-> see: Allyl chloride																														
Chlor-2-propanone, 1-	-> see: Chloroacetone																														
Chloroacetone	C_3H_5ClO	000078-95-5		(F, Xi)	X	0/0	0/0	(3)	(4)	(4)	(4)	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	0/0	
Chloroacetophenone, p-	C_8H_7ClO	000099-91-2		(Xn)		1/1	1/1	(2)	4/4	0/0	1/1	(2)	1/1	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(2)	(2)	(3)	4/4	4/4	0/0	(1)	0/0	0/0		
Chloral	-> see: Trichloroacetaldehyde																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Chloral hydrate	$C_2H_3Cl_3O_2$	000302-17-0	tech. pure	T/Xi		3/3	3/3	4/4	(3)	(4)	0/0	(3)	3/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	4/4	3/0	3/4	4/4	0/0	4/4	0/0	0/0	0/0	
Chloramine T	$C_7H_7ClNaNSO_2$	000127-65-1	diluted	Xi		1/0	1/0	4/4	1/0	0/0	0/0	(3)	(3)	0/0	0/0	0/0	1/0	0/0	0/0	(1)	1/0	3/4	1/0	4/4	1/0	0/0	3/4	2/2	1/1	0/0	Swimming pool disinfection
Phenyl chloride	-> see: Chlorobenzene																													
Chlorobenzene	C_6H_5Cl	000108-90-7		Xn	X	3/4	3/4	4/4	4/4	1/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/1	(1/1)[1]	(1/1)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chlorine bleach	-> see: Sodium hypochlorite																													
Bromochloromethane	-> see: Bromochloromethane																													
Chlorobutadiene	C_4H_5Cl	000126-99-8		F, Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/4	4/4	0/0	(3)	0/0	0/0		
Chlorobutadiene	-> see: Calcium chloride																													
Chlorodifluoromethane	$CHClF_2$	000075-45-6		N, Xn		0/0	3/0	1/0	3/0	1/0	0/0	1/0	4/4	4/4	4/4	2/0	4/4	0/0	0/0	3/3	1/0	(3)	1/0	4/4	4/4	0/0	(3)	0/0	0/0		
Chlorine dioxide	ClO_2	010049-04-4		E, T		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/0	(2)	4/4	1/0	4/4	0/0	3/4	3/4	3/4		
Chlordodecane	-> see: Lauryl chloride																													
Chloroacetic acid	$C_2H_3ClO_2$	000079-11-8	50 %	T, C		1/3	1/3	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/0	0/0	3/4	0/0	(1)	1/1	1/4	2/0	3/0	4/4	0/0	4/4	2/4	2/4	1/4	
Chloroacetic acid	$C_2H_3ClO_2$	000079-11-8		T, C		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/2	2/4	4/4	3/4	4/4	3/4	1/1	1/1	1/1	4/4	3/0	3/0	4/4	0/0	4/4	4/4	4/4	4/4	
Ethyl monochloroacetate	-> see: Ethyl chloroacetate																													
Chloroethanoic acid methyl ester	-> see: Methyl chloroacetate																													
Chlorethane	C_2H_5Cl	000075-00-3		F+, Xn	X	3/3	3/4	1/0	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/0	4/4	0/0	(3)	(1/1L)[1]	(1/1L)[1]	0/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloroethanol	C_2H_5ClO	000107-07-3	tech. pure	T+		1/1	0/0	4/4	4/4	0/0	0/0	3/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	1/1	1/0	1/3	3/0	4/4	4/4	0/0	(3)	1/0L	1/0L	1/0	
Chloroethyl alcohol, 2-	-> see: Chloroethanol																													
Chloroethylene	C_2H_3Cl	000075-01-4	tech. pure	F+, T	X	0/0	0/0	1/1	(4)	1/1	0/0		(3)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	1/1	3/0	3/0	4/4	0/0	(1)	0/0	0/0	0/0	
Chlorofluoromethane	CH_2ClF	000593-70-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	4/4	0/0	(3)	0/0	0/0		
Chlorine gas	Cl_2	007782-50-5		T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0		
Chlorinated potassium	-> see: Potassium chloride																													
Chlorinated lime	[3 x CaCl(OCl) + Ca(—		aqueous	?		0/0	0/0	4/4	(2)	3/0	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach
Chlorinated lime	[3 x CaCl(OCl) + Ca —			O, C		0/0	0/0	4/4	(2)	3/0	0/0	4/4	1/1	1/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	2/0L	2/0L	1/1	chloride of lime, bleach
Chloromethane	CH_3Cl	000074-87-3	tech. pure	F+, T	X	3/0	2/0	4/4	(3)	0/0	0/0	1/0	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/0	1/0	1/1	4/4	4/4	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]		[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloromethyl	-> see: Chloromethane																													
Chloromethylbenzene	-> see: Benzyl chloride																													
Chloromethyloxirane	-> see: Epichlorohydrin																													
Chloronaphthalene, 1-	$C_{10}H_7Cl$	000090-13-1		Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	4/4	0/0	(2)	1/0	1/0		
Nickel chloride	-> see: Nickel (II) chloride																													
Chloroform	$CHCl_3$	000067-66-3	100 %	Xn		3/4	4/4	3/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	1/1	4/4	3/4	4/4	0/0	(3)	(1/1)[1]	(1/1)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Chloroprene	-> see: Chlorobutadiene																													
Chloropentafluoroethane	C_2ClF_5	000076-15-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Chloropentane, 1-	-> see: Amyl chloride																													
Chlorophenyl methyl ketone, 4-	-> see: Chloroacetophenone, -p																													
Chloropropane, 2-	-> see: Isopropyl chloride																													
Chloropropylene, 3-	-> see: Allyl chloride																													
Chloric acid	$HClO_3$	007790-93-4	1 %	(C)		0/0	1/1	4/4	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/3	1/0	0/0	0/0	0/0	1/1	1/1	3/0	1/1	(3)	0/0	(3)	4/4	4/4	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Chloric acid	$HClO_3$	007790-93-4	10 %	(O), C		1/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	3/0	3/0	4/4	0/0	4/4	4/4	4/4	1/1	
Chloric acid	$HClO_3$	007790-93-4	20 %	(O), C		3/0	1/4	4/4	(3)	(4)	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/0	3/0	3/0	4/4	0/0	4/4	4/4	4/4	?	
Chlorosulfonic acid	$ClHSO_3$	007790-94-5	tech. pure	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	3/0	4/4	4/4	0/0	0/0	1/0	3/4	4/4	4/4	4/4	0/0	3/3	3/4	3/4	1/0	
Chlorotoluene	C_7H_7Cl	—		Xn		0/0	0/0	(2)	4/4	0/0	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(3)	1/0	1/0	1/1	Isomer not specified in the source
Chlorotoluene, alpha-	-> see: Benzyl chloride																													
Chlorine trifluoride	ClF_3	007790-91-2		(O, T)		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(4)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(4)	4/4	(4)	4/4	0/0	(4)	(4)	(4)		
Chlorotrifluoromethane	$CClF_3$	000075-72-9		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	0/0	
Chlorinated water	$Cl_2 \times H_2O$	007782-50-5		(T)		3/0	0/4	4/4	4/4	4/4	4/4	4/4	3/4	4/4	0/0	3/3	3/0	3/3	1/1	(1)	1/1	1/1	3/0	1/0	4/4	0/0	4/4	2/0L	2/0L	0/0	
Hydrochloric acid gas	HCl	007647-01-0	anhydrous	T, C		1/1	0/0	4/4	(3)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	2/2L	2/2L	0/0	
Hydrochloric gas	-> see: Hydrogen acid																													
Hydronium chloride	-> see: Hydrochloric acid																													
Chlorozinc	-> see: Zinc chloride																													
Chromium (III) potassium sulphate dodecahydrate	-> see: Chrome alum																													
Chromium (VI) oxide	-> see: Chromic acid																													
Chrome alum	$KCr(SO_4)_2 \times 12H_2O$	007788-99-0	saturated	Xn		1/1	0/0	(2)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(3)	1/3	1/3	1/1	
Chromium salts	—	—	any	T/Xn		0/0	0/0	0/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	0/0	K	K	K		
Chromic acid	CrO_3	001333-82-0	10 %	O, T, C, N		1/1	1/1	4/4	2/3	3/0	1/1	4/4	1/1	1/1	4/4	1/2	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	1/2	1/2	1/1	
Chromic acid	CrO_3	001333-82-0	20 %	O, T, C, N		0/0	1/3	4/4	3/4	(4)	0/0	4/4	3/3	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	(2)	(2)	1/1	
Chromic acid	CrO_3	001333-82-0	50 %	O, T, C, N		3/4	3/4	4/4	3/4	(4)	2/3	4/4	3/3	3/3	4/4	1/3	1/0	3/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	(3)	2/3	2/3	1/1	
Chromic acid potassium salt	-> see: Potassium chromate																													
Chromosulphuric acid	$CrO_3 + H_2SO_4$	065272-71-1	concentrated	O, T, C, N		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	4/4	4/4	1/1	0/0	1/1	4/4	4/4	1/0	4/4	4/4	4/4	2/3	2/3	0/0	
Chromium trioxide	-> see: Chromic acid																													
2-Hydroxypropane-1,2,3-tricarboxylic acid	-> see: Citric acid																													
Citric acid tributyl ester	-> see: Tributyl citrate																													
Clophen A60	—	011096-82-5		Xn, N		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	4/4	0/0	0/0	0/0	0/0	(1)	(2)	4/4	2/3	4/4	0/0	1/0	1/0	1/0	0/0	ppolychlorinated biphenyls, PCBs; Bayer
Cobalt (II) chloride	$CoCl_2$	007646-79-9	aqueous	Xn		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Cobalt dichloride	-> see: Cobalt (II) chloride																													
Colamine	-> see: Ethanolamine																													
Crotonaldehyde	C_4H_6O	004170-30-3	tech. pure	F, T	X	1/0	0/0	(2)	(4)	0/0	(4)	(2)	1/0	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	1/3	1/0	3/0	4/4	0/0	1/0	1/1	1/1	0/0	
Cumol	-> see: Cumene																													
Cumene	C_9H_{12}	000098-82-8		Xi	X	2/3	3/4	(2)	4/4	0/0	4/4	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Curry	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	3/3	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		could lead to discolouration
Ethyl cyanoacetate	-> see: Ethyl cyanoacetate																													
Cyanide	-> see: Potassium cyanide																													
Cyan potassium	-> see: Potassium cyanide																													
Cyannosodium	-> see: Sodium cyanide																													
Prussic acid	-> see: Hydrogen cyanide																													
Cyclanon	—	—		(Xn, Xi)		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/1	0/0	3/4	(1)	(1)	0/0	Polyquaternary compounds, dyeing auxiliaries; BASF
Cyclohexane	C_6H_{12}	000110-82-7		F	X	3/4	3/4	1/0	3/3	1/0	4/4	1/1	3/4	4/4	4/4	2/3	1/0	1/3	1/2	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Cyclohexanol	$C_6H_{12}O$	000108-93-0	tech. pure	Xn		1/1	1/1	1/1	3/0	0/0	1/2	1/0	1/3	3/3	1/0	1/1	4/4	1/3	0/0	(1)	1/1	1/3	4/4	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Cyclohexanone	$C_6H_{10}O$	000108-94-1	tech. pure	Xn	X	1/3	3/4	1/0	4/4	(4)	3/4	1/0	2/4	4/4	4/4	4/4	4/4	4/4	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0	
Cyclohexylmethane	-> see: Methylcyclohexane																													
Cymene, p-	$C_{10}H_{14}$	000099-87-6		F, Xn/Xi	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Steam	H_2O	—	up to 150°C	?		4	4	4/4	0/0	0	0	(3)	(3)	0	0	0	0	0	0	0/0	1	0	1	3	4/4	0	(1)	1/1	1/1		
DDT (emulsion)	$C_{14}H_9Cl_5$	000050-29-3		T		0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(3)	(3)	0/0	(2)	(2)	(2)	0/0	
Decahydronaphthalene	$C_{10}H_{18}$	000091-17-8		Xn		1/3	3/4	1/0	4/4	3/0	4/4	1/0	3/4	4/4	4/4	1/2	3/0	3/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	(1)	(1)	0/0	
Decalin	-> see: Decahydronaphthalene																													
Decane	$C_{10}H_{22}$	000124-18-5		Xn	X	0/0	0/0	(1)	(2)	(1)	(3)	1/1	(3)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	(1)	(1)		
Decanedioic acid dibenzyl ester	-> see: Dibenzyl sebacate																													
Decanedioic acid dibutyl ester	-> see: Dibutyl sebacate																													
Decanedioic acid diethyl ester	-> see: Diethyl sebacate																													
Dehydroacetic acid	$C_8H_8O_4$	000520-45-6		Xn		0/0	0/0	(3)	(2)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(4)	(1)	(1)		
Densodrin W	—	—	aqueous	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/0	0/0	0/0	1/0	0/0	0/0	0/0	0/0		Hydrophobing agent for leather, silicone derivative; BASF

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Desmodur 44	$C_{15}H_{10}N_2O_2$	000101-68-8		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2)	0/0	4/4	0/0	(1)	(1)	(1)		
Dextrin	$(C_6H_{10}O_5)_n$ x H_2O	009004-53-9	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Dextrose	-> see: Glucose																														
Diacetone alcohol	$C_6H_{12}O_2$	000123-42-2		Xi	X	0/0	0/0	(3)	(3)	0/0	0/0	1/0	2/2	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(2)	(1)	(1)		
Diamide	-> see: Hydrazine																														
Diaminoethane	-> see: Ethylenediamine																														
Diazane	-> see: Hydrazine																														
Dibenzyl ether	$C_{14}H_{14}O$	000103-50-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Dibenzyl sebacate	$C_{24}H_{26}O_4$	??		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	(4)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dibromoethane-1,2	$C_2H_4Br_2$	000106-93-4		T		(4)	(4)	(2)	(4)	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/2	4/4	(3)	4/4	0/0	(3)	1/0L	1/0L	0/0	
Dibromotetrafluoromethane	$C_2Br_2F_4$	000124-73-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0		
Dibutylamine	$C_8H_{19}N$	000111-92-2		Xn	X	0/0	0/0	(2)	(3)	0/0	(3)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Dibutyl ether	$C_8H_{18}O$	000142-96-1	tech. pure	Xi	X	3/4	1/4	(2)	(3)	1/0	(4)	(1)	3/4	0/0	3/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Dibutyl phthalate	$C_{16}H_{22}O_4$	000084-74-2	FR, 80°C	T		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	(1)	0	0	0	4/4	0	0	0	0	0/0	Plasticiser
Dibutyl phthalate	$C_{16}H_{22}O_4$	000084-74-2		T		1/3	3/3	1/0	4/4	1/0	0/2	1/0	2/2	4/4	1/0	4/4	4/4	0/4	1/1	(1)	1/1	1/3	3/0	2/3	4/4	0/0	(1)	1/1	1/1	0/0	Plasticiser
Dibutyl sebacate	$C_{18}H_{34}O_4$	000109-43-3	tech. pure	—		1/0	1/3	1/0	(3)	0/0	0/0	(2)	1/0	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dichlorocide, 1,2-	-> see: Dichlorobenzene, 1,2-																														
Dichlorocide, 1,4-	-> see: Dichlorobenzene, 1,4-																														
Dichlorobenzene, 1,2-	$C_6H_4Cl_2$	000095-50-1		Xn		3/3	3/4	(1)	4/4	0/0	3/4	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/3	(1)	1/1	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Dichlorobenzene, 1,4-	$C_6H_4Cl_2$	000106-46-7		Xn		2/3	3/4	1/0	4/4	0/0	2/3	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/3	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
DCB, o-	-> see: Dichlorobenzene, 1,2-																														
DCB, p-	-> see: Dichlorobenzene, 1,4-																														
Dichlorodifluoromethane	CCl_2F_2	000075-71-8	tech. pure	N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0	
Dichlorodifluoromethane	CCl_2F_2	000075-71-8		N		4/4	3/4	1/0	4/4	0/0	0/0	1/0	4/4	4/4	1/0	2/0	4/4	3/3	0/0	3/3	1/0	3/4	3/0	3/0	3/3	0/0	(3)	0/0	0/0	0/0	
Dichlorodiphenyltrichloroethane	-> see: DDT (emulsion)																														
Dichloroacetic acid	$C_2H_2Cl_2O_2$	000079-43-6	50 %	C		1/1	1/1	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1	
Dichloroacetic acid	$C_2H_2Cl_2O_2$	000079-43-6	tech. pure	C		1/3	3/3	4/4	(4)	4/4	0/0	4/4	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(4)	0/0	0/0	1/1	
Dichloroacetic acid methyl ester	-> see: Methyl dichloroacetate																														
Dichlorethane, 1,2-	-> see: Ethylene chloride																														
Dichlorethene, 1,1-	-> see: Vinylidene chloride																														
Dichloroethylene	$C_2H_2Cl_2$	—	tech. pure	F+, Xn	X	4/4	4/4	3/0	(4)	4/4	(4)	4/4	3/0	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/0	1/1	4/4	3/4	4/4	0/0	(3)	1/1L	1/1L	0/0	Isomer not specified in the source
Dichloroethylene, 1,1-	-> see: Vinylidene chloride																														
Dichlorofluoromethane	$CHCl_2F$	000075-43-4	100 %	N		0/0	3/0	1/0	3/0	0/0	0/0	1/0	4/4	4/4	3/0	4/4	4/4	3/3	0/0	(3)	1/0	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Dichlorohexafluorocyclobutane	$C_4Cl_2F_6$	000356-18-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	(3)	1/0	0/0	(3)	0/0	0/0		
Dichloroisopropyl ether	$C_6H_{12}Cl_2O$	—		(Xn)		(4)	(4)	(2)	(3)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		Isomer not specified in the source
Dichlormethane	CH_2Cl_2	000075-09-2		Xn		4/4	4/4	3/4	4/4	4/4	3/4	3/0	3/4	4/4	4/4	4/4	4/4	4/4	2/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	4/4	(1/1L)[1)]	(1/1L)[1)]	1/1	[1)] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Dichlorpropane	$C_3H_6Cl_2$	—	100 %	F, T/Xn	X	0/0	0/0	(3)	-4	(4)	(4)	(2)	4/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Dichlorotetrafluoroethane	$C_2Cl_2F_4$	000076-14-2		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Dicyclohexylamine (DCHA)	$C_{12}H_{23}N$	000101-83-7		C, Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Dicyclohexyl phthalate	$C_{20}H_{26}O_4$	000084-61-7	tech. pure	(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	(3)	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diesel fuel	—	—		Xn, N		1/3	0/0	1/1	3/3	1/1	0/0	1/1	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	(1)	(1)	0/0	
Diesel oil	—	068334-30-5	100 %	(Xn)		1/3	1/4	1/1	3/3	1/1	0/0	1/1	1/3	3/4	0/0	1/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	(1)	(1)	0/0	
Diethanolamine (DEA)	$C_4H_{11}NO_2$	000111-42-2	100 %	Xi		0/0	1/0	(2)	(3)	0/0	0/0	(2)	1/2	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/3	3/0	(3)	4/4	0/0	1/1	(1)	(1)	0/0	
Diethylamine	$C_4H_{11}N$	000109-89-7	tech. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/2	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/0	1/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Diethylbenzene	$C_{10}H_{14}$	000135-01-3		Xi		3/4	4/4	(1)	3/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Diethylene glycol	$C_4H_{10}O_3$	000111-46-6		T		1/1	1/1	3/0	2/3	0/0	1/1	(2)	1/1	2/2	2/2	3/4	0/0	1/1	1/1	1/1	1/1	(2)	1/0	1/0	3/0	0/0	1/1	(1)	(1)	0/0	
Diethylene glycol ether	—	—		(Xn)		1/1	1/1	3/0	3/4	0/0	1/1	(2)	1/1	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	3/0	(3)	3/3	0/0	(1)	(1)	(1)		
Diethyl ether	-> see: Ethyl ether																														
Diethyl ketone	$C_5H_{10}O$	000096-22-0		F		2/2	2/3	(3)	4/4	(4)	2/3	1/0	2/2	4/4	4/4	4/4	0/0	4/4	2/3	1/1	1/1	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	0/0	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Diethylmalonate	$C_7H_{12}O_4$	000105-53-3		Xi		1/1	1/1	(2)	3/4	0/0	1/2	(2)	1/1	4/4	3/3	2/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(4)	(3)	0/0	(1)	(1)	(1)		
Diethylmethane	-> see: Pentane																													
Diethyl sebacate	$C_{14}H_{26}O_4$	000110-40-7		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diethyl succinate	-> see: Succinic acid diethyl ester																													
Difluorochloroethane	$C_2H_3ClF_2$	000075-68-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluoroethane	$C_2H_2F_2$	000075-37-6		(E), F+		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluoromethane	CH_2F_2	000075-10-5		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0		
Difluorotetrachloroethane	$C_2Cl_4F_2$	000076-12-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	3/0	3/0	0/0	(3)	0/0	0/0		
Diglycol	-> see: Diethylene glycol																													
Diglycolic acid	$C_4H_6O_5$	000110-99-6	aqueous	Xn		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/1	4/4	0/0	3/4	1/4	1/4	1/1	
Diglycolic acid	$C_4H_6O_5$	000110-99-6	30 %	Xn, Xi		1/1	1/1	(3)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/0	1/0	1/1	4/4	0/0	3/4	1/4	1/4	1/1	
Dihexyl phthalate	-> see: Dicyclohexyl phthalate																													
Dihydroxybenzene, 1,3-	-> see: Resorcinol																													
Dihydroxybenzene, 1,4-	-> see: Hydroquinone																													
Dihydroxysuccinic acid	-> see: Tartaric acid																													
Dihydroxydiethylamine	-> see: Diethanolamine																													
Diisobutylene (DIB)	C_8H_{16}	025167-70-8		F	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	1/2	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Diisobutylketone	$C_9H_{18}O$	000108-83-8	tech. pure	Xi	X	1/4	1/3	(3)	(3)	(4)	(4)	1/0	1/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/3	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Diisooctyl phthalate (DOP)	$C_{24}H_{38}O_4$	000117-81-7	tech. pure	Xn		4/4	4/4	1/0	4/4	1/0	1/0	(2)	4/4	4/4	1/0	4/4	4/4	0/0	0/0	1/1	1/0	(2)	3/0	2/3	4/4	0/0	(1)	(1)	(1)		Plasticiser
Diisopropyl ether	-> see: Isopropyl ether																													
Diisopropyl ketone	$C_7H_{14}O$	000565-80-0		F	X	0/0	0/0	(3)	(3)	(4)	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Dimethylamine	C_2H_7N	000124-40-3	tech. pure	F+, Xn	X	1/3	1/3	1/0	4/4	0/0	0/0	(2)	1/3	0/0	0/0	3/4	4/4	0/0	0/0	(1)	1/1	3/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Dimethylaniline	$C_8H_{11}N$	—		T		0/0	0/0	(3)	4/4	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Dimethylbenzene	-> see: Xylene																													
Dimethylcarbinol	-> see: Isopropyl																													
Dimethyl ether	C_2H_6O	000115-10-6	Gas	F+	X	0/0	3/0	1/0	(3)	1/0	0/0	(2)	4/4	4/4	0/0	3/0	4/4	0/0	0/0	0/0	1/0	(3)	3/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Dimethylformamide (DMF)	C_3H_7NO	000068-12-2		T, F	X	1/1	1/3	1	4/4	1/0	1/1	1/2	1/1	4/4	4/4	3/4	0/0	4/4	2/2	1/1	1/1	4/4	2/0	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Dimethyl ketone	-> see: Acetone																													
Dimethylpentanone-3, 2,4-	-> see: Diisopropyl ketone																													
Dimethyl phthalate (DMP)	$C_{10}H_{10}O_4$	000131-11-3	100 %	(Xn)		4/4	1/3	(2)	4/4	0/0	0/0	(2)	2/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(2)	3/0	2/0	4/4	0/0	(1)	(1)	(1)	0/0	Plasticiser
Dimethylpropane	-> see: Pentane																													
Dimethyl sulphoxide (DMSO)	C_2H_6SO	000067-68-5		Xi		1/1	1/1	(2)	4/4	0/0	1/1	1/0	1/1	1/2	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(3)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		
Disodium hydrogen phosphate	-> see: Disodium phosphate																													
Disodium phosphate	Na_2HPO_4	007558-79-4		(Xi)		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	(1)	1/1	1/1	0/0	
Disodium sulphate	-> see: Sodium sulphate																													
Dinonyl phthalate (DNP)	$C_{26}H_{42}O_4$	000084-76-4	tech. pure	Xn		3/0	0/0	(2)	3/0	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioctyladipate	$C_{22}H_{42}O_4$	000103-23-1		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioctyl phthalate	-> see: Diisooctyl phthalate																													
Dioctyl sebacate	$C_{26}H_{50}O_4$	002432-87-3		—		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)		Plasticiser
Dioxane	$C_4H_8O_2$	000123-91-1		F, Xn	X	2/2	2/3	1/0	4/4	1/0	2/3	1/2	3/3	4/4	2/3	3/4	4/4	4/4	1/3	1/1	1/1	3/3	2/0	4/4	4/4	0/0	1/1	1/0	1/0	0/0	
Dioxane, 1,4-	-> see: Dioxane																													
Dipentene	-> see: Limonene, DL-																													
Dipentyl phthalate	-> see: Phthalic acid amyl ester																													
Diphenylamine	$C_{12}H_{11}N$	000122-39-4		T		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	0/0	
Diphenyleneimine	-> see: Carbazole																													
Diphenyl ether	$C_{12}H_{10}O$	000101-84-8		Xn/Xi		0/0	1/0	3/0	(3)	(4)	0/0	1/1	4/4	4/4	0/0	0/0	4/4	4/4	0/0	(1)	1/0	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Diphenylmethane diisocyanate (MDI)	-> see: Desmodur 44																													
Diphenyl oxide	-> see: Diphenyl ether																													
Diphosphorus pentoxide	-> see: Phosphorus pentoxide																													
Diphyl	—	008004-13-5		?		0/0	0/0	1/1	(3)	4/4	0/0	1/1	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)		Mixture of diphenyl and diphenyl ether; Bayer
Dipropylene glycol	$C_6H_{14}O_3$	025265-71-8		Xi		1/1	1/1	(2)	2/3	0/0	1/1	1/0	1/1	1/1	2/2	2/3	0/0	0/0	1/1	1/1	(1)	(2)	4/4	3/0	3/3	0/0	(1)	(1)	(1)		
Dipropyl ketone	$C_7H_{14}O$	000123-19-3		—	X	0/0	0/0	(3)	(4)	(4)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Dipropylmethane, n-	-> see: Heptane, n-																													
Di-sulphur dichloride	-> see: Sulphur chloride																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals		
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Dinitrogen tetroxide	-> see: Nitrogen tetroxide																													
Disulphite	-> see: Sodium disulphite																													
Divinylensulphide	-> see: Thiophene																													
Dodecanol	-> see: Lauryl alcohol																													
Dodecyl alcohol	-> see: Lauryl alcohol																													
Dodecyl chloride	-> see: Lauryl chloride																													
Dolcymene	-> see: Cymene, p-																													
Eau de Labarraque	-> see: Sodium hypochlorite																													
Edetic acid	-> see: Ethylenediaminetetraacetic acid																													
Iron (II) ammonium sulphate	-> see: Ammonium iron (II) sulphate																													
Iron (II) chloride	$FeCl_2$	007758-94-3	saturated	Xn		1/1	1/1	3/0	1/0	(2)	1/0	(3)	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	(1)	0/0	4/4	(2)	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7	saturated	(Xn)		1/1	1/1	(2)	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7	aqueous	(Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Iron (II) sulphate	$FeSO_4$	007720-78-7		Xn		1/1	1/1	(2)	1/0	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/0	(1)	0/0	4/4	1/1	1/1	1/1	
Iron (III) chloride	$FeCl_3$	007705-08-0	saturated	Xn		1/1	1/1	3/0	1/0	0/0	1/0	4/4	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	4/4	4/4	4/4	1/1	
Iron (III) nitrate	-> see: Ferric nitrate																													
Iron (III) sulphate	$Fe_2(SO_4)_3$	010028-22-5	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	1/1	1/1	1/1	
Iron alum	-> see: Ammonium iron (III) sulphate																													
Iron ammonium alum	-> see: Ammonium iron (III) sulphate																													
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	aqueous	(O, Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	saturated	O, Xn		1/1	1/1	1/0	1/0	0/0	1/0	(3)	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1	
Iron vitriol	-> see: Iron (II) sulphate																													
Glacial acetic acid	-> see: Acetic acid																													
Elaol	-> see: Dibutyl phthalate																													
Emulsifiers	—	—		?		0/0	0/0	(2)	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(3)	0/0	0/0	K	K		
Developer fluids	—	—		?		1/1	1/1	4/4	1/0	1/0	0/0	1/0	1/1	0/0	1/0	1/1	1/0	0/0	0/0	0/0	1/1	(1)	2/0	1/0	3/3	0/0	1/1	1/0	1/0	0/0	
Limescale	—	—	10% in Water	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Epichlorohydrin	C_3H_5ClO	000106-89-8	100 %	F, T	X	1/0	1/0	4/4	(4)	0/0	(4)	1/0	2/2	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(3)	3/0	4/4	4/4	0/0	(3)	0/0	0/0	0/0	
Epoxypropane	-> see: Propylene oxide																													
Epsom salt	-> see: Magnesium sulphate																													
Natural gas	—	—		F+	X	0/0	0/0	01/0	1/0	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	0/0	mainly methane
Peanut oil	—	008002-03-7		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Crude oil / petroleum	—	008002-05-9		(Xn)		0/0	0/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/3	0/0	(1)	(1)	(1)	0/0	Kerosene, lamp oil
Vinegar	$C_2H_4O_2$	000064-19-7		(Xi)		1/1	1/3	4/4	1/2	1/1	1/0	1/3	1/1	1/0	1/0	1/0	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/2	1/1	Wine vinegar, acetic acid
Acetic ester	-> see: Ethyl acetate																													
Acetic acid	$C_2H_4O_2$	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	90%	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1	1/1	
Acetic acid	$C_2H_4O_2$	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1	1/1	
Acetic acid Silver salt	-> see: Silver acetate																													
Acetic alumina	$C_4H_7AlO_5 \times H_2O$	000142-03-0	saturated	Xi		1/1	1/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	1/0	1/1	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1		
Acetic acid allyl ester	-> see: Allyl acetate																													
Acetic acid amide	-> see: Acetamide																													
Acetic anhydride	$C_4H_6O_3$	000108-24-7	tech.pure	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1	1/1	
Acetic acid benzyl ester	-> see: Benzyl acetate																													
Acetic acid butyl ester	$C_6H_{12}O_2$	000123-86-4	100 %	—	X	2/2	2/3	1/0	4/4	3/0	3/3	(2)	3/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	3/0	4/4	4/4	0/0	1/1	(1)	(1)	4/4	
Acetic acid chloride	-> see: Acetyl chloride																													
Acetic acid ethyl ester	-> see: Ethyl acetate																													
Acetic acid isobutyl ester	-> see: Isobutyl acetate																													
Acetic acid isopropyl ester	-> see: Isopropyl acetate																													
Acetic acid methyl ester	$C_3H_6O_2$	000079-20-9	tech. pure	F	X	1/0	1/1	1/0	4/4	3/0	(4)	2/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0	
Acetic acid-n-amyl ester	-> see: Amyl acetate, n-																													
Acetic acid pentyl ester	-> see: Amyl acetate, n-																													
Acetic acid propyl ester	-> see: Propyl acetate																													
Acetic acid vinyl ester	-> see: Vinyl acetate																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ethanal	-> see: Acetaldehyde																													
Ethane carboxylic acid	-> see: Propionic acid																													
Ethanediamine	-> see: Ethylenediamine																													
Ethanedicarboxylic acid	-> see: Succinic acid																													
Ethanediol	-> see: Ethylene glycol																													
Ethanedioic acid	-> see: Oxalic acid																													
Ethanol	C_2H_6O	000064-17-5	40 %	—	X	1/1	1/2	1/0	1/2	1/1	1/2	1/2	1/1	2/3	1/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Ethanol	C_2H_6O	000064-17-5	50 %	—	X	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	
Ethanol	C_2H_6O	000064-17-5	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	
Ethanolamine	C_2H_7NO	000141-43-5		Xn/Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/2	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Ethanoic acid	-> see: Acetic acid																													
Ethanethiol	C_2H_6S	000075-08-1		F, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ethene	-> see: Ethylene																													
Ether	-> see: Ethyl ether																													
Ethyne	-> see: Acetylene																													
Ethinylcarbiol	-> see: Propargyl alcohol																													
Ethoxyacetanilide, 4-	-> see: Phenacetin																													
Ethoxyethanol	-> see: Ethyl glycol																													
Ethoxyethyl acetate, 2-	-> see: Ethylene glycol monoethyl ether acetate																													
Ethyl(hydroxymethyl)-propanediol	-> see: Trimethylolpropane																													
Ethyl acetate	$C_4H_8O_2$	000141-78-6	100 %	F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/1	1/3	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	3/3	3/0	4/4	4/4	0/0	1/1	(1)	(1)	1/0	
Ethyl acrylate	$C_5H_8O_2$	000140-88-5	100 %	F, Xn	X	4/4	4/4	1/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	3/0	4/4	4/4	4/4	0/0	(1)	(1)	(1)	1/0	
Ethyl alcohol	-> see: Ethanol																													
Ethylbenzol	-> see: Ethylbenzene																													
Ethyl benzoate	-> see: Benzoic acid ethyl ester																													
Ethylbenzene	C_8H_{10}	000100-41-4		F, Xn	X	2/3	3/4	(2)	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	1/1	4/4	(2)	4/4	0/0	(1)	(1)	(1)	0/0	
Ethyl butyrate	$C_6H_{12}O_2$	000105-54-4		F	X	2/3	2/4	(2)	4/4	0/0	3/4	(2)	2/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethylcarbinol	-> see: Propanol																													
Ethyl cellosolve	-> see: Ethyl glycol																													
Ethyl chloroacetate	$C_4H_7ClO_2$	000105-39-5	tech. pure	T/Xi		1/1	1/1	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/4	3/4	0/0	0/0	(1)	1/1	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Ethyl chloride	-> see: Chlorethane																													
Ethyl cyanoacetate	$C_5H_7NO_2$	000105-56-6		Xn/Xi		1/1	1/1	0/0	3/4	0/0	1/1	(2)	1/1	2/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Ethylene	C_2H_4	000074-85-1		F+	X	0/0	0/0	1/0	(2)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(2)	(3)	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Ethylene(di)bromide	-> see: Dibromoethane-1,2																													
Ethylene(di)chloride	-> see: Dichloroethane-1,2																													
Ethylene chlorohydrin	-> see: Chloroethanol																													
Ethylene chloride	$C_2H_4Cl_2$	—		F, T	X	3/3	2/4	3/0	4/4	4/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/3	1/1L	1/1L	0/0	Isomer not specified in the source
Ethylenediamine	$C_2H_8N_2$	000107-15-3	tech. pure	C, Xn	X	1/1	1/3	1/0	(3)	0/0	1/0	1/0	1/1	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/4	1/0	4/4	3/3	0/0	1/1	(1)	(1)	0/0	
Ethylenediaminetetraacetic acid (EDTA)	$C_{10}H_{16}N_2O_8$	000060-00-4		Xi		1/1	1/1	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(3)	0/0	0/0	0/0	
Ethylene dichloride	-> see: Ethylene chloride																													
Ethylenedinitrilotetraacetic acid	-> see: Ethylenediaminetetraacetic acid																													
Ethylene glycol	$C_2H_6O_2$	000107-21-1		Xn		1/1	1/1	3/3	2/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	1/1	
Ethylene glycol ethyl ether	-> see: Ethyl glycol																													
Ethylene glycol monobutyl ether	-> see: Butyl glycol																													
Ethylene glycol monobutyl ether	-> see: Ethyl glycol																													
Ethylene glycol monoethyl ether acetate	$C_6H_{12}O_3$	000115-15-9		Xn	X	1/1	1/2	0/0	3/4	0/0	1/2	(2)	1/2	4/4	4/4	3/4	0/0	0/0	1/2	1/1	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Ethylene glycol monomethyl ether	-> see: Methyl glycol																													
Ethylene oxide	C_2H_4O	000075-21-8		F+, T	X	2/3	3/3	3/0	3/4	1/0	3/4	1/0	3/3	4/4	1/1	3/4	0/0	0/0	1/1	1/1	(1)	1/1	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Ethylene tetrachloride	-> see: Perchloroethylene																													
Ethylene trichloride	-> see: Trichloroethylene																													
Ethylethanamine, N-	-> see: Diethylamine																													
Ethyl ether	$C_4H_{10}O$	000060-29-7	tech. pure	F+, Xn	X	3/4	4/4	1/1	4/4	1/0	4/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Ethyl formate	$C_3H_6O_2$	000109-94-4		F	X	0/0	0/0	0/0	(4)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethyl glycol	$C_4H_{10}O_2$	000110-80-5	100 %	T	X	0/0	4/4	(3)	(2)	0/0	0/0	1/0	2/4	4/4	1/0	4/4	4/4	4/4	0/0	1/1	1/0	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Ethyl glycol acetate	-> see: Ethylene glycol monoethyl ether acetate																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Ethylhexanol-1	$C_8H_{18}O$	000104-76-7		Xn/Xi		0/0	1/3	(2)	(2)	(1)	1/0	1/0	1/0	3/0	0/0	1/0	4/4	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	
Ethyl lactate	$C_5H_{10}O_3$	000097-64-3		—	X	1/1	1/1	(2)	3/4	0/0	1/1	(2)	1/1	3/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	3/0	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Ethyl malonate	-> see: Diethylmalonate																													
Ethyl mercaptan	-> see: Ethanethiol																													
Ethyl methyl ketone	-> see: Methyl ethyl ketone																													
Ethyl silicate	-> see: Tetraethylorthosilicate																													
Eucalyptus oil	—	008000-48-8		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Desiccator grease	—	—		—		0/0	1/3	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(2)	(2)	0/0	(1)	(1)	(1)	0/0	
Ferrichloride	-> see: Iron (III) chloride																													
Potassium hexacyanoferrate(III)	$C_6FeK_3N_6$	013746-66-2	any	Xn		1/1	1/1	1/0	(1)	(1)	0/0	2/0	1/1	1/1	0/0	1/3	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1	1/1	
Ferrous chloride	-> see: Iron (II) chloride																													
Potassium hexacyanoferrate(II)	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	saturated	—		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(1)	1/1	1/1		
Potassium hexacyanoferrate(II)	$C_6FeK_4N_6 \times 3H_2O$	014459-95-1	diluted	—		1/0	1/1	1/0	(1)	(1)	0/0	2/0	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1		
Fat/Grease, mineral	—	—		(—)		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	(1)	1/0	0/0	(1)	1/1	1/1		
Fat/Grease, vegetable	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fat/Grease, animal	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Fatty/Greasy alcohol sulphonates	—	—	aqueous	(Xn, Xi)		1/1	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	1/1	0/0	3/4	1/0	1/0	0/0	Fatty alcohol sulphates, wetting agents/surfactants
Fat/Grease, edible oil	—	—		—		0/0	1/0	1/0	1/0	1/0	1/0	1/1	3/0	0/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Fatty acid C16	-> see: Palmitic acid																													
Spruce needle oil	—	008008-80-8		?		1/2	2/4	(2)	2/3	0/0	2/3	(2)	1/2	4/4	3/3	3/4	0/0	3/4	1/2	1/1	(1)	(2)	4/4	1/0	3/3	0/0	(1)	(1)	(1)		Pinus sylvestris
Fish oil	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/4	1/0	1/0	0/0	(1)	(1)	(1)		
Fixing salt	-> see: Sodium thiosulphate																													
Aircraft engine fuels (JP)	—	—		(Xn)		0/0	0/0	(1)	(3)	0/0	0/0	1/0	1/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	1/0	1/0	0/0	(1)	(1)	(1)		
Fluid 101, 100°C	—	—		?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	3	0	0	0	0		Brake fluid, polyglycol base
Fluorine	F_2	007782-41-4		O, T+, C+		4/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	4/4	4/4	3/0	4/4	0/0	4/4	(4)	(4)	0/0	
Fluorammonium	-> see: Ammonium fluoride																													
Fluorobenzene	C_6H_5F	000462-06-6		F, (Xn)	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0		
Fluorochloroalkanes (FCKW)	—	—		N		0/0	0/0	(2)	(3)	0/0	0/0	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(3)	(3)	0/0	(3)	0/0	(3)	0/0	0/0		Resistance varies depending on type
Fluorides	—	—		T		1/1	1/1	(2)	1/1	(2)	1/1	(1)	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	(1)	0/0	0/0	K	K		
Fluoropotassium	-> see: Potassium fluoride																													
Fluorosilicic acid	-> see: Silicofluoric acid																													
Fluorocarbons (FKW)	—	—		?		0/0	0/4	(2)	(3)	(2)	0/0	(2)	(3)	4/4	0/0	0/0	0/0	0/4	1/1	0/0	1/1	(3)	(3)	(3)	(3)	0/0	(1)	0/0	0/0		Resistance varies depending on type
Fluorosilicic acid	-> see: Silicofluoric acid																													
Fluorotrichloromethane	-> see: Trichlorofluoromethane																													
Hydrogen fluoride	HF	007664-39-3	anhydrous	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)		Hydrofluoric acid, anhydrous
Hydrogen fluoride solution	-> see: Hydrofluoric acid																													
Hydrofluoric acid	-> see: Hydrofluoric acid																													
Liquid soaps	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(2)	(2)	0/0	(3)	0/0	0/0		
Hydrofluoric acid	HF	007664-39-3	4 %	T, C		1/1	1/2	4/4	2/3	4/4	1/2	4/4	1/2	2/3	2/3	2/3	0/0	0/0	1/1	1/1	1/1	1/1	(3)	1/3	(2)	0/0	4/4	0/0	0/0	?	
Hydrofluoric acid	HF	007664-39-3	50 %	T+, C		1/1	1/1	4/4	4/4	4/4	1/1	4/4	1/1	4/4	3/4	2/3	2/0	3/3	1/1	1/1	1/1	1/1	3/4	1/3	3/4	0/0	4/4	4/4	4/4	?	
Hydrofluoric acid	HF	007664-39-3	70 %	T+, C		0/0	1/3	4/4	4/4	4/4	0/0	4/4	1/3	4/4	4/4	1/4	3/0	0/0	0/0	(1)	1/1	1/1	3/4	(3)	4/4	0/0	4/4	4/4	4/4	?	
Hydrofluoric acid	HF	007664-39-3	100 %	T+, C+		0/0	0/0	4/4	4/4	4/4	0/0	4/4	(2)	0/0	4/4	0/0	0/0	0/0	0/0	(1)	1/0	0/0	3/4	(3)	4/4	0/0	4/4	(3)	(3)	?	
Hydrofluoric acid, anhydrous	-> see: Hydrogen fluoride																													
Formaldehyde solution	CH_2O	000050-00-0	10 %	Xn		1/1	1/1	3/3	1/2	1/0	1/2	1/2	1/1	3/4	2/3	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/0	3/0	(2)	0/0	1/1	1/1	1/1	1/1	
Formaldehyde solution	CH_2O	000050-00-0	30 %	T		1/1	1/1	3/3	1/2	1/0	0/0	1/2	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	1/1	1/1	
Formaldehyde solution	CH_2O	000050-00-0	40 %	T		1/2	2/3	1/3	1/2	1/0	1/2	1/2	1/2	4/4	2/3	2/3	3/3	0/4	1/1	1/1	1/1	1/1	1/0	3/0	(3)	0/0	1/1	1/1	1/1	1/1	
Formalin	-> see: Formaldehyde solution																													
Formamide	CH_3NO	000075-12-7	tech. pure	T/Xi		1/1	1/1	1/0	(3)	0/0	0/0	1/0	1/1	1/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	3/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	
Formin	-> see: Hexamethylenetetramine																													
Formylic acid	-> see: Formic acid																													
Photo emulsions	—	—		?		1/0	0/0	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(1)	0/0	(2)	0/0	0/0		
Photo developers	—	—		?		1/3	1/1	4/4	(2)	1/0	0/0	1/3	1/2	0/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/1	1/0	1/0	1/1	
Photo fixing baths	—	—		?		1/0	1/1	1/0	(2)	0/0	0/0	1/0	1/1	0/0	0/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/0	1/0		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Freon 11	-> see: Trichlorofluoromethane																													
Freon 112	-> see: Difluorotetrachloroethane																													
Freon 113	-> see: Trichlorotrifluoroethane																													
Freon 114	-> see: Dichlorotetrafluoroethane																													
Freon 114 B2	-> see: Dibromotetrafluoromethane																													
Freon 115	-> see: Chloropentafluoroethane																													
Freon 12	-> see: Dichlorodifluoromethane																													
Freon 13	-> see: Chlorotrifluoromethane																													
Freon 13 B1	-> see: Bromotrifluoromethane																													
Freon 14	-> see: Tetrafluoromethane																													
Freon 142b	-> see: Difluorochloroethane																													
Freon 152a	-> see: Difluoroethane																													
Freon 21	-> see: Dichlorofluoromethane																													
Freon 218	-> see: Perfluoropropane																													
Freon 22	-> see: Chlorodifluoromethane																													
Freon 31	-> see: Chlorofluoromethane																													
Freon 32	-> see: Difluoromethane																													
Freon C 318	-> see: Octafluorocyclobutane																													
Freon C316	-> see: Dichlorohexafluorocyclobutane																													
Frigen 12	-> see: Dichlorodifluoromethane																													
Frigen 21	-> see: Dichlorofluoromethane																													
Frigen 22	-> see: Chlorodifluoromethane																													
Antifreeze (KFZ)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1	1/1	Glycol-water mixtures
Fruit juices	—	—		—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(2)	1/1	1/1	1/1	
Fruit sugar	-> see: Fructose																													
Fructose	$C_6H_{12}O_6$	000057-48-7	any	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Furan	C_4H_4O	000110-00-9		F+, T+	X	0/0	0/0	(3)	4/4	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Furanal	-> see: Furfural																													
Furancarbinol, 2-	-> see: Furfuryl alcohol																													
Furanmethanol, 2-	-> see: Furfuryl alcohol																													
Furfurol	-> see: Furfural																													
Furfural alcohol	-> see: Furfuryl alcohol																													
Furfuran	-> see: Furan																													
Furfural	$C_5H_4O_2$	000098-01-1		T		1/3	3/4	3/3	(3)	1/0	0/0	2/0	4/4	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	1/2	3/0	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Furfuryl alcohol	$C_5H_6O_2$	000098-00-0	tech. pure	Xn		1/1	1/3	1/0	(3)	1/0	0/0	1/0	1/3	0/0	4/4	4/4	4/4	3/4	0/0	(1)	1/1	1/3	3/0	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Furylaldehyde, 2-	-> see: Furfural																													
Furylmethanal, 2-	-> see: Furfural																													
Gallotannin	-> see: Tannin																													
Gallic acid	$C_7H_6O_5 \times H_2O$	000149-91-7		Xi		1/1	1/1	1/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/4	3/0	1/0	3/0	0/0	1/0	1/1	1/1	1/1	
Fermentation amyl alcohol	-> see: Isoamyl alcohol																													
Fermentation mash	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	(1)	1/0	4/4	0/0	(2)	(1)	(1)	0/0	
Gas oil (straight-run)	—	—		(Xn)		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Gasoline	—	008006-61-9		(F, Xn)	X	0/0	0/0	(1)	3/4	(2)	0/0	1/2	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/0	0/0	1/1	(1)	(1)		
Gas water	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(2)	0/0	(2)	0/0	0/0		
Gelatine	—	009000-70-8	any	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Genantin	—	—		Xn		0/0	0/0	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		Antifreeze, basis glycol; Clariant
Tanning extracts, vegetable	—	—	tech. common	?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Tanning extracts	—	—		?		1/1	1/1	1/0	(3)	0/0	0/0	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Tannic acid	-> see: Tannin																													
Gear oil, EP (hypoid), 110°C	—	—		?		0	0	1	1	1	0	4	(3)	0	0	0	0	0	0	0	(2)	0	4/4	0	4/4	0	(1)	1	1		
Plaster	-> see: Calcium sulphate																													
Glauber's salt	-> see: Sodium sulphate																													
Glucaric acid	-> see: Sugar acid																													
Glucose	$C_6H_{12}O_6$	000050-99-7	any	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Glucose syrup	-> see: Starch syrup																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Glycerine	$C_3H_8O_3$	000056-81-5	any	Xi		1/1	1/1	1/0	3/3	1/0	1/1	1/0	1/1	1/1	1/1	1/1	2/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Glycerol trinitrate	-> see: Nitroglycerin																													
Glycine	-> see: Aminoacetic acid																													
Glycol	-> see: Ethylene glycol																													
Glycol dinitrate	-> see: Nitroglycol																													
Glycolic acid	$C_2H_4O_3$	000079-14-1	37 %	Xn		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	2/0	1/0	0/0	1/0	1/3	1/3	1/1	
Glycolic acid	$C_2H_4O_3$	000079-14-1	70 %	C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(2)	1/0	3/0	(2)	0/0	(2)	1/3	1/3	1/1	
Glycocoll	-> see: Aminoacetic acid																													
Glycol chlorohydrin	-> see: Chloroethanol																													
Glysantin	—	—		Xn		1/1	1/1	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1		Antifreeze, basis glycol; BASF
Glycerol triacetate	-> see: Triacetin																													
Firedamp	—	—		F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		mainly methane
Uric acid	$C_5H_4N_4O_3$	000069-93-2		Xi		1/1	1/1	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	4/4	1/1	1/1	0/0	
Urea	CH_4N_2O	000057-13-6	aqueous	Xi		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, carbamide, etc.
Urea	CH_4N_2O	000057-13-6		Xi		1/1	1/1	1/0	1/1	1/0	1/2	1/1	1/1	1/2	3/3	2/4	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	1/1	Urea, carbamide, etc.
HD oil engine oil, aromatics-free	—	—		?		1/0	1/3	1/0	1/1	1/1	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	(1)	3/3	0/0	1/1	1/1	1/1		
Yeast	—	—	any	—		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	(1)	(1)		
Heating oil	—	—		Xn		3/3	3/4	1/0	3/3	1/0	2/3	1/1	1/3	3/4	1/2	1/1	3/3	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Helium	He	007440-59-7		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	1/0	1/0	1/0	0/0	1/1	1/1	1/1		
Hendecanol	-> see: Undecyl alcohol																													
Henkel-P3-solution	—	—		?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/0	0/0	0/0	1/1	1/1		Cleaning agents
Heptan, n-	C_7H_{16}	000142-82-5		F, Xn	X	2/3	3/4	1/0	1/2	1/0	3/3	1/2	2/4	4/4	1/2	2/3	4/4	1/0	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Heptanol, 1-	$C_7H_{16}O$	000111-70-6		Xn		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	(1)	(1)	(1)		
Heptanon	$C_7H_{14}O$	—		(Xn)	X	0/0	0/0	(3)	(4)	(4)	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(4)	(4)	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Heptanon-4	-> see: Dipropylketone																													
Heptyl alcohol	-> see: Heptanol, 1-																													
Hexachlorobenzene (HCB)	C_6Cl_6	000118-74-1		T		0/0	0/0	(3)	(4)	0/0	(4)	1/0	(3)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(2)	0/0	4/4	(3)	4/4	0/0	(1)	0/0	0/0		
Hexachlorobutadiene (HCBD)	C_4Cl_6	000087-68-3		T		0/0	0/0	(3)	4/4	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexachlorocyclohexane (HCH)	$C_6H_6Cl_6$	000319-84-6		T		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Hexadecanol	-> see: Cetyl alcohol																													
Hexadecanoic acid	-> see: Palmitic acid																													
Hexadecyl alcohol	-> see: Cetyl alcohol																													
Hexahydrobenzene	-> see: Cyclohexan																													
Hexahydrophenol	-> see: Cyclohexanol																													
Hexahydropyridine	-> see: Piperidine																													
Hexahydrotoluene	-> see: Methylcyclohexane																													
Hexaldehyde	-> see: Hexanal																													
Hexamethylenetetramine	$C_6H_{12}N_4$	000100-97-0		F, Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	1/1	1/1	0/0	
Hexamine	-> see: Hexamethylenetetramine																													
Hexane, n-	C_6H_{14}	000110-54-3		F, Xn	X	2/3	4/4	1/0	(2)	1/0	3/4	1/1	2/3	4/4	1/2	2/4	4/4	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Hexanal	$C_6H_{12}O$	000066-25-1		F, Xi	X	0/0	0/0	0/0	(4)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Hexanedioic acid	-> see: Adipic acid																													
Hexanol, (1-)	$C_6H_{14}O$	000111-27-3		Xn		1/0	1/0	(2)	(2)	(1)	0/0	(1)	1/2	0/0	3/0	1/0	3/0	1/3	0/0	(1)	1/0	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Hexanone-2	-> see: Methyl butyl ketone																													
Hexanetriol	$C_6H_{14}O_3$	—	100 %	?		1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	1/1	3/3	1/1	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Hexen, 1-	C_6H_{12}	000592-41-6		F, Xn	X	0/0	0/0	1/0	(2)	(1)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Hexylaldehyde	-> see: Hexanal																													
Hexyl alcohol	-> see: Hexanol, (1-)																													
Hexylene	-> see: Hexen, 1-																													
Staghorn salt	-> see: Ammonium carbonate																													
Wood alcohol	-> see: Methanol																													
Wood oil	—	008001-20-5		—		0/0	0/0	(1)	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	1/1	(1)	(1)		
Wood tar oil	-> see: Creosote																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Honey	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	0/0	(1)	(1)	(1)	0/0	
Gibbsite	-> see: Aluminium hydroxide																													
Hydraulic fluids, HFA	—	—	50°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFB	—	—	50°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0		
Hydraulic fluids, HFC	—	—	60°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	0	0	1	0	(2)	0	0		
Hydraulic fluids, HFD-R	—	—	100°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic fluids, HFD-S	—	—	100°C	?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	4	0	(2)	0	0		
Hydraulic oils (mineral oil based)	—	—		?		0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	(1)	1/0	0/0	1/1	1/1	1/1		
Hydrazine	N_2H_4	000302-01-2	10 %	T	X	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	1/1	
Hydrazine hydrate	N_2H_6O	010217-52-4	aqueous	(T, C)	(X)	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	0/0	
Hydrazinium hydroxide	-> see: Hydrazine hydrate																													
Hydrazinobenzene	-> see: Phenylhydrazine																													
Hydroquinone	$C_6H_6O_2$	000123-31-9	saturated	Xn		0/0	1/3	4/4	(3)	1/0	0/0	(3)	1/0	4/4	0/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	4/4	4/4	0/0	(1)	1/0	1/0	0/0	
Hydrosulphite	-> see: Sodium dithionite																													
Hydroxy-4-methyl-2-pentanone, 4-	-> see: Diacetone alcohol																													
Hydroxybenzaldehyde, 2-	-> see: Salicylaldehyde																													
Hydroxybenzoic acid, 2-	-> see: Salicylic acid																													
Hydroxybenzene	-> see: Phenol																													
Hydroxybenzenecarboxylic acid, 2-	-> see: Salicylic acid																													
Hydroxyacetic acid	-> see: Glycolic acid																													
Hydroxylamine sulphate	-> see: Hydroxylammonium sulphate																													
Hydroxylammonium sulphate	$H_8N_2SO_6$	010039-54-0	12 %	Xn		1/1	1/1	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	1/1	
Hydroxylammonium sulphate	$H_8N_2SO_6$	010039-54-0	any	Xn		1/1	0/0	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/3	0/0	(4)	1/1	1/1	1/1	
Hydroxymethoxybutane	-> see: Methoxybutanol																													
Hydroxymethylfuran, 2-	-> see: Furfuryl alcohol																													
Hydroxymethylfurfural, 5-	-> see: Oxymethylfurfurol, 5-																													
Hydroxymethyl tetrahydrofuran, 2-	-> see: Tetrahydrofurfuryl alcohol																													
Hydroxypropane	-> see: Propanol																													
Hydroxypropane, 2-	-> see: Isopropyl																													
Hydroxypropionic acid, 2-	-> see: Lactic acid																													
Hydroxypropionic acid ethyl ester, 2-	-> see: Ethyl lactate																													
Hydroxytoluene	-> see: Cresol (-mixtures)																													
Iminodiethanol	-> see: Diethanolamine																													
Ginger	—	—	grinded	?		0/0	0/0	(2)	(2)	(2)	0/0	(1)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Isoamyl alcohol	$C_5H_{12}O$	000123-51-3		Xn	X	0/0	0/0	(2)	3/0	1/0	0/0	1/0	1/1	1/3	0/0	0/0	0/0	1/3	0/0	(1)	!/1	1/1	3/0	2/4	3/3	0/0	(1)	(1)	(1)		
Isobutanol	$C_4H_{10}O$	000078-83-1		Xn	X	1/1	1/1	(2)	1/2	(2)	1/2	1/0	1/1	2/2	1/2	1/2	0/0	3/4	1/1	1/1	(1)	1/1	1/0	1/0	3/4	0/0	1/0	(1)	(1)	0/0	
Isobutyl acetate	$C_6H_{12}O_2$	000110-19-0		F	X	0/0	0/0	(2)	(4)	0/0	(4)	1/0	(3)	4/4	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)		
Isobutyl alcohol	-> see: Isobutanol																													
Isobutyl ketone	-> see: Diisobutyl ketone																													
Isobutyl methyl ketone	$C_6H_{12}O$	000108-10-1		F	X	1/2	2/3	1/0	4/4	(4)	3/3	(2)	2/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Isobutyltrimethylmethane	-> see: Iso-octane																													
Iso-octane	C_8H_{18}	000540-84-1	tech. pure	F, Xn	X	1/3	1/3	1/0	(2)	1/0	(4)	1/0	1/3	3/4	1/0	1/0	4/4	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Isooctanol	-> see: Ethylhexanol-1																													
Isooctyl alcohol	-> see: Ethylhexanol-1																													
Isopropyl	C_3H_8O	000067-63-0	tech. pure	F	X	1/1	1/1	1/0	1/2	1/0	1/2	1/0	1/1	2/2	1/2	1/2	4/4	1/4	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	(2)	(1)	(1)	0/0	
Isopropyl-4-methylbenzene, 1-	-> see: Cymene, p-																													
Isopropyl-5-methylcyclohexanol, 2-	-> see: Menthol																													
Isopropyl-5-methylphenol, 2-	-> see: Thymol																													
Isopropyl acetate	$C_5H_{10}O_2$	000108-21-4		F, Xi	X	1/2	2/3	1/0	4/4	(3)	2/3	1/0	2/3	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/1	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Isopropyl acetone	-> see: Isobutyl methyl ketone																													
Isopropyl alcohol	-> see: Isopropyl																													
Isopropylbenzene	-> see: Cumene																													
Isopropylbenzol	-> see: Cumene																													
Isopropyl chloride	C_3H_7Cl	000075-29-6		F, Xn	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Isopropyl ether	$C_6H_{14}O$	000108-20-3	tech. pure	F	X	3/4	3/4	4/4	(4)	1/0	(4)	(1)	3/4	4/4	1/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Isopropylidene acetone	-> see: Mesityl oxide																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Isopropyl methyl ketone	$C_5H_{10}O$	000563-80-4		F	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Jasminaldehyde	-> see: α-pentylcinnamaldehyde																													
Iodine potassium	-> see: Potassium iodide																													
Iodoform	CHJ_3	000075-47-8	100 %	Xn		3/0	3/0	(3)	3/0	0/0	0/0	(2)	3/0	3/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(2)	1/0	1/0	(3)	0/0	(3)	(1)[1)]	(1)[1)]	1/1	[1)] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Iodine pentafluoride	JF_5	007783-66-6		(T, C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Tincture of iodine	I_2	007553-56-2		Xn	(X)	1/3	1/3	4/4	3/4	0/0	1/1	1/1	1/2	3/3	0/0	4/4	4/4	3/3	1/1	0/0	1/1	1/1	2/0	1/1	3/3	0/0	1/0	2/0L	1/0L	1/1		
Cocoa	—	—		(—)		1/1	1/1	(2)	(1)	(2)	0/0	1/1	(2)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Cocoa butter	—	008002-31-1		—		0/0	0/0	1/0	(1)	1/0	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1		
Potash alum	-> see: Potassium aluminium sulphate																													
Potash lye	-> see: Potassium hydroxide																													
Potassium peroxodisulphate	-> see: Potassium persulphate																													
Potassium nitrate	-> see: Potassium nitrate																													
Potassium (hexa)cyanoferrate-(II)	-> see: Potassium hexacyanoferrate (II)																													
Potassium (hexa)cyanoferrate-(III)	-> see: Potassium hexacyanoferrate (III)																													
Potassium acetate	$C_2H_3KO_2$	000127-08-2	aqueous	Xi		1/1	1/1	1/0	(1)	(2)	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/0	1/1	1/1	3/0	3/3	0/0	1/3	1/1	1/1	0/0	
Potassium aluminium sulphate	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	diluted	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	1/1	1/1	1/1	
Potassium aluminium sulphate	$KAl(SO_4)_2 \times 12H_2O$	010043-67-1	saturated	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	0/0	
Potassium bicarbonate	-> see: Potassium hydrogen carbonate																													
Potassium bichromate	-> see: Potassium dichromate																													
Potassium bisulphate	-> see: Potassium hydrogen sulphate																													
Potassium bitartrate	-> see: Potassium hydrogentartate																													
Potassium borate	KBO_2	012228-88-5	10 %	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0	
Potassium borate	KBO_2	012228-88-5	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0	
Potassium bromate	$KBrO_3$	007758-01-2	saturated	O, T		1/3	1/3	(2)	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Potassium bromate	$KBrO_3$	007758-01-2	aqueous	O, T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Potassium bromide	KBr	007758-02-3	any	Xn		1/1	1/1	3/0	1/0	(1)	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/0L	1/0L	1/1	
Potassium carbonate	K_2CO_3	000584-08-7	saturated	Xn		1/1	1/1	1/1	3/3	(2)	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1	
Potassium carbonate	K_2CO_3	000584-08-7	aqueous	Xn		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1	
Potassium chlorate	$KClO_3$	003811-04-9	saturated	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium chlorate	$KClO_3$	003811-04-9	aqueous	O, Xn		1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium chloride	KCl	007447-40-7	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/3	1/1L	1/1L	1/1	
Potassium chromate	K_2CrO_4	007789-00-6	saturated	T		1/0	1/1	2/0	(2)	0/0	1/0	(2)	1/1	1/1	0/0	1/1	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Potassium chromate	K_2CrO_4	007789-00-6	aqueous	T		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Potassium cyanide	KCN	000151-50-8	saturated	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	4/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Potassium cyanide	KCN	000151-50-8	aqueous	T+		1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	1/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Potassium dichromate	$K_2Cr_2O_7$	007778-50-9	saturated	T		1/1	1/0	4/4	3/0	3/0	1/0	3/0	1/1	1/3	0/0	1/3	1/0	1/3	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Potassium dichromate	$K_2Cr_2O_7$	007778-50-9	aqueous	T		0/0	0/0	3/0	1/0	3/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Potassium iron (II) cyanide	-> see: Potassium hexacyanoferrate (III)																													
Potassium iron (III) cyanide	-> see: Potassium hexacyanoferrate (II)																													
Potassium fluoride	KF	007789-23-3		T		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	(1)	0/0	1/1	1/1	1/1	0/0	
Potassium hydrogen carbonate	$CHKO_3$	000298-14-6	saturated	—		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	4/4	(1)	(1)	1/1	
Potassium hydrogen sulphate	$KHSO_4$	007646-93-7	aqueous	(C)		1/1	1/1	4/4	1/0	(2)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	1/1	
Potassium hydrogen sulphate	$KHSO_4$	007646-93-7		C		1/1	1/1	4/4	1/0	0/0	0/0	2/0	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	?	
Potassium hydrogentartate	$C_4H_5KO_6$	000868-14-4	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(4)	1/3	1/2	0/0	
Potassium hydroxide	KHO	001310-58-3	10 %	C+		1/1	1/1	1/0	4/4	4/4	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	30 %	C+		1/1	1/1	1/3	4/4	4/4	1/0	(3)	1/1	1/0	1/0	1/3	1/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	50 %	C+		1/1	1/1	1/3	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/3	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	concentrated	C+		1/1	1/1	1/0	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/2	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	1 %	Xi		1/1	1/1	1/0	3/4	(4)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/3	3/3	0/0	4/4	1/1	1/1	1/1	
Potassium hypochlorite	KClO	007778-66-7	diluted	(O, C)		1/0	1/3	3/0	(3)	(3)	1/0	4/4	1/3	3/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	4/4	3/3L	2/2L	1/1	Javelle water, originally
Potassium iodate	KJO_3	007758-05-6		O		0/0	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/1	(1)	(1)	(2)	0/0	1/1	1/1	1/1	0/0	
Potassium iodide	KJ	007681-11-0	saturated	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Potassium iodide	KJ	007681-11-0	aqueous	(Xn)		1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1L	1/1L	1/1	
Potassium nitrate	KNO_3	007757-79-1	50 %	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium nitrate	KNO_3	007757-79-1	aqueous	O, Xn		1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium perchlorate	$KClO_4$	007778-74-7	saturated	O, Xn		1/1	1/1	(1)	1/0	(1)	1/0	1/1	1/1	0/0	0/0	1/3	3/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	
Potassium perchlorate	$KClO_4$	007778-74-7	aqueous	O, Xn		1/1	1/1	(1)	1/0	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Potassium permanganate	$KMnO_4$	007722-64-7	aqueous	O, Xn		0/0	0/0	4/4	1/0	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	hypermanganic potash
Potassium permanganate	$KMnO_4$	007722-64-7		O, Xn		1/3	1/1	4/4	1/0	(2)	1/1	1/1	1/1	1/3	0/0	1/3	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	hypermanganic potash
Potassium persulphate	$K_2(SO_4)_2$	007727-21-1	any	O, Xn		1/1	1/1	4/4	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/0	1/0	1/1	
Potassium sulphate	K_2SO_4	007778-80-5	aqueous	Xn		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Potassium sulphide	K_2S	001312-73-8	diluted	(C)		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	(1)	(1)	2/0	0/0	3/4	1/1	1/1	0/0	
Potassium sulphite	K_2SO_3	010117-38-1	saturated	(Xi)		1/1	1/1	(1)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/0	1/0	0/0	
Potassium thiosulphate	$K_2S_2O_3$	010233-00-8	saturated	Xi		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	3/3	0/0	(1)	(1)	(1)		
Lime, burnt	-> see: Calcium oxide																													
Hydrated lime	-> see: Calcium hydroxide																													
Lime nitrate	-> see: Calcium nitrate																													
Lime water	-> see: Calcium hydroxide																													
Cardamom	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Rubber (caoutchouc) dispersion	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(1)	(2)	0/0	(3)	(1)	(1)		Latex
Kerosene	—	008008-20-6		(Xn)		2/2	3/4	(1)	4/4	1/1	2/3	1/1	3/3	4/4	2/3	1/1	0/0	0/0	2/3	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	Lamp oil, light petroleum
Pine needle oil	—	008023-99-2		?		0/0	0/0	1/0	(3)	0/0	(4)	(2)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	0/0	Pinus sylvestris
Silicofluoric acid	H_2SiF_6	016961-83-4	32 %	C		1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	3/0	2/2	3/4	0/0	4/4	(2)	1/1	1/1	
Silicic acid	SiO_2	001343-98-2	any	—		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Silicic acid tetraethylester	-> see: Tetraethylorthosilicate																													
Bone oil	—	008001-85-2		—		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Common salt	-> see: Sodium chloride																													
Carbon (substance) disulphide	-> see: Carbon disulphide																													
Carbon dioxide	CO_2	000124-38-9	saturated	?		1/3	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbon dioxide, moist	CO_2	000124-38-9	tech. pure	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbon dioxide, dry	CO_2	000124-38-9	tech. pure	?		1/1	1/1	1/0	(1)	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	2/0	1/1	1/1	0/0	3/3	1/1	1/1	1/1	
Carbonic acid	-> see: Carbon dioxide																													
Carbonic acid dichloride	-> see: Phosgene																													
Carbon tetrabromide	-> see: Carbon tetrabromide																													
Carbon tetrachloride	-> see: Carbon tetrachloride																													
Coconut fat	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1		
Coconut oil alcohol	—	068425-37-6	tech. pure	(Xi)		1/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1		
Coconut oil	—	008001-31-8	tech. pure	—		1/3	1/3	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Aqua regia	HNO_3 + HCl	008007-56-5		C		4/4	4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	4/4	0/0	4/4	4/4	4/4	4/4	Aqua regia = Nitric acid + hydrochloric acid
Fuel + 20% ethanol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	1/1	1/1		
Fuel + 20% methanol	—	—		F, T	X	0/0	0/0	(1)	4/4	0/0	(4)	2/2	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	1/1	1/1		
Fuel, Normal	—	—		F, T	X	0/0	0/0	1/0	3/0	1/1	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Fuel, Super	—	—		F, T	X	0/0	0/0	1/0	4/4	(2)	(4)	2/2	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	1/1	1/1	1/1		
Chalk	$CaCO_3$	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	Calcium carbonate
Creosote	—	—		(T)		1/1	1/1	3/0	(3)	0/0	0/0	(3)	3/4	0/0	1/0	3/0	4/4	0/0	0/0	(1)	1/1	(3)	4/4	(3)	1/0	0/0	(2)	1/1	1/1	0/0	
Cresol (-mixtures)	C_7H_8O	001319-77-3		T, C		3/4	4/4	4/4	4/4	4/4	4/4	4/4	2/3	4/4	4/4	4/4	4/4	3/4	1/2	1/1	1/1	1/1	4/4	1/0	4/4	0/0	1/1	1/0	1/0	1/1	
Carum	—	—	grinded	?		0/0	0/0	(2)	(2)	(1)	0/0	1/1	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	4/4	(1)	(1)		
Kupfer-(I)-chlorid	CuCl	007758-89-6	aqueous	Xn		0/0	0/0	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1	
Kupfer-(I)-cyanid	-> see: Copper cyanide																													
Kupfer-(II)-chlorid	$CuCl_2$	007447-39-4	saturated	Xn		1/3	1/1	(3)	1/0	(2)	1/0	(2)	1/3	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1	
Kupfer-(II)-nitrat	$Cu(NO_3)_2$	003251-23-8	saturated	O, Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/0	1/1	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/1	1/1	1/1	
Kupfer-(II)-nitrat	$Cu(NO_3)_2$	003251-23-8	aqueous	O, Xn		0/0	0/0	(3)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	1/1	1/1	1/1	
Kupfer-(II)-sulfat	-> see: Copper sulphate																													
Copper acetate	$C_4H_6CuO_4$	004180-12-5	aqueous	Xn		1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	(3)	3/3	0/0	4/4	1/1	1/1	1/1	Cupriacetate, verdigris
Copper cyanide	CCuN	000544-92-3	saturated	T		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/3	0/0	0/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	(3)	1/1	1/1		
Copper cyanuric	-> see: Copper cyanide																													
Copper sulphate, aqueous	-> see: Copper vitriol																													
Copper vitriol	$CuSO_4 \times 5H_2O$	007758-99-8	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/0	1/0	1/1	1/1	1/0	1/3	1/0	1/1	1/1	(1)	1/1	1/1	1/0	1/1	2/0	0/0	4/4	1/1	1/1	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Nitrous oxide	N_2O	010024-97-2		(O)		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	2/0	1/0	1/0	0/0	1/1	(1)	(1)		Nitrous oxide, "nitrogen oxydul"
Lactam	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	4/4	4/4	0/0	(2)	(1)	(1)		cyclic carboxylic acid amides
Lactobiosis	-> see: Lactose																													
Lactose	$C_{12}H_{22}O_{11}$	000063-42-3	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	
Lanolin	—	008006-54-0	tech. pure	—		3/3	3/3	1/0	1/0	1/0	0/0	(2)	3/3	1/1	0/0	3/3	3/3	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Latex	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(3)	(1)	(2)	0/0	(2)	(1)	(1)	1/1	Rubber dispersion
Lauryl alcohol	$C_{12}H_{26}O$	000112-53-8	100 %	Xi		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	(1)	(1)	0/0	
Lauryl chloride	$C_{12}H_{25}Cl$	000112-52-7	100 %	(Xi)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(1)	(3)	0/0	(3)	0/0	0/0		
Lavender oil	—	008000-28-0		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	3/0	0/0	(1)	(1)	(1)		
Cod liver oil	—	008001-69-2		—		1/3	1/3	(2)	1/0	(2)	0/0	(2)	1/3	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/0	(1)	(1)	1/1	
Glue (bone glue)	—	—	any	—		1/0	1/1	(1)	(1)	1/1	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(1)	(1)	1/0	1/0	0/0	(3)	1/1	1/1	0/0	
Linseed oil	—	008001-26-1	tech. pure	—		1/1	1/3	1/0	1/0	1/0	1/0	1/1	1/1	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1	1/1	
Lemongrass oil	—	008007-02-1		(Xi)		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	(4)	0/0	(1)	(1)	(1)		
Luminous gas, benzene-free	—	—		F+, T	X	1/0	1/0	1/0	1/0	(2)	1/0	(2)	1/0	1/0	0/0	1/0	1/0	0/0	0/0	(1)	1/0	1/0	4/4	1/0	3/0	0/0	1/1	1/1	1/1	0/0	
Ligroin	—	008032-32-4		F, Xn	X	0/0	0/0	(2)	1/0	(2)	(4)	(2)	(3)	3/3	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		Light petrol
Liqueurs	—	—		—		1/0	0/0	(2)	1/0	1/0	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Limonene, DL-	$C_{10}H_{16}$	000138-86-3		Xn	X	0/0	0/0	(1)	(3)	(2)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1		
Lindane	-> see: Hexachlorocyclohexane																													
Lithium bromide	LiBr	007550-35-8		Xn		1/1	1/1	(3)	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Laurel	—	—	grinded	?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		
Lysol	—	—		T		0/0	0/0	(4)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(3)	1/1	1/1		Disinfectant, cresol + soap
Magnesite	-> see: Magnesium carbonate																													
Magnesium bromide	$MgBr_2$	007789-48-2		Xi		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	(3)	0/0	0/0		
Magnesium carbonate	$MgCO_3$	000546-93-0	saturated	—		1/1	1/1	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Magnesium chloride	$MgCl_2$	007786-30-3	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/0	1/2	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0L	1/0L	1/1	
Magnesium chlorite	$Mg(ClO_2)_2$	??		O		0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0		
Magnesium hydroxide	$Mg(HO)_2$	001309-42-8	saturated	—		1/1	1/1	1/0	(2)	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	1/1	1/1	1/1	1/1	0/0	
Magnesium iodide	MgJ_2	010377-58-9		(Xn)		1/1	1/1	(2)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/1	(1)	(2)	0/0	(2)	0/0	0/0		
Magnesium nitrate	$Mg(NO_3)_2$	010377-60-3	saturated	O, Xi		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	1/0	1/0	1/0	1/1	
Magnesium sulphate	$MgSO_4$	007487-88-9	any	—		1/1	1/1	1/0	1/0	1/0	1/0	1/0	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	0/0	1/1	1/1	1/1	1/1	
Magnesium sulphate heptahydrate	-> see: Epsom salt																													
Maize germ oil	—	008001-30-7	tech. pure	—		1/3	0/0	(2)	(1)	1/0	0/0	(2)	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	1/1	Maize oil
Maleic acid	$C_4H_4O_4$	000110-16-7	saturated	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	1/1	
Maleic acid	$C_4H_4O_4$	000110-16-7	aqueous	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Malonic ester	-> see: Diethylmalonate																													
Malonic acid diethyl ester	-> see: Diethylmalonate																													
Almond oil	—	008007-69-0		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	3/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(1)	(2)	0/0	(1)	1/1	1/1		
Margarine	—	—		—		0/0	0/0	(2)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Marmalade	—	—		—		1/1	1/1	(1)	1/1	1/1	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(2)	1/1	1/1	1/1	
Machine oil	—	—	100 %	?		0/0	1/4	(1)	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Matrium metabisulphite	-> see: Sodium disulphite																													
Matrium pyrochromate	-> see: Sodium dichromate																													
Marine water	-> see: Salt water, seawater																													
Molasses	—	—		—		1/1	1/1	1/0	(1)	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/0	1/0	3/4	
Molasses seasoning	—	—		?		1/1	1/1	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Menthadiene-1,8, p-	-> see: Limonene, DL-																													
Menthol	$C_{10}H_{20}O$	000089-78-1	solid	Xi		1/3	3/4	3/0	3/4	0/0	0/0	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	1/0	1/0		
Mercaptoacetic acid	-> see: Thioglycolic acid																													
Mercaptoethanoic acid, 2-	-> see: Thioglycolic acid																													
Mesityl oxide	$C_6H_{10}O$	000141-79-7		Xn	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	0/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methacrylic acid	$C_4H_6O_2$	000079-41-4		C		1/0	1/1	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	3/0	4/4	4/4	0/0	(4)	0/0	0/0		
Methacrylic acid methyl ester	-> see: Methyl methacrylate																													
Methane	CH_4	000074-82-8	tech. pure	F+	X	1/0	0/0	1/0	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Methanol solution	-> see: Formaldehyde solution																													
Methanamine	-> see: Methylamine, (mono)																													
Methane carboxylic acid	-> see: Acetic acid																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Methanol	CH_4O	000067-56-1		F, T	X	1/1	1/1	2/0	4/4	1/0	1/1	1/1	1/1	3/4	3/3	1/3	3/3	3/4	1/1	1/1	1/1	1/1	1/0	3/4	3/3	0/0	1/0	1/1	1/1	0/0	
Methanoic acid	-> see: Formic acid																													
Methenamine	-> see: Hexamethylenetetramine																													
Methoxybenzene	-> see: Anisole																													
Methoxybutanol	$C_5H_{12}O_2$	—	100 %	?	X	0/0	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	3/0	1/0	!/0	0/0	(1)	(1)	(1)		Isomer not specified in the source
Methoxyethanol	-> see: Methyl glycol																													
Methoxyethyl acetate	-> see: Methyl glycol acetate																													
Methoxyethyl oleate	$C_{21}H_{40}O_3$	000111-10-4		?		1/1	1/2	(2)	3/4	(2)	1/2	(2)	1/2	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(1)	(1)	4/4	(2)	4/4	0/0	(1)	(1)	(1)		Plasticiser
Methoxypropanol	-> see: Propylene glycol methyl ether																													
Methyl ethyl ether	C_3H_8O	000540-67-0	100 %	(F+)	X	0/0	3/0	(1)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(2)	4/4	4/4	4/4	0/0	1/1	(1)	(1)		
Methyl 2-hydroxybenzoate	-> see: Methyl salicylate																													
Methyl 2-methyl propionate	-> see: Methyl methacrylate																													
Methyl acetate	-> see: Acetic acid methyl ester																													
Methacrolein	-> see: Crotonaldehyde																													
Methyl acrylate	$C_4H_6O_2$	000096-33-3		F, Xn	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Methylacrylic acid	-> see: Methacrylic acid																													
Methyl alcohol	-> see: Methanol																													
Methylamine, (Mono-)	CH_5N	000074-89-5	32 %	F+, C	X	1/0	1/0	4/4	4/4	0/0	0/0	1/0	1/0	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	3/0	1/0	4/4	4/4	0/0	1/0	1/0	1/0	0/0	
Methylbenzene	C_7H_8	000108-88-3		F, Xn	X	3/4	3/4	1/0	4/4	1/0	3/3	1/3	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/3	4/4	0/0	1/1	1/1	1/1	1/1	
Methyl bromide	-> see: Bromomethane																													
Methylbutanol	$C_5H_{12}O$	—		Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	1/3	0/0	(1)	1/1	1/1	3/0	2/2	3/3	0/0	(1)	(1)	(1)		Isomer not specified in the source
Methylbutanol, 3-	-> see: Isoamyl alcohol																													
Methylbutanone-2, 3-	-> see: Isopropyl methyl ketone																													
Methyl butyl alcohol	-> see: Methylbutanol																													
Methyl butyl ketone	$C_6H_{12}O$	000591-78-6		F, T	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl cellosolve	-> see: Methyl glycol																													
Methyl chloroacetate	$C_3H_5ClO_2$	000096-34-4	tech. pure	T/Xi	X	1/1	0/0	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/0	0/0	0/0	0/0	(1)	(1)	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Methyl chloride	-> see: Chloromethane																													
Methyl chloroform	-> see: Trichloroethane-1,1,1																													
Methyl cyanide	-> see: Acetonitrile																													
Methylcyclohexane	C_7H_{14}	000108-87-2		F, Xn	X	3/0	3/0	(2)	(2)	1/0	(4)	(2)	3/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	(1)	4/4	(1)	4/4	0/0	1/1	1/1	1/1	0/0	
Methylcyclopentane	C_6H_{12}	000096-37-7		F	X	0/0	0/0	(2)	(2)	1/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Methyl dichloroacetate	$C_3H_4Cl_2O_2$	000116-54-1		(Xn)		1/1	0/0	(3)	(4)		(4)	(3)	1/1	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	3/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0		
Methylene(di)chloride	-> see: Dichloromethane																													
Methylene chlorobromide	-> see: Bromochloromethane																													
Methyl ether	-> see: Dimethyl ether																													
Methyl ethyl ketone (MEK)	C_4H_8O	000078-93-3		F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/2	1/3	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	3/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl formate	$C_2H_4O_2$	000107-31-3		F+	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl glycol	$C_3H_8O_2$	000109-86-4	100 %	T	X	1/0	1/1	1/0	3/4	0/0	1/1	1/0	1/1	4/4	3/3	3/4	4/4	0/0	1/1	1/1	1/1	1/1	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl glycol acetate	$C_5H_{10}O_3$	000110-49-6		T		0/0	0/0	1/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl isobutenyl ketone	-> see: Mesityl oxide																													
Methyl isobutyl ketone(MIBK)	-> see: Isobutyl methyl ketone																													
Methyl isopropyl ketone	-> see: Isopropyl methyl ketone																													
Methyl methacrylate	$C_5H_8O_2$	000080-62-6	100 %	F, Xi	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(3)	4/4	4/4	4/4	0/0	1/1	(1)	(1)	0/0	
Methyl methanoate	-> see: Methyl formate																													
Methyl oleate	$C_{19}H_{36}O_2$	000112-62-9		—		0/0	0/0	(2)	(3)	(2)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	4/4	0/0	(1)	(1)	(1)		
Methyl oxirane	-> see: Propylene oxide																													
Methylpent-4-en-2-one, 5-	-> see: Mesityl oxide																													
Methylpentan-2-one, 4-	-> see: Isobutyl methyl ketone																													
Methylphenol	-> see: Cresol (-mixtures)																													
Methylphenyl ether	-> see: Anisole																													
Methylphenyl ketone	-> see: Acetophenone																													
Methylpropanol-1, 2-	-> see: Isobutanol																													
Methylpropanol-2, 2-	-> see: Butyl alcohol, tertiary																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Methyl propenoate	-> see: Methyl acrylate																													
Methylpropenoic acid, 2-	-> see: Methacrylic acid																													
Methyl propyl ketone	$C_5H_{10}O$	000107-87-9		(F)	X	1/2	2/3	(2)	4/4	(4)	3/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	(1)	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)		
Methyl salicylate	$C_8H_8O_3$	000119-36-8		Xn, Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/0	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	2/0	(3)	4/4	0/0	(2)	(1)	(1)	0/0	Synthetic Wintergreen Oil/Gaultheria Oil
Methyl sulphuric acid	CH_4SO_4	000077-78-1	50 %	(C)		0/0	1/1	4/4	(4)	(4)	0/0	4/4	2/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4	
Methyl sulphuric acid	CH_4SO_4	000077-78-1	aqueous	(C)		0/0	0/0	4/4	(4)	(4)	0/0	4/4	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	4/4	
Milk	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Lactic acid	$C_3H_6O_3$	000050-21-5	3 %	?		1/1	1/2	(3)	1/2	1/0	1/2	2/4	1/2	2/2	1/1	2/3	0/0	1/1	1/1	1/1	1/1	1/1	3/4	1/1	(2)	0/0	(1)	1/1	1/1	1/1	Lactol
Lactic acid	$C_3H_6O_3$	000050-21-5	80 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/1	1/1	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1	Lactol
Lactic acid	$C_3H_6O_3$	000050-21-5	85 %	C		1/1	1/1	3/4	1/2	0/0	1/2	3/4	1/2	2/2	1/1	2/3	2/3	1/1	1/2	1/1	1/1	1/3	3/4	1/1	1/4	0/0	1/0	1/3	1/2	1/1	Lactol
Lactic acid ethyl ester	-> see: Ethyl lactate																													
Milk sugar	-> see: Lactose																													
Mineral oil	—	008012-95-1		(Xn)		1/1	2/4	(1)	1/2	1/1	1/2	1/1	1/3	1/1	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	2/2	0/0	1/1	1/1	1/1	0/0	
Mineral water	—	—		—		1/1	1/1	(1)	1/0	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	(1)	(1)	1/1	
Mohr's salt	-> see: Ammonium iron (II) sulphate																													
Whey	—	—		—		1/1	0/0	(2)	(1)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(2)	1/1	1/1		
Monobromobenzene	-> see: Bromobenzene																													
Monochlorobenzene	-> see: Chlorobenzene																													
Monochloroacetic acid	-> see: Chloroacetic acid																													
Monochloroacetic acid ethyl ester	-> see: Ethyl chloroacetate																													
Monochloroacetic acid methyl ester	-> see: Methyl chloroacetate																													
Monoethanolamine	-> see: Ethanolamine																													
Monofluorodichloromethane	-> see: Dichlorofluoromethane																													
Monopotassium tartrate	-> see: Potassium hydrogentartate																													
Monopentyl phthalate	-> see: Phthalic acid monoamyl ester																													
Morpholine	C_4H_9NO	000110-91-8	tech. pure	C, Xn	X	1/1	1/1	(3)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	3/0	2/3	4/4	0/0	1/0	(1)	(1)	0/0	
Engine oil	—	—		?		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Mowilith D	—	—		?		1/0	0/0	(2)	0/0	(2)	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(2)	(2)	(2)	0/0	(2)	(1)	(1)	0/0	Polyvinylacetatdispersion; Clariant
Nutmeg	—	—	grinded	?		0/0	0/0	(2)	4/4	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Nutmeg oil	—	008008-45-5		(Xn)		0/0	0/0	(2)	4/4	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/4	0/0	(1)	(1)	(2)	(4)	(3)	(3)	0/0	(1)	(1)	(1)		
Nail varnish remover	—	—		?	(X)	0/0	0/0	(2)	4/4	0/0	(4)	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	
Naphtha	—	008032-32-4		(Xn)		1/3	3/4	1/0	(2)	(1)	1/0	1/0	1/3	3/0	1/0	1/0	4/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	Petroleum gasoline
Naphthalene	$C_{10}H_8$	000091-20-3	100 %	F, Xn	X	0/0	1/3	1/0	(3)	0/0	0/0	1/2	1/3	3/4	1/0	4/4	4/4	1/4	0/0	(1)	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	
Naphthalene (in alcohol)	—	—		F, Xn	X	1/4	1/4	(2)	(3)	0/0	0/0	1/2	1/3	3/4	0/0	0/0	0/0	3/4	0/0	(1)	1/1	(2)	4/4	(3)	(3)	0/0	(1)	(1)	(1)	0/0	
Naphthene	-> see: Cyclohexane																													
Sodium acetate	$C_2H_3NaO_2$	000127-09-3	any	—		1/1	1/1	1/0	1/2	(1)	1/1	1/1	1/1	2/2	1/1	2/3	3/0	1/1	1/1	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	1/1	1/1	1/1	
Sodium aluminium sulphate	$NaAl(SO_4)_2$	010102-71-3		?		1/1	1/1	(3)	(2)	(1)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)		
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1	36 %	Xn		1/1	1/1	1/0	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	1/1	0/0	(1)	(1)	(1)	1/1	
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1	aqueous	Xn		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1	
Sodium benzoate	$C_7H_5NaO_2$	000532-32-1		Xn		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/0	1/0	1/1	
Sodium bicarbonate	$NaHCO_3$	000144-55-8	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium bichromate	-> see: Sodium dichromate																													
Sodium bisulphate	$NaHSO_4$	007681-38-1	10 %	(C)		1/1	1/1	4/4	1/0	1/0	0/0	2/0	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	1/2	1/1	1/1	
Sodium bisulphate	$NaHSO_4$	007681-38-1	any	(C)		1/1	1/1	1/0	1/0	0/0	0/0	(3)	1/1	1/3	0/0	1/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/3	0/0	1/3	(2)	1/1	1/1	
Sodium bisulphite	$NaHSO_3$	007631-90-5	aqueous	Xn		1/1	1/1	1/0	(2)	1/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1	1/1	
Sodium borate	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	saturated	Xi		1/1	1/1	1/0	1/0	(2)	1/0	1/1	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/3	1/1	1/1	1/1	
Sodium borate	$Na_2B_4O_7 \times 10\ H_2O$	001303-96-4	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	0/0	1/3	1/1	1/1	1/1	
Sodium bromate	$NaBrO_3$	007789-38-0	any	O, T		1/0	1/3	(3)	(2)	0/0	0/0	1/1	1/1	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	(2)	(1)	1/3	0/0	1/1	1/1L	1/1L	0/0	
Sodium bromide	NaBr	007647-15-6	any	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/3	0/0	4/4	0/0	0/0	0/0	
Sodium carbonate	Na_2CO_3	000497-19-8	saturated	Xi		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium carbonate	Na_2CO_3	000497-19-8	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium carbonate	Na_2CO_3	000497-19-8		Xi		1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	2/0	0/0	1/1	0/0	1/2	1/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	
Sodium chlorate	$NaClO_3$	007775-09-9	any	O, Xn		1/1	1/0	1/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1L	1/1L	1/1	
Sodium chlorate	$NaClO_3$	007775-09-9	aqueous	O, Xn		0/0	0/0	3/0	1/0	1/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/0	1/1L	1/1L	1/1	
Sodium chloride	NaCl	007647-14-5	any	—		1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/2	1/2	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sodium chloride	NaCl	007647-14-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/4	1/2	1/2	1/1	
Sodium chlorite	$NaClO_2$	007758-19-2	diluted	(O, Xn)		1/0	1/3	1/4	(2)	0/0	0/0	(2)	1/3	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	3/4	3/4	3/3	0/0	
Sodium chromate	$NaCrO_4$	007775-11-3	diluted	T		1/0	1/0	1/1	(2)	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	1/1	1/1	1/1	0/0	
Sodium cyanide	CNNa	000143-33-9	saturated	T		1/1	1/1	1/0	(3)	0/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	4/4	(2)	(2)	0/0	
Sodium cyanide	CNNa	000143-33-9	aqueous	T		1/1	1/1	1/0	(3)	1/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	(2)	(2)	0/0	
Sodium dichromate	$Na_2Cr_2O_7$	010588-01-9		T		0/0	1/1	1/0	1/0	3/0	1/1	(3)	1/1	1/1	0/0	1/0	0/0	0/0	1/1	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Sodium disulphite	$Na_2S_2O_5$	007681-57-4	any	Xn		1/1	1/1	1/0	(2)	(2)	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1		
Sodium dithionite	$Na_2S_2O_4$	007775-14-6	10 %	Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		
Sodium dithionite	$Na_2S_2O_4$	007775-14-6		Xn		1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1		
Sodium dodecylbenzene sulphonate	$C_{18}H_{29}NaSO_3$	025155-30-0		Xn		1/1	1/1	(2)	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(1)	(2)	0/0	(2)	(1)	(1)		
Sodium iron cyanide	-> see: Sodium hexacyanoferrate(II)																													
Sodium ferrocyanide	-> see: Sodium hexacyanoferrate(II)																													
Sodium fluoride	NaF	007681-49-4	saturated	T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/0	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	1/1	
Sodium hexacyanoferrate-(II)	$C_6FeNa_4N_6$	013601-19-9		Xn		1/1	1/1	(1)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(1)	(1)	(1)		
Sodium hexametaphosphate	$(NaPO_3)_6$	068915-31-1	saturated	—		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Sodium hydrogen carbonate	-> see: Sodium bicarbonate																													
Sodium hydrogen sulphate	-> see: Sodium bisulphate																													
Sodium hydrogen sulphite	-> see: Sodium bisulphite																													
Sodium hydrosulphite	-> see: Sodium dithionite																													
Sodium hydroxide	NaOH	001310-73-2	concentrated	C		1/1	1/1	1/3	4/4	4/4	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	4/4	3/4	0/0	4/4	(2)	(2)	?	
Sodium hydroxide	NaOH	001310-73-2	30 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/0	1/0	1/3	1/3	0/0	0/0	1/1	1/1	(2)	1/0	(3)	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	45 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/1	1/0	1/3	1/3	1/1	0/0	0/0	1/1	(2)	1/0	2/4	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	50 %	C+		1/1	1/1	1/0	4/4	4/4	1/1	1/3	1/1	2/2	1/1	1/2	0/0	0/3	1/1	1/1	1/1	3/3	1/0	3/4	3/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	60 %	C+		1/1	1/1	1/0	4/4	4/4	1/0	(3)	1/1	1/0	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	3/4	2/3	0/0	4/4	1/3	1/3	1/1	
Sodium hydroxide	NaOH	001310-73-2	1 %	Xi		1/1	1/1	1/0	3/4	(3)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	(4)	1/1	1/1	1/1	
Sodium hypochlorite	NaClO	007681-52-9	diluted	(O, C)		2/3	2/3	4/4	(3)	3/0	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	15 %	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/1	0/0	1/1	1/1	1/1	1/1	3/4	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	saturated	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	0/0	1/1	0/0	(1)	1/1	(3)	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypochlorite	NaClO	007681-52-9	12,5 % Cl	O, C		2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	Javelle water, new
Sodium hypodisulphite	-> see: Sodium dithionite																													
Sodium iodide	NaJ	007681-82-5	any	Xi		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/0	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	(1)	1/1	0/0	1/1	3/4	3/4	0/0	
Sodium metaborate peroxide	-> see: Sodium perborate																													
Sodium nitrate	$NaNO_3$	007631-99-4	saturated	O, Xn		1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	
Sodium nitrate	$NaNO_3$	007631-99-4	aqueous	O, Xn		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Sodium nitrite	$NaNO_2$	007632-00-0	saturated	O, T		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/1	0/0	1/0	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1	1/1	1/1	
Sodium nitrite	$NaNO_2$	007632-00-0	aqueous	O, T		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	1/0	1/1	1/1	1/1	
Sodium oxalate	$C_2Na_2O_4$	000062-76-0	saturated	Xn		1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	1/0	1/0	0/0	1/1	(2)	(2)		
Sodium perborate	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	saturated	(O, Xn)		1/1	1/1	4/4	(2)	0/0	0/0	2/0	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Sodium perborate	$NaBO_2(HO)_2 \times 3H_2O$	013517-20-9	aqueous	(O, Xn)		1/1	1/1	4/4	(2)	3/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0		
Sodium perchlorate	$NaClO_4$	007601-89-0	saturated	O, Xn		1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	1/1	1/1	
Sodium peroxide	Na_2O_2	001313-60-6	10 %	O, C+		0/0	1/3	4/4	(3)	(4)	0/0	4/4	272	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	3/0	0/0	4/4	1/1	1/1	0/0	
Sodium peroxide	Na_2O_2	001313-60-6	saturated	O, C+		0/0	3/3	4/4	(3)	(4)	0/0	4/4	2/2	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	(4)	0/0	4/4	(2)	(2)	0/0	
Sodium peroxodisulphate	-> see: Sodium persulphate																													
Sodium persulphate	$Na_2S_2O_8$	007775-27-1	saturated	O, Xi		1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(3)	0/0	4/4	0/0	1/0	0/0	
Sodium phosphate	$Na_3PO_4 \times 12H_2O$	010101-89-0	saturated	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium phosphate	$Na_3PO_4 \times 12H_2O$	010101-89-0	aqueous	Xi		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium phosphate, secondary	-> see: Disodium phosphate																													
Sodium phosphate, tertiary	-> see: Trisodium phosphate																													
Sodium phosphate dodecahydrate	-> see: Sodium phosphate																													
Sodium pyrosulphite	-> see: Sodium disulphite																													
Sodium silicate	$Na_2Si_2O_7$	001344-09-8	any	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium stearate	$C_{18}H_{35}NaO_2$	000822-16-2	aqueous	(Xi)		1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(1)	1/0	0/0	(1)	1/1	1/1		
Sodium sulphate	Na_2SO_4	007757-82-6	saturated	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/3	0/0	1/1	1/1	1/1	1/1	
Sodium sulphate	Na_2SO_4	007757-82-6	aqueous	—		1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	0/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Sodium sulphate	Na_2SO_4	007757-82-6		—		1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	0/0	1/1	1/1	1/1	1/1	
Sodium sulphide	Na_2S	001313-82-2	saturated	C		1/1	1/1	1/0	3/0	(1)	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	0/0	1/1	1/1	3/3	1/0	1/1	2/3	0/0	3/4	(1)	(1)	1/1	

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics					Elastomers		Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sodium sulphide	Na_2S	001313-82-2	aqueous	C		1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/2	1/2	1/1	
Sodium sulphite	Na_2SO_3	007757-83-7	saturated	Xn		1/1	1/1	1/0	(2)	(2)	1/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/3	1/1	1/1	1/1	
Sodium tetraborate	-> see: Sodium borate																														
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	any	Xi		1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/3	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	saturated	Xi		1/1	1/1	1/0	(1)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate	$Na_2S_2O_3 \times 5H_2O$	010102-17-7	aqueous	Xi		1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	Fixing soda, "sodium hyposulphite"
Sodium thiosulphate-5-hydrate	-> see: Sodium thiosulphate																														
Sodium hypochlorite	-> see: Sodium hypochlorite																														
Caustic soda	-> see: Sodium hydroxide																														
Sodium nitrate	-> see: Sodium nitrate																														
Sodium liquid glass	-> see: Sodium silicate																														
Cloves	—	—	grinded	?		0/0	0/0	(2)	4/4	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	0/0	
Neon	Ne	007440-01-9		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(1)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1		
Wetting agent	—	—	5 %	?		1/0	0/0	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(2)	0/0	0/0	K	K		Surfactants
Niacin	-> see: Nicotinic acid																														
Nickel (II) chloride	$NiCl_2$	007718-54-9	saturated	T		1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1	
Nickel (II) chloride	$NiCl_2$	007718-54-9	aqueous	T		1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1	
Nickel acetate	$C_4H_6NiO_4$	000373-02-4	aqueous	(T, N)		1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/0	0/0	4/4	0/0	0/0		
Nickel nitrate	$Ni(NO_3)_2$	013138-45-9	saturated	(O, Xn)		1/1	1/1	(3)	(2)	(1)	1/0	(2)	1/1	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Nickel sulphate	$NiSO_4$	007786-81-4	saturated	Xn		1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nickel sulphate	$NiSO_4$	007786-81-4	aqueous	Xn		1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nicotine	$C_{10}H_{14}N_2$	000054-11-5		T+		1/0	1/0	(3)	(3)	0/0	0/0	(2)	1/0	1/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/1	0/0	(1)	(1)	(1)	0/0	
Nicotinic acid	$C_6H_5NO_2$	000059-67-6	diluted	Xi		1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/0	0/0	0/0	1/1	0/0	0/0	0/0	1/1	(1)	(2)	(2)	(3)	(2)	0/0	(3)	0/0	0/0	0/0	
Nitrobenzoic acid	$C_7H_5NO_4$	—		(Xn)		1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	(3)	(2)	0/0	(3)	0/0	0/0		Isomer not specified in the source
Nitrobenzene	$C_6H_5NO_2$	000098-95-3		T		3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitroethane	$C_2H_5NO_2$	000079-24-3		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Nitroglycerin	$C_3H_5(NO_3)_3$	000055-63-0	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/0	(3)	1/0	1/0	4/4	0/0	0/0	0/0	0/0	0/0	
Nitro glycol	$C_2H_4(NO_3)_2$	000628-96-6	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(3)	1/0	1/0	4/4	0/0	0/0	(1)	(1)	0/0	
Nitropropane	$C_3H_7NO_2$	—		(T)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Nitrous gases	—	—	diluted	T		1/1	0/0	3/0	4/4	0/0	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	3/0	4/4	0/0	(2)	(1)	(1)	0/0	Nitrogen monoxide + nitrogen dioxide
Nitrotoluene	$C_7H_7NO_2$	001321-12-6	tech. pure	T		1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitro thinner	—	—		?	X	0/0	0/0	3/0	(4)	0/0	(4)	(3)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		Solvent mixture
Nonanol	$C_9H_{20}O$	000143-08-8	100 %	Xn, Xi		0/0	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Nonyl alcohol	-> see: Nonanol																														
Fruit pulp	—	—		—		1/1	1/1	(2)	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	
Fruit wine	—	—		—		1/1	1/1	(2)	(1)	1/1	0/0	1/1	1/0	0/0	0/0	1/0	0/0	0/0	1/1	1/1	(1)	1/1	1/0	(1)	1/0	0/0	(2)	1/1	1/1	0/0	
Octadec-9-enoic acid, cis-	-> see: Oleic acid																														
Octadecanoic acid	-> see: Stearic acid																														
Octafluorocyclobutane	C_4F_8	000115-25-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Octal	-> see: Diisooctyl phthalate																														
Octane, n-	C_8H_{18}	000111-65-9		F, Xn	X	1/1	1/1	1/0	2/3	(1)	1/1	1/0	1/1	4/4	2/3	3/4	3/3	1/1	1/1	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	0/0	
Octanol, 1-	-> see: Octyl alcohol, -n																														
Octyl alcohol, -n	$C_8H_{18}O$	000111-87-5		Xi		0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	1/0	1/0	3/3	0/0	(1)	(1)	(1)		
Octylcresol	$C_{15}H_{24}O$	—	100 %	?		3/0	3/0	(3)	(4)	0/0	0/0	(3)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	3/0	0/0	(1)	(1)	(1)	0/0	Isomer not specified in the source
Oils and fats, vegetable	—	—		—		1/3	1/3	(2)	(2)	1/0	0/0	(2)	1/3	3/0	0/0	1/1	3/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	(2)	0/0	(1)	1/1	1/1	0/0	
Öle, Oils, ethereal	—	—		?		4/4	3/4	(2)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	(1-3)	(3)	0/0	1/1	(1)	(1)	0/0	
Olein	-> see: Oleic acid																														
Oleum	$H_2SO_4 \times SO_3$	008014-95-7	10 % SO_3	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/0	4/4	4/4	1/0	4/4	0/0	1/3	1/2	1/1	0/0	Fuming sulphuric acid
Oleum vapours	—	—	low	?		4/4	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	1/0	(3)	1/0	(3)	0/0	(3)	(1)	(1)	0/0	Sulphur trioxide
Olive oil	—	008001-25-0		—		1/3	0/0	(2)	(2)	1/0	0/0	1/1	1/1	1/1	0/0	1/1	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Oleic acid	$C_{18}H_{34}O_2$	000112-80-1	tech. pure	Xi		1/3	1/3	1/0	1/0	1/0	0/0	2/0	1/3	1/3	0/0	1/1	0/0	1/3	0/0	(1)	1/1	1/1	4/4	2/2	3/0	0/0	1/1	1/1	1/1	0/0	
Oleic acid methoxyethyl ester	-> see: Methoxyethyl oleate																														
Oleic acid methyl ester	-> see: Methyl oleate																														

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sweet orange juice	-> see: Orange juice																													
Sweet orange peel oil	-> see: Orange peel oil																													
Ortho-silicic acid tetraethyl ester	-> see: Tetraethylorthosilicate																													
Orthophosphoric acid	-> see: Phosphoric acid																													
Oxabutyl acetate	-> see: Methyl glycol acetate																													
Oxalic acid	$C_2H_2O_4 \times 2H_2O$	000144-62-7	aqueous	Xn		1/1	1/1	4/4	(2)	(2)	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(2)	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/2	
Oxalic acid	$C_2H_2O_4 \times 2H_2O$	000144-62-7		Xn		1/1	1/1	3/4	1/0	0/0	1/1	4/4	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/3	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/3	
Oxalic acid sodium salt	-> see: Sodium oxalate																													
Oxalic acid ammonium salt	-> see: Ammonium oxalate																													
Oxirane	-> see: Ethylene oxide																													
Oxolane	-> see: Tetrahydrofuran																													
Oxydiacetic acid	-> see: Diglycolic acid																													
Oxymethylfurfurol, 5-	$C_6H_6O_3$	000067-47-0		Xi		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ozone	O_3	010028-15-6		(O, T)		3/4	3/4	4/4	1/2	0/0	1/1	4/4	3/4	2/2	1/1	1/2	0/0	1/1	1/1	1/1	(1)	1/3	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Ozone-air mixture-Luft-Gemisch	—	—		(O, T)		0/0	0/0	4/4	(2)	0/0	0/0	4/4	3/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Palmitic acid	$C_{16}H_{32}O_2$	000057-10-3	tech. pure	Xi		3/3	2/2	1/1	(2)	1/0	0/0	1/0	3/4	1/1	0/0	1/1	3/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
Palmityl alcohol	-> see: Cetyl alcohol																													
Palm seed oil	—	008023-79-8		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/3	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	
Palm oil	—	008002-75-3		—		1/3	0/0	1/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1		
Paraffins	C_nH_{2n+2}	—	100 %	?		1/0	1/1	1/0	1/0	1/0	1/1	1/1	1/0	1/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	
Paraffin emulsion	—	—		?		1/3	0/0	1/0	(2)	(2)	0/0	(2)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/0	1/1	0/0	(2)	(1)	(1)	0/0	
Paraffin wax	—	008002-74-2	melted	(—)		0	0	0	(2)	0	0	(2)	(2)	0	0	0	0	0	0	(1)	1	0	4	(2)	1	0	1	1	1		
Paraform	-> see: Paraformaldehyde																													
Paraformaldehyde	$(CH_2O)_nH_2O$	030525-89-4		F, T	X	0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	1/0	3/3	0/0	(1)	(1)	(1)		
Perfumes	—	—		?		3/0	3/0	1/0	(3)	1/0	0/0	(2)	1/0	4/4	0/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Pectin	—	009000-69-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Pectin
Pectin	—	009000-69-5		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		Pectin
Penicillin	—	—		Xn		(1)	(1)	(2)	(1)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)		Antibiotic
Pentaclorodiphenyl	$C_{12}H_5Cl_5$	—		Xn		0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0		a PCB
Pentamethyleneimine	-> see: Piperidine																													
Pentane	C_5H_{12}	000109-66-0		F	X	1/3	1/3	1/0	1/0	1/1	(3)	1/0	(3)	3/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(1)	4/4	1/0	1/2	0/0	1/1	1/1	1/1		
Pentanone, 2-	-> see: Methyl propyl ketone																													
Pentanone, 3-	-> see: Diethyl ketone																													
Pentanethiol, 1-	$C_5H_{12}S$	000110-66-7		Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(2)	(1)	(1)		
Pentylacetate, n-	-> see: Amylacetate, n-																													
Pentyl alcohol	-> see: Amyl alcohol, n-																													
Pentyl chloride	-> see: Amyl chloride																													
Pentylcinnamaldehyde, a-	-> see: α-pentylcinnamaldehyde																													
Perchlorobutadiene	-> see: Hexachlorobutadiene																													
Perchlorethene	-> see: Perchloroethylene																													
Perchloroethylene (PER)	C_2Cl_4	000127-18-4		Xn		4/4	4/4	4/4	4/4	3/4	4/4	1/3	4/4	4/4	4/4	4/4	4/4	3/3	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	(3)	0/0	0/0	0/0	
Perchloric acid	$HClO_4$	007601-90-3	70 %	E, O, C+		2/4	3/4	4/4	4/4	(4)	2/4	4/4	4/4	2/3	4/4	3/4	4/4	0/0	1/2	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	0/0	0/0	?	
Perchloric acid	$HClO_4$	007601-90-3	20 %	Xi		0/0	1/3	4/4	3/0	0/0	0/0	4/4	1/3	0/0	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	2/0	1/1	4/4	0/0	4/4	0/0	0/0	1/1	
Perfluoropropane	C_3F_8	000076-19-7		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	1/0	0/0	(3)	0/0	0/0		
Perhydroxic acid	-> see: Hydrogen peroxide 30 %																													
Petrolatum, petroleum jelly	-> see: Vaseline																													
Petroleum ether	—	008032-32-4	tech. pure	(F, Xn)	X	1/3	1/3	1/0	3/0	1/0	1/0	1/1	1/3	4/4	1/0	1/1	3/3	3/3	0/0	(1)	1/1	1/1	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	
Petroleum	—	—	tech. pure	Xn, N	X	1/3	3/4	1/0	3/0	(1)	0/0	1/1	1/3	4/4	1/0	1/0	3/0	3/4	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Pepper	—	—	grinded	?		0/0	0/0	(2)	1/0	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Vegetable oils	—	—		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Phenacetin	$C_{10}H_{13}NO_2$	000062-44-2		Xn		0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)		
Phenetole	-> see: Phenylethylether																													
Phenol	C_6H_6O	000108-95-2	10 %	T		1/1	1/1	4/4	4/4	4/4	1/0	4/4	1/1	4/4	4/4	1/3	3/3	3/3	0/0	1/0	1/1	1/1	4/4	2/3	4/4	0/0	1/1	1/2	1/1	0/0	
Phenol	C_6H_6O	000108-95-2	100 %	T, C		2/3	3/3	4/4	4/4	4/4	1/1	4/4	1/2	4/4	3/3	4/4	3/0	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	0/0	
Phenolic resin moulding compound	—	—		?		1/1	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(4)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Phenyethylene	-> see: Styrene																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							Thermoplastics												Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Phenyl-2-propenal, trans-3-	-> see: Cinnamaldehyde																													
Phenylamine	-> see: Aniline																													
Phenylaniline, N-	-> see: Diphenylamine																													
Phenyl bromide	-> see: Bromobenzene																													
Phenylcarbinol	-> see: Benzyl alcohol																													
Phenyl chloride	-> see: Chlorobenzene																													
Phenylethanol	$C_8H_{10}O$	000060-12-8		Xn		0/0	0/0	3/0	4/4	0/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(1)	(1)	(1)		
Phenyl ether	-> see: Diphenyl ether																													
Phenylethyl alcohol	-> see: Phenylethanol																													
Phenyl ethyl ether	$C_8H_{10}O$	000103-73-1		?		0/0	0/0	(2)	(4)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Phenylhydrazine	$C_6H_8N_2$	000100-63-0	tech. pure	T		3/0	0/0	(3)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/3	4/4	0/0	(2)	0/0	0/0	0/0	
Phenylhydrazine chlorohydrate	-> see: Phenylhydrazine-HCl																													
Phenylhydrazine-HCl	$C_6H_8N_2$-HCl	000059-88-1		T		0/0	0/0	(3)	(2)	0/0	0/0	(3)	1/3	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/3	1/3	0/0	(4)	(4L)	(4L)		
Phenylpropane	-> see: Cumene																													
Phenyl sulphonate	—	70528-83-5		?		0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Phenylsulfonic acid	-> see: Benzenesulfonic acid																													
Phosgene	$COCl_2$	000075-44-5	liquid	T+, C		0/0	0/0	1/0	(3)	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	1/0	3/0	0/0	(3)	3/4	3/4	0/0	
Phosgene	$COCl_2$	000075-44-5	gaseous	T+, C		0/0	3/0	1/0	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	3/0	0/0	(3)	3/4	3/4	0/0	
Phosphates	—	—	aqueous	?		1/1	1/1	0/0	0/0	(1)	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	0/0	(1)	(1)		Salts of phosphoric acid
Phosphine	PH_3	007803-51-2	concentrated	F+, T+	X	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Phosphorus (III) chloride	-> see: Phosphorus trichloride																													
Phosphorus oxychloride	PCl_3O	010025-87-3	100 %	T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	
Phosphorus oxychloride	PCl_3O	010025-87-3		T, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	(2)	1/0	1/1	4/4	0/0	1/3	1/3L	1/3L	1/1	
Phosphorus pentachloride	PCl_5	010026-13-8		T+, C		0/0	1/0	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/1	1/1	(3)	(3)	4/4	0/0	1/1	1/3L	1/3L		
Phosphorus pentoxide	P_4O_{10}	001314-56-3	tech. rein	C		1/0	0/0	(4)	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	(3)	(2)	3/4	0/0	1/1	1/0	1/0	0/0	
Phosphorus perchloride	-> see: Phosphorus pentachloride																													
Phosphoric acid	H_3PO_4	007664-38-2	30 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	85 %	C		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	1/1	1/2	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	2/4	1/3	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	1-5 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	3/4	1/1	2/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	(4)	1/1	1/1	1/1	
Phosphoric acid	H_3PO_4	007664-38-2	20%	Xi		1/1	1/1	4/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphoric anhydride	-> see: Phosphorus pentoxide																													
Phosphoric acid chloride	-> see: Phosphorus pentachloride																													
Phosphoric acid tritolyester	-> see: Tricresyl phosphate																													
Phosphorus trichloride	PCl_3	007719-12-2		T, C		3/3	3/3	4/4	4/4	0/0	0/0	4/4	1/3	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/1	1/0	3/4	4/4	0/0	1/1	0/0	0/0	1/1	
Hydrogen phosphide	-> see: Phosphine																													
Phosphoryl chloride	-> see: Phosphorus oxychloride																													
Phthalic acid	$C_8H_6O_4$	000088-99-3	saturated	Xi		1/1	1/1	3/3	(3)	1/0	0/0	1/0	1/1	1/0	0/0	1/4	0/0	1/1	0/0	1/1	1/1	1/1	1/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1	
Phthalic acid amyl ester	$C_{18}H_{26}O_4$	000131-18-0	100 %	(T)		0/0	1/3	(1)	(4)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Phthalic acid dibutyl ester	-> see: Dibutyl phthalate																													
Phthalic acid dicyclohexyl ester	-> see: Dicyclohexyl phthalate																													
Phthalic acid dimethyl ester	-> see: Dimethyl phthalate																													
Phthalic acid dinonyl ester	-> see: Dinonyl phthalate																													
Phthalic acid monoamyl ester	$C_{13}H_{16}O_4$	??		(Xn)		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	(1)	(1)		
Picric acid	$C_6H_3N_3O_7$	000088-89-1	1 % aqueous	T		1/0	1/0	3/0	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	4/4	0/0	0/0	1/0	1/0	1/1	3/0	1/0	3/4	0/0	1/0	1/0	1/0	1/0	
Pimenta, allspice	—	—	grinded	?		0/0	0/0	(2)	4/4		0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Piperidine	$C_5H_{11}N$	000110-89-4		F, T, C		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Polyester resins	—	—		(Xn)	(X)	3/4	3/4	1/0	4/4	1/0	0/0	(2)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)		
Polyethylene glycol	HO-$(C_2H_4O)_n$-H	025322-68-3	100 %	(—)		1/1	1/1	(3)	0/0	0/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2-3)	(2)	(3)	0/0	(1)	(1)	(1)	0/0	
Polyglycol	-> see: Polyethylene glycol																													
Polyoxyethylene	-> see: Polyethylene glycol																													
Polyoxymethylene	-> see: Paraformaldehyde																													
Polyran M25 N	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	3	0	0	(1)	(1)		Lubricating oil
Polyran M400	—	—	80°C	?		0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	(3)	0	0	(1)	(1)		Lubricating oil
Polysiloxane	-> see: Silicone oil																													
Polysolvan O	$C_6H_{12}O_3$	007397-62-8	100 %	Xi		0/0	1/1	(2)	(3)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	(3)	0/0	(1)	(1)	(1)		Solvent, glycolic acid butyl ester; Celanese AG

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

							---------- Thermoplastics ----------		---- Fluoroplastics ----		--- Elastomers ---		-------- Metals ---------			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Bitter orange oil	—	068916-04-1		?		2/3	3/4	(2)	3/3	1/0	3/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(2)	4/4	(2)	(4)	0/0	(1)	(1)	(1)		
Potash	-> see: Potassium carbonate																													
Compressed air	—	—	oily	—		1/0	0/0	(2)	(2)	(1)	0/0	(1)	3/0	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	1/1	1/1	1/1		
Prontosil	—	—		(Xn)		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	0/0	0/0		Chemotherapeutic agent; Bayer - no longer on the market
Prop-2-enyl acetate	-> see: Allyl acetate																													
Propane	C_3H_8	000074-98-6	liquid	F+	X	1/0	1/0	1/0	1/0	1/0	0/0	1/1	1/0	0/0	1/0	1/0	3/0	1/0	0/0	(1)	1/1	1/1	4/4	1/0	(2)	0/0	1/1	1/1	1/1	0/0	
Propane	C_3H_8	000074-98-6	gaseous	F+	X	3/4	4/4	1/0	3/4	1/0	4/4	1/1	2/4	4/4	3/3	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Propandiol, 1,2-	-> see: Propylene glycol																													
Propanol	C_3H_8O	000071-23-8		F	X	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	3/0	0/0	2/2	3/3	1/4	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/1	(1)	(1)	0/0	
Propanol, 2-	-> see: Isopropyl																													
Propanone, 2-	-> see: Acetone																													
Propanoic acid	-> see: Propionic acid																													
Propanetriol	-> see: Glycerine																													
Propargyl alcohol	C_3H_4O	000107-19-7	7 %	Xn		1/1	1/1	(3)	1/0	0/0	0/0	(2)	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/3	1/0	1/1	1/1	0/0	1/0	(1)	(1)	0/0	
Propene	C_3H_6	000115-07-1		F+	X	1/1	1/1	1/0	(3)	1/0	0/0	1/0	1/1	4/4	0/0	3/4	4/4	0/0	0/0	(1)	1/1	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1		
Propene-1-ol, 2-	-> see: Allyl alcohol																													
Propene acid ethyl ester	-> see: Ethyl acrylate																													
Propyn-1-ol, 2-	-> see: Propargyl alcohol																													
Propionic acid	$C_3H_6O_2$	000079-09-4	50 %	C, F	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/1	4/4	4/4	1/3	3/3	0/0	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	1/1	(1)	(1)	1/1	
Propionic acid	$C_3H_6O_2$	000079-09-4		C, F+	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	1/1	
Propyl acetate	$C_5H_{10}O_2$	000109-60-4		F	X	0/0	0/0	(1)	4/4	0/0	(4)	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		
Propyl alcohol	-> see: Propanol																													
Propylamine, n-	C_3H_9N	000107-10-8		F, C, Xn	X	0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Propylene	-> see: Propene																													
Propylene(di)chloride	-> see: Dichloropropane																													
Propylene glycol	$C_3H_8O_2$	000057-55-6		—		1/1	1/1	4/4	2/3	(2)	1/1	1/0	1/1	1/1	2/2	3/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	(1)	(1)	1/1	
Propylene glycol methyl ether	$C_4H_{10}O_2$	—		—	X	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		Isomer not specified in the source
Propylene oxide	C_3H_6O	000075-56-9		F+, T	X	1/1	1/2	(3)	2/3	0/0	1/2	(2)	1/2	4/4	2/2	3/4	0/0	4/4	3/4	1/1	1/0	1/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Propylidintris(methanol)	-> see: Trimethylol propane																													
Propyl nitrate	$C_3H_7NO_3$	000627-13-4		(E, Xn)	(X)	0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(2)	(1)	(1)		
Pseudocumene	C_9H_{12}	000095-63-6		Xn	X	0/0	0/0	(1)	(4)	0/0	0/0	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(2)	4/4	0/0	1/1	1/1	1/1		
Pydraul C (312, 540)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	1/0	4/4	0/0	0/0	(1)	(1)		Base phosphoric acid ester; Monsanto
Pydraul E (29, 30, 50, 65, 90, 11)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	4/4	0/0	0/0	(1)	(1)		Base phosphoric acid ester; Monsanto
Pyridine	C_5H_5N	000110-86-1		F, Xn	X	1/3	0/2	1/0	4/4	0/0	0/2	1/1	3/3	4/4	4/4	4/4	4/4	4/4	1/1	(2)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0	
Pyridine-3-carboxylic acid	-> see: Nicotinic acid																													
Pyrogallol	$C_6H_6O_3$	000087-66-1		Xn		0/0	0/0	1/0	(3)	0/0	0/0	3/4	1/0	3/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	1/1	(3)	(3)	(3)	0/0	1/1	1/1	1/1	1/1	
Pyrosulphite	-> see: Sodium disulphite																													
Pyrrole	C_4H_5N	000109-97-7		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)		
Mercury	Hg	007439-97-6	pure	T		1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(3)	1/1	1/1		
Mercury (II) chloride	$HgCl_2$	007487-94-7	aqueous	T+, C		1/1	1/1	4/4	1/0	(2)	1/1	3/0	1/1	1/3	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	(4)	(4)	1/1	Sublimate
Mercury (II) cyanide	C_2HgN_2	000592-04-1	saturated	T+		1/1	1/1	(3)	(2)	(2)	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	1/1	(1)	1/1	(2)	0/0	4/4	1/0	1/0	1/1	
Mercury (II) nitrate	-> see: Mercury nitrate																													
Mercury nitrate	$Hg(NO_3)_2$	010045-94-0	saturated	(T+)		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	1/0	0/0	1/3	1/0	0/0	(1)	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	1/1	1/1	1/1	
Mercuric nitrate	-> see: Mercury nitrate																													
Ramasit	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	Hydrophobing agent for textiles; BASF
Resorcinol	$C_6H_6O_2$	000108-46-3	5 %	—		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	2/4	0/0	3/3	1/3	1/1	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Resorcinol	$C_6H_6O_2$	000108-46-3	saturated	Xn		1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	3/4	0/0	0/0	1/1	(1)	(1)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0		
Beef tallow	—	061789-97-7		—		0/0	0/0	1/0	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1		
Beef tallow emulsion	—	—	sulphurised	(—)		1/0	0/0	(2)	(2)	0/0	0/0	0/0	1/0	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(2)	(2)	0/0	(2)	(1)	(1)	0/0	
Castor oil	—	008001-79-4	100 %	Xi		1/1	1/1	1/0	1/0	(1)	1/0	(2)	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Crude oil	—	—	100 %	(N)		0/0	1/3	1/0	(3)	1/0	0/0	1/0	1/3	3/0	1/0	1/0	3/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	3/3	0/0	(2)	(1)	(1)		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Rose oil	—	008007-01-0		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Roasting gases	—	—	any	(T)		0/0	0/0	(2)	0/0	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(4)	(2)	(2)	0/0	
Colza oil	—	008002-13-9		—		0/0	0/0	(2)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	(1)	1/1	1/1		
Rum flavouring	—	008030-89-5		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	(1)	(1)	(3)	(3)	(4)	(3)	0/0	(1)	(1)	(1)		
Sagrotan	—	—	liquid	?		1/2	1/3	0/0	3/0	0/0	0/0	(3)	1/3	3/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	3/0	0/0	(2)	(1)	(1)		Disinfectants; Schülke & Mayr
Salicylaldehyde	$C_7H_6O_2$	000090-02-8		Xn, Xi		1/1	1/2	(3)	2/3	0/0	1/2	(3)	1/2	4/4	3/3	3/4	0/0	0/0	1/4	1/1	(1)	(3)	(3)	(3)	4/4	0/0	(2)	(1)	(1)		
Salicylic acid	$C_7H_6O_3$	000069-72-7	saturated	(Xn, Xi)		1/1	1/1	1/0	1/2	1/0	1/1	4/4	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1	
Salicylic acid	$C_7H_6O_3$	000069-72-7	Powder	Xn, Xi		1/1	1/1	1/0	1/2	(1)	1/2	(3)	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1	
Salicylic acid methyl ester	-> see: Methyl salicylate																													
Salammoniac	-> see: Ammonium chloride																													
Ammonia solution	-> see: Ammonium hydroxide																													
Nitric acid	HNO_3	007697-37-2	1-10 %	C		1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1	1/1	
Nitric acid	HNO_3	007697-37-2	50 %	C+		2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO_3	007697-37-2	66 %	C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO_3	007697-37-2	100 %	O, C+		4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	0/0	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	?	
Nitric acid	HNO_3	007697-37-2	70 %	O, C+		2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2	1/2	
Hydrochloric acid	HCl	007647-01-0	1-5 %	—		1/1	1/1	4/4	1/1	(2)	1/2	4/4	1/1	1/1	1/1	1/1	0/0	1/3	1/1	1/1	1/1	1/1	1/0	1/1	3/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	35 %	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	konz.	C		1/1	1/1	4/4	4/4	(4)	1/2	4/4	1/2	3/3	1/1	2/3	3/3	1/3	1/1	1/1	1/1	1/1	3/0	1/2	4/4	0/0	4/4	4/4	4/4	1/1	
Hydrochloric acid	HCl	007647-01-0	20 %	Xi		1/1	1/1	4/4	2/3	3/0	1/2	4/4	1/1	1/1	1/1	1/3	0/0	0/3	1/1	1/1	1/1	1/1	1/0	1/1	4/4	0/0	4/4	4/4	4/4	1/1	Hydrochloric acid
Hydrochloric acid aluminium salt, anhydrous	-> see: Aluminium chloride																													
Salt brine	NaCl	007647-14-5	saturated	—		1/1	1/1	1/0	(1)	(1)	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3	1/2	0/0	
Salt water, seawater	—	—		—		1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	
Saturated steam condensate	—	—		?		0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(2)	1/1	1/1		
Oxygen	O_2	007782-44-7	tech. pure	O		1/3	1/3	2/0	1/0	(1)	0/0	1/0	1/3	1/0	0/0	1/1	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Lubricating oils	—	—		?		1/3	2/3	(2-3)	(1)	(2)	0/0	(2)	3/0	0/0	0/0	1/1	1/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0	
Lubricating soap	—	—	diluted	?		1/3	1/1	(2-3)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(1)	1/1	0/0	(2)	(1)	(1)	0/0	
Sulphur	S_8	007704-34-9	tech. pure	Xi		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	3/0	3/4	1/1	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	(1)	1/1	1/1	1/1	Sulphur, net sulphur, sulphur bloom
Sulphur, melted, 121 °C	S_8	007704-34-9		?		0	0	(4)	(3)	0	4	4	4	4	0	0	0	4	0	0	(1)	0	4	1	4	0	(3)	1	1	0/0	
Sulphur chloride	S_2Cl_2	010025-67-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	4/4	1/0	4/4	0/0	3/4	(1/1L)[1]	(1/1L)[1]	0/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Sulphur dioxide	SO_2	007446-09-5	moist	T, C		1/1	1/1	(3)	(3)	0/0	1/1	4/4	1/3	3/4	2/2	1/2	0/0	0/0	1/1	1/1	1/1	1/4	1/0	4/4	4/4	0/0	3/4	1/1	1/1	1/0	with H2O -> Sulphurous acid
Sulphur dioxide	SO_2	007446-09-5	liquid	T, C		3/4	4/4	(3)	3/4	0/0	4/4	4/4	4/4	4/4	2/2	3/4	0/0	0/0	1/2	1/1	1/1	4/4	1/0	4/4	4/4	0/0	(3)	(1)	(1)	1/0	with H2O -> Sulphurous acid
Sulphur dioxide, aqueous solution	-> see: Sulphurous acid																													
Sulphur ether	-> see: Ethyl ether																													
Sulphur hexaflurod	SF_6	002551-62-4		—		0/0	0/0	1/0	(2)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	1/0	0/0	0/0	(1)	(2)	1/0	3/0	1/0	0/0	(1)	(1)	(1)		
Carbon disulfide	CS_2	000075-15-0		F+, T	X	4/4	4/4	3/0	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/3	1/1	1/0	1/1	4/4	1/0	4/4	0/0	1/1	1/1	1/1	1/0	
Sulphur monochloride	-> see: Sulphur chloride																													
Sulphur sodium	-> see: Sodium sulphide																													
Sulphuric acid	H_2SO_4	007664-93-9	40 %	C+		1/1	1/1	4/4	2/0	(4)	1/2	4/4	1/1	2/0	3/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	(3)	1/1	4/4	0/0	3/4	2/3	2/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	60 %	C+		1/3	1/3	4/4	3/3	(4)	1/2	4/4	1/3	2/4	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	4/4	3/4	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	80 %	C+		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/1	3/4	3/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	2/4	2/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	95 %	C+		3/4	3/4	4/4	4/4	4/4	2/2	4/4	3/4	4/4	4/4	2/4	0/0	4/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	1/3	1/3	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	fuming	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	4/4	4/4	1/0	4/4	0/0	(3)	1/2	1/1	0/0	Oleum
Sulphuric acid	H_2SO_4	007664-93-9	1-6 %	Xi		1/1	1/1	4/4	1/1	0/0	1/1	4/4	1/1	1/2	1/1	1/2	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/0	0/0	(3)	2/2	1/2	0/0	
Sulphuric acid	H_2SO_4	007664-93-9	20 %	Xi		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	(3)	2/3	2/3		
Sulphuric acid copper (II) salt	-> see: Copper sulphate																													
Sulphuric acid monomethyl ester	-> see: Methyl sulphuric acid																													
Sulphur trioxide	SO_3	007446-11-9		C+		4/4	4/4	4/4	(4)	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	(2)	(2)	3/4	3/0	1/0	4/4	0/0	(3)	(1)	(1)	0/0	
Hydrogen sulphide	H_2S	007783-06-4	saturated	F+, T+	X	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	3/0	1/0	1/3	3/3	1/0	0/0	1/0	1/1	1/1	1/0	(3)	4/4	0/0	1/1	1/1	1/1	0/0	
Sulphurous acid	H_2SO_3	007782-99-2	saturated	(C)		1/1	1/1	4/4	4/4	1/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	3/0	(3)	3/4	0/0	3/4	1/1	1/1	1/1	
Sulphuric acid dichloride	-> see: Thionyl chloride																													
Pork fat	—	—		—		0/0	0/0	(2)	(1)	1/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	2/0	1/0	1/0	0/0	(1)	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sebacic acid dibenzyl ester	-> see: Dibenzyl sebacate																													
Sebacic acid dibutyl ester	-> see: Dibutylsebacat																													
Sebacic acid diethyl ester	-> see: Diethylsebacate																													
Ocean water, seawater	-> see: Salt water, seawater																													
Soap solution	—	—	any	(—)		1/1	0/0	4/4	(2)	1/1	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/1	
Mustard	—	—		—		0/0	0/0	(2)	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	1/0	1/0	0/0	(2)	1/0L	1/0L		
Mustard oil	-> see: Allyl mustard oil																													
Silver acetate	$C_2H_3AgO_2$	000563-63-3		Xi		1/1	1/1	(2)	1/2	(2)	1/1	(2)	1/1	2/2	1/1	2/2	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	(3)	0/0	(4)	0/0	0/0	0/0	
Silver cyanide	CAgN	000506-64-9		T		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	(1)	(1)	(3)	0/0	(4)	0/0	0/0	0/0	
Silver nitrate	$AgNO_3$	007761-88-8	aqueous	C		1/1	0/0	1/0	1/1	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	1/1	
Silver nitrate	$AgNO_3$	007761-88-8		C		1/1	1/2	1/0	1/1	(2)	1/1	1/0	1/2	2/3	1/1	1/2	1/3	1/2	1/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1	1/1	
Silicon dioxide	-> see: Silicic acid																													
Silicone fats	—	—		(—)		0/0	0/0	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	1/0	1/0	1/1	0/0	1/1	1/1	1/1		
Silicone oil	—	—		?		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	3/3	1/0	1/4	0/0	1/1	0/0	1/1	1/1	(1)	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	Polysiloxan
Skydrol 500 (B4)	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	0/0	1/0	4/4	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Solutia
Skydrol 7000	—	—		(Xn)		0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	1/0	2/0	4/4	0/0	0/0	(1)	(1)		Basis Phosphorsäureester; Solutia
Soda	-> see: Sodium carbonate																													
Soya oil	—	008001-22-7		—		0/0	0/0	(2)	(1)	1/0	0/0	2/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	1/1	
Spindle oil	—	—		?		3/3	2/3	(2)	(2)	1/0	0/0	(2)	1/4	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Spinning bath acids	—	—	100mg CS_2/l	?		1/0	0/0	4/4	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(3)	(2)	4/4	0/0	(4)	3/4	2/4	0/0	
Spinning solution, viscous -	—	—		(Xn, Xi)		1/1	1/1	4/4	(3)	0/0	0/0		1/1	0/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	(3)	(2)	4/4	0/0	(3)	3/4	2/4	0/0	
Spirits	C_2H_6O	—		—		1/1	1/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	1/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	0/0	Ethanol 40 %
Spirit	C_2H_6O	—		F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1		Ethanol
Rinsing agent	—	—	aqueous	?		1/1	1/1	(2)	(2)	1/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(3)	(1)	(1)	0/0	
Starch gum	-> see: Dextrin																													
Starch solution	$(C_6H_{10}O_5)_n$	—	any	—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Starch syrup	—	—		—		1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Stauffer's grease	—	—		(—)		0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	1/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	(1)	(2)	0/0	(1)	1/1	1/1	0/0	
Stearic acid	$C_{18}H_{36}O_2$	000057-11-4	fuming	Xi		1/3	1/3	1/0	1/2	1/0	1/1	1/0	1/3	1/2	2/2	1/2	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
Stearic acid zinc salt	-> see: Zinc stearate		crystals																											
Stearic acid butyl ester	$C_{22}H_{44}O_2$	000123-95-5	100 %	Xi		0/0	0/0	(1)	(3)	1/0	0/0	(2)	(2)	0/0	0/0	1/0	1/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1	0/0	
Coal tar oil	—	092045-38-0	100 %	T		1/0	1/3	1/0	(3)	0/0	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	1/1	1/1		
Nitrogen	N_2	007727-37-9		—		0/0	0/0	1/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1		
Nitrogen tetroxide	N_2O_4	010544-72-6		(O), T+, C		0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(2)	(1)	(1)		
Strontium bromide	$SrBr_2$	010476-81-0		Xi		1/1	1/1	(2)	(1)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(3)	0/0	0/0		
Strychnine	$C_{21}H_{22}N_2O_2$	000057-24-9		T+		1/1	1/1	(1)	(1)	(2)	0/0	(2)	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)		
Styrene	C_8H_8	000100-42-5	100 %	Xn, Xi	X	4/4	3/4	1/1	4/4	1/1	(4)	1/1	3/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(2)	4/4	3/0	4/4	0/0	1/1	1/1	1/1	0/0	
Sulphite lye	-> see: Calcium bisulphite																													
Sulphuryl chloride	Cl_2SO_2	007791-25-5	tech. pure	C		4/4	4/4	4/4	1/0	0/0	0/0	4/4	4/4	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/0	3/0	3/0	1/0	4/4	0/0	3/4	0/0	0/0		
Tallow	—	—	tech. pure	—		1/1	1/1	1/0	(1)	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1	0/0	
Tannin	$C_{76}H_{52}O_{46}$	001401-55-4	10 %	Xi		1/1	1/1	1/0	3/3	0/0	1/1	4/4	1/1	3/3	0/0	1/1	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	1/1	
Tannin	$C_{76}H_{52}O_{46}$	001401-55-4		Xi		1/1	1/1	1/0	4/4	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	3/3	0/0	1/0	1/1	1/1	1/1	
Tar	—	—		T		0/0	1/0	1/0	(3)	1/0	0/0	1/0	(2)	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(1)	(1)	(1)		
Surfactants	-> see: Wetting agent																													
Turpentine substitute	—	—		Xn, N	X	0/0	0/0	1/0	(3)	1/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	(3)	0/0	1/1	1/1	1/1	1/1	
Turpentine oil	—	008006-64-2		Xn	X	2/2	3/4	1/0	4/4	1/0	3/3	1/1	4/4	4/4	4/4	2/3	4/4	3/3	1/1	1/1	1/0	1/3	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
White spirit	—	—	liquid	Xn, N	X	0/0	2/3	(1)	(3)	1/0	(4)	1/0	3/4	4/4	0/0	1/3	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	1/0	0/0	1/1	1/1	1/1	0/0	
Test fuel A (ISO-Fluid A)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	1/0	0/0	(1)	(1)	(1)		
Test fuel B (ISO-Fluid B)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)		
Test fuel C (ISO-Fluid C)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	3/0	0/0	(1)	(1)	(1)		
Test fuel D (ISO-Fluid D)	—	—		(Xn, N)	(X)	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	0/0	4/4	0/0	(1)	(1)	(1)		
Tetrabromomethane (TBE)	$C_2H_2Br_4$	—	100 %	T+		4/4	3/4	(3)	4/4	(4)	(4)	(3)	3/4	4/4	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Carbon tetrabromide	CBr_4	000558-13-4		Xn, Xi		0/0	0/0	(3)	4/4	0/0	0/0	(3)	3/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	(3)	0/0	0/0		
Tetrabromomethane	-> see: Carbon tetrabromide																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Tetrachloroethane	$C_2H_2Cl_4$	—	tech. pure	T+		3/0	3/4	3/0	4/4	(4)	(4)	1/1	3/4	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0	0/0	Isomer not specified in the source
Tetrachloroethene	-> see: Perchloroethylene																													
Tetrachloroethylene	-> see: Perchloroethylene																													
Carbon tetrachloride (TETRA)	CCl_4	000056-23-5		T		4/4	4/4	4/4	4/4	1/4	4/4	2/3	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	4/4	1/1	4/4	0/0	4/4	(1/1L)[1]	(1/1L)[1]	1/1	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Methane tetrachloride	-> see: Carbon tetrachloride																													
Tetrachlorotitanium	-> see: Titanium tetrachloride																													
Tetraethyl lead (TEL)	$C_8H_{20}Pb$	000078-00-2	techn. rein	T+	X	1/0	1/0	1/4	3/0	(2)	(4)	(2)	2/4	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/0	0/0	(2)	(1)	(1)	1/1	
Tetraethylorthosilicate	$C_8H_{20}SiO_4$	000078-10-4		Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	1/0	0/0	(1)	(1)	(1)		
Tetrafluoromethane	CF_4	000075-73-0		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0		
Tetrahydro-1,4-oxazine	-> see: Morpholine																													
Tetrahydrofuran (THF)	C_4H_8O	000109-99-9		F, Xi	X	3/4	4/4	1/0	4/4	1/0	3/4	1/3	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/1	(1)	(1)	1/1	
Tetrahydrofurfuryl alcohol	$C_5H_{10}O_2$	000097-99-4		Xi		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(2)	(1)	(1)		
Tetrahydronaphthalene	$C_{10}H_{12}$	000119-64-2	tech. pure	Xi		3/4	4/4	1/0	4/4	1/0	(4)	1/0	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	1/0	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0	
Tetralin	-> see: Tetrahydronaphthalene																													
Tetramethylene oxide	-> see: Tetrahydrofuran																													
Tetraphosphorus decaoxide	-> see: Phosphorus pentoxide																													
Thiacyclopentadiene	-> see: Thiophene																													
Thiofuran	-> see: Thiophene																													
Thioglycolic acid	$C_2H_4SO_2$	000068-11-1		T, C		0/0	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	(3)	(4)	0/0	3/4	0/0	1/1	0/0	
Thionyl chloride	Cl_2SO	007719-09-7	tech. pure	C		4/4	4/4	4/4	4/4	0/0	4/4	2/0	4/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	(3)	3/0	1/0	4/4	0/0	3/4	0/0	0/0	0/0	
Thiophene	C_2H_4S	000110-02-1		F, Xn	X	3/3	3/3	(2)	4/4	0/0	(4)	(2)	3/4	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	4/4	3/0	0/0	(1)	(1)	(1)	0/0	
Thymol	$C_{10}H_{14}O$	000089-83-8		C, Xn		0/0	0/0	(3)	(3)	0/0	0/0	(3)	(3)	3/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	1/0	4/4	0/0	(1)	(1)	(1)		
Titanium chloride	-> see: Titanium tetrachloride																													
Titanium tetrachloride	$TiCl_4$	007550-45-0		C		0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(4)	0/0	0/0		
Toluene	-> see: Methylbenzene																													
Toluol	-> see: Methylbenzene																													
Toluenesulphone chloramide sodium, p-	-> see: Chloramine T																													
Tragacanth	—	009000-65-1		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1		
Transformer oil	—	—		?		1/3	3/3	1/0	(3)	1/1	1/0	3/3	1/3	1/3	1/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	2/3	3/3	0/0	1/1	(1)	(1)	0/0	
Grape sugar	-> see: Glucose																													
Triacetin	$C_9H_{14}O_6$	000102-76-1		Xn		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	3/3	0/0	(1)	(1)	(1)		
Tribromomethane	-> see: Bromoform																													
Tributyl citrate	$C_{18}H_{32}O_7$	000077-94-1		—		1/2	2/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Tributyl phosphate (TBP)	$C_{12}H_{27}PO_4$	000126-73-8	tech. pure	Xn		1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1	
Trichloroacetaldehyde	C_2HCl_3O	000075-87-6	100 %	T/Xi		1/1	1/1	4/4	(3)	(4)	0/0	(3)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	0/0	(4)	3/0	(4)	4/4	0/0	4/4	0/0	0/0	0/0	
Trichloroacetaldehyde hydrate	-> see: Chloral hydrate																													
Trichloraldehyde hydrate	-> see: Chloral hydrate																													
Trichlorobenzene	$C_6H_3Cl_3$	—	100 %	(Xn)		4/4	4/4	(3)	(3)	0/0	(4)	(2)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	(2)	(3)	(4)	(3)	4/4	0/0	(2)	0/0	0/0	0/0	Isomer not specified in the source
Trichloroacetic acid (TCA)	$C_2HCl_3O_2$	000076-03-9		C+		1/4	3/4	4/4	4/4	4/4	0/0	4/4	1/1	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	1/3	3/0L	2/0L	1/1	
Trichloroethane	$C_2H_3Cl_3$	—		Xn		3/4	4/4	3/0	4/4	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	(1)	1/3	4/4	1/0	4/4	0/0	4/4	0/0	0/0	0/0	Isomer not specified in the source
Trichloroethene	-> see: Trichloroethylene																													
Trichloroethylene (TRI)	C_2HCl_3	000079-01-6	100 %	Xn		3/4	4/4	3/0	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/4	1/2	1/1	1/0	1/1	4/4	1/3	4/4	0/0	1/3	(1/1L)[1]	(1/1L)[1]	1/0	[1] Water-free! If even traces of hydrochloric acid (HCl) are split off by moisture, there is a risk of pitting, crevice and stress corrosion cracking.
Trichlorofluoromethane	CCl_3F	000075-69-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(3)	(1)	0/0	4/4	2/0	1/0	0/0	(3)	0/0	0/0	0/0	
Trichloromethane	-> siehe: Chloroform																													
Trichloromonofluoromethane	-> siehe: Trichlorfluormethan																													

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Trichlorophenol	$C_6H_3Cl_3O$	—		(Xn, Xi)		0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(4)	(3)	(4)	0/0	(3)	0/0	0/0		Isomer not specified in the source
Trichlorophosphine	-> see: Phosphorus trichloride																													
Trichlorophosphine oxide	-> see: Phosphorus oxychloride																													
Trichlorophosphorus oxide	-> see: Phosphorus oxychloride																													
Trichlorotrifluoroethane	$C_2Cl_3F_3$	000076-13-1		?		0/0	0/0	1/0	(3)	1/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		
Triethanolamine (TEA)	$C_6H_{15}NO_3$	000102-71-6	tech. pure	Xi		1/1	1/2	(2)	(2)	1/0	0/0	2/2	1/1	1/1	0/0	3/0	4/4	1/1	0/0	1/1	1/0	1/0	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Triethylamine (TEA)	$C_6H_{15}N$	000121-44-8	tech. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	1/1	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	3/4	4/4	3/0	3/4	0/0	(1)	(1)	(1)	0/0	
Triethylene glycol	-> see: Triglycol																													
Triethylene glycol diacetate	-> see: Triglycol acetate																													
Trifluorotrichloroethane	$C_2Cl_3F_3$	—	100 %	?		4/4	3/4	1/0	3/0	0/0	0/0	1/0	4/4	4/4	1/0	3/4	4/4	3/3	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		Isomer not specified in the source
Triglycol	$C_6H_{14}O_4$	000112-27-6		Xi		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	(3)	0/0	(1)	(1)	(1)	0/0	
Triglycol acetate	$C_{10}H_{18}O_6$	000111-21-7		?		0/0	0/0	(3)	(3)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)		
Trihydroxybenzoic acid, 3,4,5-	-> see: Gallic acid																													
Trihydroxybenzene, 1,2,3-	-> see: Pyrogallol																													
Trihydroxybutane	-> see: Butanetriol																													
Trihydroxypurine, 2,6,8-	-> see: Uric acid																													
Trihydroxytriethylamine	-> see: Triethanolamine																													
Triiodomethane	-> see: Iodoform																													
Triisopropylbenzene	$C_{15}H_{24}$	000717-74-8		—		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	1/0	0/0	1/1	(1)	(1)		
Tricresyl phosphate (TCF)	$C_{21}H_{21}PO_4$	—	tech. pure	T/Xn, N		1/1	1/1	1/0	4/4	1/0	0/0	1/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	1/1	1/1	1/1	1/1	Isomer not specified in the source
Trimethylbenzene, 1,3,4-	-> see: Pseudocumene																													
Trimethylolpropane	$C_6H_{14}O_3$	000077-99-6	aqueous	—		0/0	0/0	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	0/0	(1)	(1)	(1)		
Trimethylpentane, 2,2,4-	-> see: Iso-octan																													
Trisodium phosphate	Na_3PO_4	007601-54-9		Xi		1/1	1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	(4)	1/1	1/1		
Trisodium phosphate, tribasic	-> see: Sodium phosphate																													
Trinitrophenol, 2,4,6-	-> see: Picric acid																													
Trioctyl phosphate	$C_{24}H_{54}PO_4$	000078-42-2	tech. pure	(Xn)		3/0	1/0	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	(1)	(1)	(1)	0/0	
Tripen	-> see: Hexachlorobutadiene																													
Tripropylene glycol (TPG)	$C_9H_{20}O_4$	024800-44-0		(—)		1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/1	(2)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Tris(2-ethylhexyl) phosphate	-> see: Trioctyl phosphate																													
Tris(hydroxyethyl)-amine	-> see: Triethanolamine																													
Tris(hydroxymethyl)propane	-> see: Trimethylolpropane																													
Tropic acid tropylester sulphate	-> see: Atropine sulphate																													
Tung oil	-> see: Wood oil																													
Turbine oil (mineral oil base)	—	—		?		0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	(2)	1/0	0/0	1/1	1/1	1/1		
Superchloric acid	-> see: Perchloric acid																													
Undecanol	-> see: Undecyl alcohol																													
Undecyl alcohol	$C_{11}H_{24}O$	000112-42-5		Xi		1/2	1/3	(1)	2/3	(1)	1/2	1/0	1/2	2/2	3/3	1/3	0/0	1/1	1/2	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(1)	(1)	(1)		
Urine	—	—		—		1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	3/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1	
Urotropine	-> see: Hexamethylenetetramine																													
Vaseline	—	008009-03-8	tech. pure	(—)		3/4	2/3	1/0	1/0	1/0	0/0		1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Vaseline oil	—	008012-95-1	100 %	?		0/0	1/3	1/0	(2)	1/0	1/0		1/3	1/0	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	Paraffin oil
Vaseline oil	—	008012-95-1		?		1/1	1/3	1/0	1/0	1/0	0/0	1/1	1/3	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/3	0/0	1/1	1/1	1/1	1/1	Paraffin oil
Vinyl acetate	$C_4H_6O_2$	000108-05-4	tech. pure	F	X	0/0	1/1	1/0	4/4	(3)	(4)		1/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	1/0	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Vinylbenzene	-> see: Styrene																													
Vinylcarbinol	-> see: Allyl alcohol																													
Vinyl chloride	-> see: Chlorethylene																													
Vinyl cyanide	-> see: Acrylonitrile																													
Vinyl ethylene	-> see: Butadiene, 1,3-																													
Vinylidene chloride	$C_2H_2Cl_2$	000075-35-4		F+, Xn	X	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	2/3	1/1	(1)	(2)	4/4	3/0	4/4	0/0	(3)	0/0	0/0	0/0	
Vitamin C	$C_6H_8O_6$	000050-81-7	liquid	—		1/1	1/1	(2)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	(1)	(1)		
Wax alcohol	—	—	tech. pure	(—)		3/4	3/4	(2)	(2)	1/0	0/0		3/4	0/0	0/0	1/1	3/4	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	(1)	(1)	0/0	
Waxes	—	—		—		0/0	1/3	1/1	1/1	1/1	0/0		1/3	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	(4)	1/0	(1)	0/0	1/1	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics														Fluoroplastics				Elastomers			Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Walnut oil	—	008024-09-7		—		0/0	0/0	(2)	(2)	1/0	0/0		1/3	3/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	(1)	1/1	1/1		
Spermaceti	—	008002-23-1		—		0/0	1/3	(1)	1/1	1/0	0/0		1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1	1/1	
Detergent	—	—		?		1/1	1/1	1/0	1/1	1/1	0/0		1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	(2)	0/0	1/1	1/1	1/1	1/1	
Water	H_2O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Water, distilled ~	H_2O	007732-18-5		—		1/1	1/1	1/0	1/1	1/1	1/0	1/1	1/1	1/0	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	
Water glass	$Na_2Si_3O_7$	001344-09-8	saturated	C, Xn		1/1	1/1	1/0	1/0	1/0	0/0	0/0	1/1	1/1	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	Aqueous solution of alkali silicates
Hydrogen	H_2	001333-74-0	tech. pure	F+	X	1/1	1/1	1/0	1/0	0/0	0/0		1/1	1/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	
Hydrogen peroxide	H_2O_2	007722-84-1	30 %	C		1/1	1/2	4/4	1/1	1/0	1/2	4/4	1/3	1/2	1/1	1/1	0/0	1/0	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	(3)	1/1	1/1	1/1	
Hydrogen peroxide	H_2O_2	007722-84-1	100 %	O, C		1/4	1/4	4/4	0/0	0/0	0/0	4/4	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(3)	(1)	(1)	?	
Hydrogen peroxide	H_2O_2	007722-84-1	90 %	O, C		1/1	1/2	4/4	1/1	0/0	1/2	4/4	1/3	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/3	4/4	0/0	(3)	1/1	1/1	?	
Hydrogen peroxide	H_2O_2	007722-84-1	3 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	1/0	1/1	1/2	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	3/4	0/0	(3)	1/1	1/1	1/1	
Oxygenated water	-> see: Hydrogen peroxide																														
Plasticiser	—	—		?		1/3	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	3/3	0/0	(1)	(1)	0/0	(2-3)	0/0	4/4	0/0	(1)	(1)	(1)		
Wines	—	—		—		1/1	1/1	1/0	1/0	1/1	1/0	(2)	1/1	1/1	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	1/1	1/1	1/1	
Spirit of wine	C_2H_6O	—	50 %	(F)	X	1/0	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	Ethanol
Spirit of wine	C_2H_6O	—	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	Ethanol
Tartaric acid	$C_4H_6O_6$	000087-69-4	aqueous	Xi		1/1	1/1	3/3	1/2	0/0	0/0	(3)	1/1	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2	1/1	
Tartaric acid	$C_4H_6O_6$	000087-69-4		Xi		1/1	1/1	4/4	1/2	0/0	1/1	(3)	1/1	2/2	1/1	1/2	1/3	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	0/0	(4)	1/3	1/2	1/1	
Cream of tartar	-> see: Potassium hydrogentartate																														
Whiskey	—	—		—		0/0	0/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1		Whisky, Scotch, Bourbon
White spirit	—	008042-47-5		Xn		1/0	1/0	(1)	(3)	1/0	(4)	1/0	1/3	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	1/0	(2)	0/0	1/1	1/1	1/1		
Wool grease	-> see: Lanolin																														
Xenon	Xe	007440-63-3		—		0/0	0/0	1/0	(1)	1/1	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1		
Xylol	-> see: Xylene																														
Xylene	C_8H_{10}	001330-20-7		(F), Xn	X	3/4	3/4	1/0	4/4	0/0	3/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/0	1/3	4/4	1/3	4/4	0/0	1/1	1/1	1/1	1/1	
Cedar oil	—	008000-27-9		?		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(4)	(2)	(3)	0/0	(1)	(1)	(1)		
Cinnamon	—	—	grinded	?		0/0	0/0	(2)	1/0	(2)	0/0	(2)	(2)	3/0	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Cinnamaldehyde	C_9H_8O	000104-55-2		Xn, Xi		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(1)	(1)	(1)		
Cinnamon oil	—	008007-80-5		Xn, Xi		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Zinc acetate	$C_4H_6ZnO_4$	000557-34-6	aqueous	Xn, Xi		1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/3	0/0	(3)	(1)	(1)		
Zinc bromide	$ZnBr_2$	007699-45-8		C, Xn		1/1	1/1	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(2)	(1)	(2)	0/0	(3)	0/0	0/0		
Zinc carbonate	$ZnCO_3$	003486-35-9	saturated	?		1/1	1/1	(1)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	No chemical effect expected due to low solubility
Zinc chloride	$ZnCl_2$	007646-85-7	aqueous	(C, Xn)		1/1	1/1	3/4	(2)	0/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1	
Zinc chloride	$ZnCl_2$	007646-85-7	10 %	C, Xn		1/1	1/1	3/4	1/0	0/0	1/1	2/0	1/1	1/3	0/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1	
Zinc nitrate	$Zn(NO_3)_2$	007779-88-6		O, C, Xn		1/1	1/1	1/4	(2)	0/0	0/0	(2)	1/1	1/0	1/0	1/0	1/0	1/1	0/0	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(3)	(1)	(1)	0/0	
Zinc oxide	ZnO	001314-13-2	solid	Xn, Xi		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		No chemical effect expected due to low solubility
Zinc phosphate	$Zn_3(PO_4)_2$	007779-90-0	saturated	?		1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	
Zinc ointment	—	—		?		0/0	0/0	(1)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	(4)	(2)	(2)	0/0	(2)	(1)	(1)		
Zinc sludge	—	—		?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	(3)	0/0	0/0		
Zinc stearate	$C_{36}H_{70}ZnO_4$	000557-05-1		Xi		1/1	1/1	(1)	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	(2)	0/0	(2)	(1)	(1)		
Zinc sulphate	$ZnSO_4$	007733-02-0	10 %	—		1/1	1/1	(3)	1/0	(2)	1/0	2/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	1/1	
Zinc vitriol	-> see: Zinc sulphate																														
Tin (II) chloride	$SnCl_2$	007772-99-8	aqueous	(C, Xn)		1/1	1/1	(4)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	1/1	
Tin (II) chloride	$SnCl_2$	007772-99-8	saturated	C, Xn		1/1	1/1	4/4	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	1/1	
Tin (IV) chloride	$SnCl_4$	007646-78-8	aqueous	C		1/1	1/1	4/4	(3)	0/0	0/0	(4)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	4/4	3/4		
Tin dichloride	-> see: Tin (II) chloride																														
Tin protochloride	-> see: Tin (II) chloride																														
Tin tetrachloride	-> see: Tin (IV) chloride																														
Lemon juice	—	—		—		1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	1/0	1/1	0/0	(1)	1/1	1/1		
Citric acid	$C_6H_8O_7$	000077-92-9	10 %	Xi		1/1	1/1	1/1	1/2	1/3	1/1	2/4	1/1	1/2	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/1	1/1	1/1	
Citric acid	$C_6H_8O_7$	000077-92-9	50 %	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1	
Citric acid	$C_6H_8O_7$	000077-92-9	saturated	Xi		1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1	
Lemon peel oil	—	084929-31-7		Xi	(X)	0/0	0/0	(2)	(3)	1/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	3/3	0/0	1/0	(1)	(2)	4/4	(2)	3/3	0/0	1/1	(1)	(1)		mainly limes
Citrus juices	—	—	aqueous	—		1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	1/1	0/0	(2)	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

						Thermoplastics													Fluoroplastics				Elastomers				Metals			
MEDIUM	FORMULA	CAS NO.	CONCENTRATION	HAZARD INFORMATION	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HARD	PVC SOFT	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C	REMARK
Sugar beet juice	—	—		—		1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)		
Sugar acid	—	—	saturated	(Xi)		1/1	1/1	(3)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(3)	0/0	0/0		
Sugar syrup	—	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Two-stroke oil	—	—	100 %	—		0/0	1/3	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

Resistance

Two values are given for each medium:
left number = value at +20°C / right number = value at +50°C

0	no information available/no statement possible
1	very good resistance/suitable
2	good resistance/suitable
3	limited resistance
4	not resistant
K	no general information possible
L	Risk of pitting or stress corrosion cracking
( )	Estimated value

Hazard preventions

E	explosive
O	oxidising
F	inflammatory
F+	extremely inflammable
T	toxic
T+	very toxic
C	caustic
Xn	harmful to health
Xi	irritant
N	environmentally hazardous

Name of materials

Thermoplastics

HDPE	High density polyethylene
LDPE	Low density polyethylene
PA	Polyamide (nylon)
PC	Polycarbonate
PETG	Polyethylene terephthalate glycol (co-
PMP	polyester) Polymethylpentene (TPX)
POM	Polyoxymethylene
PP	Polypropylene
PS	Polystyrene
PSU	Polysulfone
PVC	Polyvinyl chloride
SAN	Styrene acrylonitrile

Fluoroplastics

E-CTFE	Ethylene-chlorotrifluoroethylene (Halar)
ETFE	Ethylene tetrafluoroethylene
FEP	Tetrafluoroethylene-perfluoropropylene (Teflon,
PTFE	FEP) Polytetrafluoroethylene (Teflon)
PVDF	Polyvinylidene fluoride

Elastomers

EPDM	Ethylene propylene terpolymer rubber
FPM/FKM	Fluoropolymer (Viton)
NBR	Nitrile rubber
SI	Silicone rubber

Metals

Al	Aluminium
V2A	Stainless steel 1.4301 (AISI 304)
V4A	Stainless steel 1.4401 (AISI 316)
Hastelloy C	Nickel-chromium-molybdenum alloy